USE OF HIGH SURFACE NANOFIBROUS MATERIALS IN MEDICINE

S.V. Mikhlovsky¹, L.I. Mikhlovska¹, V.G. Nikolaev³,
V.I. Chernyshev², V.V. Sarnatskaya³, K. Bardakhivskaya³,
A.V. Nikolaev⁴, L.A. Sakhno³,

¹*School of Pharmacy and Biomolecular Sciences, University of Brighton, Lewes Road, Brighton, BN2 4GJ, UK;* ²*AV Palladin Institute of Biochemistry, National Academy of Sciences, Kiev, Ukraine;* ³*RE Kavetsky Institute of Experimental Pathology, Oncology and Radiobiology, National Academy of Sciences, Kiev, Ukraine;* ⁴*Moscow Institute of Physics and Technology, Russia.*

1. INTRODUCTION

Interest in potential biomedical applications of nanomaterials and nanostructured materials arises from the perception that they are able to interact with individual biomolecules, cells and their individual parts and other biological structures of similar size in the micrometre and nanometre range. They may also have properties different from micro- and macro-objects. Recently nanofibres (NF) were mentioned as a connection between the nanoscale world and the macroscale world, because at least in theory, having diameter of a fraction of a micron, nanofibres may be infinitely long [1]. Production of nanofibres by electrospinning has been extensively studied recently and a variety of porous NF made by different modifications of this method has been described. They include polylactide (PL), poly-glycolide (PG), polyethylene terephthalate, polyacrylonitrile, polyvinyl-carbazole, polycarbonate, polystyrene/polymethylmethacrylate, PL/PEO, PL/polyvinylpyrrolidone and PL/(polyethylene oxide), [2]. Co-electro-spinning of colloidal particles such as hydroxyapatite with polymer solutions results in the production of NF with incorporated nanoparticles. Carbon nanotubes were co-electrospun with PEO and nanocomposite fibrils with very high mechanical strength were obtained [3]. Similarly, if polymer NF are produced from a drug containing solution, controlled drug release systems can be obtained [4]. Nanofibres of biodegradable polymers such as PL and PG are of particular interest for tissue engineering scaffolds, as they will completely dissolve after implantation thus leaving no foreign material in the body [5]. Using electrospinning technique, collagen fibres of 100 nm in diameter have been produced, which is similar to the size of natural collagen fibres [6]. The electrospun collagen NF were shown to promote cell growth and penetration into the engineered tissue scaffold.

Currently the main problem with a large scale production of nanofibres is an extremely slow rate of the electrospinning process. Non Woven

Technologies, Inc. Georgia, USA, has developed a thin-plate die technology that the company claims to have created a route to the cost effective production of NF using an alternative and more conventional meltblown technology [7]. A few other companies reported recently about achieving a large scale NF production using a modified electrospinning process. STAR Inc., NY, claim that they can produce electrospun nanofibres in bulk quantities and the mesh made from these NF could be used as a biodegradable anti-adhesion biomaterial preventing scar tissue formation during post-operative wound healing [8]. So far, the material has proven effective at reducing tissue adhesions in animal trials and the Phase III clinical trials (on humans) are being planned. The company also plans to use their nanomesh for drug delivery. eSpinTechnologies, founded in Chattanooga, TN are also commercialising nanofibres made of organic and biological polymers for use in biomedical devices and filtration systems [9]. Donaldson Co., Inc., Minneapolis, MN has patented its EON Nanofibers made with an electrospun process [10]. The most obvious and logical biomedical application of NF seems to be for filtration of biological media in order to remove pathogenic substances and micro-organisms. By producing filters from nanofibres it is possible to achieve high surface area with controlled pore size, and in this case NF have a strong advantage over microfibrils. Filters made using microfibrils have much smaller surface area – a few square metres per gram vs a few hundred square metres per gram in nanofibre-made filters. Nanofibrous filters may become an efficient means for water purification and thus could be used against bio-terrorism. Recently reported filters made from alumina NF by Argonide, Sanford, FL are capable of removing heavy metals, viruses and bacteria from water and protein separation [11]. These alumina whiskers produced by have an average diameter of 2 nm and surface area of 500-650 m²/g. Alumina nanofibre-based filters are a result of successful collaboration between the American business, Los Alamos National Laboratories and Russian scientists from Special Design and Technology Centre, Tomsk, and Vector Virological Institute, Novosibirsk.

An interesting example of man-made self-assembling peptide NF was reported in [12]. The authors synthesised and studied peptide-amphiphile molecules, which reversibly self-assembled into nanofibrous networks resulting in the formation of aqueous gels. These structures could be further reversibly polymerised to enhance their stability.

Electrospun polymer NF were used as a template for producing nanotubes by coating nanofibres with another material and then removing the polymer core [13]. Using this approach, aluminium and titanium dioxide hollow fibres were produced [14].

Nanomaterials and nanofibres in particular are not a recent invention of a human genius, as they are widespread in living nature. Such different materials as wood, silk, hair, connective tissue, bones, skin and blood vessels – to name just a few – are all formed by some regular and repetitive arrangement of NF, usually made up by proteins or polysaccharides. The molecule of DNA itself is an example of a nanofibre, about 2 nm in diameter and hundreds of nanometres long. A

striking example of a nanostructured material used by nature is blue feathers, such as those of the bluebird. There is no blue pigment in the feather and its colour is due to its sophisticated nanostructure. Colour production in bluebird is caused by coherent light scattering owing to a nanostructural arrangement of keratin and air bubbles in the feather barbs [15,16]. One of the most studied systems containing natural nanofibres is that of fibrin(ogen) polymerisation followed by blood clot formation. It is an example of a self-assembling macro-molecular structure and it is the result of the final stages of the blood coagulation cascade. The clot assembly consists of several distinctive steps, which influence the rate of fibrin fibres assembly and the spatial arrangement of fibres in the final clot. The first step is the proteolytic cleavage of plasma protein fibrinogen (factor I in the blood coagulation system) by the enzyme thrombin. Thrombin cleaves low molecular peptide fragments known as fibrinopeptide A and fibrinopeptide B from the fibrinogen molecule. This leads to the formation of monomeric fibrin, which has exposed binding sites and immediately forms dimers and small oligomers. Oligomers grow to yield protofibrils [17]. After reaching the critical mass the protofibrils form fibrils and finally form a clot network [18]. *In vivo* fibrin monomers spontaneously form a solid polymer (fibrin clot), which is covalently cross-linked by the blood plasma enzyme trans-glutaminase into insoluble polymer. However, *in vitro* fibrin polymer could be polymerised reversibly and re-polymerised with a predictable structure. It is possible to form a fibrin network with a wide spectrum of fibre thickness, branching and finally a polymer with different porosity and pore size distribution. Several factors appear to play an important role in determining the final fibre diameter and network structure, such as ionic strength, pH, fibrinogen/thrombin ratio or the presence of other plasma proteins [19,20]. Fibrin self-assembling occurs mainly via non-covalent intermolecular A- α and B- β binding between the complementary polymerisation sites localised in the central E-domains and peripheral D-domains of fibrin. The physicochemical nature of the noncovalent binding depends on the electrostatic interactions and hydrogen bonding between amino acid residues in the course of fibrin self-assembly. The significance of the electrostatic interactions became clear from observations of the effect of ionic strength on the polymerisation rate [21]. E.Mihalyi [22] suggested hydrogen bonding as the main mechanism of non-covalent binding for fibrin polymerisation. Later on it was shown that beside electro-static and hydrogen bonding, hydrophobic interactions also participate in fibrin polymerisation [23]. The study of fibrin network structure is of great academic and clinical interest. On the one hand, it is particularly relevant to such common diseases and conditions as bleeding, thrombosis, arterio-sclerosis and wound healing and on the other hand fibrin networks have a potential for use as a drug carrier, tissue scaffold or wound sealant. In this work an investigation of fibrin clot structure has been carried out using scanning and transmission electron microscopy.

Activated carbon fibres (ACF) is another interesting example of nanostructured fibrous materials that have high potential for medical

applications. Although the fibre diameter is in the micrometre range, ACF have large internal surface area due to the presence of micro- (pore width <2 nm), meso- (2-50 nm) and macropores (>50 nm). This classification is based on the difference in mechanism of gas adsorption according to the IUPAC recommendations [24]. All three types of pores contribute to the nanostructure of ACF and should be regarded as nanopores as they have at least one dimension at nanometre scale. Granulated activated carbon (GAC) adsorbents have been used in extracorporeal blood purification (haemoperfusion) since 1970s [25]. Preliminary results of the comparative study of ACF vs. GAC in several potential medical applications are presented and discussed in this paper.

2. MATERIALS AND METHODS

All reagents and solvents were used as purchased without further purification.

2.1. Preparation of Fibrin Monomer and Fibrin Films

Fibrin monomer (F-1) solution was prepared from aseptically collected fresh blood containing trisodium citrate. Fibrin monomer concentration determined by turbidimetry was 22.5 mg/cm^3 . The pH of F-1 solution was 4.4. 2% agarose gel was prepared using a mixture of 0.2M acetate/0.75M bicarbonate buffer (7:1 w/w) with pH 7.3. The agarose gel was used as hydrophilic surface. Polyethylene (Goodfellow, UK) was used as a hydrophobic surface. Fibrin films were prepared by spraying F-1 solution onto a surface from the distance of 5 cm. The samples were then incubated at ambient temperature for 30 min. in a humid chamber prior to fixation for electron microscopy studies. Afterwards the samples were fixed in 2% (v/v) glutaraldehyde solution in 0.1M cacodilate buffer, pH 7.4, followed by treatment with 1% (w/v) osmium tetroxide solution in 0.05M cacodilate buffer, pH 7.4. After fixation the samples were treated with aqueous 2% (w/v) tannic acid for 1 h and then the samples were dehydrated by sequential treatment with a series of water-acetone mixtures with increasing concentration of acetone (30, 50, 70, 90 and 100%, volume/volume). Finally, the samples were cut into two pieces. One piece was freeze-dried and sputter-coated with gold [26] and examined with a Scanning Electron Microscope, SEM (JEOL JCM-840, Japan). The other piece was embedded in epoxy resin (Araldite-Epon) at 60 C for 48 hours and 50-100 nm sections were cut with Ultratom LKB-V, Sweden. The sections were further coated with carbon by glow discharge procedure and negatively contrasted with 1% (w/v) uranyl acetate for 1 h followed by a 2-min treatment with a lead-containing solution (Reynolds) at ambient temperature [27]. These samples were examined with a Transmission Electron Microscope, TEM (Hitachi H-600, Japan).

2.2. Activated Carbons

Activated carbon fibres were produced from hydrated cellulose fibres using carbonisation and steam activation. Properties of ACF are given in Table 1. Pore size distribution in ACF was obtained from nitrogen adsorption isotherm at 77 K (Table 2). Activated carbon SCN commonly used in haemoperfusion was produced by pyrolysis of poly(4-vinylpyridine) cross-linked with di-vinyl-benzene followed by steam activation. As it is widely used in haemoperfusion, SCN has been chosen as a reference material to compare with ACF. Powdered activated carbon Norit A Supra was used as received (Table 1).

Table 1. Characteristics of activated carbons.

Activated carbon	Particle shape	Particle size, μm	Bulk density γ , g/cm ³	Total pore volume Vs, cm ³ /g*
ACF	Fibres	(7.0–9.0) (D) x 50 (L)	0.07 – 0.09	0.80 - 1.50
SCN	Spherical beads	300-1000	0.19-0.41	0.85 - 2.15
Norit A Supra	Irregular particles	10 x 25	0.30	0.81

* Vs was estimated from benzene vapour adsorption.

2.3. Adsorption Experiments

Unconjugated bilirubin adsorption was studied from 0.18 mg/mL solution of bilirubin in 3.0% human serum albumin (HSA) in single-pass column experiments at flow rate of 2.5 ml/min for 4 hours at room temperature (RT). Column volume was 20 cm³. Unconjugated bilirubin content was determined by Jendrassik-Grof method using diagnostic kit 605-C (Sigma, USA) [28].

Creatinine and vitamin B₁₂ adsorption were studied in batch experiments from 0.3 g/L and 1.0 g/L solution, respectively, with adsorbent/adsorbate ratio (w/v) 1:200 g/mL, for 1 hour at RT. Creatinine and vitamin B₁₂ content were determined with UV-Vis spectrophotometry.

Adsorption of bacterial endotoxin (BET) was carried out in batch from 10 mL of PBS (pH 7.2) containing 0.05 g/L of *E. coli* 055:B5 lipopolysaccharide (L4005, Sigma, USA) for 60 min. BET concentration was measured by spectrophotometric determination of 3-deoxysugars [29].

Table 2. Pore surface area S (m²/g) and total pore volume Vs (cm³/g) of carbon samples and their bilirubin adsorption capacity (mg/g of carbon)

Sample	S _{micro}	S _{meso}	S _{macro}	S _{total}	Vs	Bilirubin adsorption
ACF1	610	620	14	1250	0.80	9.4
ACF2	820	670	14	1505	1.10	20.5
ACF3	1250	670	15	1930	1.50	50.1
SCN1	n.d.*	n.d.	n.d.	900	0.85	3.2
SCN2	n.d.	n.d.	n.d.	1200	1.20	4.8
SCN3	n.d.	n.d.	n.d.	1320	2.15	18.0

* not determined.

2.4. Experiments with Biospecific Adsorbents

Native double-strained (ds) DNA from calf thymus (Sigma, USA) was immobilised by physical adsorption on activated carbons Norit A Supra and ACF2 (**DNA-Norit** and **DNA-ACF** adsorbents, respectively) as in [30]. Single-strained (ss) DNA was obtained by thermal denaturation of ds-DNA. Efficiency of DNA-immobilised adsorbents was studied in single-pass column experiments by perfusion of blood plasma of patients with systemic lupus erythematosus (SLE) through 2.5 cm³ microcolumn at flow rate of 0.2 mL/min for 1h at RT. Anti-DNA antibodies concentrations were measured using ELISA.

Inactivated *Staphylococcus Aureus* Cowan (SAC) cells were immobilised by physical adsorption on ACF3 (**SAC-ACF** adsorbent). SAC suspension was inactivated by incubation in 0.5 % formaldehyde for 3 h at RT, washed 5 times in PBS (pH 7.4) and finally heat treated at 80° C for 10 min.

Plasma immunoadsorption (IA) was performed in 13 mongrel dogs with histologically confirmed malignant mammary tumours of third and fourth stages. Plasma was perfused through a 100-cm³ column packed with 15 g of a SAC-ACF or uncoated ACF adsorbent at flow rate of 20 mL/min for 30-80 min. Anti-tumour effect of IA was estimated by tumour regression and ulcer healing [31]. IgG content was determined by rocket immunoelectrophoresis. Circulating immune complexes (CIC) were determined in plasma by precipitation with polyethylene glycol [32].

BET-ACF adsorbents were prepared by shaking carbon fibres and saline solution of *E. coli* 055:B5 for 3 h at RT. The mixture was centrifuged at 50g and the supernatant was analysed for BET concentration. Carbon fibres were washed three times with saline solution and packed in 2-cm³ columns (0.27 g fibres per column).

Guerin carcinoma was induced in rats by hypodermic inoculation with 25% suspension of viable tumour cells (2 mL/kg). The animals were used to estimate the anti-tumour effect of direct haemoperfusion (DHP) through the column packed with BET-ACF adsorbent (n=8 animals) and with ACF (n=7) as well as of intravenous injection of 0.75 mg BET per kg of body weight (n=8). The control group of rats (n=9) were intravenously injected with saline solution. The rats were treated 24 h after operation on the primary tumour on the 6th day after inoculation of tumour cells.

2.5. Bactericidal Properties of ACF

ACF impregnated with metallic copper (**ACF-Cu**), 2.5-3.5% w/w, was obtained by magnetron sputtering in low temperature argon plasma [33]. To evaluate bactericidal properties of ACFs, 0.5 mL of one of the following microbial cultures – *P. mirabilis*, *E. coli*, *S. aureus* or *P. aeruginosa* was distributed on a Petri dish with beef-extract agar as a nutrient medium. Dishes were completely covered with gauze, ACF or ACF-Cu and incubated for 45 min at 37°C. After removing the covers,

dishes were incubated for 24 h at 37°C and the numbers of bacteria were counted.

3. RESULTS AND DISCUSSION

3.1. Nanofibrous Fibrin Structures

Fibrin monomer was sprayed as droplets from the spray nozzle to the target site, and this flight took between 100 – 120 ms (data not presented). Confocal microscopy showed that the sprayed F-1 formed a heterogeneous film with high density boundary on the surface. Electron micrographs may be interpreted noting that in TEM mode the samples are sectioned and dark regions represent proteins with higher density than the background, hence they are seen as dark regions on micrographs. SEM, on the other hand, shows only the surface structures and on SEM micrographs dark regions correspond to the background or fluid filled space, whereas light regions correspond to proteins. The micrographs shown in Figures 1 and 2 are representative of a large number of images taken.

Investigation of fibrin clot structure using scanning and transmission electron microscopy revealed sequential steps of fibrin network formation (Figure 1, a-d). Formation of fibrin dimer (1a), protofibril formation (1b), branching of fibrils into fibrin network (1c) and finally the morphology and fibrin clot structure (1d) are clearly observed.

Figure 1. Different steps of fibrin network formation. a – fibrin dimer formation; b – protofibril formation; c – fibrin network; d – fibrin clot. a, b and c are TEM micrographs, x 60,000 (a) and x 35,000 (b and c); d is SEM micrograph, x 7,000.

Fibrin film produced on a hydrophobic polyethylene surface is easily detachable from the surface without being damaged. It retains contours of

the surface on which it was polymerised and the micrograph shows that fibrin is concentrated at the interface (Figure 2a). Fibrin sprayed over the hydrophilic agarose surface behaves very differently. It does not form any film structure as shown in Figure 2b.

Figure 2. Polymerisation of fibrin polymer at (a) hydrophobic polyethylene surface and (b) hydrophilic agarose surface. TEM micrographs, $\times 17,500$ (a) and $\times 35,000$ (b). 22.5 g/L fibrin monomer sprayed on the surface and incubated for 30 min at RT. Black blobs – fibrin.

To explain these observations, the events at the air/water interface should be taken into account. The droplets of fibrin monomer during their short flight are exposed to air, which should cause concentration of the protein at the air/solution interface, as it was established earlier [34]. This observation allows us to suggest that hydrophobic media (air in this case) promote formation of a fibrin film at their interface which is further developed once the droplets reach a hydrophobic surface. Mobility of proteins at air/liquid interface is higher than at solid/liquid interface [35], however the time of flight is perhaps too short (in the order of milliseconds) to establish strong links within the fibrin network of the single droplet. Hence, on the hydrophobic polyethylene the fibrin network expands over the whole surface (Figure 2a), whereas it breaks down on the hydrophilic agarose surface and no film is observed (Figure 2b). It was shown that platelet adhesion to fibrin(ogen) coating is influenced by the nature of the underlayer surface [36]. The effect of surface hydrophilicity/hydrophobicity on the fibrin film formation should be considered in medical applications of fibrin as a sealant.

3.2. Medical Applications of ACF

As expected, adsorption efficiency of ACF is related to their surface characteristics and porosity. ACF samples with higher degree of burn-off have larger V_s , S_{micro} and S_{total} . As a result, adsorption capacity of ACF3 towards unconjugated bilirubin from protein-containing solutions is five times higher than that of ACF1 (Table 2). Analysis of the distribution of specific surface area for different ACF samples shows that unconjugated bilirubin is mostly adsorbed in micropores.

It should be noted that ACF showed excellent operating stability with no signs of saturation after 4 h perfusion. Projection of the experimental data on the treatment of patients with hepatic failure suggests that a 180-200 cm³ column packed with highly activated ACF would be able to remove up to 600 mg of bilirubin from the blood plasma during 4 h perfusion at a flow rate of 25 mL/min.

In batch experiments DNA-ACF showed significantly higher adsorption efficiency than DNA-Norit towards anti-DNA antibodies removal from the blood plasma of SLE patients (Fig.). This result demonstrates high potential of DNA-containing ACF immunoadsorbents in the treatment of autoimmune diseases associated with elevated levels of anti-DNA antibodies.

Plasma IA performed in dogs with malignant tumours using SAC-ACF has resulted in a statistically significant reduction of the tumours. *Staphylococcus Aureus* Cowan suspension that has also been used in such cases is highly toxic and its use is associated with frequent and grave side effects. SAC immobilised on ACF showed little or no side effects. Plasma perfusion over SAC-ACF or ACF exhibits immunomodulatory effect withdrawing IgG and CIC from circulation, although IA seems to be more efficient (Table 3).

Table 3. IgG and CIC levels in blood plasma of dogs with mammary adenocarcinoma during plasma perfusion (B, pre-column level, P, post-column level) and one day after (A)

Solute	Adsorbent	Points and time of sample withdrawal (min)				
		B-30	P-30	B-60	P-60	A
IgG (g/L)	ACF	4,76±0,4	4,15±0,3	4,92±0,36	4,61±0,34	5,22±0,51
	SAC-ACF	4,45±0,3	2,94±0,2	4,50±0,24	3,45±0,36	4,21±0,25
CIC (a.u.)	ACF	44,7±3,1	20,6±3,0	50,6±3,2	37,4±3,5	63,3±3,1
	SAC-ACF	77,5±2,5	34,0±2,4	62,1±3,4	45,6±3,1	61,3±3,7

Similarly, ACF-immobilised bacterial endotoxin is a safer option for cancer treatment than a free BET suspension. Despite well-known anti-tumour activity of BET, their therapeutic applications are discouraged by

BET-induced toxic reactions. A single direct haemoperfusion through a microcolumn packed with BET-ACF resulted in the increase of the average life span of animals to 76.2 ± 11.4 days in comparison with 52.7 and 54.2 days in groups of rats after DHP through microcolumn packed with uncoated ACF and after BET injection, respectively. Complete regression of tumour was observed only in the group of animals treated with haemoperfusion over BET-ACF.

Incorporation of metals in dressing materials is used to make them bactericidal (e.g., silver impregnated carbon dressing "Actisorb Plus", Johnson & Johnson). Bactericidal properties of ACF-Cu, ACF and hygroscopic cotton gauze were compared in model experiments (Fig. 4).

Figure 4. Bactericidal effect of ACF and ACF-Cu. 1 – Gauze, 2 – ACF, 3 – ACF-Cu. I – *P. mirabilis*; II – *E. coli*; III – *S. aureus*, IV – *P. aeruginosa*.

After contact with the gauze the bacterial growth did not differ from that in the control. ACF exhibited a bacteriostatic effect with slight inhibition of *P. mirabilis* and *P. aeruginosa* growth and 3-fold reduction of *S. aureus* and *E. coli* colonies. In presence of ACF-Cu growth of all colonies was completely oppressed. It can be concluded that ACF-Cu has a strong bactericidal effect on different microorganisms combined with high adsorption potential.

The results presented in this paper confirm a large number of opportunities for medical applications of nanofibres such as fibrin or nanostructured fibres such as ACF. In case of natural fibrin fibres their properties can be significantly modified for a particular application by forming their network at different interfaces. Adsorptive properties of ACF can be significantly altered by their surface chemical or physical modification. It is important to realize that despite successful demonstration of these approaches in designing fibres, there is a lot of room for further improvement. A simple calculation allows estimation of nonporous nanofibrous carbon surface area as being between 200 and 2000 m²/g for the fibre diameter 100 nm and 10 nm, respectively. (In this

calculation the density of carbon fibre was taken as 2.0 g cm^{-3}). Such a large surface area is comparable with that of ACF but it does not require the activation stage, which significantly reduces mechanical strength of carbon materials. It is also an easily accessible external surface which has no intraporous diffusion limitation that may reduce the adsorption rate by porous carbons. Although carbon nanofibres are not produced on a large scale yet, recent advances in making polymeric nanofibres make possible production of carbon nanofibres by polymer pyrolysis in the near future, and that will open exciting opportunities for medical applications of these materials.

Acknowledgments: The authors are grateful to NATO for their support of this work via Collaborative Linkage Grant LST.CLG.978860 and to the Royal Society (VN and KB) for having sponsored their visit to Brighton. SM acknowledges NATO support for attending the ASI 'Nanoengineered Nanofibrous Materials'. Part of the work on fibrinogen was funded by Oxford Bioresearch Laboratory.

References

1. Frenot A., Chronakis I.S. Polymer nanofibers assembled by electrospinning. *Current Opinion in Colloid and Interface Science* 2003; 8:64–75.
2. Bognitzki M., Czado W., Frese T., *et al.* Nanostructured fibres via electrospinning. *Adv Mater* 2001; 13:70.
3. Ko F., Gogotsi Y., Ali A., *et al.* Electrospinning of continuous carbon nanotube-filled nanofiber yarns. *Adv Mater* 2003; 15:1161–5.
4. Kenawy E.R., Bowlin G.L., Mansfield K., *et al.* Release of tetracycline hydrochloride from electrospun poly(ethylene-co-vinyl acetate), poly(lactic acid) and a blend. *J Contr Release* 2002; 81:57–64.
5. Boland E.D., Wnek G.E., Simpson D.G., Pawlowski K.J., Bowlin G.L. Tailoring tissue engineering scaffolds by employing electrostatic processing techniques: a study of poly glycolic acid. *J Macromol Sci* 2001; 38:1231–43.
6. Matthews J.A., Wnek G.E., Simpson D.G., Bowlin G.L. Electrospinning of collagen nanofibers. *Biomacromolecules* 2002; 3:232–8.
7. USP 6,114,017 (2000).
8. Zong X., Kim K., Fang D., *et al.* Structure and process relationship of electrospun bioabsorbable nanofiber membranes. *Polymer* 2002; 43:4403–12.
9. Doshi J., Reneker D.H. Electrospinning process and applications of electrospun fibers. *J Electrostatics* 1995; 35:151–60.
10. Grafe T., Graham K. Polymeric nanofibers and nanofiber webs: A new class of nonwovens. *Proceedings of the International Nonwovens Technical Conference (Joint INDA – TAPPI Conference)*; 2002 September 24–26; Atlanta, GA.
11. Tepper F., Lerner M., Ginley D. Nanosized Alumina Fibers. *American Ceramic Society Bulletin* 2001; 80:57–60.
12. Hartgerink J.D., Beniash E., Stupp S.I. Peptide-amphiphile nanofibers: A versatile scaffold for the preparation of self-assembling materials, *PNAS* 2002; 99:5133–8.
13. Bognitzki M., Hou H., Ishaque M., *et al.* Polymer, metal, and hybrid nano- and mesotubes by coating degradable polymer template fiber (TUFT process). *Adv Mater* 2000; 12:637–40.
14. Caruso R.A., Schattka J.H., Greiner A. Titanium dioxide tubes from sol–gel coating of electrospun polymer fibers. *Adv Mater* 2001; 13:1577–9.
15. Prum R.O., Torres R.H., Williamson S., Dyck J. Constructive interference of light by blue feather barbs. *Nature* 1998; 396:28–9.
16. Shawkey M.D., Estes A.M., Siefferman L.M., Hill G.E. Nanostructure predicts intra-specific variation in structural plumage colour. *Proc Roy Soc, Ser B* 2003; 270:1455–60.
17. Doolittle R.F. Fibrinogen and fibrin. *Ann Rev Biochem* 1984; 53:195–229.

18. Henschen A. On the structure of functional sites in fibrinogen. *Thromb Res* 1983; Suppl 5:27-39.
19. Doolittle R.F., Blomback M., Henschen A., *et al.* N-terminal disulphide knot of human fibrinogen. *Nature* 1968; 218:130-4.
20. Kudryk B., Reuterby J., Blomback B. Adsorption of plasmin fragment D to thrombin modified fibrinogen-Sepharose. *Thromb Res* 1973; 2:297-303.
21. Ugarova T.P., Budzynski A.Z. Interaction between complementary polymerisation sites in the structural D and E domains of human fibrin. *J Biol Chem* 1992; 267:13687-93.
22. Mihalyi E. Transformation of fibrinogen into fibrin: II Changes in pH during clotting of fibrinogen. *J Biol Chem* 1954; 209:733-41.
23. Collen D., Vandereycken G., de Maeyer L. Influence of hydrostatic pressure on reversible polymerisation of fibrin monomer. *Nature* 1970; 220:669-71.
24. Sing K.S.W., Everett D.H., Haul R.A.W., Moscou L., Pierotti R.A., Rouquerol J., Siemieniowska T. Reporting physisorption data for gas solid systems with special reference to the determination of surface-area and porosity (recommendations 1984). *Pure & Appl Chem* 1985; 57:603-19.
25. Mikhlovsky S.V. Emerging technologies in extracorporeal treatment: focus on adsorption. *Perfusion* 2003; 18, Suppl 1:47-54.
26. Langer B.G., Weisel J.W., Dinanier P.A., *et al.* Deglycosylation of fibrinogen accelerates polymerisation and increases lateral aggregation of fibrin fibers. *J Biol Chem* 1988; 263:15056-63.
27. Weisel J.W., Stauffacher C.V., Bullit E., Cohen C. A model for fibrinogen: domains and sequence. *Science* 1985; 230:1388-91.
28. Varley Harold, Gowenlock Alan H., Bell Maurice. *Practical Clinical Biochemistry*, v. 1. London: Heinemann, 5th Ed., 1980.
29. Cynkin M., Ashwell G. Estimation of 3-deoxysugar by means of the malonaldehyde thiobarbituric acid reaction. *Nature* 1960; 186:155-6.
30. Beloglasov V.A., Snezhkova E.A., Nikolaev V.G. Hemoperfusion through DNA-coated and uncoated synthetic activated charcoals as an additive to the bronchial asthma traditional treatment. *Artif Cell Blood Sub* 1998; 26:191-7.
31. Terman D.S., Yamamoto T., Mattioli M., *et al.* Extensive necrosis of spontaneous canine mammary adenocarcinoma after extracorporeal perfusion over *Staphylococcus aureus* Cowan I. *J Immun* 1980; 124:805-15.
32. Creighton W.D., Lambert P.H., Miescher P.A. Detection of antibodies and soluble antigen-antibody complexes by precipitation with polyethylene glycol. *J Immun* 1973; 3:1219-27.
33. Eretskaya E., Sakhno L., Pimonenko N., *et al.* Method for obtaining the metallised carbon dressing material. SU Patent 1,817,483.
34. Bagnall R.D. Adsorption of plasma proteins on hydrophobic surfaces. II - Fibrinogen and fibrin-containing protein mixtures. *J Biomed Mater Res* 1978; 12:203-17.
35. Baszkin A., Boissonnade M.M. Competitive adsorption of albumin and fibrinogen at solution-air and solution-polyethylene interfaces. *In situ* measurements. In: *Proteins at Interface II*, TA Horbett and JL Brash, eds. Washington, DC: Amer Chem Soc, 1995, Ch. 15, pp. 229-27.
36. Kiaei D., Hoffman A.S., Horbett T.A. Platelet adhesion to fibrinogen adsorbed on glow discharge-deposited polymers. In: *Proteins at Interface II*, TA Horbett and JL Brash, eds. Washington, DC: Amer Chem Soc, 1995, Ch. 32, pp. 450-62.

NANO-SCALE ENGINEERING OF SURFACES

Functionalized Nanoparticles as Versatile Tools for the Introduction of Biomimetics on Surfaces

V. PRASAD SHASTRI*, A.M. LIPSKI, J.C. SY, W. ZNIDARSIC, H. CHOI AND I-W. CHEN

Department of Materials Science and Engineering & Laboratory for Research in Structure of Matter, University of Pennsylvania, Philadelphia PA, USA 19104 and Joseph Stokes Research Institute, The Children's Hospital of Philadelphia, PA 19104

Abstract: Historically, advances in materials synthesis and processing have been pivotal in the emergence of advanced medical technologies. Tissue Engineering (TE) and other organ regenerative techniques depend on the creation of a mechanically well-defined environment (scaffold) that is rich in biomolecular signals to achieve its objectives, namely the growth of functional neo-tissue. The evolution of neo-tissue is governed by material-cellular interactions, which in turn are dictated by surface characteristics such as texture and chemical functionality. To enable predictive outcomes in TE, polymeric fibers and cellular solid scaffolds should be engineered to include the presentation of biomolecular signals. Since information that is introduced on the material surface is processed as biomechanical and biochemical signals through receptors, which are nano-meter sized entities on cell surfaces, it is therefore important that this information be presented on the same length scale as it occurs in nature. A robust, reproducible and simple way to assembly physical and biochemical information therefore needs to be developed. We hypothesized that an assembly of functionalized particles could serve as a versatile tool for imparting texture and chemical functionality on a variety of surfaces. We further hypothesized that nano-scale resolution of physical and chemical information can be achieved using functionalized nanoparticles (FNP) as building blocks. Pre-functionalization allows for the precise control over density and spatial distribution of information on the surface. Using functionalized inorganic oxides; surfaces of hard (stainless steel and titanium) and soft (polyurethane) substrates have been modified so as to impart reproducible texture and chemically derivatizable functionality. These surface modification coatings can be tuned to possess tethered or covalently adsorbed biomolecules such as peptides, growth factors and proteins and can serve as a platform for engineering biomimetic interfaces to modulate cellular behavior toward implants and in scaffolds for TE.

1. INTRODUCTION

Depending on the surface chemistry and physical characteristics of a biomaterial (metallic or polymeric) the cellular response to the material interface can be varied. Although local modulation of cellular events is influenced to a significant extent by the layer of adsorbed serum proteins at the interface, it is not the sole determinant in the long-term compatibility of a material. Several other factors play a key role and they include chemistry of the surface (lipophilic versus hydrophilic), surface texture, local pH and degradation products.

When a material is chemically inert or slow degrading the typical response entails the encapsulation of the implant within an avascular fibrous capsule. The fibrous capsule serves to sequester the implant from the body's immune system while localizing the undesirable effects of the implant. This isolation process is effective from the body's perspective, nevertheless it is a barrier to transport and can serve as an impediment to the functioning of an implanted biosensors or drug delivery device. Such a fibrotic response is typically observed around polymers like Teflon, Silastic and polyurethane [1].

However, when a degradable material is implanted, the response can vary from integration of the implant with the surrounding tissue, i.e., if the implant is porous or fibrous; to a strong inflammatory response, typically triggered by localized accumulation of degradation products [2]. The inflammatory response may be acute and get resolved favorably or be sustained resulting in the rejection of the implant. Degradable polymers elicit such responses depending on their chemical make-up and configuration, i.e., fiber, film, particles or solid. The mass of the material has a direct bearing on the local changes in pH and accumulation of degradation products, while the configuration and chemistry of the material plays an important role in dictating cell attachment and cell morphology [3]. The latter is of extreme importance in the development of tissue-augmentation devices (e.g., bone pins, bone screws) and in tissue engineering where cell recruitment, proliferation and differentiation in a localized and controlled manner is vital for directing tissue-morphogenesis [4].

Surface modification offers a means to alter interfacial properties without affecting the bulk characteristics of a material. Some of the commonly used processes for the modification of chemical composition or texture of a material include; (a) chemical etching, (b) oxidative plasma treatment (typically used for metals), (c) chemical and plasma enhanced vapor deposition and (d) physisorption and chemisorption of block co-polymers and biopolymers [5-8]. Common drawbacks with these approaches are that they are usually material specific, i.e., limited to modification of either a hard or soft material, and they do not provide a means of precisely and reproducibly controlling chemical functionality and texture. In addition, seldom can both texture and chemical functionality be controlled in a single step or process.

It occurred to us that one could affect both chemical composition and texture of surface via the assembly (or coating) or functionalized nanoparticles. The advantages of this paradigm over conventional methodologies are the following:

1. Particles allow for control over surface characteristics from the sub-micron to nanometer length scale,
2. Pre-functionalized particles enable a high degree of control over density and spatial distribution of functional moieties,
3. Spherical morphology of the particles lend themselves to self-assembly and hence a high degree of order and reproducibility in surface chemistry and texture,
4. Since the assembly process can be done from aqueous phase, it is compatible with biological systems,
5. Complex surface chemistries can be attained by varying the size and chemical composition of the particles, and
6. The approach can be applied to both hard and soft material and in any configuration (wires, fibers, mesh, porous body, solid).

We have demonstrated the suitability of this approach in the modification of both metal and polymer surfaces and shown that precise control of chemical composition and texture may be achieved by varying the chemical, physical and structural characteristics of the nanoparticles.

2. EXPERIMENTAL

2.1 Synthesis and Characterization of Amine-Functionalized Silica Nanoparticles (FSNP)

Silica nano-particles were prepared using the Stober process, via the controlled hydrolysis of tetraethylorthosilicate (Aldrich), using ammonia and alcohol as catalyst [10]. Functionalization of the silica nanoparticle surface with primary amines (Si-O-R-NH_2) was achieved by condensation with aminopropyltriethoxysilane (APS). The mean particle diameter and size distribution was ascertained using Dynamic Laser Light Scattering and Transmission Electron Microscopy (TEM). The presence of amine functionality on the surface of the particles was visualized using salisaldehyde. The surface charge was determined by Zeta Potential measurement.

2.2 Coating of Metal and Polymer Substrates

316-L stainless steel and titanium foil substrates (Goodfellow Corporation) were cut into rectangle pieces (0.7mm x 10mm), ultrasonically

cleaned in organic solvents of increasing polarity, followed by rinsing in deionized water and then dried in a 60° C oven for 24 hours prior to use. FSNP were then assembled from an ethanolic solution onto metal substrates using spin coating (50 μ L/deposition, 1 wt%, 2000 rpm, total of 10 sequential depositions). An identical procedure was employed to coat polyurethane (PU) thin films that were prepared by spin casting from a tetrahydrofuran solution onto borosilicate glass slides.

2.3. Characterization of FSNP Modified 316-L Stainless Steel and Titanium Surfaces

The modified metal surfaces were characterized using Scanning Electron Microscopy (SEM), Energy Dispersive X-ray Analysis (EDAX), Rutherford Back Scattering (RBS), X-ray Photoelectron Spectroscopy (XPS), and Atomic Force Microscopy (AFM, tapping mode image). The concentration of amine groups on the surface was determined by a quantitative assay as described in the literature [11]. The assay involves first reacting the amine group with sulfo-SDTB followed by hydrolysis of the adduct with perchloric acid to liberate a colored cation that is assayed spectrophotometrically at 498 nm.

3. RESULTS

Silica nanoparticles ranging from 50- 800 nm in mean diameter with polydispersity (PD) of less than 0.1 were prepared successfully using the modified-Stober process. Functionalization of the nanoparticles surface via the silanol groups with a silane coupling agent aminopropyltriethoxysilane yielded amine modified silica nanoparticles with no appreciable change to both particle size and PD (Table 1, Figure 1). The surface modification was

Figure 1. TEM images of silica nanoparticles before (A) and after (B) functionalization

Table 1. Characteristics of silica nanoparticles

	SiO ₂	SiO ₂ -NH ₂
Mean Diameter (nm)	56.0	60.2
PD	0.07	0.09
Zeta Potential (mV)	-30	+26

accompanied by reversal of surface charge, which was confirmed by zeta potential measurements (Table 1). 316-L stainless steel and titanium foil surfaces were successfully modified using non-functionalized and amine-functionalized silica nanoparticles (FSNP). SEM analysis of the surface confirmed the presence of a silica nanoparticle assembly on the surface (Figure 2). Quantification of chemically accessible amine groups on the modified metal surfaces indicates that amine group density as high as 0.6 NH₂ groups/Å² may be achieved. Analyses of modified metal surfaces using RBS indicate that nanoparticle assemblies are reproducible in thickness for given substrate and coating conditions (number of depositions and nanoparticle concentration). For 10 depositions, typical thickness range from 350 to 450 nm. AFM analyses reveal that although the titanium surface exhibits much

Figure 2. SEM image of amine-FNSP modified titanium surface (left, scale bar: 100 nm) and EDAX spectrum of the surface (right)

greater surface roughness than the stainless steel surface, after coating with amine-FSNP the surface roughness of both surfaces were comparable (Table 2). In fact, even more dramatic contrast can be seen in the case of PU surface, which has a initial surface roughness of ~ 3 nm and a roughness post-coating of ~ 32 nm. Finally, the coatings appear to be quite robust and capable of withstanding handling by forceps and chemical environments that are typically used in the coupling of proteins, peptides and growth factors to surfaces.

Table 2. Roughness of metal and PU substrates before and after modification with functionalized silica nanoparticles

Substrate	Average Surface Roughness (nm) (determined from AFM)
Titanium	51.4
Titanium-Amine-FSNP	21.1
Stainless Steel	31.0
Stainless Steel-Amine-FSNP	27.3
PU	3.1
PU-Amine-FSNP	31.8

4. DISCUSSION

We have demonstrated that metal and polymer surfaces can be modified with functionalized nanoparticles to bear well-defined chemical functionality and topography. These coatings appear to be quite robust and resistant to mechanical abrasion due to typical handling procedures. Both titanium and stainless steel surfaces bear an oxide layer due to the spontaneous oxidation of titanium and, iron/chromium, respectively. It is plausible that this oxide layer facilitates the covalent binding of the silica nanoparticles to the metal surface via metal-silicate bonds. The AFM analyses of the metal surfaces before and after modification reveal that both metal and polymer surfaces post-coating exhibit similar surface roughness. This suggests that if the coating is of substantial thickness then the roughness of the underlying surface is of little consequence in the evolution of the surface topology, i.e., no epitaxial effects are in play. The underlying surface roughness has only bearing on the thickness of the coating for a given number of depositions. That is, greater initial roughness yields thinner coating for identical coating conditions as some of the nanoparticles serve to fill the crevices on the surface prior to achieving topological uniformity. The amine quantification studies reveal that the modified metal surfaces are rich in amine functionality and that the amine groups are chemically accessible and can be modified in a reproducible manner under reaction conditions similar to those used for protein coupling chemistry.

Thus these coatings are highly suitable for surface biomimetic engineering. We are currently exploring layer-by-layer assembly of biologically relevant information such as collagen, polysaccharides and apatite onto these functionalized nanoparticles and studying their assembly into 2-dimension and 3-dimensional hierarchies. It is hypothesized that these biomimetic particles can be assembled into 3-dimensional assemblies by either coating or dispersion in polymeric fibers (Figure 3) and porous media

to present biologically relevant information in a spatially well defined manner for tissue regenerative and drug delivery applications.

Figure 3. Poly(L-lactic acid) fibers containing poly(acrylic acid) functionalized silica nanoparticles on the fiber surface

5. CONCLUSIONS

Functionalized nanoparticles are excellent vehicles for the modification of chemical and topological characteristics of surfaces. Via these nanoparticle assemblies, roughness and texture of the surface, as well as spatial resolution of the chemical functionality can be simply controlled by varying the chemistry and size of the nanoparticles (colloids). It is envisaged that these functionalized nanoparticle assemblies will serve as a platform for the further assembly of biologically relevant information such as peptide-aggregates, enzymes, apatites and genetic material. This paradigm has been extended to include synthetic polymeric surfaces and polymeric nanoparticles. In addition, we are currently exploring the assembly of such nano-scale-functionalized hierarchies on collagen fibrils and electro-spun polymeric felts.

Acknowledgements: The authors wish to thank the National Science Foundation, National Institutes of Health, the State of Pennsylvania and Ben Franklin Technology Partners through the Nanotechnology Institute for funding of this work.

References

1. Jennings, D., Morykwas, M., DeFranzo, A. and Argenta, L. (1991), Analysis of silicon in human breast and capsular tissue surrounding prostheses and expanders, *Ann. Plastic Surg.*; **27**, 553–558
2. Martin, C., Winet, H. and Bao, J. (1996), Acidity near eroding polylactide-polyglycolide in vitro and in vivo in rabbit tibial bone chambers, *Biomaterials*, **17**, 2373-2380

3. Bergsma, E., Rozema, F., Bos, R. and de Bruijn, W. (1993), Foreign body reaction to resorbable poly(L-lactide) bone plates and screws used for the fixation of unstable zygomatic fractures, *J Oral Maxillofac. Surg.*, **51**, 666-670
4. Langer, R and Vcanti, J. (1993), Tissue Engineering, *Science*, **260**, 920-926
5. Nitschke, M., Schmack, G., Janke, A., Simon, F., Pleul, D. and Werner, C. (2002), Low pressure plasma treatment of poly(3-hydroxybutyrate): toward tailored polymer surfaces for tissue engineering scaffolds, *J Biomed Mater Res.* **59(4)**, 632-638
6. Gao, J., Niklason, L. and Langer, R., (1998), Surface hydrolysis of poly(glycolic acid) meshes increases the seeding density of vascular smooth muscle cells. *J Biomed Mater Res.* **42(3)**, 417.
7. Clarotti, G., Schue, F., Sledz, J., Ait Ben Aoumar, A., Geckeler, K.E., Orsetti, A. and Paleirac, G. (1992), Modification of the biocompatible and haemocompatible properties of polymer substrates by plasma-deposited fluorocarbon coatings, *Biomaterials*, **13(12)**, 832-840
8. Park, S., Bearinger, J.,P., Lautenschlager, E.P., Castner, D.G. and Healy KE. (2000), Surface modification of poly(ethylene terephthalate) angioplasty balloons with a hydrophilic poly(acrylamide-co-ethylene glycol) interpenetrating polymer network coating, *J. Biomed. Mater. Res.* **53(5)**, 568-576
9. Nitschke, M., Menning, A. and Werner, C. (2000), Immobilization of PEO-PPO-PEO triblock copolymers on PTFE-like fluorocarbon surfaces, *J Biomed Mater Res.* **50(3)**, 340-343
10. Choi, H. and Chen, I-W. (2002), Surface-modified silica colloid for diagnostic imaging, *J. Colloids. Interf. Sci.* **258**, 435-437
11. Gaur, R.K. and Gupta, K.C. (1989), A spectrophotometric method for the estimation of amino groups on polymer supports, *Anal. Biochem.* **180(2)**, 253-258

CATALYTIC FILAMENTOUS CARBONS (CFC) AND CFC-COATED CERAMICS FOR IMMOBILIZATION OF BIOLOGICALLY ACTIVE SUBSTANCES

G.A. KOVALENKO, D.G. KUVSHINOV,
O.V. KOMOVA, A.V. SIMAKOV, N.A. RUDINA
Borshkov Institute of Catalysis, Novosibirsk 630090, Russia

Abstract: Adsorption properties of granulated catalytic filamentous carbons (CFC) and CFC-coated macrostructured ceramics (honeycomb monoliths, foams) have been studied for adsorptive immobilization of biologically active substances including enzyme glucoamylase, invertase-active yeast membranes and non-growing cells of bacteria. The effect of morphology of the surface carbon layer on the adsorption efficiency of the supports and on the biocatalytic properties (stability and activity) of immobilized enzymes has been investigated.

Key words: catalytic filamentous carbon; carbonized ceramics; adsorptive immobilization.

1. INTRODUCTION

The problem of developing efficient supports for adsorptive immobilization of biologically active substances and microorganisms is still relevant because of its importance for various applications including medicine, biotechnology and pharmaceutical industry. Obviously, such *supports-adsorbents* must meet certain criteria. Firstly, they should have sufficient adsorption capacity with respect to such substances and microorganisms and have to strongly bind them to the surface. Secondly, they should retain and stabilize the biological activity of the immobilized substances at a relatively high level. Thirdly, they should possess high mechanical strength and resistance to biological and chemical degradation. Finally, their cost should be relatively low. Apparently, carbon-containing inorganic supports satisfy these requirements [2,3,5].

The present investigation has been carried out to study the granulated catalytic filamentous carbons (CFC) and CFC-coated macrostructured ceramics as supports – adsorbents for immobilization of enzyme glucoamylase, invertase-active yeast membranes and the non-growing bacterial cells. The effect of morphology of surface carbon layer on the adsorption efficiency of the supports and on the biocatalytic properties

(stability and activity) of immobilized enzymatic active substances has been investigated.

2. EXPERIMENTAL

Granulated catalytic filamentous carbons (bulk CFC) with diameter up to 5 mm were prepared by catalytic pyrolysis of methane on Ni / Al_2O_3 and $Ni, Cu / Al_2O_3$ catalysts [1,2]. The carbon yield (Y) expressed in g of carbon deposit per 1 g of the catalyst was varied from 1 to 180 g/g.

Macrostructured ceramics were used as honeycomb monoliths and foams described in [3,4]. These supports were coated by a carbon layer of different morphology, such as *i)* graphite-like (G) layer (Fig.1 a), *ii)* fur-like layer (F) formed by thick and short carbon filaments (Fig.1 b), and *iii)* hair-like layer (H) formed by thin and long carbon filaments (Fig.1 c), which were synthesized by methods described in [3]. Thus, the graphite-like carbon layer was synthesized by thermal decomposition of sucrose impregnated into the support pores at 500°C in H_2 flow for 2 hours. The catalytic filamentous carbon layers were synthesized by catalytic pyrolysis of a propane-butane mixture over $Ni / Al/Si$ catalyst at 500°C.

Fig.1. Scanning electron micrographs of carbon layers synthesized on ceramic surface.

- a) graphite-like carbon layer (G) on foam-like ceramics,
- b) fur-like carbon layer (F) on foam-like ceramics and Al/Si honeycomb monoliths,
- c) hair-like carbon layer (H) on cordierite honeycomb monolith.

The adsorptive immobilization of the biologically active substances on the carbon-containing supports was performed under conditions described in [2,5]. The amount of adsorbate was calculated from the difference of its contents in solution before and after adsorption and expressed in mg/g of the support.

Scanning electron microscopy (SEM) studies of the support surfaces and the adsorbed bacteria were performed with REM-100Y microscope. The samples for microscopy were prepared as described in [2,5]. The labels in the micrographs correspond to distance in micrometers (μ .)

3. RESULTS AND DISCUSSION

Comparative investigation of adsorption properties of granulated bulk CFCs with respect to various biological substances were carried out in [2]. The main conclusion was that the value of *accessible surface area* is of crucial importance in the adsorption of adsorbates of biological origin [2]. As for microorganisms, they were adsorbed exclusively on the external surface of CFC granules; inner surface was not accessible for large bacterial cells (1-2 μ in size) [2,5]. An additional key factor affecting

the adsorption of bacterial cells was *roughness* of the surface determined by the carbon yield (Y) [2,5]. It was shown that the adsorption capacity for the non-growing bacterial cells (*E.coli*, *Bacillus* sp. and *Rhodococcus* sp.) was lower for CFCs with dense and smooth surface (at high Y) and higher for CFCs with rough “carbon fur coating” (at low Y) whereas the surface area accessible to bacteria did not depend on Y [2]. The cross-linking of bulk CFC granules by the similar carbon filaments increased significantly both the inner area accessible for bacteria adsorption due to channel formation (Fig.2a) and the roughness of the surface via additional synthesis of “carbon fur coat” (Fig.2b). The adsorptive immobilization of bacteria on the cross-linked CFC granules was found to be highly efficient. In the SEM micrograph the adsorbed bacterial cells of *Rhodococcus ruber* were packed closely together (Fig.3).

As a conclusion, granulated bulk CFC supports with «carbon fur coating» were found to be efficient adsorbents for biologically active substances.

Fig.2. Scanning electron micrographs of the surface of cross-linked CFC granules
a) channels on the external surface of granules;
b) the “carbon fur coating”

Fig.3. Scanning electron micrograph of the *Rhodococcus ruber* immobilized on cross-linked CFC granules.

To increase the accessible surface area and the mechanical strength of the supports and at the same time to retain the morphology of filamentous carbons, the macrostructured ceramics, in particular foams were used and methods of synthesis of CFC layers on the alumina-silica surfaces were developed. To study the effect of carbon layer morphology on stability and biocatalytic activity of immobilized enzymatic active substances, the ceramics coated by graphite (G)-, fur (F)- and hair-like (H) carbon layers

were synthesized. When enzyme *glucoamylase* was adsorbed on the supports with graphite-like carbon layer, the stability of biocatalyst was relatively low [3]. The stability of glucoamylase increased by an order of magnitude via immobilization of enzyme on ceramics coated by filamentous carbon layer [3]. Also, filamentous carbon layer was found to provide the highest operational stability of immobilized glucoamylase. In the continuous hydrolysis of corn dextrinized starch the activity of the biocatalyst remained constant for several hundred hours at 50-55°C.

The effect of carbon layer morphology on the stability and biocatalytic activity of immobilized *invertase*-active cell membranes of autolyzed baker yeast was studied. Supports coated by catalytic filamentous carbon ensured the highest stabilization. The best result on stability was that the biocatalysts retained over 50% of the initial activity for 0,5-year storage at ambient temperature. Unlike glucoamylase, activity of immobilized invertase was found to depend strongly on the morphology of the carbon layer (Table 1). Invertase-active yeast membranes adsorbed on the graphite-like carbon layer synthesized on foam-like ceramics (Fig.1, a) showed a ~10-fold decrease of biocatalytic activity in comparison with fur-like carbon (Fig.1, b) perhaps due to hydrophobicity of graphite. Moreover, invertase adsorbed on hydrophobic carbon supports specially modified to increase the surface hydrophobicity has lost the biocatalytic activity completely. The activity of invertase-active yeast membranes immobilized on hair-like carbon layer synthesized on cordierite monolith was shown to be comparatively low because of diffusion limitations (Table 1).

Table 1. The effect of macrostructure of supports and morphology of carbon layer on activity of biocatalysts prepared via adsorption of yeast cell membrane.

Macrostructure of support	$S_{\text{specific}}, m^2/g$ of non-carbonized support	Carbon content, w/w%	$S_{\text{specific}}, m^2/g$ of carbonized support	Morphology of carbon layer*	Activity, U/g of biocatalyst
Foam	0.5	0.6	2.7	G	2.2
Foam	0.5	1.0	6.5	F	18.4
Monolith	24	1.4	27	G	12.5
Monolith	24	5.6	60	F	15.6
Monolith	0.15	0.5	0.8	H	7.2

The following designations are used: G – graphite-like carbon layer (Fig.1a), F – fur-like carbon layer (Fig.1 b), H – hair-like carbon layer (Fig.1c)

4. CONCLUSIONS

Comprehensive investigations of granulated CFC supports and CFC-coated ceramics demonstrate their high adsorption efficiency with respect to biologically active substances (enzymes, yeast membranes and non-growing bacteria) due to filamentous morphology of the surface carbon layer. Cross-linked CFC granules possess the highest adsorption capacity for the non-growing bacterial cells.

Filamentous carbon provides the highest long-term and operational stability of the heterogeneous biocatalysts based on immobilized enzyme

glucoamylase. In the continuous hydrolysis of corn dextrinized starch their activity remains constant for several hundred hours at 50-55°C.

The activity of immobilized invertase-active yeast membranes depends strongly on the morphology of carbon layer. Invertase adsorbed on graphite-like carbon layer has low biocatalytic activity. The significant (up to 10-fold) increase of invertase activity is observed when yeast membranes are immobilized on foam-like ceramics with fur-like carbon layer.

The highly efficient CFC-based adsorbents have potential for applications in biotechnology and medicine.

Acknowledgement: The work was partly funded by INTAS grant 01-2151.

References

1. Pat.RU 2064889 (1993).
2. Kovalenko GA, Kuznetsova EV, Mogilnykh YuI, Andreeva IS, Kuvshinov DG, and Rudina NA. (2001) Catalytic filamentous carbons for immobilization of biologically active substances and non-growing bacterial cells, *Carbon* **39**, 1133 – 1143.
- 3 Kovalenko GA, Komova OV, Simakov AV, Khomov VV, Rudina NA. (2002) Macrostructured carbonized ceramics as adsorbent for immobilization of glucoamylase, *J.Mol.Catal.A: Chemical* **182-183**, 73-80.
- 4 Pat.RU 2167197 (2001).
5. Kovalenko GA, Semikolenov VA, Kuznetsova EV, Plaksin GV, Rudina NA (1999) Carbonaceous materials as adsorbents for biologically active substances and bacterial cells, *Colloid J.* **61**, 729-736.

HYBRID THREE TERMINAL DEVICES BASED ON MODIFIED DNA BASES AND METALLOPROTEINS

ROSS RINALDI, GIUSEPPE MARUCCIO,
ALESSANDRO BRAMANTI, PAOLO VISCONTI,
PIER PAOLO POMPA, ADRIANA BIASCO,
ROBERTO CINGOLANI

*National Nanotechnology Laboratory – University of Lecce , Lecce
ITALY*

Abstract: The key challenge of current research in nanoelectronics is the realization of biomolecular devices. The use of DNA bases and electron-transfer proteins, such as blue copper protein azurin (Az), is particularly attractive because of their natural self assembly capability. We will present our results concerning the fabrication, characterization and modeling of hybrid three-terminal devices based on deoxiguanosines (modified DNA bases) and azurins. These molecular devices exhibit novel operational functions, thus opening the way to the implementation of a new generation of logic architectures

1. INTRODUCTION

Molecular electronics is one of the potential roadblocks to continue the scaling beyond the 50nm node for the implementation of nanoelectronic devices. Recently key demonstrations of molecular electronics devices have been reported, primarily through the use of carbon nanotubes and polymers [1], suggesting that the obstacles to the accomplishment of molecular electronic devices are more technical than conceptual and mainly concerns issues such as device aging, lifetime and reproducibility. In particular, the demonstration of a three-terminal field effect device (field-effect transistor) consisting of source (s) and drain (d) contact interconnected by a molecular layer, and a third contacts (gate) to modulate the source-drain current (I_{ds}), is a crucial step for the development of a molecular electronics. However, the implementation process of a reliable three terminal device based on a few organic molecules at nanometer scale is still a demanding and difficult step [2]. An alternative route is to exploit conduction of self-assembled biomolecules, in order to achieve devices based on highly ordered engineered layers (bottom-up approach), taking advantage of the specific reactivity of molecules having functional groups with affinity for specific

surfaces and/or molecules. While engineers and scientists have been long aspiring to manipulate structures controllably and specifically at the micro- and nanometer scale, nature has been performing these tasks with great accuracy and high efficiency using highly specific biological molecules such as DNA and proteins. Electronic conduction through biological macromolecules and biomolecular monolayers has been demonstrated [3]. Pioneering investigations showed that biomolecules were stable in air and at room temperature and behave like active elements in the devices. In this paper we describe and discuss the basic nanotechnological issues for the implementation of hybrid three terminal devices based on deoxyguanosine derivatives (a DNA base) and metalloproteins. We also present a phenomenological explanation of the operational principles of such devices. Finally the interconnection problem of the hybrid devices is discussed on the basis of a finite element simulation, providing a full electromagnetic characterization of the structure. A thorough analysis of device ageing and degradation is also given.

2. DEVICES BASED ON DNA BASES

Recently, there has been great theoretical and experimental efforts aimed at assessing the problem of electrical transport in DNA strands. Due to the considerable difficulties in connecting single DNA ropes to electrodes separated by few tens of nanometers, we adopted a different strategy choosing a single modified DNA base, the lipophilic deoxyguanosine, as the basic molecular constituent of our nanodevices. The guanine exhibits a low oxidation potential -which favors charge transport- and spontaneous self-assembling properties both in solution and in the solid state [4]. The base was modified, in the lipophilic deoxyguanosine derivative form [5] (Fig.1a), to favor the formation of ordered supramolecular structures thanks to its peculiar sequence of H-bond donor and acceptor groups and side chains (Fig. 1b).

The nanodevices were fabricated by cast deposition. A 2 μ l drop of deoxyguanosine solution in chloroform was prepared (10^{-1} - 10^{-4} M) and deposited in the gap between two metallic contacts. Upon controlled evaporation, Atomic Force Microscopy (AFM) studies of the molecular layer showed that the deoxyguanosines self-assemble in supramolecular ribbon-like structures (Fig. 1c).

To interconnect guanosine-ribbons and implement the hybrid molecular electronic devices, planar metal-insulator-metal nanojunctions (Fig. 2a) were fabricated on the surface of thermally oxidized silicon wafers. The oxide layer was 100 nm thick and constituted the gate oxide, while a silver

Figure 1 : (a) The molecule used in this study and (b) the self organized ribbons of dG(C₁₀)₂. (c) AFM image of the guanosine layer morphology. The ribbons form an ordered supramolecular structure, laying parallel to each other with a periodicity of 2.5 nm and a length up to $l \approx 100$ nm. Over such a length scale, the packed lamellar structure of the SAGC, physisorbed on the surface between the electrodes, gives rise to an orthorombic unit cell of size $a = 1.3 \pm 0.1$ nm and $b = 2.5 \pm 0.2$ nm. For distances longer than 100 nm, that ordering is lost, and the ribbons form randomly oriented SAGCs.

back-electrode –deposited on the degenerated doped silicon substrate– was chosen as the gate electrode. The source and drain Cr/Au (8nm/35nm) electrodes were realized by electron beam lithography followed by lift-off. Typical inter-electrodes distances were in the range between 20 and 40 nm [6]. The fabricated planar electrodes were inspected by plan-view and cross-section scanning electron microscopy (SEM) in order to check the success of the whole technological process and to estimate the separation between the Cr/Au nanotips. All contact pairs were then tested by current-voltage measurements. Open-circuit resistance as high as 100-200G Ω were obtained in all working devices. Typical process yield – i.e. the percentage of good contact pairs where no significant current was observed to flow under open-circuit configuration – was around 90%.

Current-voltage experiments on the guanosine-based devices were focused on the DC behavior and were carried out by using a semiconductor parameter analyzer (HP Agilent 4155B) in the voltage range between –3.5 and 3.5 V at room temperature and in air. The gate and drain voltage were applied with respect to the grounded electrode (source). Drain-source and gate current were recorded simultaneously. Fig. 2b shows a 3D plot of the drain-source current as a function of the drain-source voltage V_{ds} and the gate voltage V_g . In the low drain-source bias region, the device was almost non conductive. All the measured characteristics showed the existence of a well-defined threshold voltage and indicated that conduction can be activated at higher bias. By increasing the gate voltage from 0V to 1V, this threshold voltage gradually increased following an almost linear trend. This behavior can be explained in terms of resonant tunneling.

Figure 2 (a) High magnification SEM image of the planar nanoelectrodes. (b) 3D plot of the drain-source current as a function of the drain-source voltage V_{ds} and the gate voltage V_g

Due to the difficulty in creating an ideal Ohmic molecule-metal contact, two potential barriers arise at the interfaces between the organic/inorganic layers. Moreover, since the molecules were found to aggregate spontaneously to form ordered self-assembled guanosine crystals (SAGCs), we could model the molecular part as a semiconductor material, characterized by energy bands. At low voltage, the molecular layer behaved as an insulator. On the other hand, transport above threshold can be explained in terms of resonant tunneling. When the applied drain-source bias aligns the electrodes Fermi levels to one molecular miniband, the conduction is activated. The energy shift of the molecular band due to the gate field induces a change in the alignment condition and therefore an increase in the threshold voltage, was required to recover the resonant tunneling process. We found that the threshold voltage increased almost linearly with the gate voltage.

The field effect was found to have a profound effect on the drain-source current at constant drain-source voltage, as manifested by a fivefold decrease of its value as a function of V_g (for drain-source voltage around 3 V, the current I_{ds} changes from 250 pA at $V_g=0$ V to 50 pA at $V_g=1$ V resulting in an on-off ratio around 5). It is worth noting that I_{ds} decreases as in a p-channel MOSFET, but no saturation was observed in the I_{ds} - V_{ds} characteristics. A maximum voltage gain (given by the product of the transconductance and the output resistance) as high as 0.76 was found (small-channel molecular devices usually exhibit gain in the range between 0.3 and 0.5).

Although these nanodevices can be probably further improved, to enhance their performance and reduce their aging, some interesting architecture can already be proposed. The lack of saturation in the source-drain current makes the output current quite sensitive to small changes in the source-drain voltage. The behaviour of our nanodevices is dual with

respect to a standard field-effect transistor. In fact, the V_{ds} - I_{ds} is similar to the I_{ds} - V_{ds} curve of a standard FET. Our devices is stable when guided in current rather than in voltage. Moreover, an on-off ratio around 5 could be enough for some logic applications, such as static random access memory (S-RAM).

3. DEVICES BASED ON AZURIN MONOLAYERS

The blue copper protein *Pseudomonas aeruginosa* azurin (14.6 kDa) is one of the best characterized redox metalloproteins [7]. It mediates electron transfer in the denitrifying bacteria; specifically, it transports electrons from cytochrome c_{551} to nitrite reductase in the electron transport chain of respiratory phosphorylation [8]. The central Cu atom, the redox active site, is coordinated to 5 aminoacid ligands in a distorted trigonal bipyramid geometry [8]. The tertiary structure of azurin is strongly asymmetric for the presence of a S-S bridge opposite to copper. Azurin fold into an eight-stranded Greek key β -barrel motif with only a α -helix present. Given to this secondary structure and also to the disulfide bond, it can be regarded as a very stable protein. Due to their physical and chemical properties, Az proteins are good candidates for bio-electronic applications.

Covalent attachment on self assembled monolayers (SAMs), consisting of molecules adsorbed from solution onto solid substrates [9] has been employed to achieve an appropriate and permanent localization of biomolecules on Si/SiO₂. Azurin proteins have been adsorbed on self assembled 3-mercaptopropyltrimethoxysilane (3-MPTS), dissolved in absolute ethanol. A very diluted solution (2%) of 3-MPTS has been used to obtain ordered monolayers and to prevent from the multilayer formation. Sulfide groups are adsorbed from high purity ethanol solution and at the solid-liquid interface a strong chemisorption of the head group (Si) gives rise to highly ordered architectures. The promoted surfaces were exposed to commercial Az solutions and gently dried at room temperature. Adsorption of Az was performed from 10^{-4} M solution with a pH 4.6 (Az isoelectric point) prepared dissolving Az in 50 mM ammonium acetate buffer. In these conditions no charges are present on the biomolecule surface and the adsorption process isn't affected by electrostatic attractive or repulsive forces.

3-MPTS was used as a cross-linking agent because it ensures orientation of the protein deposited film. In fact, the protein adsorption on 3-MPTS SAM occurs by the unique disulfide bridge. Therefore, proteins are well-ordered in the molecular film and the molecular architecture is similar to that of immobilized protein molecules on gold [10]. The obtained tapping-mode AFM image with a scan size of $0.88 \mu\text{m} \times 0.88 \mu\text{m}$ is presented in Fig 3a.

This image is an evidence for azurin adsorption since it reveals features uniformly distributed across the surface, which were not present on SAMs

substrates. The presence of these topographic features was reflected in the roughness. The protein adsorption, in fact, is responsible for an rms roughness increase up to ten times. The recognizable granular structures are adsorbed proteins and the surface is totally covered by proteins. The width of these structures is overestimated due to the geometrical effect of the AFM tip. It is known that Az has a dimension of 4.4 nm. Considering the tip convolution effect, the apparent width measured by AFM (19-21 nm) corresponds to $d = 4.5\text{-}5.5$ nm; not very different from values reported in literature.

Fig 3: (a) AFM topography image of azurin immobilized on self-assembled 3-MPTS film. (b) Fluorescence spectrum of azurin in solution and adsorbed onto surface.

It is noteworthy that the immobilization procedure is a very demanding aspect because it must preserve the molecular functionality.

Conformational properties of the azurin monolayers were investigated by intrinsic fluorescence spectroscopy. Using this technique, it is possible to analyze the conformational and structural alterations that proteins experience during immobilization on solid films. Since the fluorescence parameters of the aromatic residues are highly sensitive to the microenvironment of fluorophores in protein structures, the use of intrinsic fluorescence spectroscopy allows us to directly monitor the conformational equilibrium induced by the immobilization procedure, thus determining the occurrence of perturbations in protein folding, possibly resulting in physical-chemical changes of the copper active sites. Azurin has only one tryptophan residue (Trp48) which is responsible for protein fluorescence. The photoluminescence spectrum of native azurin is centered at an unusually short wavelength ($\lambda_{\text{max}} \approx 308$ nm) owing to the highly hydrophobic microenvironment surrounding Trp48. Despite the holo- and apo-azurins exhibit identical fluorescence spectra, the emission

of the holo-protein is strongly quenched by the presence of the copper. Therefore, we utilized the apo-form of azurin to optically investigate the protein monolayers on SiO₂.

With respect to free apo-azurin fluorescence in buffer, the spectrum of the protein immobilized in the film is characterized by a comparable line-shape (Fig. 3b) and a slight red-shift (~3 nm), accounting for the fact that immobilization binding does not interfere with the fold pattern of the native protein. This result is supported by the comparison of the photoluminescence spectrum of protein monolayer with the broadband, red-shifted emission of a denatured sample of azurin (see also the inset of Fig. 3b). According to the experimental evidence and to the photophysics of aromatic amino acids, it seems that the tryptophan residues in native and immobilized proteins are found in similar locations. The small spectral shift is the only minor effect detectable in azurin upon immobilization. This suggests the possibility of a very weak internal rearrangement due to the interaction of the ligand binding, without affecting the actual fold pattern.

Having demonstrated the integrity of the azurin monolayer, we proceeded to the fabrication of the protein transistor prototype. The device structure consisted of a planar metal-insulator-metal nanojunction, comprising of two Cr/Au (6nm/35nm) arrow-shaped metallic electrodes facing each other at the oxide side of a Si/SiO₂ substrate connected by the molecular layer (drain and source electrodes). The fabrication of planar nanojunctions was carried out using the same procedure described in section 2. The disulfide bridge S-S of Azurin was broken to form covalent bond on SiO₂ substrate, properly functionalized by means of 3-MPTS. Current-voltage experiments were carried out by using a semiconductor parameter analyzer (HP Agilent 4155B) in the voltage range between -6 and 6 volts, at room temperature and ambient pressure. The gate voltage (V_g) was changed in order to investigate its influence on the current (I_{ds}) between the source (s) and drain (d) electrodes. Before the deposition of molecules, all devices were tested to verify that the channel was insulated (resistance = 100 G Ω). The current-voltage characteristic (I_{ds} - V_{ds}) of the protein transistor under forward drain-source bias (V_{ds}) exhibits a low-current plateau at low field and then rises up to hundreds of pA as shown in Fig. 4a.

The room-temperature drain-source current as a function of the gate potential, for $V_{ds} = 5.5$ V, is displayed in Fig. 4b. The transfer characteristic exhibits a pronounced resonance with a bell shape centred at $V = 1.25$ V. In this region, the transconductance changes from positive to negative values. The peak to valley ratio and the FWHM are 2 and 0.3 V, respectively. This feature gradually disappears after some cycles of measurement due to the aging of the molecular layer, which is not encapsulated.

Fig. 4: (a) Characteristic of protein FET. 3D plot of the drain-source current as a function of the drain-source bias (V_{ds}) and of the gate bias (V_g) measured in the dark and at room temperature. (b) Transfer characteristic of protein FET.

These results originate from the unique transport mechanism of our biomolecular devices. Redox proteins devices are very different from standard inorganic semiconductors. Silicon MOSFETs and thin-film transistor (TFTs) are based on a gate field modulating the width and the conductance of a semiconducting channel. In proteins, the long range electron transfer (ET), which represents one of the key processes of living systems involved in photosynthesis and respiration, occurs between a donor (D) and an acceptor (A) site. Two different models for ET have been proposed [12], i.e. a superexchange mechanism (consisting of direct quantum tunneling between the donor and acceptor) or a sequential (incoherent) hopping between adjacent sites.

The transport of electrons through systems containing redox sites occurs via electron hopping from one reduced ($Cu(I)$) molecule to an adjacent oxidized ($Cu(II)$) molecule [13]. Therefore, the presence of two adjacent Az molecules in the $Cu(I)$ and $Cu(II)$ redox states is required to have current flux between two planar electrodes. Since the protein is chemisorbed onto the SiO_2 surface with the natural electron transfer route – which joins the copper site to the disulfide-bridge – almost perpendicular to the surface, we believe the vertical field applied along this direction (due to V_g) modifies the oxidation state and induces a change in the equilibrium of the redox reaction, thus modifying the balance between the two populations. As a consequence, the current as a function of V_g is maximum when the populations of protein in the $Cu(II)$ and $Cu(I)$ state become equals, otherwise the current is lower. This phenomenological model explains the presence of the resonance in the transfer characteristics shown in Fig. 4b.

4. DEVICES AGEING AND DEGRADATION ANALYSIS

Finally, the issues of device reproducibility, aging and lifetime must be addressed for molecular electronics [14,15,16]. Among all the fabricated nanodevices, only a limited group exhibited a clear gate effect, whereas in the others significant current fluctuations and failure occurred. Inspection by means of scanning electron microscope demonstrated that the failure was primarily due to the electrode burning and possibly metal electro-migration during operation. Two main phenomena concerning device damage can be distinguished: (1) nanojunctions can blow up due to the local heating during the current flow or (2) the formation of various aggregates can be observed on the contacts. When we apply a bias, a very high electric field arises between the nanoelectrodes, due to the small tip separation and to the drastic change in the dielectric constant at the interface between SiO_2 and the metal. The very intense electric field, combined with the low adherence of the metal layer, favours the diffusive movement of metal mass. We found an experimental relationship, according to which for increasing contact separation the activation voltage for the device damage increases (as expected from a field or current related phenomenon) with a nearly linear trend. Typical values ranged from ~ 4 V at 50 nm to ~ 7 V at 300 nm. The extrapolated linear regression, however does not intersect the origin, so predicting a nonzero activation voltage for shot-circuited contact pairs. Clearly, the phenomenon can no longer be treated in terms of macroscopic quantities such as the voltage and gap width – or, which is equivalent, the average electric field. Instead, a more accurate analysis of the local relevant quantities is required, in particular the local electric field, current density and temperature. The simulations were performed solving the Poisson conductive media equation, by the commercial finite element code FEMLAB. In particular, we simulated contact pairs with different separations ranging from 40 to 300 nm. The voltage applied to each configuration was taken according to the linear interpolation of the experimental data; then the electric field in air and current density inside gold were analyzed, to find recurring values or at least orders of magnitude related with breakdown. A thermo-electrical simulation allowed to exclude any significant temperature increase (temperature differences were always less than 1 K); therefore we concluded that heating could not be the primary cause for breakdown. The electric field was analyzed in the *highest intensity region* in air, to evaluate its possible effect on the molecular material. We took as *high intensity region* (or hot-spot) the one in which the electric field intensity values were always bigger than the 75% of the maximum of electric field probability distribution. The spatial average for the electric field values was computed in this region.

Current density too was spatially averaged over its hot-spot (visible in Fig. 5a, inside one contact), defined as for the electric field but this time

located inside the gold contact. However, the spot is near the tip's end, where current lines concentrate, while some samples look spoiled also far from the sharp part; thus, we spatially averaged the current density also over the whole contact.

Fig. 5: (a) Current density hot-spot at the far end of the gold tip (magnitude in Am^{-2}); the other visible region is the SiO_2 layer (air and Si are modeled, but not rendered in this color map). (b) Average current density in the hot-spot (triangles) and over the whole tip (stars) with interpolating curves

In Fig. 5b we report the results for current density, averaged over the hot-spot (triangles) and whole tip (stars). The hot-spot density decreases with increasing contact separation, with a steeper slope in the first part and getting asymptotically closer to a plateau, in the second part; a knee could be located around 100 nm. The reason for this non-uniform descent is that, with small contact separation, the current density distribution around one tip is greatly affected by the distance from the other tip; 'far' contacts, on the other hand, asymptotically resemble a single tip configuration. The electric field-vs.-separation curve (not reported) looks qualitatively similar. The situation is different with current density averaged over the whole tip, where the dependence on the contact distance is less pronounced. This behavior means that the applied voltage-vs.-separation law, obtained by the experiments, is the result of a nearly constant mean current density in the contact. These results provide an indication that breakdown is triggered by a critical level of current density. According to our simulations, such level should be fixed between 300 and 400 A/m^2 . These values cannot generate an electromigration process, since the typical current densities involved are at least 10 orders of magnitude larger [17] than the one we found. The most likely explanation is that current triggers a chemical etching of the contacts, possibly starting from 'weak points' such as bubble defects in the metallic electrodes [18]. This process can cause the contact to blow up and the degradation of the molecular layer.

5. CONCLUSIONS

In conclusion, we demonstrated a transistor based on a deoxyguanosine derivative and a protein FET exploiting the redox and self-assembly properties of the metallo-protein azurin, both operating at room temperature and ambient condition. The novelty of both the active material and the transport mechanism makes such devices very interesting for molecular electronics application.

Acknowledgements: We are thankful for the invaluable support and exciting collaboration with various colleagues. We would like to thank Elisa Molinari, Rosa Di Felice, Francesca De Rienzo, Paolo Facci at S³-INFM research center in Modena (Italy), Gerard Canters and Martin Verbeet at Leiden University (NL), Salvatore Masiero, Tatiana Giorgi, Gianpiero Spada and Giovanni Gottarelli at University of Bologna (Italy).

Financial support by NNL-INFM, by the Italian Ministry of University and Research (MIUR) through the FIRB project “molecular nanodevices” and by EC through SAMBA project are gratefully acknowledged.

References

- [1] Joachim, C., Gimzewski, J.K., and Aviram, A., 2000 Nature 408, p.541;
- K.S.Kwok and J. Ellenbogen, Materials Today, Feb. 2002, p.28;
- M.A. Reed, J.Chen, A.M.Rawlett, D.W.Price and J.M.Tour, “Molecular random access memory cell”, *Appl.Phys.Lett.*, 78, 3735-3737, 2001
- [2] R.Metzger, *Chemical Review*, Oct. 2003
- [3] R.Rinaldi, A.Biasco, G.Maruccio, R.Cingolani, D.Alliata, L.Andolfi, P.Facci, F.De Rienzo, R.Di Felice, E.Molinari, 2002, “*Solid-State Molecular Rectifier based on self-assembled metalloproteins*”, Adv. Mater. 20, p.1453, R.Rinaldi, A.Biasco, G.Maruccio, V.Arima, P.Visconti, R.Cingolani, P.Facci, F.De Rienzo, R.DiFelice, E.Molinari, M.Ph Verbeet, G.W.Canters, 2003, *Appl. Phys. Lett.* 82, p.472; D. Porath, A. Bezryadin, S. de Vries and C. Dekker, Nature (London) 403, 635 (2000)
- [4] G.Gottarelli, S.Masiero, E.Mezzina, G.P.Spada, P.Mariani and M.Recanatini, *Helv.Chim.Acta*, **81**, 2078, 1998
- [5] G.Gottarelli, S.Masiero, E.Mezzina, S.Pieraccini, J.P.Rabe, P.Samori and G.P.Spada, *Chem.Eur.J.*, **6**, 3242, 2000; R.Rinaldi, G.Maruccio, A.Biasco, V.Arima, R.Cingolani, T.Giorgi, S.Masiero, G.P.Spada and G.Gottarelli, *Nanotechnology* **13**, 398-403 (2002)
- [6] G. Maruccio, P.Visconti, S.D’Amico, P.Calogiuri, E.D’Amone, R.Cingolani, R.Rinaldi, Planar nanotips as probes for transport experiments in molecules. *Microelectronic Engineering* 67-68, 838-844 (2003)
- [7] E.T. Adman, R.E. Stenkamp, L.C. Sieker and L.H. Jensen, *J. Mol. Biol.* 123 (1978) 35.
- [8] M.A. Webb, C.M. Kwong and G.R. Loppnow, *J. Phys. Chem.* B101 (1997) 5062.5.
- [9] C.H. Kobler and D.K. Schwartz, *Curr Opin Colloid Interface Sci* 4 (1999) 46.
- [10] B. Schnyder, R. Kotz, D. Alliata and P. Facci, *Surf. Interface Anal.* 34 (2002) 40.7.
- [11] S. Heinze, J. Tersoff, R. Martel, V. Derycke, J. Appenzeller, and Ph. Avouris *Phys. Rev. Lett.* 89 (2002) 106801
- [12] O. Kuhn, V. Rupasov and S. Mukamel, *J. Chem. Phys.* 104 (1996) 5821
- [13] D.N. Blauch and J.M. Saveant, *J. Am. Chem. Soc.* 114 (1992) 3323
- [14] J.Park, A.N.Pasupathy, J.I.Goldsmith, C.Chang, Y.Yaish, J.R. Petta, M.Rinkoski, J.P.Sethna, H.D.Abruna, P.L.McEuen and C.Ralph, Nature 417 (2002) 722

- [15] J. Lee et al., Nano Letters 3, 113-117 (2003) ; C. R. Kagan et al., Nano Letters 3 (2003) 119
- [16] Metzger, R. M.; Chen, B.; Hopfner, U.; Lakshmikantham, M. V.; Vuillaume, D.; Kawai, T.; Wu, X.; Tachibana, H.; Hughes, T. V.; Sakurai, H.; Baldwin, J. W.; Hosch, C.; Cava, M. P.; Brehmer, L.; Ashwell, G. J. J. Am. Chem. Soc 119. (1997) 10455.
- [17] Z. Li, G. Wu, and Y. Wang, *Journ. Mat. Sci. Electr.*, vol. 10, pp. 653-659, 1999.
- [18] P. E. Burrows, V. Bulovic, S. R. Forrest, L. S. Sapochak, D. M. McCarthy, and M. E. Thompson, *Appl. Phys. Lett.*, vol. 65, no. 23, pp. 2922-2924, December 1994.; V. N. Savvate'ev, A. V. Yakimov, D. Davidov, R. M. Pogreb, R. Neumann, and Y. Avny, *Appl. Phys. Lett.*, vol. 71, no. 23, pp. 3344-3346, December 1997.

POLYPHOSPHAZENE NANOFIBERS FOR BIOMEDICAL APPLICATIONS: PRELIMINARY STUDIES

CATO T. LAURENCIN^{1,2,3} AND LAKSHMI S.
NAIR¹

¹Department of Orthopaedic Surgery, University of Virginia,
Charlottesville, VA-22903; ²Department of Biomedical Engineering,
University of Virginia, Charlottesville, VA-22903; ³Department of
Chemical Engineering, University of Virginia, Charlottesville, VA-
22903

Abstract: Polyphosphazenes form novel class of inorganic polymers having backbone composed of phosphorous and nitrogen atoms with each phosphorous atom bearing two organic or organometallic groups. The side groups on phosphorous atoms play a crucial role in determining the properties of corresponding polyphosphazenes. Thus, polymers with unusual thermal, electrical, optical, electrolytic conductivity, electroactivity, oxidative stability, biocompatibility and biodegradability have been synthesized by the incorporation of appropriate side groups. Many of these polymers have been identified as excellent candidates for biomedical and high technological applications. Polymeric nanofibers due to their very high surface area, remarkable surface properties and superior mechanical properties are assuming great interest lately. We have demonstrated that nanofibers of polyphosphazenes can be prepared by electrospinning wherein submicron sized fibers are produced from an electrostatically driven jet of polymer solution. The diameter as well as the morphology of the resulting fibers can be efficiently tuned by varying process parameters such as viscosity of the solution and potential gradient. By combining the advantages of nanoscale fibers with the unusual property profile available with polyphosphazenes, novel materials with excellent properties can be developed.

Keywords: Polyphosphazene, nanofibers, biodegradable.

1. INTRODUCTION

Nanotechnology is an emerging field which uses the principles of science and engineering to fabricate materials or structures of dimensions in the nanometer scale [1]. The great interest in nanoscale materials spur from the unusual and unique property profile these materials exhibit compared to macromaterials. Novel physical, chemical and biological

properties such as unique shape, orientation, surface chemistry, topology and reactivity exhibited by these materials originate from their small dimensions. These material properties translate into unusual electrical, optical, magnetic, mechanical, thermal and biological properties for these materials. Some of the nanostructures or nanoscale materials currently under investigation include quantum dots and wires, nanoscale self-assemblies and thin films, nanocrystals, nanotubes, nanowires, nanorods, nanofoams, nanospheres and nanofibers. Almost all the classical materials available such as metals, nonmetals, ceramics, organic molecules, organometallics, polymers, biomolecules and composites are actively being investigated for developing these nanoscale materials. Some of the next frontier areas that will benefit from these nano scale materials include nano electronics [2], nano electromechanical devices [2] and nano optical devices [3].

Among the nanostructures discussed above, nanofibers form one of the most extensively investigated areas recently [4]. The word nanofiber refers to fibrous structures usually made of carbon, organic polymers or organometallic polymers with diameter less than one micrometer. This review however, focuses on polymeric nanofibers. Literature shows that polymeric nanofibers can be fabricated using various processing techniques such as drawing [4,5], self assembly [4,6], template synthesis [4,7], phase separation [4,8] and electrospinning [4]. Among these, electrospinning is the most general and simplest technique that can be used to fabricate polymeric nanofibers. The process of electrospinning, initially called electrostatic spinning was first studied by Zeleny in 1914 [9]. The process for developing polymeric fibers via electrostatic spinning was first patented by Formhals in 1934 [10]. Even though there are literature evidences showing work in this area from 1934 onwards, the past few years has seen a renewed interest in polymeric nanofibers and hence the process of electrospinning. This can be attributed to the recent tremendous growth in nanotechnology and also electrospinning forms the simplest and inexpensive way to create ultrafine polymeric fibers.

In electrospinning, a non woven mat of polymeric nanofibers will be created from an electrostatically driven jet of polymer solution. **Scheme 1** shows a general representation of an electrospinning apparatus used to create polymeric nanofibers. The three basic elements of an electrospinning system consist of a high voltage supply (5-40kV), a source electrode and a grounded collector electrode and a capillary tube with a needle of small diameter. Both polymer solution as well as polymer melt can be used to create nanofibers by the process of electrospinning. Briefly, in electrospinning the high voltage electric field is applied to a polymer droplet held by surface tension at the end of the needle. During this process, the polymer droplet gets charged and mutual charge

Scheme 1. Schematic representation of electrospinning apparatus

repulsion within the droplet will give rise to a force that opposes the surface tension. At a critical voltage, the droplet elongates to form a cone called Taylor cone at the tip of the needle [11]. When the applied voltage exceeds the critical voltage, the electrical force within the liquid overcomes the surface tension forces and a fine jet of polymer emerges from the cone. The viscosity of the polymer solution/melt is very crucial in producing nanofiber from the emerging jet. In the case of solutions with low viscosity, the emerging jet breaks into droplets due to surface tension and the process is called electrospraying. However, in the case of high viscosity solutions, the emerging jet does not break into droplets. The charged polymer jet will be directed to the grounded electrode and it has been found that the path taken by the jet to the grounded electrode is not straight instead it undergoes a whipping motion resulting in a progressive decrease in the diameter of the jet. As the jet travels in air, the solvent evaporates, leaving behind a charged polymer fiber which is collected as a non woven mat on the collecting screen.

Several parameters affect the process by which polymer solutions are converted into nanofibers. As discussed before the viscosity of the solution plays a very important role in the formation of nanofibers from polymer solutions. The parameters that affect electrospinning can be broadly classified into 1. polymer solution parameters such as viscosity, conductivity/polarity and surface tension of the solution, 2. process parameters such as applied electric potential, the distance between the needle tip and the collecting screen, size of the needle tip, feed rate and the hydrostatic pressure applied to the polymer solution and 3. ambient parameters such as temperature, air velocity and humidity of the

electrospinning chamber [4,12,13] . Studies are currently undergoing to develop mathematical models that could possibly predict the effect of these parameters on the electrospun polymer fibers [4, 14].

The characteristics of electrospun nanofibers that are of great interest are the fiber diameter and the surface morphology. It has been found that the fiber diameter obtained by electrospinning depends on the viscosity of the polymer solution as well as the electrical potential applied.

More than about 40 different polymers (natural and synthetic) have been electrospun so far [4]. However, studies show that the electrospinning parameters for each of these polymer systems varies depending on the polymer as well as the nature of the solvent system used. So parameters should be optimized for each polymer system. Moreover, conventional electrospinning process always results in the formation of nonwoven mat with no orientation. Attempts are currently underway to develop uniaxial polymer fiber bundles via electrospinning even though it is a difficult target to achieve due to the whipping motion of the polymer jet during spinning [4,15,16].

The properties of nanofibers such as fiber diameter, diameter distribution and surface morphology are usually characterized using scanning electron microscopy (SEM) [4]. Other techniques employed for fiber characterization include transmission electron microscopy (TEM) and atomic force microscopy (AFM). The surface chemistry of the electrospun nanofibers can be determined by techniques such as X-ray photoelectron spectroscopy (XPS), contact angle measurements and by Attenuated total reflectance Fourier transform infra red spectroscopy (FTIR-ATR). The structures of the polymer molecules within the nanofibers can be characterized by Fourier transform infra red spectroscopy (FTIR) and Nuclear magnetic resonance (NMR). The formation of thin polymer fibers from polymer solution usually changes the orientation of polymer chains. The configuration of the polymer chains in the nanofiber is usually determined by differential scanning calorimetry (DSC), wide angle X-ray diffraction (WAXD) and optical birefringence.

2. APPLICATIONS OF POLYMERIC NANOFIBERS

Due to the very small diameter of the polymer fibers obtained by electrospinning, the surface area to volume ratio of the fibers is significantly high. The nonwoven mats formed from nanofibers have very small pore sizes, however, the total porosity of the mats will still be very high. This makes them excellent candidates for use in filtration and membrane application. Due to the high filtration efficiency, the polymer nanofiber based filtration devices are now commercially developed for industrial air filtrations, as filters for gas turbine generators and filters for heavy duty engines. Recently it has been demonstrated that the filtration

efficiency of these membranes can be increased by using charged fibers which would modify the electrostatic attraction of the particles [17].

Electrospinning has the potential to develop into the future fabrication process for developing protective clothing. Optimal protective clothing should satisfy properties such as it should be permeable to both air and water vapor, should be reactive with toxic gases and chemicals, should be insoluble in solvents and should have light weight. As discussed before due to very small pore size of the nanofiber mats, they provide an impermeable barrier to toxic chemical agents. Also the high surface area to volume ratio of the nanofibers enables them to form light weight fabrics with remarkable breathing properties [18].

Due to the simplicity and versatility of the electrospinning process, conductive fibers can be fabricated from polymers with unusual electrical, electronic, ionic, photoelectric and piezoelectric properties. These fibers could be used in the fabrication of novel nanoelectronic devices, nanoelectronic machines and sensors for high technology applications [19].

Another actively investigated area of application of polymeric nanofiber is the biomedical field [4]. Both non degradable and degradable polymers have been investigated for various applications. As early as 1977, it has been proposed that non degradable polymeric nanofibers can be used for developing prosthetic medical devices such as blood vessels and vascular grafts [20]. Recently it has been shown that electrospinning can be used to create porous thin films with structural gradients and controlled morphology on prosthetic devices in order to facilitate the integration of the devices with the body and thereby enhance their biocompatibility. Another potential medical application of non woven polymer nanofibers is in the area of tissue engineering. The role of biomaterial in tissue engineering is to act as a scaffold for the cells to attach to and organize into tissue. The ideal tissue engineering scaffold should mimic the extracellular matrix, the natural abode of cells. The structure and morphology of non woven nanofiber mats closely match the structure of extracellular matrix of natural tissue. Studies have shown that cells seeded on biodegradable polymeric nanofiber mats can attach, proliferate and maintain their phenotype expression [21,22]. Development of nanofiber based three dimensional scaffolds using various biopolymers and synthetic biodegradable polymers has currently become an active area of research. Polymeric nanofibers have also been investigated as novel wound dressing and as haemostatic devices [4]. The high surface area of the nanofiber matrix allows oxygen permeability as well as prevents fluid accumulation at the wound site. On the other hand, the small pore size of the matrix efficiently prevents bacterial penetration making them ideal candidates for wound dressings. Further, flexibility of the electrospinning process allows co-spinning polymers with drugs or proteins thereby making the non woven nanofiber mat as a drug delivery matrix which could enhance wound healing.

3. POLYPHOSPHAZENES

The wide range of organic polymers developed from petrochemical sources has undoubtedly contributed to the advancement of modern science and technology. However, materials with better physical, chemical, mechanical and biological properties are constantly in demand to tune with the requirements of modern technology. The advancement in synthetic organic chemistry and development of novel polymer synthetic routes provide us with a wide array of organic polymer with wide spectrum of properties. However, the organic polymers are associated with some innate drawbacks [23]. Most of the organic hydrocarbon based polymers have low oxidative stability, low resistance to temperature and organic solvents, low fire and light resistance and most of them except polyanilines have low electrical conductivity. In the biomedical field, even though organic polymers are extensively investigated as candidates for various applications, the performance of most of them are far less than optimal. The low thermal, optical and oxidative stability of organic polymers can be attributed to the presence of aliphatic C-C and C-H bonds present in these polymers. On the other hand, inorganic materials such as ceramics combine the properties of high thermal and oxidative stability, high solvent resistance and exhibit high mechanical strength and biocompatibility. However inorganic systems are often associated with high brittleness and low processability. Logically, the development of inorganic polymers with organic substituents is one way to solve most of the problems posed by organic polymers and inorganic materials. Main group elements of group III, IV, V and VI such as aluminum, silicon, phosphorous, sulfur, germanium, arsenic and selenium are ideal candidates for hetero atom polymer formation and these elements can form bonds with other elements which have longer bond lengths than that formed by carbon [24]. The longer bond length in these polymers could impart high flexibility to these polymers compared to organic polymers. The search led to the development of the first synthetic inorganic polymer poly(organosiloxane) by the ring opening polymerization of organocyclosiloxanes in 1940's. The polymer exhibits high flexibility, elasticity, high resistance to temperature and organic solvents, has ease of fabrication and biocompatibility. The initial success led to the development of other inorganic polymer systems such as polysilazenes, polysilanes, polygermanes, polystannanes and polyphosphazenes. Among these, polyphosphazenes form an interesting class of polymer which could develop as promising candidates for high technology and biomedical applications due to their synthetic flexibility and versatile adaptability for applications.

R = alkoxy, aryloxy or amino groups

Scheme 2. General structure of polyphosphazene

Polyphosphazenes are inorganic polymers having a backbone of alternating phosphorous and nitrogen atom and each phosphorous atom is attached to two organic / organometallic side groups [25]. The general structure of polyphosphazene is shown in **Scheme 2**. The synthesis of polyphosphazene involves a two step process: The first step involves the thermal ring opening polymerization of a cyclic trimer, hexachlorocyclotriphosphazene (**Scheme 3; 1**) in the melt at 250°C, to form the linear high molecular weight polymer poly(dichlorophosphazene) (**Scheme 3; 2**). This route was perfected by Allcock and Kugel in 1965 by carefully controlling the time and temperature of the ring opening polymerization [26]. The intermediate, poly(dichlorophosphazene) is

Scheme 3. Scheme showing the ring opening polymerization of hexachlorocyclotriphosphazene

unstable due to the highly reactive phosphorous-chlorine bonds present in it. Consequently, the polymer rapidly hydrolyzes upon exposure to atmospheric moisture to form phosphoric acid, ammonia and hydrochloric acid. The second step in polyphosphazene synthesis is the macromolecular substitution reaction which involves the replacement of reactive chlorine atoms of poly(dichlorophosphazene) with hydrolytically stable

nucleophiles such as alkoxy, aryloxy or amino groups. The synthesis of the first hydrolytically stable, high molecular weight linear polyphosphazene was reported by Allcock et al in 1966 [27]. The high reactivity of phosphorous-chlorine bonds in poly(dichlorophosphazene) enables the replacement of chlorine atoms with a wide range of nucleophiles such as alcohols, phenols, amines or organo-metallic reagents.

Scheme 4. Scheme showing the general route for synthesizing substituted polyphosphazenes from poly(dichlorophosphazene)

This forms the basis of the unprecedented diversity of polyphosphazenes, wherein different polymers can be synthesized from a single macromolecular precursor. Different classes of polyphosphazenes have been synthesized so far by replacing the chlorine atoms of poly(dichlorophosphazene) by alkoxides/aryoxides, primary/secondary amines and organometallic reagents [25]. **Scheme 4** shows the general route for synthesizing substituted polyphosphazenes.

Ring opening polymerization of hexachlorocyclotriphosphazene results in high molecular weight poly(dichlorophosphazene) with broad polydispersities. Attempts were therefore made to develop poly(dichlorophosphazene) with controlled molecular weight and narrow

polydispersity since it is the intermediate from which almost all the polyphosphazenes are currently being made. Thus, an ambient temperature method to synthesize poly(dichlorophosphazene) intermediate with precise molecular weight control and narrow polydispersities by living cationic polymerization of phospharanimines was developed by Allcock et al. [28]. One advantage of the living cationic polymerization route is that the living sites at the ends of the polymer chain offer the possibility for the formation of block co-polymers either with other phosphazene monomers or with organic monomers [29]. In addition to the two step synthetic route described above a direct synthetic route for polyphosphazenes has also been attempted by Allcock et al. It involves the ambient temperature polymerization of mono- and di-substituted organophosphoranimines such as $\text{PhCl}_2\text{P}=\text{NSiMe}_3$ induced by PCl_5 [30].

As in the case of other inorganic polymers discussed before, one versatile property of polyphosphazenes is their unusual backbone flexibility which arises from the torsional and angular freedom within the $-\text{P}-\text{N}-$ skeletal system. Unlike organic systems, the conjugated double bonds in polyphosphazenes are made up of $d\pi-p\pi$ bonds which do not impose severe conformational restrictions upon the molecule since any one of the five phosphorous 3d orbitals can π bond to the nitrogen p-orbitals [31].

Due to the innate skeletal flexibility, the steric and polar interactions of the side groups determine the polymer flexibility and the resulting physico-chemical properties [32]. This offers the opportunity for synthesizing polymers with wide spectrum of properties in terms of crystallinity, solubility, processability, hydrophobicity/ hydrophilicity and biodegradability depending on the nature of the side groups from poly(dichlorophosphazene). Another unique feature of polyphosphazene chemistry is the ability to incorporate two or more different side groups, which could add another dimension, to fine tune the properties of the polymer. Thus, two or more different side groups can be introduced along the polymer chain by simultaneous, sequential or metathetical ligand exchange reaction [33]. More than about 700 different polyphosphazenes have been synthesized so far, by varying the nature and ratios of the side group from a single macromolecular precursor poly(dichlorophosphazene).

The effect of side groups on the nature and properties of resulting polyphosphazenes can be illustrated using examples as below. Poly[bis(trifluoroethoxy)phosphazene] (**Scheme 5: polymer 3**), which in fact is the first stable poly(organophosphazene) made, is a flexible film or fiber forming polymer, soluble in organic solvents and highly water repellent due to the presence of fluorinated side groups. It has a T_g of -66°C and remains flexible from its T_g to its melting point (242°C). The regular packing of the trifluoroethoxy side groups along the polymer chain imparts microcrystallinity and the polymer is thermoplastic. However, the polymer can be easily converted into a useful elastomer by the random

introduction of other fluoro-alcohols along with trifluoroethoxy side groups by simultaneous substitution or using metathetical ligand exchange reaction. These elastomers are potential candidates for developing gaskets, O-rings and low-temperature fuel lines.

Similarly the Tg of polyphosphazenes can be increased by incorporating rigid, bulky side groups which will restrict the main chain mobility, the extent of which depends on the nature and size of the side groups. The highest Tg polyphosphazene synthesized so far is the polymer (**Scheme 5: polymer 4**) with a phenyl phenoxy side groups (Tg 93°C). Incorporation of phenoxy side groups along with phenyl phenoxy side groups (**Scheme 5: polymer 5**) by sequential macromolecular substitution significantly decreases the Tg of the polymer (Tg 43°C) [34].

The alkoxy and aryloxy polyphosphazenes discussed above are soluble in organic solvents. However, the hydrophilicity of polyphosphazenes can be significantly improved by incorporating hydrophilic side groups such as amino groups or alkoxy groups such as polyethylene glycols/glyceryl groups. All the amino phosphazene polymers are film forming thermoplastic polymers with Tg usually higher than alkoxy and aryloxy derivatives. This can be attributed to inter and intra molecular hydrogen bonding possible with these groups which consequently reduce the torsional mobility of the phosphazene backbone. Some of the amino phosphazenes are soluble in aqueous media rather than organic solvents.

The development of amino acid ester polyphosphazenes paved the way for a new class of polyphosphazenes called biodegradable polyphosphazenes [35]. Biodegradable polymers are those which degrade *in vitro* and *in vivo* either into products that are normal metabolites of the body or into products that could be completely eliminated from the body with or without further metabolic transformations. The biodegradable polyphosphazenes undergo hydrolytic degradation resulting in neutral and

Scheme 5. Structures of various polyphosphazenes

non toxic degradation products such as phosphates, ammonia and corresponding side groups. It has been found that a variety of aminated and alkoxy side groups can impart biodegradability to polyphosphazenes. Biodegradable aminated polyphosphazenes include polyphosphazenes with side groups such as amino, amino acid ester and imidazole. The rate of degradation of these polymers depends on the nature of the side groups with imidazole substituted polyphosphazenes being the most hydrolytically sensitive phosphazene synthesized. In the case of amino acid ester substituted polyphosphazene the rate of degradation depends on the nature of the ester groups and the α -substituents on the amino acid

ester. Further, it has been demonstrated by Laurencin et al that the rate of degradation of amino acid ester substituted polyphosphazenes can be further modulated by incorporating hydrolytically less sensitive aryloxy groups along with the amino acid ester polyphosphazenes. Thus, it is possible to control the rate of degradation of the polyphosphazenes over periods of hours, days, months or years by carefully controlling the nature and composition of side group substituents. The biodegradable alkoxy substituted polyphosphazenes are those which have side groups such as glyceryl, glycosyl and glycolic or lactic acid esters.

4. BIOMEDICAL APPLICATIONS OF POLYPHOSPHAZENES

The high biocompatibility of polysiloxane, the first commercially developed inorganic polymer raised interest in this class of polymer as biomaterials. The fluorinated polyphosphazene poly[bis(trifluoroethoxy)]phosphazene (polymer **3**) due to its resemblance to Teflon® a biocompatible organic polymer is the first polyphosphazene investigated as a biomaterial. The blood compatibility of polymer **3** (**Scheme 5**) was investigated by Welle et al by coating the polymer onto various surfaces [36]. The study showed the high blood compatibility of polyphosphazene **3** (**Scheme 5**), and this has been attributed to the preferential adsorption of albumin on the surface as well as the lack of denaturation of the adsorbed protein on the surface of polymer **3** (**Scheme 5**). The excellent biocompatibility of many of these polymers has been established by intramuscular implantation in a rat model [37]. Another class of polyphosphazene extensively investigated for biomedical applications is the aryloxy phosphazene (**Scheme 5**: polymer **6**). The high chemical stability of phosphorous-nitrogen backbone coupled with the ease of functionalizing the aromatic side groups makes aryloxy phosphazenes excellent candidates for surface modification and as substrates for immobilizing biologically active molecules [38]. Thus, sulfonated polyphosphazenes have been developed from aryloxy phosphazenes which showed high blood and cytocompatibility *in vitro* [39]. Attempts were also made to develop the blood compatibility of aryloxy polymers by incorporating the biologically active molecule heparin on the surface [40]. The heparin immobilized polyphosphazene showed prolonged blood clotting time which is several-folds higher than the unheparinized polymer. The ease of functionalization of aryloxy phosphazenes makes them preferred candidates for developing carrier matrices for chemotherapeutic drugs as well as other biologically active agents. Several prototypes for chemotherapeutic agents were developed by Allcock et al. based on polyphosphazene carriers [41].

Biodegradable polyphosphazenes such as amino acid ester polyphosphazenes are perhaps the most extensively investigated polyphosphazenes for biomedical application. One of the active area of

research in biomedical field where biodegradable polymers find application is in developing controlled drug delivery systems. The controlled drug delivery systems are aimed to achieve effective therapies using a drug by partially or completely eliminating the potential for under or overdosing of drugs commonly associated with traditional drug administration. The synthetic flexibility and non toxicity of degradation products makes polyphosphazenes potential candidates for the development of polymer drug conjugates [35]. Several biodegradable polyphosphazene drug conjugates were developed which include steroids such as dexamethasone, estrone and 17β -estradiol, anesthetics such as procaine and chlorprocaine as well as anti-inflammatory drugs such as naproxen have been immobilized and released in a controlled manner by the hydrolytic degradation of the backbone.

Polymeric monolithic drug delivery systems where drug is dispersed throughout the matrix polymer is the most extensively investigated controlled drug delivery system so far. The rate of drug release from such a system depends on a multitude of factors such as nature of the polymer matrix, matrix geometry, nature of drug, initial drug loading and drug-matrix interaction if any [42]. Most of the initially developed monolithic devices were two dimensional (2-D) matrices where, drug is dispersed in a thin film of the polymer. However, the 2-D matrices suffer from the disadvantage that they need to be implanted in the body. Therefore, various other dosage forms such as microspheres and nanospheres were later developed which could be administered via parenteral routes. The microsphere based drug delivery system has been extensively investigated for the controlled delivery of various drugs such as anti-inflammatory agents, anticancer agents, antibiotics, hormones, steroids and vaccines. Many of these delivery systems are currently available in the market. In order to form an ideal candidate for developing a drug delivery system, the polymer should be biodegradable, degradation products should be non-toxic, have appropriate solubility, ease of fabrication and have appropriate degradation rate. Biodegradable polyphosphazene due to its synthetic flexibility and neutral and non-toxic nature of the degradation products has the potential to develop as an ideal candidate for fabricating drug delivery systems [35]. The initial studies using monolithic polyphosphazene drug delivery systems were carried out by Laurencin et al.[43]. The copolymer poly[(imidazolyl)(p-methyl phenoxy)phosphazene] was used to develop a delivery system for progesterone and the efficacy was evaluated *in vitro* and *in vivo* using a rat model. The rate of release of the drug from these matrices was modulated by varying the ratio of the imidazolyl and p-methyl phenoxy groups in the polymer. It has been found that increasing the amount of imidazolyl side groups in the polymer significantly increases the rate of degradation of the polymer and consequently the release of drug from the matrix. Followed by this several monolithic drug delivery systems for anti-inflammatory agents and antibiotics have been developed using various amino acid ester

polyphosphazenes. The high solubility and processability allows the fabrication of these polymers into microsphere monolithic devices using various processing techniques such as emulsion/solvent evaporation or solvent emulsion/extraction-evaporation and spray drying [44].

Due to its high matrix permeability, biodegradable polyphosphazenes can form potential candidates as protein delivery vehicles [35]. The feasibility of using polyphosphazenes as delivery vehicle for macromolecules was first demonstrated by Laurencin et al using poly[(imidazolyl)(p-methyl phenoxy)phosphazene] and bovine serum albumin (BSA) as the model drug [43]. Controlled delivery of various macromolecules such as insulin, inulin and dextran has been investigated so far using different biodegradable polyphosphazenes [35].

Over the last decade considerable efforts are going on to engineer/develop tissues *in vitro* which can specifically meet the needs of individual patients to circumvent the problems associated with autografts and allografts. Tissue engineering is now considered as a novel therapeutic strategy to repair or reconstruct damaged tissues or organs. Tissue engineering has been defined as the application of biological, chemical and engineering principles towards the repair, restoration or regeneration of living tissues using biomaterials, cells and factors alone or in combination [45]. Biodegradable polymers are usually employed as biomaterials in tissue engineering. The role of the biomaterial is to provide a three dimensional scaffold onto which cells can grow and organize into tissue. The biomaterial should satisfy certain criteria to be considered as appropriate candidate for tissue engineering applications. The material should be biocompatible and have appropriate mechanical properties to provide structural support to cells, depending on the corresponding tissues to be developed. The rate of degradation of the polymer is also very crucial and should match the rate of matrix synthesis *in vitro/in vivo* by the cells. The processability of the material in order to form a 3-D matrix is also important, since the volume of tissue that can be developed using the scaffold depends on the pore size and pore tortuosity of the matrix developed. The wide range of degradation rate, wide spectrum of properties, ease of processability and the neutral and non-toxic degradation products of polyphosphazenes make them potential candidate as scaffolds for tissue engineering.

The first attempt towards using biodegradable polyphosphazenes for tissue engineering was carried out by Laurencin et al [46]. They investigated various amino acid ester polyphosphazenes as candidate materials for bone tissue engineering. It has been found that the rate of cell adhesion and proliferation significantly depends on the nature of the side groups present and rate of degradation of the polymer. Thus the rate of adhesion of osteoblasts on the homopolymer poly[bis(ethyl glycinato)phosphazene] was found to be low even though the polymer as well as the degradation products was found to be non-toxic to cells. This has been attributed to the high rate of degradation of the polymer.

However, by modulating the degradation rate of ethyl glycinato polymer by incorporating hydrolytically less sensitive groups such as p-methyl groups in polymer poly[(ethyl glycinato)(p-methyl phenoxy)phosphazene], the rate of cell adhesion was found to be significantly improved [47]. In many formulations, the number of cells present on polyphosphazenes was found to be higher than tissue culture polystyrene (TCPS). The ease of processability of these polymers was demonstrated by developing a three dimensional (3-D) matrices of poly[(50% ethyl glycinato)(50%p-methyl phenoxy)phosphazene] via salt leaching. After 21 days of incubation of osteoblast like cells (MC3T3-E1) on 3-D and 2-D matrices as well as TCPS, the number of cells on the 3-D matrices were found to be significantly higher than that found in 2-D polyphosphazene matrices as well as TCPS [48]. The high *in vivo* osteocompatibility of the above mentioned polyphosphazenes were demonstrated using a 5 mm defect model in rabbit [49]. Other biodegradable polyphosphazenes investigated for tissue engineering application includes poly[bis(ethyl alanato)phosphazene] and poly[(ethyl alanato)(imidazole)phosphazene] as conduits for nerve regeneration and poly[(80% phenyl alanine ethyl ester)(20% imidazole)phosphazene] for guided tissue regeneration in the periodontal cavity [50].

5. NANOFIBER MATRICES FOR TISSUE ENGINEERING AND DRUG DELIVERY

As discussed earlier, the architecture of non woven nanofiber matrices, due to their structural similarity to natural extracellular matrix could present an ideal substrate on which cells can adhere, proliferate and organize into tissue. Further, the high surface area to volume ratio of the fibers can lead to high rates of delivery of drugs or bioactive molecules from these matrices making them potential candidates for developing controlled drug delivery systems. In our initial studies we have used a commercially available FDA approved biodegradable polymer poly(lactide-co-glycolide) (PLGA) to develop nanofiber based devices for tissue engineering and drug delivery. Nanofibers of PLGA were prepared by the process of electrospinning discussed earlier, using a solvent system consisting of 1:1 tetrahydrofuran and dimethylformamide [21]. Ultrafine fibers of diameters in the range 500-800 nm were obtained by the process. **Figure 1** shows the SEM of electrospun non woven mat of PLGA.

Figure 1. SEM showing the nanofibers of PLAGA
[Reprinted from Li et al (21)]

The mechanical properties of the electrospun non woven mats of PLAGA were evaluated and have been found to be comparable to those of human cartilage and bone. The ability of cells to attach and proliferate on the scaffold was evaluated using mouse fibroblast cells. It has been found that the macroporous nanofibrous structure, due to the high surface area, allows for high cell adhesion and proliferation. **Figure 2** shows the SEM of mouse fibroblast cells on PLAGA nanofiber mat after 3 days of culture. However, it has been found that by 7 days of culture, the cell number plateau on the PLAGA nanofiber scaffolds. According to the authors, one possible reason for this observation is that the acidic degradation products of PLAGA may be hindering the cell proliferation. The nanofiber structure, due to the high surface area to volume ratio, would significantly increase the rate of degradation of the polymer. This would decrease the local pH of the environment due to the acidic nature of PLAGA degradation products.

This shows the pressing need to develop novel biodegradable polymer systems which degrade to non toxic degradation products, for the development of nanofiber based matrices for biomedical application. Biodegradable polyphosphazenes due to the non-toxic and neutral degradation products and other versatile properties discussed earlier could form a potential candidate for developing nanofiber based scaffolds for tissue engineering. We have recently demonstrated (US Patent pending)

Figure 2. SEM showing the mouse fibroblast cells on PLAGA nanofiber mat developed by electrospinning after 3 days of culture [Reprinted from Li et al (21)]

the ability to develop nanofibers from a wide range of non degradable and degradable polyphosphazenes via electrospinning. It has been found that diameter and morphology of the resulting fibers depends on various process and solution parameters that effect electrospinning technique as discussed earlier, however the optimal parameters vary with each polymer system. **Figure 3** shows the electrospun nanofibers obtained from a non degradable polyphosphazene poly[bis(methyl phenoxy)phosphazene]. It can be seen that defect free nanofibers with smooth surface morphology having diameters varying from 0.5-1 μ m can be obtained from electrospinning the polymer under optimized conditions (**Figure 3**). It has been found that the same electrospinning process can be extended to other non degradable polyphosphazenes of biomedical interest such as poly[bis(carboxylato phenoxy)phosphazene] (PCPP) and poly[bis(phenoxy)phosphazenes]. Some of the biodegradable polyphosphazenes electrospun so far include various amino acid ester polyphosphazenes and the copolymers of amino acid ester phosphazenes where, the degradation rate of the polymers has been modulated by the incorporation of various aryloxy side groups. The electrospinning process also enabled us to co-spin polyphosphazenes with other polymers as well as low molecular weight drugs or other nanoparticles. These composite nanofiber matrices will allow us to develop novel drug delivery systems, wound dressings or tissue engineering scaffolds based on polyphosphazenes for biomedical applications.

Figure 3. SEM showing the nanofibers of poly[bis(methyl phenoxy)phosphazene].

6. CONCLUSIONS

Polyphosphazene nanofibers which combine the versatile property profile and biocompatibility of the base polymer and the amazing characteristics of the nanostructure could form potential candidates for various biomedical applications. Current work is in progress in our laboratory to develop nanofiber matrices from polyphosphazenes of appropriate physical, chemical, mechanical and biological properties and evaluate their performance as scaffolds for regenerating a broad range of tissues *in vitro* and *in vivo*.

Acknowledgement: Authors acknowledge NIH#46560 for financial assistance.

References

1. Nalwa, H.S., Handbook of nanostructured materials and nanotechnology, Academic Press, San Diego, 2000.
2. Krupke R., Hennrich F., Lohneysen H.V., Kappes M.M., Separation of Metallic from semiconducting single walled carbon tubes. *Science* 2003; 301:344-47.
3. Joannopoulos J.D., Villeneuve P.R., Fan S. *Nature* 1997; 386:143-
4. Huang Z.M., Zhang Y.Z., Kotaki M., Ramakrishna S. A review on polymer nanofibers by electrospinning and their applications in nanocomposites. *Composites Science and Technology* 2003;63:2223-53.
5. Ondarcuhu T., Joachim C. Drawing a single nanofibre over hundreds of microns. *Europhys Lett* 1998; 42:215-20.
6. Whitesides G.M., Grzybowski B. Self-assembly at all scales. *Science* 2002; 295:2418-21.
7. Martin C.R. Membrane-based synthesis of nanomaterials. *Chem Mater* 1996;8:1739-46.
8. Ma P.X., Zhang R. Synthetic nano-scale fibrous extracellular matrix. *J Biomed Mater Res* 1999;46:60-72.
9. Zeleny J. *Phys Rev* 1914;3:69-91.
10. Formhals A. US patent 1,975,504, 1934.

11. Taylor G.I. Disintegration of water drops in an electric field. *Proc R. Soc London, Ser A* 1964; 280:383-397.
12. Zong X., Kim K., Fang D., Ran S., Hsiao B.S., Chu B. Structure and process relationship of electrospun bioabsorbable nanofiber membranes. *Polymer* 2002;43:4403-12.
13. Deitzel J.M., Kleinmeyer J., Harris D., Beck Tan N.C. The effect of processing variables on the morphology of electrospun nanofibers and textiles. *Polymer* 2001;42:261-72.
14. Abdel-Ghani M.S., Davies G.A. Simulation of non-woven fiber mats and the application to coalescers. *Chemical Engineering Science* 1985;40:117-29.
15. Matthews JA, Wnek GE, Simpson DG, Bowlin GL. Electrospinning of collagen nanofibers. *Biomacromolecules* 2002; 3:232-38.
16. Theron A., Zussman E., Yarin A.L. Electrostatic field-assisted alignment of electrospun nanofibers. *Nanotechnology* 2001;12:384-90.
17. Tsaia P.P., Schreuder-Gibson H., Gibson P. Different electrostatic methods for making electret filters. *Journal of Electrostatics* 2002; 54:333-41.
18. Smith D., Reneker D.H. PCT/US00/27737, 2001.
19. MacDiarmid A.G., Jones W.E., Noris I.D. et al. Electrostatically generated nanofibers of electronic polymers. *Synthetic Met* 2001; 119:27-30.
20. Martin G.E., Cockshott I.D., Fildes F.J.T. US patent 4044404, 1977.
21. Li W.J., Laurencin C.T., Caterson E.J., Tuan R.S., Ko F.K. Electrospun nanofibrous structure: A novel scaffold for tissue engineering. *J Biomed Mater Res* 2002;60:613-21.
22. Yoshimoto H., Shin Y.M., Terai H., Vacanti J.P. A biodegradable nanofiber scaffold by electrospinning and its potential for bone tissue engineering. *Biomaterials* 2003; 24: 2077-82.
23. Allcock H.R. Polyphosphazenes, and the inorganic approach to polymer chemistry. *Sci Prog Oxf* 1980;66:355-69.
24. Allcock H.R. "Inorganic macromolecules and the search for new electroactive and structural materials" In *Design of New Materials*, Cocke D.L and Clearfield A, eds, Plenum Publishing Corporation, 1987.
25. Allcock H.R. *Chemistry and Applications of Polyphosphazenes*. Wiley Interscience, New Jersey, 2002
26. Allcock H.R., Kugel R.L. Synthesis of high polymeric alkoxy and aryloxy phosphonitriles. *J Am Chem Soc* 1965;87:4216-17.
27. Allcock H.R., Kugel R.L., Valan K.J. Phosphonitrilic compounds. VI. High molecular weight polyalkoxy-and aryloxy phosphazenes. *Inorg Chem* 1966;5:1709-15.
28. Allcock H.R., Crane C.A., Morrissey C.T., Nelson J.M., Reeves S.D., Honeyman C.H., Manners I. Living cationic polymerization of phosphoranimines as an ambient temperature route to polyphosphazenes with controlled molecular weights. *Macromolecules* 1996; 29:7740-47.
29. Allcock H.R., Reeves S.D., Nelson J.M., Crane C.A., Manners I. Polyphosphazene block copolymers via the controlled cationic, ambient temperature polymerization of phosphoranimines. *Macromolecules* 1997;30:2213-15.
30. Allcock H.R., Nelson J.M., Reeves S.D., Honeyman C.H., Manners I. Ambient temperature direct synthesis of poly(organophosphazenes) via the living cationic polymerization of organo-substituted phosphoranimines. *Macromolecules* 1997;30:50-53.
31. Allcock H.R. Inorganic macromolecules: Developments at the interface of inorganic, organic and polymer chemistry. *Chem Eng News* 1985;63:22-36.
32. Allcock H.R., Connolly M.S., Sisko J.T., Al-Shali S. Effects of organic side group structures on the properties of poly(organophosphazenes). *Macromolecules* 1988; 21:323-34.
33. Allcock H.R. Poly(organophosphazenes)-Unusual new high polymers *Angew Chem Int Ed Engl* 1977;16:147-56.

34. Allcock H.R., Mang M.N., Dembek A.A., Wynne K.J., Poly[(aryloxy)phosphazenes] with phenylphenoxy and related bulky side groups. Synthesis, thermal transition behavior and optical properties. *Macromolecules* 1989;22:4179-90.
35. Lakshmi S., Katti D.S., Laurencin C.T. Biodegradable polyphosphazenes for drug delivery applications. *Adv Drug Delivery Rev* 2002;55:467-82
36. Welle A., Grunze M., Tur D. Blood compatibility of poly[bis(trifluoroethoxy)phosphazene]. *J Appl Medical Polym* 2000;4:6-10.
37. Wade C.W.R., Gourlay S., Rice R., Hegyeli A., Singler R., White J. Biocompatibility of eight poly(organophosphazenes) In: *Organometallic polymers*, Carraher C.E., Sheats J.E., Pittman C.U., Editors., Academic Press, New York, 1978.
38. Allcock H.R., Morrissey C.T., Way W. K., Winograd N. Controlled formation of carboxylic acid groups at polyphosphazene surfaces: oxidative and hydrolytic routes. *Chem Mater* 1996;8:2730-38.
39. Allcock H.R., Fitzpatrick R.J. Sulfonation of (aryloxy) and (arylamino) phosphazene: Small molecule compounds, polymers and surfaces. *Chem Mater* 1991;3:1120-32.
40. Neenan T.X, Allcock H.R. Synthesis of a heparinized poly(organophosphazene). *Biomaterials* 1982;3:78-80.
41. Allcock H.R., Neenan T.X., Kossa W.C. Coupling of cyclic and high polymeric (aminoaryloxy)phosphazenes to carboxylic acids: Prototypes for bioactive polymers. *Macromolecules* 1982;15:693-96.
42. Mathiowitz E, *Encyclopedia of Controlled Drug Delivery*. New York, John-Wiley, 1999. .
43. Laurencin C.T., Koh H.J., Neenan T.X., Allcock H.R., Langer R. Controlled release using a new bioerodible polyphosphazene matrix system. *J Biomed Mater Res* 1987;21:1231-46.
44. Veronese F.M., Marsilio F., Caliceti P., De Filippis P., Giunchedi P., Lora S., Polyorganophosphazene microspheres for drug release: polymer synthesis, microsphere preparation, in vitro and in vivo naproxen release. *J Controlled Rel* 1998; 52:227-37.
45. Laurencin C.T., Ambrosio A.A., Borden M.D., Cooper J.A. Tissue Engineering: Orthopaedic Application: In : *Annual Review of Biomedical Engineering* Yarmuch M.L., Palo Alto, editors., Annual Reviews Inc. 1999.
46. Laurencin C.T., Morris C.D., Jacques H.P., Schwartz E.R., Keaton A.R., Zou L. Osteoblast culture on bioerodible polymers: Studies of initial cell adhesion and spread. *Polym Adv tech* 1992;3:359-64.
47. Laurencin C.T., Norman M.E., Elgendy H.M., El-Amin S.F., Allcock H.R., Pucher S.R., Ambrosio A.A. Use of polyphosphazenes for skeletal tissue regeneration. *J. Biomed Mater Res.* 1993;27:963-73.
48. Laurencin C.T., El-Amin S.F., Ibim S.E., Willoughby D.A., Attawia M.A., Allcock H.R., Ambrosio A.A. A highly porous 3-dimensional polyphosphazene polymer matrix for skeletal tissue regeneration. *J. Biomed Mater Res.* 1996;30:133-38.
49. Laurencin C.T., Ambrosio A.M.A., Bauer T.W., Allcock H.R., Attawia M.A., Borden M.D., Gorum W.J., Frank D. The biocompatibility of polyphosphazenes. Evaluation in Bone, Soc for Biomat. 24th annual meeting in conjunction with 30th international symposium, 1998 April 22-26, San Diego, CA.
50. Aldini N.N., Fini M., Rocca M., Martini L., Giardino R., Caliceti P., Veronese F.M., Lora S., Maltarello M.C. Peripheral nerve reconstruction with Bioabsorbable polyphosphazene conduits. *J Bioact Comp Polym* 1997;12:3-13.

BIONANOCOMPOSITES BASED ON NANO-CARBON MATERIALS FOR CULTURE CELLS MEDIA

LUMINITA STAMATIN*, IOAN STAMATIN**

* "Longhin Scarlat" Dermato- Venereology Clinical Hospital,
Biocomposites & Sensors Lab, Serban Voda, 214, Bucharest

** University of Bucharest, Faculty of Physic Diamond films,
Plasma Polymerization & Novel Carbon lab, Bucharest- Magurele
MG-11, Romania

Abstract: This study focused on an appropriate bionanocomposite, containing nano-carbon, to replace the cells culture media with aim to find a rapid answer to staphylococcal infections this study enlarges implications, which the nanoparticles may have in our daily life. The interrelations nanoparticles - environment- microbes development are taken in account.

Keywords: Bionanocomposites, nanocarbons, cell biology, environment

1. INTRODUCTION

The diversity of micro-particles, existent in dust or as aerosols often influences the microbe's development and infectious diseases spreading. Micro-particles and aerosols from the industrial activity induce a large disease class: mines (silicoses), paper printing (the lead disease), diamond micro/ nano-powder (lung caverns) etc. Once with the advances in materials nanotechnology and electronic at nanometric scale have appeared a large class of nanopowders and nanometric devices dimensional compatible with biological structures. Accidentally or not, they escape to environment direct from industry, cars, or human activity. If they have or do not a major influence to the people healthy is the question, to which the scientific world is trying to find answers. It is worthy of note that nanoparticles may have an unimaginable impact on cells/microbes and viruses, owing to their reactivity and the photo-catalytic influence in environment. Nanoparticles can modify the growth rate of the microbes like staphylococcus and streptococci revealed by this contribution. The aim is to find useful applications with carbon nanoparticles to get timed information about microbes in a disease. In particular, a nanocarbon-based bionanocomposite (BNC) for the culture cell media has been designed. Any microbial specie involved in cutaneous pathology (a particular case) need to be identified, after they grow in a culture media for 24h in a thermostat at 37°C. Further, biochemical tests and the antibiotic response assessment give a medical treatment. Unfortunately takes more than 2 days and clinical analysis claim a short evaluation. Also in any place, it is need to have a rapid evaluation of the microbial attack and their virulence. The actual

active media, used for the bacteria growing and identification, are complex gels with specific nutritive elements and indicators, which define if a microbial class is present. The species into a class need more biochemical investigations. The need to have a rapid response in clinical analysis impose the designing of new materials where bacteria should be seeded and identified in same day if not possible shorter. The bionanocomposites based on nanocarbons (gel-nanocarbons mixed in a proper way at nanometric level) speed up the microbes growing, especially aerobic bacteria. They give shorter response if a bacteria colony is in development and specifying, by pigmentation, which kind of infection took place (in this case *Staphylococcus Aureus*). The method proved to be useful in bio-analytical and clinical laboratory methods for staphylococcal infection. The first preliminary observations when was started with nanocarbon insertion into a cell culture media have been: microbes grow faster, the colonies are much more developed, different type of microbes have more or less affinity to nanocarbon (carbon black and active-coal are not so specific in effects). At a glance seems to be nothing new than a simple add-on of growth centers. The carbon in forms of active-coal and carbon black has been used long time in drug delivery and curative aim. The nanocarbon resulted from laser or CVD pyrolysis is quite different as carbon-black. With an apparently similarity in turbostratic organization the LPNC (laser pyrolysis nanocarbon) is much more rich in free bonds and hydrogen adsorbed on its surface. It can be defined oxygen-free NC. In contact with oxygen, nanocarbons absorb large quantities becoming a good supplier for aerobic bacteria. Nanocarbons exist in environment from amorphous to fullerene-like structures and many common features are with the synthesizable one. Three directions arise: 1. The carbon nanoparticles have a major role in the interaction with living cells and with unpleasant microbes or viruses. 2. The carbon particles from micrometric to nanometric level, dispersed in atmosphere, are compatible vectors to transport microbes and interact with the skin (an excellent natural culture media for microbe growing and then attack to human body). 3. The environment is "full" of micro and nanoparticles of different species compatible or not with viruses and bacteria. Each particle is a possible vector to transport them. Are nanoparticles benign or actives? Bionanocomposites (BNC), special designed for culture cell media, are usefully instruments to analyze these kinds of nanoparticles and their role giving good results in much more shorter time. In our particular case BNC were used to clinical diagnostic in dermatology. Many pathogen agents (bacteria, fungi, parasites) are involved and a fast and clear diagnostic is sometimes impossible without a precise laboratory analysis. The status in this field consists of a gel media (culture media) where bacteria are grown at all with no specificity in identification. In next step the biochemical analysis are approached for identifications. *The study one of the most aggressive pathogens, Staphylococcus Aureus (Gram-positive pathogen agent), given us a perspective to interrelate data with bionanocomposites based on different species of nanocarbons and to make a projection to environment implications.* The results with BNC based on nanocarbon species for microbe's growing, implied in a large class of infectious diseases are pre-

sented. In addition, a collection of nanocarbon typology, with features close to what is finding atmosphere is given.

2. EXPERIMENTAL DETAILS

2.1 Nanocarbons with Compatible Features as Those in the Environment

Carbons resulted from pyrolysis of organic precursors at moderate temperature ($<1700^{\circ}\text{C}$) are usually called carbon blacks. All are under 100 nm. They are often described as amorphous or graphitic (turbostratic structures). As a primary definition, they are forms with irregular arrangement of its carbon atoms and a randomized arrangement of graphene can be considered. Sometimes they contain polynuclear hydrocarbon (fused aromatic rings or interconnected rings with sp^3 and sp^1 carbon chains). Carbon blacks may be produced by different techniques, low-tech [5] (incomplete burning of hydrocarbons like methane, acetylene, oil) and high-tech (laser pyrolysis and thermal assisted-CVD) [5-7]. The variety of the synthesis techniques give results in many morphological forms of carbon particles with diameters in a typical range of 10-100 nm. The multi-scale organization (structure, micro-texture, texture) of carbons resulting from pyrolysis of organic precursors at moderate temperature ($<1400^{\circ}\text{C}$) is not yet fully understood, despite numerous works carried out for half a century. These carbons are frequently met in nature or synthesized for industrial applications (blast furnace cokes, active carbon). The nanocarbons are very hard graphitizing like any amorphous carbon (over 2500°C), good criteria for appreciation the level of organization in its structure. Studies based on X-rays techniques and transmission electron microscopy (TEM), have introduced the concept of basic structural units (BSU) [18,19-21]. Such carbons described as elemental bricks were constituted by stacking a few aromatic layers of nanometric size. The BSU size was usually considered as quasi-constant, in the entire carbonization temperature range. It must be noticed that only BSU (intuitively, sufficiently organized as stacks of graphene layers) give the 002 diffracted beams used in X-ray diffraction (XRD) or in the dark-field and lattice fringe TEM modes. The multi-scale organization, of nanocarbons [20], is studied over more than six orders of magnitude by using successively different techniques. The structure (organizational the atomic scale) and micro-texture (spatial distribution of the aromatic layers) can be directly observed by HRTEM, due to its high-resolution mode allowing imaging the profile of the aromatic sheets. Table 1, sketches the most representatives nanocarbons considered for study with designed bionanocomposites. For convenience, there is assigned carbon black (CB) that nanocarbon produced with low-tech (including that of engine gas exhaust or furnace) and nanocarbon that is produced with high-tech methods (NC). Some of the representative features with TEM for four classes, sketched in figure 1, are as follows ; regular carbon black, turbostratic of laser pyrolysis with alkenes/ alkynes precursors, with polyaromatics and fullerene fragments content [6] of benzene

precursors produced by LP and of toluene produced by CVD. Consequently, these techniques are blind for a more or less important fraction of possible single layers, pore activity, biological activity. Transmission IR spectra recorded using FTIR spectrometers (Digilab model 2002) at a resolution of 4 cm^{-1} is a good tool to appreciate the composition. The determination allows direct comparison between IR spectra of deposits obtained with different conditions of reaction and if any changes appear with oxidation or oxygen absorption.

Table 1- Nanocarbons compatible with dust and aerosols of environment, used for NBC designing

Type	Source/method	Main feature	Principal components
Regular CB -R	Incomplete burning; oil and gases, acetylenes	The surface area of blacks used for rubber reinforcement ranges (10-150 m ² /g) when determined by nitrogen adsorption that the ultimate black particle have an average diameter of 20 to 300 nanometers.	Oxygen, hydrogen, and sulfur are main impurities. Oxygen and hydrogen are combined chemically with carbon on the surface of the particle. The ratio of hydrogen to oxygen varies with the manufacturing process. In contact (channel) blacks, oxygen content is 2-5% while hydrogen amounts to about 0.5%; in furnace blacks, the oxygen content of the black depends on that of the hydrocarbon feed.
Pigment CB- P	Incomplete burning in furnace with high cyclone	Pigment-grade blacks have surface areas of 300-500 m ² /g.	
NC-LP1 NC- CVD1	Precursors ethylene, butadiene	Turbostratic structures,	Hydrogen adsorbed on surface
NC- LP2	Acetylene with sensitizer	Turbostratic structures	Sulfur and fluorine are in large quantity
NC-LP3 NC-CVD2	Benzene Benzene, toluene,	Fullerene fragments in very small quantity.	Multiple Polyaromatics (PAH)

CB-R & CB-P, mixtures supplied by Research Inst for Electrical Engineering- Advanced research (ICPE-CA). In experiments all samples were sterilized; NC-LP, supplied by National Institute, Laser Plasma and Radiation (NILPRP), Bucharest; NC-CVD, soot synthesized in Diamond films, Plasma Polymerization & Novel Carbon lab.

Nanocarbon samples were deposited on Si-100 using electro-spray technique. The IR spectra, after subtraction of the silicon substrate contribution on samples used in NBC have had typical features: The bands can be assigned to CH and CC bonds, on positions well established for hydrogenated carbon compounds [22, 23]. Three groups are representatives. In the range $2700\text{--}3400\text{ cm}^{-1}$ corresponds to the C-H stretching vibrations. The band at $3040\text{--}3050\text{ cm}^{-1}$ attributed to aromatic compounds is always the most intense; the C-H stretching modes (2970 and 2915 cm^{-1}) of aliphatic compounds are much weaker. A second group of bands, between 1000 and 2000 cm^{-1} comprises essentially the in plane vibration modes of aromatic CC and CH bonds. The emergent bands at 1600 and 1440 cm^{-1} are due to aromatic CC stretching, symmetric and anti-symmetric ring modes, respectively. Both are infrared-allowed here, due to a high level of non-symmetric substitution in the aromatic units as expected from an irregular network of aromatic units. The in-plane bending CH modes give a large bump around of 1150 cm^{-1} . A third group of bands is found, between 600 and 1000 cm^{-1} , characteristic of the aromatic C-H out of plane bending modes. The large intensity of these bands shows the strong aromatic character of the deposits. These modes are very sensitive to the ring sub-

stitution and give rise to three main components according to the number of adjacent hydrogen atoms on a ring.

Figure 1- Nanocarbons from different synthesis sources, TEM features

A. a) CB-R, scale 100nm; b) model for CB, randomized distribution of BSU a CB sphere c) CB heated at 3000K, BSU- circumferential alignment, d) the graphene stacking in CB e) CB partial etched [11,14, 16]; B. NC-LP1-ethylene/acetylene precursors, typical turbostratic structures a) scale 100nm b) 10 nm c), morphological details. d) TEM-phase contrast; C. LP-NC3 of benzene precursor, structure with fullerene like multishell and large quantity of polyaromatics D. NC-CVD2, of toluene precursors, chained structures of nanocarbon spherules

The band at 752 cm^{-1} corresponds to three and four adjacent H, the feature exhibiting two maxima at 839 cm^{-1} and 815 cm^{-1} is due to two adjacent H, and the band at 885 cm^{-1} is attributed to lone H. The corresponding summation bands can be found in the $2000\text{--}1650\text{ cm}^{-1}$ region. Finally, minor bands can be observed in the spectra, due to alkynes groups at 3290 and 2103 cm^{-1} , and to mono and di-substituted aromatic rings as well as olefin groups in the $1200\text{--}400\text{ cm}^{-1}$ region. The samples NC-LP3 and NC-CVD2 did not present the specific lines for any type of fullerene (C_{60} , 1424 and 1183 cm^{-1}) but the figure 1 C and D show some similar fullerene-like multi-shell structures of $20\text{--}30\text{ nm}$. The third band group is not well defined for these structures. When NCs are dispersed and sonicated in PSS9 (see experimental) C-H bands decreased and bands corresponding for three, two and mono adjacent hydrogen vanished with appearance of the bands centered on 1650 cm^{-1} (carbonyls group) and --OH (band centered at 3370 cm^{-1}). The effect was prominent in case of turbostratic structures NC-LP1 and NC-CVD1 weak for NC-LP3 and NC-CVD-2 not relevant for CB-R.

2.2 Culture Media with Nanocarbon

A special gel-containing agar and nutrients was selected. In the reference sample (R) there was added 10ml physiological saline solution 9%0 (PSS9), boiled and poured in Petri dish with all sterile conditions maintained. For a fine dispersion of nanocarbons into gel, an ultrasonically instrument was adapted to a heating source. In 10ml PSS9, nanocarbon was added for a specific weight concentration reported to the reference sample, R. The solution was sonicated for 15 min at room temperature, ultrafiltered on G1-G3 glass and sonicated again at the same time. A very fine nanocarbon dispersed solution can be obtained and particles keep this state without coalescence or sedimentation for long time. In the reference sample, heated in sonic field, they poured the nanocarbon-dispersed solution by using a milliliter syringe with continuous stirring. This stage took 20 min. Finally, the sample is cooled at room temperature and kept in the same condition as the reference sample. A series of 0.01, 0.1 and 1% weight concentrations with nano carbons has been prepared. The nanobio-composites with agar-gel and nanocarbon have all the properties for a culture cell medium. In addition to that, the nano carbon is very finely dispersed in lattice without coalescence. The samples inseminated with *Staphylococcus aureus* bacteria were processed according to the bacteriological protocol: thermostat at 37°C for 24h, ambient conditions. Each hour, optical image microscopy inspected the samples watching the virulence of bacteria growth.

3. RESULTS AND DISCUSSIONS

To reduce the enormous experimental data a trial series was done in a concentrated formula. The interest is to set the minimum concentration level, with any effect, and to set a maximum level where there is any saturation or the inhibition is present. It is typical for *Staphylococcus aureus* (pathogen) in proper conditions to develop colonies with yellow citrine color (pigmentation genesis) and it is more virulent and pathogen when the pigmentation genesis appears in early growth stages. Table2 presents the virulence induced by the three types of nanocarbons with the specific features: carbons of incomplete combustion, turbostratic of alkenes, and aromatics (benzene, toluene), which have in content PAH and fullerene like fragments. Figure 2 presents some exemplars of bacteria colonies grown with BNC containing nanocarbon species with detailed comments of table 2.

Table 2 Qualitative comparison of the virulence in BNC by comparison with reference sample

	0.01%	0.1%	1%
BNC			
CB-R	N. O	M	as in R
CB-P	N.O	M to WD	as in R
NC-LP1	W D	Explosive	Atypical Pigment genesis
NC-LP2	weak	no	no
NC-LP3 & NC-CVD2	atypical shapes	W. D with atypical pigment genesis	Not distinguishable

N.O- sample has same aspect as the reference; M- moderate development but colonies are not well developed ; WD- well developed as in R;

Figure 2. Bacteria colonies grown with BNC containing nanocarbon species

All BNC samples, being seeded in the same conditions according to standard protocol, are compared to the sample R. BNC with CB-R and CB-P did not show any spectacular improvement in the development of fast growing process and no any virulence has been noticed. The analysis of the structure in CB-R (fig.1A) gives details of randomized graphene stacking in small units of crystallites. In graphitized samples, the crystallites are ordered with graphene perpendicular on radius. The oxidizing process induces etching of the side part and active centers at nanopore level are created. Some impurities originated from raw materials, neutralize the specific activity and quantity of absorbed oxygen is reduced. In all studied cases, it

Figure. 3 The growing rate for two concentrations and the reference. The arrow indicate the time when colonies are eye visible. BNC with 0.1% nanocarbon LP-1, develops in 24 h, 40 times more colonies than the reference.

is shown a reduced influence on the bacteria growth but it is not clear whether it is a consequence of the impurities or of its inertness. An inhibition effect had BNC with NC-LP2. High content of sulfur and fluorine due to the specific process of synthesis induce a clear poisoning of the bacteria. BNC with NC-LP3 or NC-CVD2 have very strange behavior. The bacteria colonies are developing in atypical shapes; the pigmentation turns to black yellow, average dimension is higher than in reference. This proves that *Staphylococcus aureus* has a good affinity for poly-aromatics and fullerene fragments but the modification induced is not clear. BNC with NC-LP1 0.1% show an exceptional bacteria development. All bacteria are extremely well developed with their specific citrine yellow pigmentation. By comparison this Petri dish look like one in the reference sample for 48-60h. An extreme virulence of the bacteria colonies has been evidenced. Samples with 1% NC are not so well developed. Inhibition affects such as fast oxygen consumption in early growth stage takes place. Aiming a fast growing culture medium, the appropriate one is NBC with NC-LP1. The figure 3 shows the growing rate for two concentrations and the reference. After 4 hours, the bacteria can be seen with the naked eye, samples with 0.1% and after 6-8 hours those with 0.01%. The sample, reference, shows visible effect after 24hours. We notice that the growth rate with BNC with 1%NC is multiplied up to 40 times. The biochemical tests and specific coloration shows the bacteria colonies did not have any modification. When BNC is used with NC-LP3, some atypical forms appeared but it was not clear which kind of modifications had been induced (figure3, NC-LP3, 0.1% shows a yellowish center surrounded by a black cage). It can be appreciated that nanoparticles dispersed in the gel lattice, work like oxygen absorbent and as oxygen pump for aerobic bacteria. It is interesting to prove, for *Staphylococcus aureus*, whether polypeptides and nucleoprotein fractions, components of the antigenic structure, have the property to couple nanoparticles. That is possible as the above-mentioned bacteria have free nucleus. If they increase the adherence in contact with a healthy tegument, they induce the phenomena of pathogenesis or necrotizing toxins in primary irritant dermatitis. Another aspect is that nanoparticles have the behavior of nano-electrolyte. As mentioned above, FT-IR spectra of the nanocarbons, after the ultrasonic processing in PSS9, show the presence of OH and carbonyl groups, relevant to consider it has had an ion exchange. That is benefic for aerobic bacteria where oxygen absorption is needed but could have major effects when nanoparticles are in contact with the skin and teguments. The nano-electrolytes with hydrogen ions change the pH of the hydro-lipid film and the acidity of the healthy skin. Therefore many channels are opened to a microbial infection.

4. CONCLUSIONS

BNC designed, as a gel, specific nutrients and turbostratic nanocarbons are good culture cells medium that accelerate the aerobic bacteria growth, particularly *Staphylococcus*.

Not all nanocarbons are good suppliers of oxygen, the turbostratic structures proved to have this property. Nanocarbons with polyaromatic struc-

tures and with fullerene fragments induce some modifications, which need a much deeper investigation. At the superior limit, carbon black has, apparently, no major influence, but many aspects have not been considered yet, such as a study on the activity of different absorbed gases. BNCs designed in this study have two aspects. Firstly, with minimum conditions a diagnosis on an infection can be predictable in less than 6h. This is very important to establish the main diagnosis and the suitable antibiotic class for a specific treatment. Secondly the existent nanoparticles in atmosphere can be tested using specially designed nanobiocomposites. Micro and nanoparticles are in direct contact with microbes. They interfere either by attachment or by other uncontrolled ways. It is not excluded an inductive effect such as increased resistance to antibiotics. In contact with teguments, atypical behavior and diseases are induced.

Acknowledgement: The present research developed as an extension of the NATO-SfP 974214 project with all the support assured by its infrastructure.

References

1. Hamburg, Margaret A. (2002) Bioterrorism: responding to an emerging threat, *Trends in Biotechnology*, **20**(7):296–298.
2. Demidov, V.V. (2002) Bioterrorism: how well are we protected? *Trends in Biotechnology*, **20**(5):192.
3. Leong, John M., Parveen N., Goguen Jon D, (2002) New approaches and old problems in the shadow of bioterrorism, *Trends in Microbiology*, **10**(3):112–114.
4. Venter, A. (2001) Defending against bioterrorism. *Trends in Microbiology*, **9**(11):52
5. Lahaye J, Prado G.(1978) vol. 14, In: Walker PL, Ed, *Chemistry and physics of carbon*, New York: Marcel Dekker, Inc, p. 167.
6. Galvez A, Herlin-Boime Nathalie, Reynaud Cecile , Clinard Ch. Rouzaud Jean-Noel, (2002) Carbon nanoparticles from laser pyrolysis, *Carbon* **40**, 2775–2789
7. Haggerty J. S. et. al.(1981) Chap. 3, in. Steinfeld J. I Ed, *Laser – Induced Chemical Processes*, Plenum Press, New York
8. G. Benedek, P. Milani and V.G. Ralchenko (2001) *Structure, Properties and Applications of Nanostructured Carbon Architectures in Nanostructured Carbon for Advanced Applications*, Kluwer Academic Publishers,
9. Kroto H.W., Heath J.R., O'Brien S.C., Curl R.F. and Smalley R.E., (1985) *Nature* **318**, 162
10. Kaae J.L., (1985) *Carbon* **23**, 665
11. Bockhorn H., in Bockhorn H. Ed, (1994) *Soot Formation in Combustion*, Springer Verlag: New York, p. 4
12. Robertson D.H., Brenner D.W. and White C.T. (1992) *J. Phys. Chem.* **96** 6133
13. Heckman T.A., Harling D.F., (1966) *Rubber Chem. Technol.* **39**, 1
14. Siegl D.C. and Smith G.W. Editors (1981) *Particulate Carbon*, New York: Plenum Press, p. 33-55
15. Grieco W., Howard J., Rainey L.C., Van Sande J.B.(2000) *Carbon* **38**, 4 635
16. Symons G.H., Ed. (1953) *Fluorine Chemistry, Vol. 1*, Inostr. Lit., Moscow, p. 81 (translated into Russian)
17. Alexandrescu R., Armand X., Cauchetier Herlin M., Petcu N., S., Voicu I., (1998) *Carbon* **36**, 1285.
18. Franklin R E. (1950), Crystallites size in graphitizing and non-graphitizing carbons. *Proc R Soc*, **209**:196–218.
19. Thrower PA, Editor, (1989) *Chemistry and Physics of Carbon*, vol. **22**, New York: Marcel Dekker, pp. 1–143.
20. Lahaye J, Ehrburger P, Editors,(1991) *Fundamental issues in control of carbon gasification reactivity*, Dordrecht: Kluwer Academic Publishers, pp. 257–68.

21. Rouzaud JN, Duber S, Clinard C, Pusz S. (2000) Optical properties of porous carbons, *Extended Abstracts, International Conference, Carbon 2000*, 9–14 July, pp. 187–188.
22. Dischler B, Bubenzer A, Koidl P. (1983); *Solid State Commun* **48**:105–8.
23. Lin-Vien D, Colthup NB, Fateley WG, Grasselli JG. (1991) *The handbook of infrared and Raman characteristic frequencies*, New York: Academic Press.

CONTACT-INDUCED PROPERTIES OF SEMICONDUCTING NANOWIRES AND THEIR LOCAL GATING

Eric Gallo, Amro Anwar and Bahram Nabet
*Electrical and Computer Engineering Department
Drexel University – Philadelphia, PA 19104, USA*

Abstract: Contacts and interfaces between three-dimensional and quasi-one dimensional structures may dominate charge transfer behavior in the nano-scale regime. Properties arise as a result of such contacts that reside in neither system alone. Of particular interest is when a Schottky barrier is formed between the metallic contact and a semiconducting one-dimensional (1D) nanowire. We show how current conduction is modified as a result of reduced dimensionality and present a model that examines the effect of Coulombic force on the Schottky barrier formed between a 1D semiconductor and a metallic electrode. Using existing theories of Schottky contacts, we introduce a capacitively coupled charge that further modifies the potential profile of the interface and changes both thermionic and tunneling currents through such a metal-1D junction. We model changes in the Schottky barrier height due to a superposition of the electric field, the image force and this Coulombic potential.

Keywords: Schottky Contacts, Thermionic Emission, Heterodimensional Contacts

1. INTRODUCTION

As new materials and techniques are discovered for use in nanoscale electronics, a deeper understanding of the physics at this scale becomes necessary. In conventional solid state devices, transitions from p to n and metal to semiconductor often dominate device behavior; examples include PN junctions, metal-semiconductor junctions and heterojunctions that can be used to create transistors, detectors, light emitters and many other useful devices¹. The nanoscale regime introduces a new type of contact, a heterodimensional junction between materials of differing dimensions. By contacting a quasi-one-dimensional (1D) semiconductor to a three dimensional metal contact new behaviors arise due to the confined states of the semiconductor wire^{2, 3}. One can expect these contacts to dominate charge transport, as contacts between materials dominate such behavior in bulk devices. In this paper we examine nanoscale Schottky contact between a metallic electrode and a 1D semiconductor and investigate some of the expected behavior changes. In particular we demonstrate the changes

in the model of thermionic emission from the metallic contact to the wire which is quite applicable to room-temperature operation of such a device. We also describe a new mechanism of affecting current through this junction, which is not observed in bulk semiconductor contacts. By using an electronically isolated local gate, the height and shape of the Schottky barrier can be modified, thereby affecting current through the junction.

2. HETERODIMENSIONAL SCHOTTKY CONTACTS

Contacts between heterogeneous materials generally play a dominating role in most conventional semiconductor devices. One would expect that at the nanoscale the same to be true. The characterization of a contact on the nanoscale can show significantly different properties than that of a bulk contact. We will address the specific case of a 3D metallic contact to a 1D semiconducting wire. The properties of this junction, such as the shape of the depletion region and the current through the junctions can be changed due to the heterodimensional nature of the contact. Contacts to nanowires can be rectifying, ohmic or tunneling barriers, our interest is on rectifying contacts, hence what follows applies to room temperature operation of a diode more so than transport at Fermi level in low temperatures.

2.1 Schottky or Blocking Contacts

Formation of an energy barrier between metal and semiconductor upon contact has been known since the 1930's.^{4,5} Current transport between metal and semiconductor has also been intensely studied^{6,7} although proper treatment of current conduction mechanisms, and effects such as the role of interface states are still actively debated.^{8,9} Schottky contacts to 1D systems have also been studied especially as they apply to the carbon nanotube.^{10,11,12,13} Here we outline a semi-classical treatment that can demonstrate expected differences between current conduction across a metal-1D junction compared to a metal-3D. Rectifying contacts result in systems of different electron affinities with current transport being based on kinetic energy requirements for motion from one system to another. Hence, in Schottky diodes thermionic emission over the barrier, rather than tunneling through it, is the main transport mechanism for semiconducting wires although it is possible that the latter dominates in other 1D devices.¹⁴ In a 3D-1D contact, calculation of thermionic emission current proceeds similar to its classic derivation⁷ or derivation of 3D-2D by summing the flux of electrons with proper velocity that overcome the barrier¹⁵

$$(1) \quad J_{th} = \int_{v_x(E_F + q\phi_B)}^{\infty} q v_x dn$$

Here dn is the incremental change in carrier concentration given by the product of the density of states (DOS) and Fermi function $dn = N_{1D}(E)f(E)dE$, and v_x is carrier velocity perpendicular to the contact along the axis of the wire; the lower limit of the integral is the required minimum kinetic energy. Using Boltzmann distribution and the 1D density of states (DOS) function, thermionic emission current is derived as¹⁶

$$(2) \quad J_{th} = \frac{qk_B}{\pi\hbar} T \exp\left(-\frac{E_{oy} + E_{oz}}{k_B T}\right) \exp\left(-\frac{q\phi_{Bn}}{k_B T}\right) [\exp((qV)/k_B T) - 1]$$

where E_{oy} and E_{oz} are the first discrete energy levels due to confinement in y and z , respectively. This equation then describes thermionic emission current for a metal-1D Schottky diode. For the case of a cylindrical wire $E_{oy} = E_{oz} = E_o$, and the reverse saturation current becomes

$$(3) \quad J_{th} = \frac{qk_B}{\pi\hbar} T \exp\left(-\frac{q\phi_{Bn}}{k_B T}\right) \exp\left(-\frac{2E_o}{k_B T}\right)$$

Equation (3) can now be compared to the 3D-2D case¹⁵

$$(4) \quad I_{2D} = WA_{2D}^* T^{3/2} \exp\left(-\frac{q\phi_B}{kT}\right) \exp\left(-\frac{E_0}{kT}\right),$$

or to the conventional (3D-3D) contact^{7,1}

$$(5) \quad I_{3D} = A_{eff} A^* T^2 \exp\left(-\frac{q\phi_B}{kT}\right) \exp\left(\frac{\Delta\phi_{im}}{kT}\right).$$

Important differences exist between these cases. A barrier height increase by $2E_0$ is observed that for a typical GaAs system causes a current reduction at room temperature by about a factor of 150. The pre-factor also shows a linear dependence on temperature as opposed to T^2 and $T^{3/2}$ in 3D and 2D cases, respectively. Hence, there exist critical thicknesses below which injected current to a nanowire significantly changes in magnitude, turn-on behavior, saturation current and temperature dependence.

In addition to room temperature operation of a Schottky (nano)diode, formation of a Schottky barrier strongly affects current transport, with carbon nanotubes being probably the best understood family of molecular conductors and closest to an ideal 1D system. Recent experimental progress has made it clear that contacts between a nanotube and metallic electrodes define the properties of the resulting circuit. This is particularly true for single wall carbon nanotubes (SWNTs), where contact to a metal electrode forms a Schottky barrier.^{17,18} This barrier is the critical factor that determines the operating characteristics of a carbon nanotube field effect transistor (CNFET). When the transistor is “off”, transport may be reduced to the level of thermionic emission (3), while in “on” state tunneling can draw large currents ultimately limited by quantum conductance. In above derivation, one dimensionality has been incorporated through inclusion of a

1D DOS, and quantized confined energies in two dimensions, hence we expect the treatment to be applicable to other wires, including polymer nanowires.

3. LOCAL GATING

The nanoscale regime also allows for new opportunities in controlling the behavior of junctions. It has been shown that gating in nanotube devices affects band bending at the contacts to control the behavior of a particular device^{14,17,19}. In what follows, we examine how the presence of charge in the vicinity of a wire can modify the electrostatic potential profile at the junction thus affecting the barrier height and its shape. This leads to significantly altering current conduction across the barrier, be it over the barrier as is the case of thermionic emission or through the barrier via tunneling processes of field emission and thermionic field emission. One point, also worth stressing, is that it is the small scale of nanowires that allows for electrostatic forces outside the wire to directly affect carriers within the wire. The small scale allows the electric field to penetrate and influence the carriers involved in conduction, unlike in bulk material where the electric field would be screened near the surface and not affect the behavior of most carriers.

The most straightforward mechanism of introducing isolated charge in the vicinity of a metal-1D wire is by means of the voltage biased conductive tip of an AFM, as schematically shown in Figure 1a^{17,20,21}. If no current flows between the tip and the surface below, it acts as an isolated charge suspended over the sample. Another possibility is the introduction of a thin static gate. This gate could be another nanowire positioned perpendicular to the contacted wire and separated by an insulating layer, as shown schematically in Figure 1b. For simplicity we consider a point charge and analyze its effect on conduction.

Figure 1: Schematic of two practical systems with Coulombic interaction at the Schottky Barrier interface. (a) is a voltage biased AFM tip. (b) is a perpendicular gating wire separated from the semiconductor by an insulating layer. The AFM tip is charge contained at a point in space, while the wire is charge distributed over a region.

3.1 Barrier Lowering due to Coulombic Potential

Consider a point charge, Q , held over the semiconducting wire at height h and located a distance r from the carrier as shown in Figure 2. The charge is free to move laterally and vertically near the contact. The potential due

to the isolated charge is modeled by considering the electric field generated by its presence. The electric field generated by Q is:

$$(6) \quad E = \frac{Q}{4\pi\epsilon r^2}$$

where ϵ is the permittivity of free space and Q is charge in Coulombs. The force exerted on a carrier in the semiconducting wire is found by multiplying this electric field by the charge on a single carrier, q . This force can be decomposed into two parts, the force in the x direction (along the wire) and the force in the y direction (perpendicular to the wire), neglecting the height of the wire. Since the carrier is confined to a quasi-one dimensional wire as it moves through the interface we need only consider the lateral force in x , which can be found by multiplying the force due to Q by the cosine of the angle between r and h . This force generates a potential energy experienced by a carrier moving through the wire, which can be found by integrating the force from infinity to a position x :

$$(7) \quad PE = - \frac{Qq}{4\pi\epsilon \sqrt{X_Q^2 - 2X_Qx + x^2 + h^2}}$$

where X_Q is the position of Q along the x axis and $r = \sqrt{(X_Q - x)^2 + h^2}$.

Assuming Q is a charge equal and opposite to the carrier, the potential seen by the carrier, as defined by (7), is shown in Figure 3.

Figure 2 Schematic showing a point charge Q located near metal electrode-semiconductor interface. The charge moves along the x -axis.

Figure 3 The potential profile seen by a carrier moving along x due to Q . Q is located at $x=50\text{nm}$. The potential is minimum directly below Q and increases as the carrier moves away from the x position of the charge.

It is known that at the interface of a metal-bulk semiconductor, the total barrier seen by a carrier is the result of a superposition of the image force potential and the electric field potential¹. Adding the effect of the charge Q on the potential landscape can further modify this barrier. By locating the charge at a fixed distance X_Q from the interface and a fixed height h , the potential landscape of the overall interface is altered as seen in Figure 4. The barrier height is now further reduced by the attractive force

Figure 4 – Plot of the Potential at the interface without Q present (dashed line) and with Q located 50nm from the interface (solid line). The maximum barrier is lowered by an additional value $\Delta\Phi_Q$ from the original barrier lowering due to the image potential.

of the isolated Coulombic charge and shown as $\Delta\Phi_{BQ}$. This change is greatly dependent on the location of the charge relative to the interface. As the isolated charge moves towards the metal electrode, the lowering increases to a peak. As it then continues to move closer to the interface the effect decreases once again. This strong dependence on lateral position can be seen in Figure 5, as the change in barrier height is plotted versus the charge location at a fixed height. The change is also highly dependent on the position of the charge above the wire, as seen in the inset of Figure 5. If the lateral position is held constant and h increases, the overall effect of the charge diminishes. The change in barrier height is also dependent on the amount of charge present and the applied electric field at the interface.

This change in the height of the barrier exponentially affects thermionic emission current. The relation for metal-1D contact of Equation (2) above can now be modified by adding an additional term $\Delta\Phi_Q$:

$$(8) \quad J_{th} = \frac{qk_B}{\pi\hbar} T \exp\left(-\frac{q\phi_B - \Delta\phi_B - \Delta\phi_Q}{k_B T}\right) \exp\left(-\frac{2E_o}{k_B T}\right) (A/cm^2)$$

The change of the barrier height, also indicates a change in barrier shape thus affecting direct tunneling and thermally assisted tunneling currents¹.

As seen in Figure 4, the barrier can be thinned at the top due to the charge Q . This thinning and reduction of barrier height will increase the observed

Figure 5 – Plot of the additional barrier lowering as a function of the position of Q . As Q moves towards the interface the barrier lowering increases, until it reaches a peak and then begins to decrease as it further approaches the metallic electrode. The position of the peak barrier lowering is dependent on the electric field present in the interface. The inset compares barrier lowering to height of Q above the nanowire in a fixed lateral position

tunneling currents. This can be seen if we consider the equation for tunneling current from a metal to a semiconductor:

$$(9) \quad J_{tun} = \frac{A^* T}{k} \int_0^{q(V_g - \Delta\Phi_B - \Delta\Phi_Q)} F_M T(\eta) (1 - F_S) d\eta$$

where F_M and F_S are occupancy factors in metal and semiconductor, respectively. The change in barrier height modifies the limits of integration, and the change in height and shape will modify the transmission coefficient, $T(\eta)$. As expected, thinning the barrier will increase transmission probability and therefore the tunneling current¹.

3.2 Barrier Width Change due to Coulombic Potential

Further change in the potential profile at the interface can also be found by considering the perpendicular component of the force due the isolated charge. If we assume the charge Q is held on a metallic gate we can estimate the effects of the capacitive coupling between the charged material and the quantum wire. As with metal-oxide-semiconductor (MOS) capacitors, it is expected that the capacitive coupling should affect the carrier concentration within the wire in a region near the gate. The issue of modeling the capacitance at this small scale becomes complex due to the close proximity to the wire and its small size and length²².

In traditional MOS models, the difference between the work functions of the metal gate and the semiconducting wire would create band bending at the interface. This bending creates accumulation or depletion of charge without an applied voltage, similar to a Schottky contact separated by a thin oxide layer¹. Given the difference in work functions would lead to the conclusion that this charge accumulation, with no voltage difference, would also occur in the metal gate, quantum wire configuration. This issue has not yet been explored fully for nano-scale systems and more work is needed to understand the accumulation or depletion effect in quantum wires. Applying bias to the gate induces additional carriers locally within the semiconducting wire, as seen in Figure 6. If the gate is located in close proximity to the contact, this change in carrier concentration will also modify the barrier seen by carriers. Using the Schottky model, the height of the barrier will change, by changing the internal electric field of the region, and the width will be altered, by varying the carrier density.

We have primarily dealt with Q as a method to increase conduction. By changing the polarity of Q , the models presented will also serve to increase the barrier seen by a carrier, as well as increase the width of the depletion region, decreasing tunneling current in the device. The model of barrier

Figure 6 The presence of Q above the semiconductor creates additional carriers in the semiconductor below Q . This increase in carrier alters the potential landscape of the interface by altering the electrical field in the barrier region.

lowering using a point charge gives an understanding of what a Coulombic potential might do to a barrier at a Schottky interface. The point charge model can be extended to create a practical model of an actual device.

4. DISCUSSION AND CONCLUSIONS

Research has primarily concentrated on tunneling and thermally assisted tunneling currents as the only current mechanism in nano-scale contacts. With respect to carbon nanotube circuits, the Schottky Barrier Transistor Model theorizes that gating modifies the Fermi level within a carbon nanotube and in doing so thins the tunneling barriers seen by a carrier entering or leaving the tube¹⁴. Other proposals suggest that in nanoscale

contacts, tunneling dominates over thermionic due to the dimensions of the materials involved²³.

One basis for this tunneling only theory has been the observed temperature dependence of devices. For instance, tunneling currents into a Luttinger liquid should follow a $T^{0.7-0.9}$, which has been observed in single-walled carbon nanotube devices²⁴. We have shown here, however, that Thermionic emission between a metal contact and a 1D semiconducting wire should have a T dependence, which is much closer to this observed dependence than the bulk value of T^2 . Further experimental evidence that thermionic emission should not be ruled out on the nanoscale is found in results from large diameter carbon nanotube circuits. Larger diameter tubes are expected to have a smaller bandgap than narrower tubes. These devices clearly show two separate temperature dependencies in their current-voltage characteristic^{25,26}, further evidence that tunneling may not be the only mechanism present in the device. We expect that different mechanisms should dominate in particular devices, however thermionic emission must be incorporated into an accurate model of conduction in nanoscale devices, particularly for room temperature operation and for calculation of reverse saturation currents.

In summary, we have derived the change in thermionic emission in a heterodimensional metal-semiconductor contact. We have also shown how an electronically isolated local Coulombic potential can alter the behavior of a nanoscale Schottky contact. The Coulombic force can penetrate into the device to directly affect the height and shape of the barrier region at the junction. These changes to the barrier in turn modify the current flow through the contact. Reduction in the height of the barrier increases thermionic emission, while a reduction in height and width can increase tunneling currents. This behavior presents a new technique for controlling conduction in the nanoscale that is not applicable for large scale devices. Heterodimensional contacts and their properties present new possibilities for devices and behaviors in electronics.

Acknowledgements: This work was supported in part by Ben Franklin Technology Partnership of Pennsylvania through a Nanotechnology Institute funding; EG was supported by NSF graduate fellowship.

References

1. S.M. Sze, *Physics of Semiconductor Devices*, 2nd Ed., J Wiley and Sons, 1981.
2. *Electronic Transport in Mesoscopic Systems*, S. Datta, Cambridge University Press (1995).
3. "Conductance Viewed as Transmission" Y. Imry, R. Landauer *Reviews of Modern Physics* 71, 2 (1999)
4. W. Schottky, "Halbleitertheorie der sperrschicht," *Naturwissenschaften*, vol.26, no.52, p.843 (1938).
5. J. Bardeen, "Surface states and rectification at a metal semi-conductor contact", *Phys. Rev.*, vol. 71, no. 10, pp. 717-727 (1947)
6. H. A. Bethe, "Theory of boundary layer of crystal rectifiers," MIT Radiation Lab Report, pp. 43-52, (1942).

7. C. R. Crowell and S. M. Sze, "Current Transport in Metal-Semiconductor Barrier Diode," *Solid State Electron*, 9, 1035. (1966)
8. E.H.Rhoderick and R.H. Williams, *Metal-Semiconductor Contacts*, 2nd ed, Oxford Press (1988)
9. R.B.Darling, "Current-voltage characteristics of Schottky barrier diodes with dynamic interfacial defect state occupancy", *IEEE Trans on Elect. Devices*, Vol. 43, no. 7, 1153-1160 (1996).
10. Z. Yao, H.W.Postma, L. Balents, and C. Dekker, "Carbon nanotube intramolecular junctions" *Nature*, Vol. 402, pp. 273-275 (1999)
11. M.P.Anantram, S.Datta, Y. Xue, "Coupling of Carbon Nanotubes to Metallic Contacts", *Phys. Rev. B*, vol. 61, no. 20, pp.14219-14224 (2000)
12. A.A. Odintsov and Y. Tokura, "Contact phenomena and Mott transition in carbon nanotubes" *Journal of Low Temp. Phys.* 118 pp. 509-518, (2000)
13. F. Leonard and J. Tersoff, "Role of Fermi-Level Pinning in Nanotube Schottky Diodes", *Phys. Rev. Lett.*, vol. 84, no. 20 pp. 4693-4696 (2000)
14. S. Heinze, J. Tersoff, R. Martel, V. Derycke, J. Appenzeller, and Ph. Avouris, "Carbon Nanotubes as Schottky Barrier Transistors", *Phys. Rev. Lett.* 89, 106801. pp1-4 (2002)
15. A. Anwar and B. Nabet, "Barrier Enhancement mechanisms in heterodimensional contacts and their effect on current transport", *IEEE Trans. On Microwave Theory and Techniques*, Vol. 50, No. 1, pp68-71(2002)
16. A. Anwar, "Heterodimensional Schottky Contacts to Modulation-Doped Heterojunction with Application to Photodetection," PhD Thesis, Drexel University, Philadelphia, PA, 2001.
17. "Controlled Creation of a Carbon Nanotube Diode by a Scanned Gate", M.Freitag, M.Radosavljevic, Y.Zhou, A.T.Johnson, and W.F.Smith; *App.Phys.Lett.*, 79 (2001).
18. M. Radosavljevic, M. Freitag, K.V. Thadani and A.T. Johnson, "Nonvolatile molecular memory elements based on ambipolar nanotube field effect transistors" *NanoLetters* 2, 761 – 764 (2002).
19. "Ambipolar Electrical Transport in Semiconducting Single-Wall Carbon Nanotubes", R.Martel, V.Derycke, C.Lavoie, J.Appenzeller, K.K.Chan, J.Tersoff, and Ph.Avouris; *Phys.Rev.Lett.*, 87 (2001).
20. "Scanned Probe Microscopy of Electronic Transport in Carbon Nanotubes", A.Bachtold, M.S.Fuhrer, S.Plyasunov, M.Forero, E.H.Anderson, A.Zettl, and P.L.McEuen; *Phys.Rev.Lett.*, 84 (2000).
21. "Local Electronic Properties of Single-Wall Nanotube Circuits Measured by Conduction-Tip AFM", M.Freitag, M.Radosavljevic, W.Clauss, and A.T.Johnson; *Phys.Rev.B*, 62 (2000).
22. *Classical Electrodynamics*, J.D. Jackson, John Wiley and Sons (1962).
23. "Scaling of nano-Schottky-diodes", G.D. Smit, S. Rogge, T.M. Klapwijk; *Appl. Phys. Lett.* 81, 20 (2002).
24. "Luttinger Liquid Behaviour in Carbon Nanotubes", M.Bockrath, D.H.Cobden, J.Lu, A.G.Rinzler, R.E.Smalley, L.Balents, and P.L.McEuen; *Nature*, 397 (1999).
25. "Electrical Measurement of Individual Semiconducting Single-Walled Carbon Nanotubes of Various Diameters", C.Zhou, J.Kong, and H.Dai; *Appl.Phys.Lett.*, 76 (2000).
26. "Electrical Properties and Devices of Large-Diameter Single-Walled Carbon Nanotubes", A.Javey, M.Shim, and H.Dai; *App.Phys.Lett.*, 80 (2002).

BESPOKE CARBON NANOTUBE DEVICES AND STRUCTURES

D.C. COX*, R.D. FORREST, P.R. SMITH and S.R.P.
SILVA

*Advanced Technology Institute, School of Electronics and
Physical Sciences, University of Surrey, Guildford-Surrey, GU2
7XH, UK*

Abstract: For carbon nanotubes to be used in large-scale electronic applications a suitable method of interconnection between individual nanotubes must be available. Recently it has been shown that it is possible to manipulate and ‘solder’ individual nanotubes in a scanning electron microscope (SEM), using carbon-based contaminating material present in differential pumped vacuum systems, or metal inorganic vapours, by focusing the electron beam on the region to be connected for several minutes.

By comparison, in this paper we report the welding of individual carbon nanotubes to other nanotubes and metal substrates, on a selective basis, to produce joints of both good electrical conductivity and mechanical integrity, without the need for a ‘soldering’ material. Carbon nanotubes have been manipulated *in-situ* in a SEM and have subsequently been cut to specific, pre-determined lengths, joined to substrates or to each other using only carefully applied voltages with limited currents.

Our studies of the connections formed between carbon nanotubes and substrates have indicated that only certain metals appear to form mechanically strong, low resistance, connections. Results on connections to metals indicate preliminarily that welds form in carbide forming metals, whereas non-carbide formers behave poorly.

This procedure may be utilised as a proof of concept technique to construct carbon nanotube-based devices and connections in electronic applications.

Keywords: Nanotubes, Manipulation, Devices, Connections

1. INTRODUCTION

The extreme electronic and microstructural properties of carbon nanotubes have been well documented[1]. However, to realise applications in the area of electronics, such as quantum wires[2], ballistic conductors[3], microchip interconnects[4] and transistors[5] the need to reproducibly fabricate connections between individual nanotubes has been identified as a major impediment[6]. The fabrication of all but the most

simple electronic devices and structures using carbon nanotubes, reliably, with high yield and accuracy is being hampered by the unavailability of a technique that allows in-situ manipulation coupled with direct observation. Connecting and “soldering” of individual nanotubes using an AFM[7] and an SEM[8] has been demonstrated, but in both cases nanotube connections can take upwards of tens of minutes per joint, and hence fabrication of even simple structures is at best very slow, and often not possible at all.

In this paper we introduce a method that allows for the design and fabrication of tailor-made freestanding carbon nanotube structures with unrivalled accuracy and nano-construction capability on a 3-D field. We show the nanotube constructions to be both mechanically robust and electronically active. The technique shows the means to select and manipulate carbon nanotubes, and produce joints between nanotubes and substrates, and other nanotubes, without the need for a solder material, and with significantly reduced time taken per connected joint.

2. EXPERIMENTAL DETAILS

Two types of nanotubes were used in this study: Catalytically grown multiwall CVD nanotubes on silicon substrates, and arc-discharge grown multiwall nanotubes embedded in polystyrene, but exposed via cleavage of the polymer[9]. The nanotubes, on their substrates, were mounted on an electrically isolated specimen stage in a Cambridge Instruments SEM that includes electrical feedthroughs connected to a pair of sharp tungsten tips, and the specimen substrates on the stage. The tungsten tips are sharpened via electrochemical etching using a method used to prepare tips for STM. It is not necessary to achieve tips as sharp as that required for STM, but we routinely use tips with tip radii of less than 1µm. Two computer-controlled Keithley 238 source/measurement units, running under a Labview program, allow us to electrically characterise the nanotubes, and provide the means for welding and cutting of the nanotubes.

The tips can be moved within the SEM, independently of the stage, and each other, by six piezo-sliders (Omicron Nanotechnology, MS5), with a minimum step size of 40 nm, and up to 5 mm total travel. The piezo-sliders are grouped into two sets of three providing three-axis movement for both tips. Control of the piezo-sliders is provided by a simple keypad control box (Omicron) that allows real-time movement of the tips, and hence nanotube manipulation, while the SEM is in operation.

Also attached to the stage, and electrically connected, is a range of substrates to which the nanotube constructions can be attached. For this study a number of suitable substrates such as 50 µm wires, thin metal foils and deposited films on insulating substrates were used.

3. RESULTS AND DISCUSSION

The first stage in producing nanotube structures by our *in-situ* manipulation method is

Figure 1: Nanotube connected to tungsten tip

Figure 2: I-V curves for the nanotube-tip-substrate connection showing conditioning

to choose and then connect one of the tips to a suitable nanotube. Examination of the nanotubes on their substrates in the SEM reveals nanotubes extending from the substrate, and when one is chosen, one of the tips is brought close to the free end of the nanotube. The gap between tip and nanotube end is then reduced until contact is made (Figure 1). Often electrostatic attraction pulls the nanotube onto the end of the tip relieving the need for accurate positioning. A voltage is then applied across the nanotube to establish an electrical contact. Typically, a poor contact is initially achieved with almost no current flow detected until a threshold voltage ($\sim 3\text{V}$) is reached. At this point, the current then increases by several orders of magnitude up to a pre-determined limit of 10^{-5}A , as the voltage is raised. On reducing the voltage we observe that the connection has improved and the resistance lowered. Subsequent cycling of the voltage to the current limit results in a further lowering of the resistance with each successive cycle down to approximately $150\text{ k}\Omega$ for the connection shown (Figure 2). We have however, seen values as low as $12\text{ k}\Omega$ depending on CNT and substrate. The CNT to substrate or nanotube contact is now mechanically robust and electrically active. We believe this conditioning behaviour is due to the intense ohmic heating, caused by the large current densities, facilitating alloying at the connection.

Typically the conditioning process can be completed in under a minute, and despite the high current densities observed, the total power dissipated is under 5 mW , demonstrating that creating a stable connection is inherently a low power process. We observe that the resistance also decreases with increasing power, and hence temperature, in agreement with Peng *et al* [10]. Initially, the current limit of 10^{-5}A is observed at around 4.5V , but following cycling the same current can be achieved at lower than 2.5V . After typically ten cycles stable I-V behaviour is obtained, with no further conditioning. At this point it is possible to increase the voltage further until the current is high enough to evaporate the central region of the tube ($>40 \times 10^{-5}\text{A}$). As these current levels are reached thermionic emission from the nanotube is detected by the

secondary electron detector in the SEM. We further monitored the thermionic emission with a simple Cu-wire detector placed few mm from a connected nanotube. As current is passed through the nanotube we observe peak emission currents of $6.2 \times 10^{-8} \text{ A}$ in the non-optimised detector. Making the assumption that the whole of the nanotube is emitting, and with a work function of 4.5 eV, we estimate the temperature of the nanotube to be well in excess of 2700K, the vaporisation temperature of single wall carbon nanotubes [11].

Allowing the current to rise to the point that the central region of the tube vapourises can be used as a crude form of cutting. This method leaves a short section of nanotube attached securely to the tip that can in turn be used as a very sharp extension of the tip itself. However, cutting nanotubes to a pre-determined length is made possible by utilising the second tip. A nanotube is held between the first tip and the substrate with a voltage of 2-3 V applied. On bringing the second tip, with a similar voltage, into contact with the nanotube, at the point cutting is required, and then raising the voltage on both tips simultaneously, a small region of around 100-150 nm vaporises near to the point of contact of the second tip, leaving the desired length of nanotube attached to the first tip. This process is somewhat easier with a section of nanotube attached to the second tip (Figure 3). It is now possible to bring a new substrate to the tip

Figure 3: Micrograph showing selected nanotube about to be cut

and attach the nanotube to it by moving it into contact and applying a voltage in the same manner as the initial nanotube to tip connection. Removing the nanotube from the tip is achieved by cutting the nanotube near to the tip connection, in the same manner as before, leaving the tube attached securely to the substrate.

Our studies of the connections formed between carbon nanotubes, metal tips and substrates have indicated that only certain metals appear to form mechanically strong, low resistance connections. The tungsten tips are effective, as is iron wire, chromium foils, and 7 μm diameter carbon fibre. However, with gold, platinum and nickel, after many voltage cycles, and using higher voltages, we were unable to form connections reliably.

This observation infers that welds form easily in carbide forming metals, whereas non-carbide formers behave poorly. A study is currently underway to elucidate this further. In addition to attaching nanotubes to new substrates, it is further possible to connect additional nanotubes to the previously deposited ones. As with attaching to substrates, the nanotubes are brought into contact at the desired point on the previously deposited nanotube and cut off from the tip as before. However, when nanotubes are connected together no conditioning behaviour is observed and the I-V behaviour of the connection is stable and reproducible despite repeated cycling.

As a demonstration of the versatility of this new technique, Figure 4 shows several aspects that would be useful in the construction of bespoke electronic devices incorporating carbon nanotubes. This figure shows the letters A, T and I constructed from arc discharge grown carbon nanotubes

Figure 4: Secondary electron micrograph of nanotube construction of letters A, T and I (a), and schematic diagram showing order in which the nanotubes were attached and the connections formed (b). The nanotubes were placed in the order shown numerically (1-6) and the connections made in the alphabetical order also shown in the schematic diagram.

and deposited onto the edge of a chromium foil. The height of the three letters is approximately $1.8\text{ }\mu\text{m}$, occupying a length of less than $4\text{ }\mu\text{m}$. The figure demonstrates the most important requirements necessary for bespoke devices; the ability to pick and place a single nanotube onto a substrate with a specific length (letter I), the ability to attach a second nanotube to the first, (letter T) and the ability to connect nanotubes together that have previously been attached to a chosen substrate, mechanically as well as electrically (letter A). The combination of these procedures realises the desire to produce

nanotube based electronic components and provides the tools necessary to achieve this. Another important point is that we have routinely removed these structures from the vacuum of our lower-resolution 'manipulation SEM' and placed them in other higher resolution instruments, clearly demonstrating the robustness of the structures formed.

4. CONCLUSIONS

In conclusion, we demonstrate that it is possible to weld nanotubes to metal contacts and to each other with both good electrical and mechanical quality. Providing the manipulation tips and substrates are of a suitable 'carbide-forming' metal it is possible to construct robust and relatively complex freestanding structures *in-situ*, at the rate of one connection every few minutes. Additionally no connecting medium is required and both the cutting and connecting of nanotubes is carried out entirely by carefully applied voltages and regulated electrical currents. This procedure may be utilised as a proof of concept technique to construct carbon nanotube-based devices and connections in electronic applications

Acknowledgements: We acknowledge the support received from the EPSRC, UK in the form of a Portfolio Partnership grant and the Carbon Based Electronics Programme.

References

1. Dresselhaus, MS, Dresselhaus G and Avouris P, (eds), *Carbon Nanotubes: Synthesis, Structure, Properties and Application*, Springer, (2000).
2. Tans, SJ, *et al.*, Individual single-wall carbon nanotubes as quantum wires. *Nature*, 386, 474 (1997).
3. White, CT and Todorov, TN. Carbon nanotubes as long ballistic conductors. *Nature*, 393, 240 (1998).
4. Li, J, *et al.*, Bottom-up approach for carbon nanotube interconnects. *Appl. Phys. Lett.*, 82, 2491 (2003).
5. Martel, R. Nanotube electronics: High-performance transistors. *Nature Materials*, 1, 203 (2003).
6. Baughman, RH, Zakhidov AA, de Heer WA. Carbon nanotubes - the route toward applications. *Science*, 297, 787 (2002).
7. Henk, W, Postma C, de Jonge, M, Yao, Z and Dekker, C. Electrical transport through carbon nanotube junctions created by mechanical manipulation. *Phys. Rev. B*, 62, 10653 (2000).
8. Barnhardt, F. The Formation of a Connection between Carbon Nanotubes in an Electron Beam. *Nano Lett.* 1, 329 (2001).
9. Poa, CH *et al.*, Field emission from non-aligned carbon nanotubes embedded in a polystyrene matrix. *Appl. Phys. Lett.* 80, 3189 (2002).
10. Peng, L, *et al.*, Polarized incandescent light emission from carbon nanotubes. *Appl. Phys. Lett.* 82, 1763 (2003).
11. Collins, PC Arnold MS, Avouris P. Engineering carbon nanotubes and nanotube circuits using electrical breakdown. *Science*, 292, 706 (2001).

VACUUM ELECTRONIC APPLICATIONS OF NANO-CARBON MATERIALS

A.N. OBRAZTSOV

*Physics Department of Moscow State University
Moscow 119992, Russia*

Abstract: Carbon materials attract great attention for use in vacuum electronic devices as cold cathodes. High aspect ratios and strong interatomic bonds provide stable and intensive electron emission at moderate electric fields from nanotubes, fibres as well as from other forms of essentially graphitic carbon. The evaluation of device applicability of carbon cathodes requires a better understanding of the process used for their synthesis and the mechanisms of electron emission. Chemical vapor deposition of carbons was studied in our work to find conditions providing better electron emission properties of cathodes. Raman spectroscopy, cathodoluminescence, various microscopy techniques, XPS, UPS and other methods were used in our experimental studies for a comparative study of various carbon materials. We propose an original model of emission sites in nano-carbon emitters having heterogeneous sp^2 - sp^3 structure. This model is in good agreement with theoretical analyses and numerical estimations. Applicability of the nano-carbon emitters are demonstrated by a few examples of vacuum light emitting devices including flat panel display prototype, triode- and diode-type lamps.

1. INTRODUCTION

Electron field emission (FE) from surface of conductive materials induced by strong electric field has great importance for fundamental and applied science [1,2]. Various carbon related materials show low-field electron emission and are therefore highly attractive as replacement for metals and semiconductors for FE cold cathodes. One of the main advantages of carbon materials for FE applications is the extremely strong interatomic σ - σ covalent bonding force providing high mechanical strength and chemical inertness appropriate for cathode materials operating in vacuum devices under intense electric field of the order of 10^7 - 10^8 V/m and in the harsh conditions of residual gas ion bombardment. However, despite the strongest interatomic bonds in graphite, the usual graphitic carbons with sp^2 atomic coordination are not suitable for FE because of their layered structure with rather weak interlayer bonding. So, while each layer itself is very stable, the entire material combined of a number of parallel layers can be destroyed easily by applying a strong electric field, and this instability is known to take place for carbon fibers [3] and graphite particles [4].

Carbon nanotubes (CNT) consisting of sp^2 coordinated atomic layers are much more stable under strong electric field action because of their cylindrical shapes preventing layers chipping off. An additional advantage is the high aspect ratio of CNT emitters, providing electric field focusing and corresponding significant reduction of applied voltages (see, for example, [5]). Similar increase of FE stability and voltage reduction can be obtained in materials composed of nano-graphite crystallites (NGC), which have bent atomic layers at the crystallite edges [6]. Layer bending at graphite crystallite edges is rather usual phenomena

(see, for example, [7-9]) that may explain the efficient and stable electron emission from various carbon materials containing NGC: polycrystalline diamonds [10], diamond-like films [11], carbon fibers [3], and graphite powders [4].

Other carbon materials with sp^3 coordination (diamond and diamond-like) have been believed to be prospective for FE applications also due to their unique property of negative electron affinity (NEA). NEA decreases up to zero the potential barrier for electrons escaping into vacuum from the diamond conduction band [12]. However, undoped diamond (as well as other diamond-like materials) has a wide band gap (WBG) with a negligible density of free electrons in the conduction band and it is therefore unlikely that NEA and the required high electron conductivity can be combined in the doped forms of any diamond-like material. This consideration allows the attribution of the numerous experimental observations of low-field electron emission from diamond materials to non-diamond carbon inclusions existing in polycrystalline diamond films obtained by chemical vapor deposition (CVD) [4,10], in single crystal diamonds [13] and in diamond composites and powders [14,15].

Thus two main approaches for the explanation of field electron emission from carbon materials exist. One of them considers FE on the basis of Fowler-Nordheim (FN) theory, assuming that emission occurs from conductive carbon material under a strong electric field enhanced due to morphological features on the emitter surface. Another approach assumes that FE originates from the NEA property of diamond and diamond-like species. The various mechanisms explaining electron injection into the conduction band of WBG diamond and diamond-like material and electron transport to the emitter surface have been proposed for this second approach. These two approaches consider separately either conductive (graphite-like) or non-conductive (diamond-like) carbons. At the same time, experimental observations show that graphite-like (conductive) emitters may exhibit properties similar to dielectric one, including electroluminescence accompanying FE [16,17], charging of the carbon nanotube surface during FE [18,19], and non-linear I-V dependence behavior in FN coordinates [20]. Other distinctions of carbon nanotube FE from those known for conductive tip emitters consists in the controversial facts that single-wall carbon nanotubes having higher aspect ratios than multiwall carbon nanotubes show a surprisingly higher emission threshold for electric field [21] and that better FE occurs from CNT aligned across the electric field direction [22].

In our studies we performed comparative characterization of various properties of carbon materials with different compositions obtained using the CVD method. Different features of the CVD process were investigated to evaluate the optimal conditions for fabrication of thin film field emitters. The obtained carbon cold cathodes were used for the manufacturing of the vacuum electron device prototypes.

2. CARBON THIN FILM MATERIALS FABRICATION BY CVD METHOD

The remarkable flexibility of the chemical vapor deposition process allows one to employ similar technologies for the production of materials with dramatically different properties (e.g. diamond [23], carbon nanotubes [24]) by changing the geometry of the reactor chamber and the discharge type used in the plasma enhanced CVD process. A fully controllable growth of various carbon films can be achieved in the same dc discharge CVD system by changing the pressure and composition of the hydrogen-methane mixture along with the substrate temperature, discharge current and voltage [25-29]. Standard Si wafers,

Ni, W, Mo and some other metal sheets and films were used in our experiments as substrates with sizes up to 50 mm in diameter. The carbon films depositions were carried out using a hydrogen-methane gas mixture. Our experimental CVD setup was described in detail elsewhere [29]. In brief, the distance between the cathode and tungsten anode in the reactor chamber is 50 mm. The substrate for carbon film deposition is located on the water-cooled anode. The internal diameter and height of the cylindrical reactor chamber is 400 mm. The chamber has water-cooled walls with quartz windows, which allows visual observation and optical measurements.

TABLE 1 Experimental parameters for carbon films deposition in dc discharge plasma.

Type of CVD film material	Substrate temperature, °C	Methane concentration, %	Total gas pressure, Torr
diamond	850-900	0.5-2	60-90
nano-diamond	900-1000	2-5	60-100
graphite-like	1050-1100	5-10	60-100
soot	1100-1250	over 15	50-100

Figure 1. Raman spectra of polycrystalline diamond (1), nanocrystalline diamond (2), nanostructured graphitic materials (CNT and/or NGC) (3), and carbon soot (4).

The CVD chamber is equipped with optical systems allowing in-situ measurements of Raman spectra for deposited carbon materials [27] and optical emission spectra (OES) of the plasma in the CVD reactor [28]. Also dc discharge current and applied voltage were measured to characterize the deposition process [28]. The typical sets of parameters of the CVD process providing deposition of diamond, CNT and disordered graphite (soot) films are listed in TABLE 1. Raman spectra of these materials are shown in Fig. 1. In these spectra, Raman lines at 1140 and 1470 cm^{-1} are specific for diamond particles with sizes smaller than 2 nm, while 1330 cm^{-1} corresponds to “usual” diamond particles, which have larger diameters [30]. Raman lines at 1350 cm^{-1} and in the vicinity of 1580 cm^{-1} (between 1550 to 1620 cm^{-1}) are attributed to different forms of disordered graphite. It should be noted that a similar 1580 cm^{-1} line is typical for multiwall carbon nanotubes [31,32].

The most important CVD films composed of nanosized graphite-like species seen as multiwall CNT and graphite nanocrystals (NGC) were obtained at relatively high concentrations of methane in the gas mixture. OES data show the presence of C_2 dimers in the plasma containing a high concentration of methane [28]. These carbon dimers play a dominant role in the synthesis of the nanocrystalline diamond (see e.g. [33]). In particular, insertion of the C_2 into acetylene-like C-C bond to produce a carbene structure is the most energetically

favorable scenario. Empirical calculations have shown [33] that the addition of C_2 may result in the evolution of critical nuclei into two-dimensional graphite-like sheets, which become mechanically unstable and roll up spontaneously to form CNT in a non-catalytical process [26]. The experimental confirmations of this model were found by using scanning electron microscopy (SEM) observations [28]. Another important circumstance of the CNT and NGC species formation is a substrate temperature of about 1000°C (see TABLE 1).

3. COMPARATIVE STUDY OF FE FROM CARBON MATERIALS

The FE tests were performed in our experiments using a vacuum diode configuration with a flat parallel anode and cathode. The anode was a glass plate coated with a transparent, conducting indium and tin oxide (ITO) film. This schema provided a very easy yet adequate method of determining the macroscopic values of electric field strength and FE current density in contrast to any tip-like or ball-like anode probe configurations (see [5,15,34] e.g.). The conducting anode film was covered with a phosphor layer allowing an image of FE site distribution over the cathode surface to be obtained. Typical images of FE site distributions for carbon films with different composition are shown in Fig. 2. The images were obtained at the same applied voltage (1600 V) and cathode-to-anode distance (200 μm) and illustrate a significant increase of emission site density from about 10^2 for polycrystalline diamond to 10^5 - 10^6 for graphitic material. In the last case it is impossible to determine the actual density of emission sites because the phosphor grains have sizes in the range of 3 to 7 μm , which is comparable with the distances between FE sites.

The significant improvement of FE properties with decreasing diamond component in the CVD films was detected also in current-voltage dependencies. Fig. 3 shows typical plots of the vacuum diode emission current (I) as a function of applied voltage (V) for cathodes made from those three type of CVD films. It is seen from the plots that threshold macroscopic electric field (E), determined as $E=V/d$ (where d is the interelectrode distance), at which electron emission can be detected is 4 V/ μm for polycrystalline diamond, 2 V/ μm for nanocrystalline diamond, and less than 1.5 V/ μm for nano-graphitic material. With the reduction of the threshold field we detect an increase of the maximal values of emission current.

Figure 2. The images of anode screen obtained for polycrystalline diamond (1), nanocrystalline diamond (2), and nano-graphite (3) cathodes.

Figure 3. Current-voltage dependencies for field emission from CVD films having various composition (polycrystalline diamond – 1, nano-diamond – 2, and nano-graphite – 3). Inset shows Fowler-Nordheim plots for the same curves.

Our comparative experimental studies performed for various CVD film materials as well as for bulk and powdered graphite, carbon fibres and other carbon materials clearly show similarity in the field emission properties for all of them. The most efficient electron emission including, the lowest threshold field, and the highest current and emission site densities was obtained for well structured nano-sized graphite type materials. The most distinctive features of the FE characteristics of these materials are: (i) a linear I - V curve in FN coordinates over a wide range of voltages and currents; (ii) substantial curvature of the FN I - V plot at low voltages and currents; (iii) homogeneity of the FE site distribution over the film surface. An evaluation of the FE mechanism requires a corresponding analysis of these features.

4. STATISTICAL ANALYSIS OF FIELD EMISSION CHARACTERISTICS

The linear character of the FN plot corresponds to classical electron tunneling mechanism of FE [1] while its substantial curvature may be explained by the statistical distribution of the emitting sites: geometrical, structural and electronic characteristics [35]. Although FE site characteristics have complex physical origins, a normal (Gaussian) distribution can be a good first approximation to the actual distribution of their heights and/or diameters. The FE image homogeneity at moderate electric field (see Fig.2) is evidence of a narrow width of the normal distribution with a small standard deviation σ . To simplify further consideration we assume that the subject for the statistical distribution has an effective size (radius r) of emission sites only. The normal distribution of the FE site radius is given by $n(r) = \frac{N}{\sqrt{2\pi}\sigma} \exp[-(r-r_0)^2/2\sigma^2]$, where r_0 is an average

size of radius. By having the total number of emission sites on the cathode surface equal to N , it may be written that $N = \int n(r)dr$. Thus the total FE current is $I = \int JdS = \int J\pi r^2 n(r)dr$, by assuming that emission occurs from the entire surface area ($S = \pi r^2$) of each emission site.

In FN theory the density of FE current is expressed by the equation

$$J = \frac{A}{\phi} F^2 \exp[1.03Be^3\phi^{-1/2}] \exp[-0.95B\phi^{3/2}F^{-1}], \quad (1)$$

where F is the local electric field at the emission site surface, ϕ is the work function of the cathode material; constants A and B are combinations of electron charge (e), mass (m) and Planck's constant h : $A = \frac{e^3}{8\pi h}$, $B = \frac{8\pi\sqrt{2m}}{3he}$. The constants values for the units of current density (J) A/m², electric field (F) – V/m, and work function (ϕ) – eV are: $A=1.5414 \times 10^{-6}$ A eV V⁻², $B=6.8309 \times 10^9$ eV^{-3/2} V m⁻¹, and $1.03Be^3=10.1$ eV.

The most common method to interpret local field value F relationships with applied voltage V is to believe their linear conversion: $F = \frac{H}{r} E = \frac{H}{r} \frac{V}{d}$, where E is the macroscopic field in planar electrode configuration with an interelectrode distance d and aspect ratio for a separate FE site equal to the ratio of its height (H) over the substrate surface to its radius which may be believed to be the same order as the radius of the emission site area - r . By assuming a value unity for the height H for all of the emission sites we obtained (see [36]) a formula describing

the total emission current dependence on the macroscopic field (or on the applied voltage $V=Ed$) as

$$I = CNE^2 \exp\left[-\frac{Dr_0}{E} + \frac{\sigma^2}{2}\left(\frac{D}{E}\right)^2\right]; \quad C = \frac{A\pi H^2}{\phi} \exp[10.1/\sqrt{\phi}]; \quad D = 0.95B \frac{\phi^{3/2}}{H}. \quad (2)$$

The last formula (2) shows that the I - V dependence differs from the classical expression deduced from FN theory for FE from metals in the second term of exponent. Fig. 4 illustrates the corresponding agreement of the experimental results with the calculation, derived by using equation (2) for $\sigma=0.1r_0$. The second term causes excess current and upward curvature in the FN plot. This term vanishes when all emission sites have the same geometrical characteristics since $\sigma=0$. But the term increases at lower values of macroscopic field (or applied voltage) if $\sigma \neq 0$. The inputs of both terms in (2) are comparable at σ values in the range of $0.5\text{\AA}$ to $2\text{\AA}$ when we assume that $r=5\text{nm}$, $H=1\mu\text{m}$, $\phi=5\text{eV}$ and with E in the range of $1\text{V}/\mu\text{m}$ to $10\text{V}/\mu\text{m}$, correspondingly. This numerical estimation is in agreement with our initial assumption about the narrow width of the normal distribution with σ , whereas for the linear part of the plot we assume that σ and the corresponding second term in (2) are equal to zero.

Comparison of the theoretical results (formula (2)) and the experimental I - V curve (see Fig.4) allows us to obtain empirical relationships for two parameters - work function ϕ and field enhancement factor β : $\beta = H/r$; $\frac{\phi^{3/2}}{\beta} = 7.4 \times 10^{-3} \text{ eV}^{3/2}$.

This relationship is shown in Fig. 5 graphically. One can observe that the expected range for work function is in the range of 4 to 5 eV corresponds to the field enhancement factor of about 10^3 . This value of β contradicts to our SEM and TEM observations of the geometrical shapes of CNT and GNC species on the carbon cathode surface. Since a typical size of the sharp edge is about 10nm, these carbon structures have heights up to $5\mu\text{m}$ and the corresponding geometrical field enhancement factor may be in the range of 50 to 500 (see [25,26,28,29]).

Figure 4. Typical I - V experimental dependence plotted in FN coordinates (dots) and fitted curve calculated by using Eq. 3 with $\sigma=0.1r_0$ (line).

Figure 5. Empirical relationships for work function ϕ and field enhancement factor β obtained from comparison of theoretical I - V dependence and experimental curve.

Another contradiction relates to the estimate of the number of emission sites N . This estimation may be made for the linear part of the FN plot from an intercept by assuming that all emission sites have the same surface area $S = \pi r^2$. Thus, for the particular case of the FN plot in Fig. 6 we have $N \approx 10^6 \text{ cm}^{-2}$, that is in well agreement with our observations made using the phosphor screen (see Fig. 2 and [25,26,28,29]). However, for the low-voltage range curved part of the plot our estimation shows a value of $N \approx 10^{13} \text{ cm}^{-2}$. This estimation was made by the

fitting theoretical curve (3) to the experimental dependence by variation of N as a parameter. The emission site density decrease with voltage increase may be explained by a screening effect leading to the suppression of emission from the sites having smaller field enhancement factors. But even in the case of screening, the number $N \approx 10^{13} \text{ cm}^{-2}$ is possible only if the emission sites have atomically small sizes.

The alternative explanation consists in the suggestion that emission occurs from an area beyond the top edge of the nano-carbon species and including some part of their lateral surface also. In this case, the estimated number of emission sites will be decreased on two or three orders without an extreme decrease of the characteristic sizes of the emitting carbon species. This explanation agrees with the model of emission sites proposed in our publications (see, e.g. [25,26]) as well as with other observations showing the origination of field emission from CNT lateral walls [37,38]. A mechanism providing such lateral emission is nonmetallic behavior of nano-carbon emitters and electron tunneling through a potential barrier, which is reduced in the vicinity of defects of sp^2 coordinated graphite-like carbon atom network [25,26].

5. TWO-BARRIER MODEL FOR FIELD EMISSION FROM NANO CARBON MATERIALS

The model of FE sites on the surface of nano-carbon material is comprised of graphitic material covered by an atomically thin layer of carbon with diamond-like electronic structure. The energy-band diagram of such a heterogeneous surface includes two potential barriers on the interfaces between the different carbon phases and between the cathode surface and vacuum (see Fig.6). In the band diagram analysis one should consider the atomistic structure of the emitter material, emphasizing the importance of the outer atomically thin layer. Thus a bulk graphitic part of the cathode is represented schematically in Fig. 6 by a periodic array of quantum wells each corresponding to carbon atoms with the Fermi level lying above the wells. The outer layer of carbon atoms with diamond-like properties is represented by a separate quantum well with the Fermi level inside a gap between the lowest unoccupied and highest occupied bands of electronic states (LUS and HOS correspondingly). The LUS-HOS gap width is assumed to be similar to that in defective diamonds and according to our cathodoluminescent studies it can be taken slightly larger than 4 eV [25].

Figure 6 Schematic energy band diagram presentation of vacuum-cathode interface without (a) and with (b) external field. The straight lines show simplified two-barrier structure including rectangular barrier between two carbon phases and outer potential barrier. The dashed lines show quantum wells corresponding to separate carbon atoms in the presurface layer with graphite properties and surface cluster with diamond-like properties similar to WBG semiconductor having gap in density of electron states between highest occupied state (HOS) and lowest unoccupied states (LUS). The electron states in the quantum wells are shown by gray and resonance electron states (RES) in HOS-LUS gap are shown by black. The height of rectangular barrier and work function of surface cluster ($E_{\text{vac}} - E_F$) is about 4.5 eV.

The application of an external field to the cathode surface leads to the deformation of this two-barrier structure. In the simplest approximation the first barrier remains to have a rectangular shape and the second one becomes triangular as sketched in Fig. 6. The main properties of FE are determined by the probability of electrons to tunnel through these two barriers at various values of the external field F . By considering the probabilities for electron tunneling through this two-barrier structure we obtain an expression for emission current density [39]:

$$J = \frac{e^3}{8\pi\hbar} \frac{1}{\left[\frac{\varphi^{1/2}}{eF} - \frac{w}{\sqrt{\chi}}\right]^2} \exp\left(-\frac{4\pi\sqrt{2m}}{h} \left(\frac{2(\varphi)^{3/2}}{3eF} - \sqrt{\chi}w\right)\right) \quad (3)$$

where w is the width of the rectangular barrier, χ – the energy difference between the Fermi level and the top of the rectangular barrier, and φ is the work function of the cathode surface.

This formula is different from the usual Fowler-Nordheim law by the second additional term in the exponent. This new term ($\chi^{1/2}w$) may lead to a significant increase in the current density. Using for estimation $\varphi=4.5$ eV, $\chi=4.5$ eV and $w=4$ Å, we obtain a current density increase of 4 orders for the same field in comparison with the value predicted by the FN model for metal emitters as is evident from Fig. 7, which clearly show a reduction of the threshold field and a dramatic increase of the current density for the two-barrier emitters with resonant electron states.

Figure 7. Current-vs-field dependencies for electron emission calculated in accord with FN law (dots line) and with respect of two-barrier model using formula (4) (straight line).

It follows from our analysis, that the presence of the resonant electronic states (RES) in the quantum well corresponding to the WBG layer is an important feature, which provides intensive electron emission at low fields. Efficient electron tunneling requires the special energetic position of these RES near the Fermi level and slightly above it to explain the existence of nonzero FE thresholds. When an external field is applied to the cathode surface, these resonant electronic states are shifted down due to a partial voltage drop in the diamond-like carbon layer (see Fig. 6). Various carbon materials including CNT, GNC, nanodiamonds etc. show very similar threshold values in the range of 1 to 1.5 V/μm (see e.g., [2-6]) that may be considered as evidence of the similarity their emission mechanisms.

6. LIGHTING ELEMENT PROTOTYPES

Our studies show that the field emission characteristics of carbon cathodes result from the unique structure and physical properties of the nanosized graphitic species. These species may be found in various carbon-related materials including

diamonds (single crystal, polycrystalline and nanocrystalline films and powders), diamond-like and tetrahedral amorphous films, carbon fibres and carbon nanotubes, graphite powders etc. The most important parameters for application: low-field emission threshold, high density of emission sites and emission current, emission stability of the carbon emitters, are determined by the arrangement of these nano-carbon species in the cathode material. To evaluate device applicability of our nano-carbon (nC) cathodes made by the CVD method, a few vacuum light emission lamps were designed and manufactured [40].

The simplest prototype of the light emitting device with a nC cold cathode was made as a flat vacuum diode lamp (see Fig. 8). The glass envelope of the lamp cells was assembled using two glass slides 40×50 mm in size coated with ITO and a phosphor layer. The nC cold cathode (25×25 mm) was fixed to the bottom slide using conductive epoxy. The glass slides were fixed to each other using vacuum cement allowing spacing between the phosphor layer and the cathode within the 0.1-1 mm range. The total cell thickness is about 3 mm. The residual pressure in the flat glass cell is about 10^{-6} Torr after pumping and sealing. The operation voltage for this type of lamp ranges from 200V to 2 kV depending on the type of phosphor and the vacuum gap distance. A very uniform, stable and high-brightness light emission was obtained from these lamps and they can be considered as a prototype of the flat-panel display. However, the intensity of the light emitted by the diode lamps is limited to the value of about 1000 cd/m² and the total power efficiency is about 10% due to the low efficiency of the phosphors operated at low anode-to-cathode voltages. This low voltage value is, in fact, one of the main advantages of the nC cold cathode, so, an improvement of phosphor properties is necessary to use the simplest flat diode scheme.

Figure 8. Schema and photograph of flat diode lamp taken with CRT screen image as background.

Figure 9. Schema and photograph of triode lamp with flat FE cathode of nC film material.

A significant increase in light intensity and power efficiency was obtained for the lamps with a triode configuration (see Fig. 9). This type of vacuum device has a more complicated structure including a grid electrode located near the flat nC cathode with approximately the same distance between them as between the cathode and anode in the flat diode lamps. This allows electron emission at the same low voltages applied between the cathode and the grid. The anode-to-grid distance and voltage can be much higher, providing high-energy electrons and high-efficiency radiation from the phosphor layer with the use of standard TV phosphors. The intensity of emitted light for such lamps exceeded 20000 cd/m² when an accelerating voltage of 5 kV was applied between the anode and the grid. The estimated power efficiency of the triode lamps is about 15%. The triode lamp seems to be the most convenient in such applications where low-voltage switching is necessary.

An alternative scheme providing high electron energy and corresponding high efficiency of light emission exploits a cylindrical diode configuration. An important advantage of the cylindrical diode configuration in comparison with the planar one is that for the same applied voltage V , the macroscopic electric field

$F=V/[r \ln(R/r)]$, as compared to $F=V/d$ for two planar electrodes with an interelectrode distance d . Practically, this means that the macroscopic field at the cathode surface $F(r)$ will be much higher in the cylindrical case than for the identical $d=R-r$ and V . This makes possible to realize a field emission diode working at suitable voltages applied between electrodes separated by a rather large distance. An essential improvement of the lamp parameters was achieved by using a scheme with the reflecting Al layer deposited on the glass tube instead of ITO. This configuration and the lamp photograph are shown in Fig. 10. The lamp brightness is achieved up to 2×10^5 cd/m². The power efficiency of the lamps with a reflecting Al anode exceeds 30%. Such power efficiency is an absolute record for light emission devices and is obtained due to the combination of an excellent nC cold cathode and a lamp configuration providing more optimal conditions for excitation of the phosphor by electrons in comparison with other similar devices. The other advantage of our lamp is the high efficiency obtained from the direct output of light generated in the phosphor layer in contrast to lamps using transparent anodes where CL light must penetrate through the phosphor layer.

Figure 10. Schema and photograph of the cylindrical diode lamp using nC cold cathode.

Acknowledgements: This work has been supported in part by INTAS grant no. 01-0254.

References

1. Gomer, R. (1993) *Field Emission and Field Ionization*, AIP, NY.
2. Temple, D. (1999) Recent progress in field emitter array development for high performance and applications, *Mat. Sci. and Eng.* **R24**, 185-239.
3. Latham, R.V., Wilson, D.A. (1982) The development of high-definition cathode-ray tube using a carbon-fibre field-emission electron source, *J. Phys. E: Instrum.* **15**, 1083-1093.
4. Xu, N.S., Tzeng, Y., Latham, R.V. (1993) Similarities in the 'cold' electron emission characteristics of diamond coated molybdenum electrodes and polished bulk graphite, *J. Phys. D: Appl. Phys.* **26**, 1776-1780.
5. Gröning O., Küttel O.M., Emmenegger Ch., Gröning P., Schlapbach L. (2000) Field emission properties of carbon nanotubes, *J. Vac. Sci. Technol. B* **12**, 665-678.
6. Obratsov A.N., Volkov A.P., Pavlovsky I.Yu., Chuvilin A.L., Rudina N.A., Kuznetsov V.L. (1999) Role of the curvature of atomic layers in electron field emission from graphitic nanostructured carbon, *JETP Lett.* **69**, 411-417.
7. Hiura H., Ebbesen T.W., Fujita J., Tanigaki K., Takada T. (1994) Role of sp^3 defect structures in graphite and carbon nanotubes, *Nature* **367**, 148-151.
8. Kuznetsov V.L., Chuvilin A.L., Butenko Yu.V., Stankus S.V., Khairulin R.A., Gutakovskii A.K. (1998) Closed curved graphite-like structures formation on micron-size diamond, *Chem. Phys. Lett.* **289**, 353-360.
9. Huang J.Y., Yasuda H., Mori H. (1999) Highly curved carbon nanostructures produced by ball-milling, *Chem. Phys. Lett.* **303**, 130-134.
10. Zhu W., Bower C., Kochanski G.P., Jin S. (2001) Field emission properties of diamond and carbon nanotubes, *Diamond and Related Mat.* **10**, 1709-1713.
11. Cui J.B., Robertson J., Miln W.I. (2001) Field emission site densities of nanostructured carbon films deposited by cathodic arc, *J. Appl. Phys.* **89**, 5707-5711.

12. Himpfel F.J., Knapp J.A., VanVechten J.A., Eastman D.E. (1979) Quantum photoyield of diamond(111) – A stable negative-affinity emitter, *Phys. Rev. B* **20**, 624-627.
13. Steeds J.W., Gilmore A., Busmann K.M., Butler J.E., Koidl P. (1999) On the nature of grain boundary defects in high quality CVD diamond films and their influence on physical properties, *Diamond and Related Mat.* **8**, 996-1005.
14. Cui J.B., Stammler M., Ristein J., Ley L. (2000) Role of hydrogen on field emission from chemical vapor deposited diamond and nanocrystalline diamond powder, *J. Appl. Phys.* **88**, 3667-3673.
15. Karabutov A.V., Frolov V.D., Konov V.I., Ralchenko V.G., Gordeev S.K., Belobrov P.I. (2001) Low-field electron emission of diamond/pyrocarbon composites, *J. Vac. Sci. Technol. B* **13**, 965-970.
16. Latham R.V., Wilson D.A. (1981) Electroluminescence effects associated with the field emission of electrons from a carbon fibre micropoint emitter, *J. Phys. D: Appl. Phys.* **14**, 2139-2145.
17. Bonard J.-M., Stoeckli Th., Maier F., de Heer W.A., Chatelain A., Salvelat J.-P., Forro L. (1998) Field-Emission-Induced Luminescence from Carbon Nanotubes, *Phys. Rev. Lett.* **81**, 1441-1444.
18. Wang Z.L., Gao R.P., de Heer W.A., Poncharal P. (2002) In-situ imaging of field emission from individual carbon nanotubes and their structural damage, *Appl. Phys. Lett.* **80**, 856-858.
19. Zhou G., Duan W., Gu B., Kawazoe Y. (2002) Emission probabilities of π electrons in carbon nanotubes, *Appl. Phys. Lett.* **80**, 1999-2001.
20. Dean K.A., von Allmen P., Chalamala V.R. (1999) Three behavioral states observed in field emission from single-walled carbon nanotubes, *J. Vac. Sci. Technol. B* **17**, 1959-1969.
21. Choi W.B., Chung D.S., Kang J.H., Kim H.Y., Lee Y.H., Jung J.E., Lee N.S., Park G.S., Kim J.M. (1999) Fully sealed, high-brightness carbon-nanotube field-emission display, *Appl. Phys. Lett.* **75**, 3129-3131.
22. Chen Y., Shaw D.T., Guo L. (2000) Field emission of different oriented carbon nanotubes, *Appl. Phys. Lett.* **76**, 2469-2471.
23. Spitsyn B.V. (1994) Growth of Diamond Films from the Vapour Phase in D.T.J. Hurtle *Handbook of Diamond of Crystal Growth*, vol.3, Elsevier Science, pp.403-456.
24. Saito R., Dresselhaus G., Dresselhaus M.S. (1998) *Physical Properties of Carbon Nanotubes*, Imp. College Press.
25. Obratsov A.N., Pavlovsky I.Yu., Volkov A.P., Petrov A.S., Petrov V.I., Rakova E.V., Roddatis V.V. (1999) Electron field emission and structural properties of carbon vhemically vapor-deposited films, *Diamond and Related Materials* **8**, 814-819.
26. Obratsov A.N., Volkov A.P., Nagovitsyn K.S., Nishimura K., Morisawa K., Nakano Y., Hiraki A. (2002) CVD growth and field emission properties of nanostructured carbon films *J. Phys. D: Appl. Phys.* **35**, 357-362.
27. Obratsov A.N., Pavlovsky I. (1997) Raman spectrometer for in-situ study of diamond growth in DC discharge plasma CVD reactor *SPIE Proc.* **3484**, 53-58.
28. Obratsov A.N., Zolotukhin A.A., Ustinov A.O., Volkov A.P. Svirko Yu.P. (2003) Chemical vapor deposition of carbon films: in-situ plasma diagnostics *Carbon* **41**, 836-839.
29. Obratsov A.N., Pavlovsky I.Yu., Volkov A.P. (1998) Field emitter and method for producing the same, *PCT Application* WO 99/44215.
30. Lopez-Rios, T., Sandre, E., Leclercq, S., Sauvain, E. (1996) Polyacetylene in Diamond Films Evidenced by Surface Enhanced Raman Scattering *Phys. Rev. Lett.* **76**, 4935-4938.
31. Lespade, P., Al-Jishi, R., Dresselhaus, M.S. (1982) Model for Raman scattering from incompletely graphitized carbons *Carbon* **20**, 427-431.
32. Saito, R., Dresselhaus, G., Dresselhaus, M.S. (1998) *Physical Properties of Carbon Nanotubes*, Imp. College Press, Singapore.
33. Krauss, A.R., Auciello, O., Gruen, D.M., Jayatissa, A., Sumant, A., et. al. (2001) Ultrananocrystalline diamond thin films for MEMS and moving mechanical assembly devices *Diamond and Related Mat.* **10**, 1952-1961.
34. Zhirnov, V.V., Lizzul-Rine, C., Wojak, G.J., Sanwald, R.C., Hren, J.J. (2001) "Standartization" of field emission measurements *J. Vac. Sci. Technol. B* **19**, 87-93.
35. Levine, J.D. (1995) Statistical analysis of field emitter emissivity: Application to flat displays *J. Vac. Sci. Technol. B* **13**, 553-557.
36. Obratsov, A.N., Zakhidov, A.I.A., Volkov, A.P., Lyashenko, D.A. (2003) Non-classical electron field emission from carbon materials *Diamond and Related Mat.* **12**, 446-449.
37. Wang, Z.L., Gao, R.P., de Heer, W.A., Poncharal, P. (2002) In situ imaging of field emission from individual carbon nanotubes and their structure damage *Appl. Phys. Lett.* **80**, 856-858.
38. Chen, Y., Shaw, D.T., Guo, L. (2000) Field emission of different oriented carbon nanotubes *Appl. Phys. Lett.* **76**, 2469-2471.
39. Obratsov, A.N., Zakhidov, A.I.A. (2003) Low-field electron emission from nanocarbons, Rep. On Diamond 2003 Conf. (Abs. DM 15 PR), Salzburg (Austria), Sept. 2003, to be published in *Diamond and Related Mat.*
40. Obratsov, A.N., Volkov A.P., Zakhidov, A.I.A., Lyashenko D.a., Petrushenko, Yu.V., (2003) Satanovskaya, O.P., Field emission characteristics of nanostructured thin film carbon materials *Appl. Surf. Sci.* **215**, 214-221.

MoS_(2-x)I_y NANOTUBES AS PROMISING FIELD EMITTER MATERIAL

A. MRZEL¹, V. NEMANIČ¹, M. ŽUMER¹, B. ZAJEC¹, J. PAHOR¹, M. REMŠKAR¹, E. KLEIN², D. MIHAILOVIČ¹

¹ Jozef Stefan Institute, Jamova 39, 1000 Ljubljana, Slovenia

² Weizmann Institute of Science, Rehovot 76100, Israel

Abstract: We have investigated the field emission (FE) properties of MoS_(2-x)I_y (y~1/3) nanotubes. The MoS_(2-x)I_y nanotubes are all sub-1-nm diameter and grow in sharp bundles, each typically consisting of up to million identical nanotubes. As-grown material was dispersed in ethanol and the individual bundles were then glued with the silver conducting paste to an aluminized glass fiber. The FE measurements of single bundles were performed under continuous bias conditions at room temperature with voltages from 0.1 to 2.4 kV. The emission current at cycling experiments from individual sites reached up to 80 nA at a macroscopic field 0.9 Vμm⁻¹. On a time scale of some ten hours the current was stable. Short term FE currents up to 10 microamperes were obtained from an individual bundle without a noticeable degradation of the FE performance. All single bundle measurements have shown virtually identical FE properties. They appear to be inert and unsusceptible to vacuum-related problems, including intermediate exposure to air. The ease of processing and good dispersion characteristics in combination with their stable reproducible FE performance suggest that MoS_(2-x)I_y NT may offer specific advantages in some applications.

1. INTRODUCTION

Nanowires and nanotubes have attracted research interest in recent years as their functional properties hold promise for incorporation into nanoscale devices and systems [1]. Field-emission properties of nanotubes are one of the forefront of worldwide nanotechnology research. The unique geometry of nanotubes suggests that they are likely to be ideal field emitters for some applications like flat panel displays [2].

So far, mostly carbon nanotubes (CNT) were studied extensively in several laboratories, which had also led to many improvements of their FE performance. Carbon nanotubes have been investigated as field electron emission sources for a number of applications including field-emission displays [3], microwave power amplifiers, gas discharge tubes [4], and nanolithography systems [5]. These applications require that nanotubes

provide a stable field-emission current at required current densities without compromising device lifetime. It was shown that CNTs do exhibit serious advantage compare to technology using tungsten or molybdenum metal tip arrays, such as operating under moderate vacuum conditions of 10^{-6} mbar. They also appear to be self-healing to some extent [6], which is thought to be the reason for their stable operation in excess of 10^4 h at average current densities of up to 0.1 A/cm^2 [7]. Bright displays were fabricated in a few years [8] but the point-like character of the light emission from these displays was probably the main disappointment. The reason is uncontrolled emission site density arising also from the difficulty in processing and dispersing CNTs [9].

In addition to carbon nanotubes, other materials were also recently tested as field emitters. Though promising results were achieved with hydrogenated diamond like carbon [10] and silicon nanowires [11], none of them displayed enough feasibility for technological applications. A hybrid emitter is a relatively a new trend. The examples are carbon nanotubes grown on the top of a tungsten-wire tip [12], diamond coated silicon tips [13] and sharp molybdenum needles coated with BN nanoparticles [14]. Also several other nanostructured materials have been reported to exhibit FE properties (BCN [15], TiN [16], Nb_2N [17], GaN [18], Mo nanowires [19]....).

It is important to stress that a quantitative comparison of their FE properties with CNTs can not be easily made, since they have not been characterized by identical methods [20]. Although comparisons are difficult to make at this stage, the search for the most suitable nanotube-shaped material for use in different FE applications is clearly just beginning.

2. EXPERIMENTAL WORK

Here we report on the FE properties of $\text{MoS}_{(2-x)}\text{I}_y$ ($y \sim 1/3$) transition metal chalcogenide nanotubes which were grown by a catalyzed transport method [21]. The iodine in the formula signifies the presence of interstitial iodine between the MoS_{2-x} nanotubes and could be largely removed by heating in vacuum. The nanotubes are all sub-1-nm in diameter and grown in form of bundles, each typically consisting of up to 10^6 identical nanotubes. Bundles range from 20 nm up to $0.5 \mu\text{m}$ in diameter and can be up to several 100 μm long. The bundles end in a sharp tip with a single or few protruding NTs at the end (Figure 1).

Figure 1 SEM image of as-grown material in the form of bundles of $\text{MoS}_{(2-x)}\text{I}_y$. The bundles end in a sharp tip with a single or few protruding nanotubes at the end.

The bundles can be dispersed in some polar solvents (e.g., ethanol; N,N-dimethylformamide, water) into smaller bundles and eventually into individual nanotubes. Transport measurements on individual small diameter bundles of $\text{MoS}_{(2-x)}\text{I}_y$ nanotubes suggest that they are metallic for transport along the tube axis [22].

2.1 Experimental Setup

The measurements were performed in a FE microscope (FEM), where the emission pattern was observed on a 22-mm-diameter aluminized luminescent screen. The screen material (designated as P-43) is composed of ultrafine particles of gadolinium oxysulfide, activated with terbium. After deposition of the luminescent material, the screen was aluminized, forming a point-to-plane geometry with the cathode pin. The distance from the pin to the screen was set to 5 mm. The base pressure below 10^{-7} mbar was obtained readily by a turbomolecular and ion-getter pump within a few hours. The FE measurements were performed under continuous bias conditions at room temperature at high voltage supplied by a stabilized voltage supply (EMI PM 28B) ranging from 0.1 to 2.8 kV or a custom designed supply for potentials up to 5 kV. The emission current was recorded by an ammeter (Keithley K 485). A 33 M Ω series resistor was used to limit the current. This combination allowed us to measure the time-averaged emission current versus voltage and the current stability at the set voltage. The photo of the setup is represented in Figure 2a and the schematic presentation in Figure 2b.

Figure 2 (a) The photo of the setup is represented (b) The schematic presentation of the setup.

3.RESULTS

In order to compare FE data with published results for other materials, we can either: (a) measure the field emission from an individual site or (b) measure the average current from a well-defined and sufficiently large emitting area. The latter requires a sizeable amount of material and a suitably reproducible deposition method, which is quite difficult to achieve.

This was the reason that in the first step of measurements only the observation and preliminary FE measurements from a large surface but with unknown number of sharp emitters were performed. First results in this initial step when the emission was observed from several bundles (global monitoring) showed that the current was some tens of μA at 2.7 kV and

Figure 3 First results in this initial step when the emission was observed from several bundles (global monitoring) caused an interesting image on the FEM screen

caused an interesting image on the FEM screen (Figure 3).

All further measurements were made with single bundles, which were supposed to end into a few FE tips. This allowed more quantitative results to be obtained. As-grown $\text{MoS}_{(2-x)}\text{I}_y$ material was first dispersed in absolute ethanol using an ultrasonic bath, and the individual bundles were then glued with the silver conducting paste (Flash-DryTM Paint, SPI) to an aluminized 5–10 μm diameter glass fiber. The assembly was then glued with the same silver paste to the metal pin. In all our experiments, the field-emission current, originating from a few sites, prevailed, which enabled us to reproducibly measure its emission current characteristics. A scanning electron microscope (SEM) image of a typical FE tip assembly, prior to mounting into the FEM, is shown in Figure 4a. In spite of the fact that the bundles are very malleable and are easily deformed in the mounting procedure, the FE pattern was always found in the form of the same shape (Figure 4b). At present, we refrain from attributing this pattern to any particular molecular orbital configuration, although the reproducibility suggests that always the same nanotube-end configuration is emitting electrons.

Figure 4 (a) A SEM image of a bundle of $\text{MoS}_{(2-x)}\text{I}_y$ on the fiber prior to mounting into the FEM. (b) Typical sequence of field emission patterns from a single bundle on the FEM screen.

The field emission characteristics (I - U) of the same sites from Figure 4b are shown in Figure 5a. The corresponding Fowler–Nordheim (F–N) plots are shown in Figure 5b. Each point in the diagram represents the current averaged over 15 s. We omitted the low-field region where the FE current cannot be clearly distinguished from the leakage current. The leakage current, which may limit the accuracy of the measurements at low FE currents, was determined by reversing the polarity of the FEM terminals, and was found to be between 10 – 20 pA at 4.5 kV. A small hysteresis was observed when comparing measurements in increasing and decreasing current modes at start and after the initial stability measurement at the fixed voltage $U = 2800$ V. The improvement after 17 hours is in accordance with the graph given in Figure 6.

Figure 5 (a) FE characteristics (I - U) of the same sites as shown in Figure 5(b) at start and after the initial 17 hours stability measurement. The corresponding Fowler–Nordheim plot shows that the FE current fits to the standard model, usually used to describe field emission.

The low-field region is frequently misinterpreted in terms of a "low emission threshold," whereas in fact the leakage current is being measured. For viability in commercial applications, the high current region is important, with the requirement for *stable* emission under appropriate vacuum conditions. We present a typical initial stability measurement of the emission current from a single bundle in Figure 6. The voltage was fixed to 2800 V. The current fluctuations were calculated to lie within 6 % during 15 h after the burn-in phase (2 h).

Figure 6 The initial stability of the emission current from a single bundle.

Although the current cycling experiments were performed up to 80 nA, short term FE currents up to 10 μA were obtained from individual bundles *without a noticeable degradation* of the FE performance. Because of the risk of damage to our measuring instruments and the P43/aluminized anode above 10 μA , we did not test the FE tips for burn-out.

4. CONCLUSIONS

The initial investigations of FE properties of $\text{MoS}_{(2-x)}\text{I}_y$ nanotubes show that they have very promising FE properties. Although the emission current at cycling experiments from individual sites reached up to 80 nA at a macroscopic field $0.9 \text{ V}\mu\text{m}^{-1}$ and the emitter-to-anode distance equal to 5 mm, short term FE currents up to 10 μA were obtained without a noticeable degradation. To conclude, these experiments on field emitters based on $\text{MoS}_{(2-x)}\text{I}_y$ nanotubes, show reproducibility both in terms of emission geometry and FE current characteristics. Indeed in the present series of experiments, all measurements performed on single bundles showed very similar FE properties. Moreover, they appear to be inert and unsusceptible to vacuum-related problems, including intermediate exposure to air. The ease of processing and very good dispersion characteristics in combination with their stable reproducible FE performance suggests that $\text{MoS}_{(2-x)}\text{I}_y$ nanotubes may offer specific advantages in applications where these are important parameters.

References

1. Baughman, R., Zakhidov, A. A. and de Heer, W. A. (2002) Carbon Nanotubes-the Route Toward Applications, *Science* **297**, 788-792.
2. Bonard, J.-M., Kind, H., T. Stockli and Nilsson L.A. (2001) Field emission from carbon nanotubes: the first five years, *Solid State Electron.* **45**, 893-914.
3. N. S. Lee, D. S. Chung, J. H. Kang, H. Y. Kim, S. H. Park, Y. W. Jin, Y. S. Choi, I. T. Han, N. S. Park, M. J. Yun, J. E. Jung, C. J. Lee, J. H. You, S. H. Jo, C. G. Lee, and J. M. Kim, Jpn. (2000) *J. Appl. Phys.*, Part **1** **12B**, 7154.
4. Rosen, R., Simendinger, W., Debbault, C., Shimoda, H., Fleming, L., Stoner, B. and O. Zhou (2000) Application of carbon nanotubes as electrodes in gas discharge tubes, *App.Phys. Lett.* **76**, 1668-1670.
5. Okazaki, A., Akita, S., Nishijima, H. and Y. Nakayama, (2000) Nanolithography of Organic Polysilane Films Using Carbon Nanotube Tips, *Jpn. J. App.Phys.Part I* **39B**, 3744-3746.
6. Dean, K. A., Burgin, T. P. and Chalamala B. (2001) Evaporation of carbon nanotubes during electron field emission, *App.Phys. Lett.* **79**, 1873-1875.
7. Saito, Y., Hamaguchi, K., Mizushima, R., Uemura, S., Nagasako, T., Yotani, J. and T. Shimojo (1999) Field emission from carbon nanotubes and its application to cathode ray tube lighting elements, *App. Surf. Sci.* **146**, 305-311.
8. Choi, W. B., Chung, D.S., Kang, J.H., Kim, H.Y., Jin, Y.W., Han, I. T., Lee, Y. H., Yung, J.E., Lee, N. S., Park, G. S., Kim, J. M. (1999) Fully sealed, high-brightness carbon-nanotube field-emission display, *Appl. Phys. Lett.* **75**, 3129-3131.
9. S. Uemura, J. Yotani, T. Nagasako, H. Kurachi, H. Yamada, T. Ezaki, T. Maesoba, T. Nakao, Y. Saito, and M. Yumura, SID 02 Digest, 2002, p. 1135.

10. Bandis, C., Pate, B. B. (1996) Simultaneous field emission and photoemission from diamond, *App.Phys. Lett.* **69**, 366-368.
11. Zhang, Y. F., Tang, Y. H., Wang, N., Yu, D. P., Lee, C. S., Bello, I. and Lee, S. T. (1998) Silicon nanowires prepared by laser ablation at high temperature, *App.Phys. Lett.* **72**, 1835-1837.
12. Sharma, R. B., Tondare, V. N., Joag, D. S., Govindaraj A., and Rao, C. N. R. (2001) Field emission from carbon nanotubes grown on a tungsten tip, *Chem. Phys. Lett.* **344**, 283-286.
13. Rangelow, I.W., Shi, F., Hudek, P., Grabiec, P., Volland, B., Givargizov, E.I., Stepanova, A.N., Obolenskaya, L.N., Mashkova, E.S. and Molchanov V.A. (1998) Micromachined ultrasharp silicon and diamond-coated silicon tip as a stable field-emission electron source and a scanning probe microscopy sensor with atomic sharpness, *J. Vac. Sci. Technol. B* **16**, 3185-3191.
14. McCarron, B. L., Schlessner, R., McClure, M. T., and Sitar Z. (1998) Electron emission mechanism from cubic boron nitride-coated molybdenum emitters, *App.Phys. Lett.* **72**, 2909-2911.
15. Bai, X. D., Guo, J. D., Yu, J., Wang, E. G., Yuan, J. and Zhou, W. Z. (2000) Synthesis and field-emission behavior of highly oriented boron carbonitride nanofibers, *App.Phys. Lett.* **76**, 2624-2626.
16. Lee, D. G., Baik, D. K., Kang, N. S., Cho, W. K., Yoon, S. J., Kim, T. Y., Hwang, H. D., Ahn, D. H. and Park, M. H. (2000) Fabrication of volcano-type TiN field emitter arrays, *J. Vac. Sci. Technol. B* **18**, 1085-1088.
17. M. Endo, H. Nakane, and H. Adachi, (2001) *J. Vac. Sci. Technol. B* **14**, 2114-2118.
18. Hwa-Mok Kim, Kang, T. W., Chung, K. S., Hong J. P., and Choi W. B. (2003) Field emission displays of wide-bandgap gallium nitride nanorod arrays grown by hydride vapor phase epitaxy, *Chem. Phys. Lett.* **377**, 491-494.
19. Zach, M. P., Kwok H. Ng, Penner R. M. (2000) Molybdenum Nanowires by Electrodeposition, *Science* **290**, 2120-2123.
20. Zhirnov, V., Lizzul-Rinne, C., Wojak, G. J., Sanwald, R. C. and Hren, J. J. (2001) "Standardization" of field emission measurements, *J. Vac. Sci. Technol. B* **19**, 87-93.
21. Remskar, M., Mrzel A., Skraba, Z., Jesih, A., Ceh, M., Demsar, J., Stadelmann, P., Levy F. and Mihailovic D (2001) Self-Assembly of Subnanometer-Diameter Single-Wall MoS₂ Nanotubes, *Science* **292**, 479-481.
22. Remskar, M., Mrzel, A., Sanjines, R., Cohen, H. and Levy F. (2003) Metallic Sub-Nanometer MoS_{2-x} Nanotubes, *Adv. Mater.* **15**, 237-240.

X-RAY SPECTROSCOPY CHARACTERIZATION OF CARBON NANOTUBES AND RELATED STRUCTURES

A.V. OKOTRUB, A.V. GUSEL'NIKOV AND
L.G. BULUSHEVA

*Nikolaev Institute of Inorganic Chemistry SB RAS, pr. Ak.
Lavrentieva 3, Novosibirsk 630090, Russia*

Abstract: X-ray emission spectroscopy was applied for revealing the peculiarities in the electronic structure of different carbon nanotubes. The $\text{CK}\alpha$ -spectra of graphite and arc-produced multiwall carbon nanotubes (MWNTs) were shown to be similar in appearance indicating essentially no difference in the electronic state of carbon atoms constituting both materials. Slight changes detected in the spectrum of arc-produced single-wall carbon nanotubes (SWNTs) were attributed to the π -system perturbation due to curvature of small diameter graphite shells. The $\text{CK}\alpha$ -spectrum of catalytic MWNTs showed the enhanced density of high-energy states that by the results of quantum-chemical calculations on various tube models could be caused by development of vacancies in the tube walls. The angular dependence of X-ray fluorescence from the samples of the oriented MWNTs was compared with that measured for graphite. The dependence can be used for qualitative characterization of tube alignment and definition of the width of occupied π -band and defect structure of graphitic materials.

Key words: Carbon nanotubes; graphite; X-ray fluorescent spectroscopy; electronic structure; anisotropy of chemical bonding.

1. INTRODUCTION

Morphology and atomic arrangement of carbon nanotubes are mainly determined by synthetic conditions [1]. The most perfect multiwall carbon nanotubes (MWNTs) are produced using the arc-discharge evaporation of graphite in an inert atmosphere [2]. The nanotubes formed in the cathode deposit have a diameter of 5–15 nm and free from catalyst. Inserting the different catalysts into electric arc makes it

possible to prepare single-wall carbon nanotubes (SWNTs) with varied diameter [3]. Chemical vapor deposition (CVD) of hydrocarbons over metallic catalysts yields the carbon nanotubes and filaments with diameter changed from 1 to 100 nm depending on the synthetic technique, temperature, kind and size of catalyst [4]. Relatively mild conditions of CVD method can result in imperfections of tube arrangement. Really, the catalytic carbon nanotubes are often bent and curved, have compartments (bamboo-shaped tubes) and layers oriented at an angle to the tube axis (fishbone packing).

Defect structure of carbon nanotubes is revealed using various structural (electron microscopy, X-ray diffraction, etc.) and spectroscopic (Raman and X-ray spectroscopy) methods. X-ray spectroscopy is one of the direct methods for probing the electronic structure of solids [5]. X-ray emission spectroscopy indicates features of the occupied electronic states while X-ray absorption spectroscopy gives information about the unoccupied states. Carbon atoms formed a perfect hexagonal network and those constituted a defect should be different in the electronic state and increase of the defect portion in a material will have stronger effect on its electronic structure. The measured energy and density of electronic states can be directly related with the results of quantum-chemical calculations. The comparison between experimental and theoretical data can be considered as the test on the applicability of the concrete quantum-chemical method to the investigated objects. From the other side, the quantum-chemical modeling itself can explain the many peculiarities existing in the X-ray spectra of the real samples. The plotting of the theoretical spectra for proposing models and the comparison of them with experiment allow choosing the most appropriate type of defects and estimating defect concentration.

With investigation of the electronic structure of carbon nanotubes, graphite could be a reference compound. Chemical bonding of perfect graphite layer has clearly defined anisotropic character caused by two-dimensional structure of solid. The measurement of angle dependence of X-ray fluorescence from high quality graphite single-crystals allows separation of σ - and π -bands [6]. Namely the distribution of π -electrons should be more sensitive to the imperfections in the graphite structure. It is very interesting the experimental definition of σ - and π -bands in carbon nanotubes that could be possible only for the samples having a certain orientation of tubes. However the recently attempted measurement of angle dependence of near-edge X-ray absorption of catalytic MWNTs had no advances [7].

The aim of the present work is demonstration of possibilities of ultra-soft X-ray spectroscopy for structural characterization of carbon nanotubes and graphite and revealing the electronic state of defects.

2. EXPERIMENTAL AND CALCULATION DETAILS

2.1. Synthesis of the Samples

The apparatus for arc-discharge graphite evaporation is described elsewhere [8]. The cathode deposit was produced by a simultaneous evaporation of seven graphite rods in helium gas of 800 Torr. The d.c. arc current was typically 1000 A at 35–40 V. The inner part of the deposit had a laminated texture and as was estimated by transmission electron microscopy (TEM) to consist of 80% MWNTs [9]. The soot containing SWNTs was prepared by arc-discharge evaporation of a rod filled by a mixture of graphite with 2.5 wt% Co and 2.5 wt% Ni [10]. To purify SWNTs the soot was heated in nitric acid.

The catalytic MWNTs were produced by decomposition of acetylene at 700°C over 2.5 wt% Co - 2.5wt% Fe / NaY zeolite catalyst. After reaction, the catalyst was removed by repeated dissolution in hydrofluoric acid. Since the nanotubes contained some pyrolytic carbon, it was eliminated by oxidation using KMnO_4 in diluted sulphuric acid solution at room temperature [11]. The tube annealing was carried out in argon atmosphere at 1000°C.

The films of vertically aligned nanotubes on silicon and quartz substrates were prepared by thermal catalytic chemical vapour decomposition (CCVD) of ferrocene/ fullerene mixture [12]. The horizontal CCVD apparatus consists of a stainless steel gas flow reactor of 1 m length and 3.4 cm diameter and a tubular furnace with a heating length of 30 cm. A ceramic boat with a mixture of fullerene C_{60} and ferrocene $\text{Fe}(\text{C}_5\text{H}_5)_2$ taken in the ratio of (1:1) was placed inside the quartz tube under the silicon (quartz) plate of size 10×10 mm. The pyrolysis was performed at 950°C and atmospheric pressure in an argon flow (3 l/min).

The micrographs of the products were obtained with a JSM-T200 scanning electron microscope (SEM) and a JEM-2010 transmission electron microscope.

2.2. Measurement of X-Ray Spectra

$\text{CK}\alpha$ -spectra of the carbon nanotube and graphite samples were recorded with a laboratory X-ray spectrometer «Stearat» using ammonium biphthalate (NH_4AP) single crystal as a crystal-analyzer. This crystal has nonlinear reflection efficiency, which is corrected by the procedure described elsewhere [13]. Angle dependence of X-ray emission spectra of graphite and MWNTs was measured at different orientations of sample surface to the take-off θ direction of the emitted

radiation. An angle between exiting beam and emitting one was constant and equal to 70° . The sample of arc MWNTs was evenly abraded on the polished copper support. The film of aligned MWNTs was forced against the polished copper support by a nickel mask. The samples were cooled down to liquid nitrogen temperature in the vacuum chamber of the X-ray tube with copper anode ($U=6$ kV, $I=0.5$ A). Determination accuracy of X-ray band energy was ± 0.15 eV with spectral resolution of 0.5 eV. The spectra were normalized at the maximal intensity.

2.3. Computation

The quantum-chemical calculations of carbon models were carried out using the semi-empirical AM1 method within the GAMESS package [14]. The geometry of ideal (8,8) tube and bent tube was optimized by standard BFGS procedure to the gradient value of 10^{-4} Ha/Bohr. X-ray transition intensity was calculated by summing the squared coefficients with which carbon 2p atomic orbitals (AOs) involved in the concrete occupied molecular orbital (MO). The energy location of intensity corresponded to the MO eigenvalue. Calculated intensities were normalized by maximal value and broadened by convolution of Lorentzian functions with half width at half maximum (HWHM) of 0.5 eV.

3. RESULTS AND DISCUSSION

3.1. Electronic Structure of Diverse Carbon Nanotubes

TEM pictures of the measured carbon materials are shown in Fig. 1. The arc-produced SWNTs having diameter of 1.3 nm form long ropes (Fig. 1(a)). The sample heated in acid still contains some amount of amorphous carbon and metal particles. The material from the inner part of cathode deposit consists of MWNTs and multiwall polyhedral particles (Fig. 1(b)). The outer tubes diameter is in the range of 10–15 nm. The arc-produced MWNTs have well graphitized shells. The catalytic MWNTs with diameter of 15–20 nm are characterized by bent and wavy walls (Fig. 1(c)). The tube tips were opened during the oxidation step.

Figure 2 compares the $CK\alpha$ -spectra measured for polycrystalline natural graphite and materials containing diverse carbon nanotubes. The spectra show three main features. The maxima A and C in the graphite spectrum originate from the occupied π - and σ -states respectively. Both types of states are involved in the formation of shoulder B [15]. The spectra of graphite and multiwall carbon nanoparticles from the cathode

Figure 1. TEM pictures of SWNTs (a) and MWNTs (b) prepared in electric arc and catalytic MWNTs (c).

deposit are in good agreement (Fig. 2(a, b)). The typical arc-produced MWNTs are straight with the defects concentrated close to the tips mainly. Hence, the portion of defects in such tubes may be assumed to be about the same as that in natural graphite, the boundary grain atoms in which are different from the bulk atoms in the electronic state.

The $CK\alpha$ -spectrum of arc-produced SWNTs (Fig. 2(c)) is somewhat distinguished from the top spectra by intensity and structure of main features, namely, the maxima C and A are broadened and the latter maximum is slightly increased. The broadening of the maximum C is likely to be due to the residual contaminations in the sample. The changes in the maximum A can be attributed to

the redistribution of π -electrons with rolling of graphene sheet into a small diameter cylinder [16]. The recently performed measurements on the SWNTs produced by laser vaporization method support this conclusion. The comparison between $CK\alpha$ -spectra of graphite and purified SWNTs in 'bucky paper' had detected the high-energy maximum in the latter spectrum was slightly broadened and increased in relative intensity by about 10% [17].

$CK\alpha$ -spectrum of catalytic MWNTs is significantly different from other spectra by increase of intensities of the features B and A (Fig. 2(d)). As π -electrons participate in origin of both these features the valence band of catalytic tubes is characterized by rising density of π -states that may be connected with high portion of defects breaking the uniformity of hexagonal carbon network.

Three kinds of defects can be generated in the graphitic shells of carbon nanotubes: topological defects, sp^3 -hybridized carbon atoms, and incomplete bonding [1]. Topological defect in the graphite layer is a ring, which is different of hexagon. Occurrence of pentagons and heptagons gives a clearly visible effect on tube structure, namely, tube

Figure 2. CK α -spectra measured for polycrystalline graphite (a), arc-produced MWNTs (b), arc-produced SWNTs (c), catalytic MWNTs (d), and catalytic MWNTs annealed at 1000°C (e).

hybridized carbon atoms link the inner and outer shells of double (4,4)@(8,8) tube [19]. Geometry of the double tube fragment was relaxed by the molecular mechanic MM+ force field. The optimized length of the bonds between sp^3 -hybridized atoms is equal to 1.61 Å, the maximal intershell spacing is about 2.92 Å, that is somewhat different from that in MWNTs. The dangling bonds at the ends of bent tube and double tube fragments were saturated by hydrogen atoms. The vacancies in the (8,8) carbon nanotube were generated by removing of two neighboring atoms (two-atomic vacancy). Theoretical CK α -spectra calculated for the tube models are compared in Fig. 3 (left part). The spectrum of ideal (8,8) tube shows three features A, B, C (Fig. 3(a)) with relative intensity and separation being in well agreement with those of the arc-produced MWNTs spectrum (Fig. 2(b)). Slightly enhanced intensities of the features A and B in the theoretical spectrum could be attributed to rather small diameter of the calculated tube.

The density of 2p-electron states for carbon atoms composing the pentagon-heptagon defect in the bent (8,8)-(14,0) tube is presented in Fig. 3(b). Compared with the spectrum of ideal tube, the spectrum of the topological defect is characterized by increase of intensity of the

bend [18]. The relative position of these rings in the otherwise perfect hexagonal network determines the angle of bending. The sp^3 -hybridization of carbon atoms can be realized due to intershell linkages in MWNTs that might account for the waviness and segmentation of tube layers. The incomplete bonding is attributed to the edge carbon atoms, which constitute the open tube ends or boundary of vacancies.

To check the effect of various defects on the shape of CK α -spectrum we compared the results of quantum-chemical calculations of ideal carbon tube and defective ones. The armchair (8,8) tube with 1.1 nm diameter was chosen as a model. The calculated tube structures are shown in Fig. 3 (right part). The ideal (8,8) tube has closed ends. The bent tube is a junction of armchair (8,8) and zigzag (14,0) tubes realized by insertion of pentagon and heptagon in diametrically opposite position. The sp^3 -

Figure 3. Theoretical $CK\alpha$ -spectra calculated for ideal (8,8) tube (a), pentagonal and heptagonal rings in bent (8,8)-(14,0) tube (b), marked hexagon from the outer shell of double (4,4)@(8,8) tube (c), and tube with two-atomic vacancies (d). The dangling edge bonds of bent and double tube fragments are saturated by hydrogen atoms.

shoulder B and almost the same relative intensity of the maximum A. It is believed that occurrence of pentagons and heptagons in the carbon nanotube structure cannot provide high density of weekly bonding π -states. The sp^3 -hybridized atoms have a perturbing action on the π -system of graphite shell that causes a pronounce enhancement of both high-energy features, A and B, in the density of states calculated for the atoms composing a convexity of the outer shell of double (4,4)@(8,8) tube (Fig. 3(c)). Nevertheless, incorporation of such kind of defects into the tube construction cannot satisfactory explain the features in the spectrum of catalytic MWNTs. Theoretical spectrum plotted for the (8,8) tube with vacancies shows a considerable rise of the maximum A (Fig. 3(d)). The changes in the spectrum of ideal (8,8) tube with producing of vacancies have a tendency similar to that revealed at the comparison between $CK\alpha$ -spectra of arc-produced and catalytic MWNTs. Increase of density of high energy states is caused by contribution of electrons of dangling bonds at the vacancy boundaries. The vacancy can be developed during the synthesis in the case of deficient in carbon atoms for perfect network formation or with the

purification of nanotube containing material. Healing of vacancies can be achieved with high temperature annealing of carbon nanotubes. Actually, the CK α -spectrum of catalytic MWNTs annealing at 1000°C (Fig. 2(e)) demonstrates decrease of intensity of maximum A relative to that in the spectrum of pristine material (Fig. 2(d)).

3.2. Anisotropy of Chemical Bonding in Graphite and Carbon Nanotubes

Anisotropy of chemical bonding in graphite crystal causes a dependence of the CK α -spectrum shape on the radiation take-off angle θ measured with respect to the graphite layer planes. The spectral bands originated from transition of π - and σ -electrons exhibit a different angular dependence that provides information on the spatial orientation of C2p-orbitals. The graphite CK α -spectrum mainly corresponds to the σ -subband when the angle between (001) graphite planes and emitting fluorescence direction is equal to $\theta = 90^\circ$. The π -electrons give the greatest contribution to the spectrum with the angles θ close to zero. Figure 4 (a) demonstrates the angular dependence of X-ray fluorescence from highly oriented pyrolytic graphite (HOPG). Detectable intensity of the feature A in the CK α -spectrum measured at $\theta = 90^\circ$ indicates the imperfection and mosaic structure of the investigated HOPG sample. Separation of the graphite π -subband was achieved following the procedure described in [20]. The spectral intensity measured at $\theta = 90^\circ$

Figure 4. CK α -spectra of HOPG measured for the radiation take-off angles $\theta = 10^\circ$, 45° , and 90° (a). The scheme shows relation between θ and graphite layers plane. Selection of π -band in the HOPG spectrum measured at $\theta = 45^\circ$ (b).

Figure 5. STM picture of inner part of the cathode deposit (a) shows predominant orientation of carbon nanotubes in a layer. CK α -spectra of arc-produced MWNTs measured for the take-off angles $\theta = 15^\circ$, 45° , and 75° . Selection of π -band in the carbon nanotube spectrum measured at $\theta = 45^\circ$ (c).

was subtracted from that obtained for $\theta = 10^\circ$ and then the resultant difference was fitted by intensity to the short-wave side of the CK α -spectrum measured at $\theta = 45^\circ$ (Fig. 4(b)). The distribution of occupied π -electrons in HOPG has almost symmetrical shape and width about 7 eV.

Carbon nanotubes, the walls of which are represented by the rolled graphene sheets, have the chemical bonding anisotropy also. Radial directed carbon AOs are analogous to the π -orbitals in graphite. The AOs, which are tangential to a tube surface, are σ -like orbitals. Because of a cylindrical, nonplanar, surface of tube shells, the observed angular dependence of X-ray emission for the carbon nanotubes sample should be smaller than that for the graphite. The reason is the angular independence of X-ray emission intensity when the radiation is perpendicular to the graphitic cylinder surface.

Optimization of conditions of arc-discharge graphite evaporation, particularly configuration of anode and value of helium pressure, had lead to the predominant orientation of carbon nanotubes in the layers of material deposited onto cathode [9]. SEM image of the material presented in Fig. 5(a) shows the bundles of MWNTs. The sample for the angular measurements was mounted by such way that MWNTs were mainly adhesive parallel to the support surface with even azimuthal distribution. The CK α -spectra were obtained for three orientations of the sample surface $\theta = 15^\circ$, 45° , and 75° with respect to the take-off direction of the emitted radiation (Fig. 5(b)). The principal distinguish between the spectra is a change of relative intensity of the features A

Figure 6. SEM images of carbon nanotube forest grown on a Si substrate: side view (a) and top view (b). TEM picture of a bundle splitting into individual carbon nanotubes (c). CK α -spectra of the film measured at two take-off angles 15° and 90° of X-ray fluorescence (d). The π -band was obtained as difference of the spectra.

and B. Both these features are formed with the participation of π -electrons, as the maximum C corresponds to the σ -electrons only [21]. The angular dependence of X-ray fluorescence for arc-produced MWNTs is considerably less than that obtained for HOPG. In addition to the cylindrical symmetry effect, the other reason of reduced variation in the high energy spectral intensity is poor alignment of MWNTs. Distribution of π -electrons in the valence band of arc-produced MWNTs was obtained by subtraction of the CK α -spectrum taken at $\theta = 75^\circ$ from the spectrum obtained for $\theta = 15^\circ$. The resultant intensity was normalized to the 281 eV feature of the CK α -spectrum measured at $\theta = 45^\circ$ (Fig. 5(c)). The obtained π -electrons distribution is characterized by large fluctuations that could be due to weak interactions between carbon nanotubes in the samples. Compared to HOPG, the π -band of arc-produced MWNTs is slightly wider and has an asymmetric shape. The asymmetry of π -band in the low-energy spectral region arises from high intensity of the feature B indicating rather perfect arrangement of graphitic shells of arc-MWNTs.

One of the simplest methods for preparation of MWNTs with good alignment is CCVD technique [22]. Figure 6(a) shows a carbon nanotubes forest grown on a Si substrate. The tubes are closely packed and vertically aligned in the sample. The SEM image of the film surface demonstrates rather uniform distribution of the tube tops (Fig. 6(b)). The TEM picture reveals the MWNTs being about 100 Å in diameter form ropes (Fig. 6(c)). The CK α -spectra of the sample produced measured at

two take-off angles $\theta = 15^\circ$ and 90° of X-ray fluorescence are shown in Fig. 6(d). The spectra have the dominant maximum around 277 eV, the shoulder at 278.5 eV, and the less intense maximum at 281 eV, which are close in energy to main features in the $\text{CK}\alpha$ -spectra of graphite and arc-produced MWNTs. The enhanced intensity of the 278.5 eV shoulder in the measured spectra compared to the spectrum of arc-produced MWNTs might be caused by an additional contribution from the iron carbide Fe_3C [23]. The principal distinguish between two measured spectra is a change of relative intensity of the high-energy features. In contrast to the angular dependence obtained for the $\text{CK}\alpha$ -spectra of HOPG and arc-produced MWNTs the spectrum taken at $\theta = 90^\circ$ exhibits the higher intensity of the features. The inverse angular dependence of X-ray emission from CCVD carbon nanotubes is due to their perpendicular deposition to the support. The smaller variations in the $\text{CK}\alpha$ -spectra of vertically aligned MWNTs compared to those observed for other graphitic samples could be due to larger defectness of the CCVD tubes. Really, the π -band being a difference between $\text{CK}\alpha$ -spectra taken for $\theta = 90^\circ$ and 15° is considerably different from the π -bands of HOPG and arc-produced MWNTs. The π -band of the CCVD tubes exhibits a new feature around 281.5 eV indicating lowering of density of weekly bonding π -states. The reason is most likely to be disruption of the hexagonal carbon network uniformity.

The comparison of π -systems selected from the angular dependence of X-ray fluorescence measured for graphitic-like materials showed that the arc-produced MWNTs are characterized by most perfect atomic arrangement in the considered series. The density of π -occupied states of arc-MWNTs has maximum around 282 eV while this value is equal to 280.8 and 279.8 eV for HOPG and CCVD MWNTs respectively. The detected shift toward the low-energy region indicates increase of π -electrons bonding that could be caused by decrease of the π -system size. Really, the defects in arc-produced MWNTs are mainly concentrated at the tubes ends and, hence, the perfect shells areas should be compared with the average tubes length (~ 1000 nm). The investigated HOPG sample was estimated from X-ray diffraction measurements to consist of the graphitic crystallites with about 100 nm dimension. Finally, the layers of CCVD MWNTs often have the fishbone packing that can reduce the size of graphitic fragments up to 10 nm.

4. CONCLUSION

X-ray fluorescent spectroscopy is one of the direct methods for probing the electronic structure of solids. Furthermore, the measurements of angular dependence of X-ray fluorescence from

anisotropic solids allow experimental definition of π -system. We applied the ultra-soft X-ray emission spectroscopy for investigation of carbon nanotubes prepared in different synthetic conditions. $CK\alpha$ -spectra of arc-produced MWNTs and SWNTs were shown to be similar to the spectrum of natural graphite. High temperatures of the electric arc provide generation of the perfect graphitic shells and the portion of topological defects needed for tube closing is comparable with that in polycrystalline graphite, which boundary grain atoms are differed by electronic states from the central atoms. Slight change in intensity detected for the high-energy region of the SWNTs $CK\alpha$ -spectrum was attributed to the π -system perturbation with formation of small diameter graphitic cylinder. The processes of decomposition of hydrocarbons over metallic nanoparticles proceed at rather mild conditions that often results in tube bending and coiling, formation of compartments and poor layer graphitization. Imperfection in the tubes arrangement led to considerable enhancement of density of high-energy occupied states in the $CK\alpha$ -spectrum of catalytic MWNTs. Three tubular models involving pentagon-heptagon pair, sp^3 -hybridized carbon atoms, and incomplete bonds were calculated using a quantum-chemical method for revealing the effect of different kinds of defects on the density of occupied states. Comparison of the $CK\alpha$ -spectra plotted by the results of defective structures calculations with the spectrum of ideal tube showed only vacancies can provide the spectral changes observed in the experiment. Electrons of dangling bonds at the vacancy boundaries have almost the same energy as the localized π -states that gives essential addition to the intensity of high-energy maximum of the theoretical spectrum. The sp^3 -defects, which could be realized as the linkages between tube shells or as the hydrogenated carbon atoms, increase the π -electrons localization that however is insufficient for the experiment interpretation. The topological defects were found to produce no gain in the intensity of high-energy occupied states.

The angular dependence of $CK\alpha$ -spectra was compared for HOPG and MWNTs produced by arc-discharge and CCVD methods. The predominant orientation of MWNTs in a certain direction was achieved directly in the synthesis. The measurements of X-ray fluorescence for different take-off angles were shown to provide information about the sample texture, namely, orientation of graphitic layers respect to the substrate surface and layer ordering. The smallest variations in the $CK\alpha$ -spectra observed for the catalytic MWNTs are associated not only with poor alignment of tubes in the sample but with high defect structure of tube shells as well. The systematic low-energy shift of the maximum of density of π -occupied states was detected for arc-produced

MWNTs, HOPG, and catalytic MWNTs and correlated with the size of graphitic fragments.

Acknowledgments: We thank Dr. A. Fonseca for the sample of catalytically produced nanotubes, Dr. V.S. Danilovich, Dr. A.L. Chuvilin and O.G. Abrosimov for SEM and TEM characterization of samples. The work was financially supported by the INTAS (projects 01-254, 01-822) and the RFBR (grants 03-03-32336, 03-03-32286).

References

1. Ebbesen, T.W., Takada, T. (1995) Topological and sp^3 defect structures in nanotubes, *Carbon* **33**, 973-978.
2. Ebbesen, T.W., Ajayan, P.M. (1992) Large-scale synthesis of carbon nanotubes, *Nature*, **358**, 220-222.
3. Journer, C., Maser, W.K., Bernler, P., Loiseau, A., Lamy de la Chapelle, M., Lefrant, S., Denlard, P., Lee, R., Fisher, J.E. (1997) Large-scale production of single-walled carbon nanotubes by the electric-arc technique, *Nature*, **338**, 756-758.
4. Ivanov, V., Nagy, J.B., Lambin, Ph., Lucas, A., Zhang, X.B., Zhang, X.F., Bernaerts, D., Van Tendeloo, G., Amelinckx, S., Van Landuyt, J. (1994) The study of carbon nanotubules produced by catalytic method, *Chem. Phys. Lett.* **223**, 329-335.
5. Maizel, A., Leonhardt, G., Sargan, R. (1981) *X-ray Spectra and Chemical Binding*, Naukova Dumka Publishers, Kiev.
6. Beyreuther, Chr., Hierl, R., Wiech, G. (1975) Zur elektronenstruktur von graphite and bormitrid, *Berichte der Bunsen-Gesellschaft fur Physikalische Chemie* **79**, 1081-1085.
7. Tang, Y.H., Sham, T.K., Hu, Y.F., Lee, C.S., Lee, S.T. (2002) Near-edge X-ray absorption fine structure study of helicity and defects in carbon nanotubes, *Chem. Phys. Lett.* **366**, 636-641.
8. Okotrub, A.V., Romanov, D.A., Chuvilin, A.L., Shevtsov, Yu.V., Gutakovskii, A.K., Bulusheva, L.G., Mazalov, L.N. (1995) Frame carbon nanoparticles: synthesis, structure and properties, *Phys. Low-Dim. Struct.* **8/9**, 139-158.
9. Okotrub, A.V., Bulusheva, L.G., Romanenko, A.I., Chuvilin, A.L., Rudina, A.L., Shubin, A.L., Yudanov, N.F., Gusel'nikov, A.V. Anisotropic properties of carbonaceous material produced in arc discharge (2001) *Appl Phys A* **71**, 481-486.
10. Okotrub, A.V., Romanenko, A.I., Yudanov, N.F., Bulusheva, L.G., Asanov, I.P., Anikeeva, O.B., Chuvilin, A.L., Boronin, A.I., and Bonard J.-M. (2002) Fluorine effect on the structure and electrical transport of arc-produced carbon nanotubes, in H. Kuzmany, J. Fink, M. Mehring, and S. Roth (eds.), *Structural and Electronic Properties of Molecular Nanostructures*, AIP Conference Proceedings **633**, pp.263-266.
11. Bulusheva, L.G., Okotrub, A.V., Asanov, I.P., Fonseca, A., Nagy, J.B. (2001) Comparative Study on the electronic structure of arc-discharge and catalytic carbon nanotubes, *J. Phys. Chem. B* **105**, 4853-4859.
12. Grobert, N., Hsu, W.K., Zhu, Y.Q., Hare, J.P., Kroto, H.W., Walton, D.R.M., Terrones, M., Terrones, H., Redlich, Ph., Ruhle, M., Escudero, R., Morales, F. (1999) Enhanced magnetic coercivities in Fe nanowires, *Appl. Phys. Lett.* **75**, 3363-3365.

13. Okotrub, A.V., Bulusheva, L.G. (1998) CK α - spectra and investigation of electronic structure of fullerene compounds, *Fullerene Science and Technology* **6**, 405-432.
14. Schmidt, M.W., Baldrige, K.K., Boatz, J.A., Elbert, S.T., Gordon, M.S., Jensen, J.H., Kosaki, S., Matsunaga, N., Nguyen, K.A., Su, S.J., Windus, T.L., Dupluis, M., and Montgomery, J.A. (1993) *J. Comput. Chem.* **14**, 1347-1363.
15. Bulusheva, L.G., Okotrub, A.V., Romanov, D.A., Tomanek D. (1998) Electronic structure of carbon nanotubes, *Phys. Low-Dim. Struct.* **3/4**, 107-134.
16. Okotrub, A.V., Bulusheva, L.G., Gusel'nikov, A.V., Chuvilin, A.L., Fonseca A. (2000) Comparative study of electronic structure of diverse carbon nanotubes, in P.V. Kamat, D.M. Gidi, K.M. Kadish (eds.), *Recent Advances in the Chemistry and Physics of Fullerenes and Related Materials* **10**, 229-235.
17. Eisebitt, S., Karl, A., Eberhardt, W., Fischer, J.E., Sathe, C., Agui, A., Nordgren, J. (1998) Electronic structure of single-wall carbon nanotubes studied by resonant inelastic X-ray scattering, *Appl. Phys. A* **67**, 89-93.
18. Han, J., Anantram, M.P., Jaffe, R.L., Kong, J., Dai, H. (1998) Observation and modeling of single-wall carbon nanotube bend junction, *Phys. Rev. B* **57**, 14983-14989.
19. Bulusheva, L.G., Okotrub, A.V., Fonseca, A., Nagy, J.B. (2001) Electronic structure of multiwall carbon nanotubes, *Synthetic Metals* **121**, 1207-1208.
20. Simunek, A., Wiech, G. (1987) σ - and π -bands of potassium-intercalated graphite C₈K studied by angle-resolved X-ray emission spectroscopy (ARXES), *Solid State Commun.* **64**, 1375-1378.
21. Okotrub, A.V., Bulusheva, L.G., Tomanek, D. (1998) X-ray spectroscopic and quantum-chemical study of carbon tubes produced in arc-discharge, *Chem. Phys. Lett.* **289** 341-349.
22. Huczko, A. (2002) Synthesis of aligned carbon nanotubes, *Appl. Phys. A* **74**, 617-638.
23. Fabian, D.G. (ed.) (1968) *Soft X-ray Band Spectra*, Academic Press, London and New York, 117.

HIGHLY FUNCTIONAL MAGNETIC NANOWIRES THROUGH ELECTRODEPOSITION

N. D. Sulitanu

*Department of Solid State Physics, Faculty of Physics,
"Al.I.Cuza" University, Iasi 700506, Romania*

Abstract: There has been increasing interest in the fabrication of nanostructured magnetic materials because of their unusual properties compared to bulk materials and for their potential applications to ultra-high-density magnetic recording, sensors and other devices. Many different techniques have been employed to produce nanoscaled materials. Among them, electrodeposition is a simple, low-cost and high throughput technique. In this paper, we focus on a particular category of magnetic nanowires and multilayered nanowires fabricated by electrodeposition into templates. The template synthesis has recently proved to be an elegant chemical approach for the fabrication of nanoscale materials and an alternative to sophisticated methods such as molecular beam epitaxy and microlithography. In this method, thin fibers are electrochemically synthesized into nanometer-wide cylindrical pores of a porous material. Interestingly, depending on the nature of the material and on other factors, such as the chemistry of the pore wall, these deposited cylinders may be solid (a nanowire) or hollow (a nanotube). This work is referring to thin fibers of magnetic materials that were electrochemically synthesized within the nanosized pores of nuclear track-etched porous membranes (PET films typically of 5-50 μm thick). Obtained nanowires have a diameter in the range 10-50 nm for a length of the order of 10 μm , and can be composed of a stack of layers of different metals with thickness in the nanometer range (multilayered nanowires). The paper describes the preparation methods, presents structural characterization and magnetic properties of nanowires. Finally, are suggested some possible applications.

1. NANOSCIENCE AND NANOTECHNOLOGY – TOWARDS AN ULTIMATE LIMIT

Nanometer scale structure and nanostructured materials play an increasing pervasive role in a wide range of scientific disciplines ranging from solid state physics through to molecular biology. In response to the ever-increasing demands for high performance data storage media and sensing devices, great effort is currently put into the development and studies of innovative magnetic materials [1-3]. As the sizes of devices are reduced, and as more and more information is packed into smaller and

smaller volumes, nanotechnology tends *towards an ultimate limit*, which is set by the *quantum properties* of matter. Just where does that limit lie? How small are the smallest devices which can be made? Should nanoscale devices be built up atom by atom or engineered by refining conventional fabrication techniques? What will be the applications of nanotechnology in computing? in medicine? Will nanotechnology revolutionize our future? Does the nanoscale hold new and fundamental scientific and social challenges? Many of these questions will find its answer in the near future as a result of large contribution of the scientists' cooperative from different preoccupation field: physics, chemistry, materials science and engineering, biology, medicine etc.

Nanofabrication offers the technical ability to fabricate objects with nanometric scale precision having unique optical and electronically properties, and which may be tailored by manipulating the size, the shape, or the composition of the nanostructures. Many of the unusual magnetic properties of the nanomagnets come about by imposing a geometrical restriction on the magnetization. As the size of the nanomagnets becomes comparable to key magnetic length scales, such as the exchange length (in the nm range), or the domain wall width (nm – μm range), the magnetization configuration may indeed be strongly affected. The understanding of how finite lateral size may affect the magnetic behavior of nanostructures is of primary importance from practical and theoretical viewpoints. For example, necessary to achieve ultra high density in magnetic storage media is that the lateral size of the information bits be as small as possible, without though the bit volume reaches the superparamagnetic limit beyond energy needed to switch the magnetization of a bit becomes less than the thermal energy [1]. Also required is that the transmission region between two bits of opposite magnetization be as narrow as possible, which in continuous thin film media is clearly hindered by the finite width of the domain walls. A promising way to achieve small lateral size, with comparatively large volume and hence high magnetic anisotropy energy of the bits is to realize nanowire arrays.

Magnetic nanowires, fabricated by various methods, represent an important family of magnetic nanostructures. Many different techniques have been employed to produce magnetic nanowires [2, 4, 5]. Among them, electrodeposition is a simple, low-cost and high throughput technique.

In this article, we review the recent investigations as well as some open issues in magnetic nanowires, and arrays of nanowires, in terms of the fabrication technique (electrodeposition) as well as their physical properties. This subject has been briefly reviewed earlier [1-12], and here we present a more exhaustive description of the state-of-the-art. Note that electrodeposition techniques discussed here are also common to other types of nanostructures, magnetic or not, ordered or not.

2. FABRICATION

Nanowires and arrays of nanowires are usually fabricated by filling a porous template that contains a large number of straight cylindrical holes with a narrow size distribution. Filling proceeds in solution by electrochemical deposition. Useful templates for electrochemical deposition of nanowire arrays include porous alumina films formed by anodic oxidation of aluminium (alumite membranes or anodized aluminium films), nuclear track-etched porous membranes, nanochannel array-glass and mesoporous channel hosts. The first two are commercially available. The properties of nanowire arrays are directly related to properties of the nanoporous templates such as the relative pore orientations in the assembly, the pore size distribution, and the surface roughness of the pores. Most works have focused on nanowire arrays grown in polymer (polycarbonate, PET, PVDF etc) membranes. These membranes are made using the nuclear track-etched technology in which a film (typically 5-50 μm thick) of polymer is bombarded by heavy ions of high-energy accelerated in a cyclotron. The irradiated film is then etched in an adequate media where tracks are revealed, leading to the formation of pores with a diameter depending on the etching time. Recently, the technology has been improved in order to produce reliable and reproducible nanoporous polymer membranes. These membranes exhibit improved properties in terms of pore shape, minimal size, size control and parallel arrangement of the pores [1, 12].

Co, Ni and Fe nanowire arrays can be fabricated using commercially available polycarbonate membranes (Nucleopore Inc.). These membranes are approximately 6 μm thick and have relatively high pore densities of about $6 \times 10^8 \text{ cm}^{-2}$. Prior to electrodeposition, a metallic (Cu, Au) film serving as cathode is evaporated on one side of the membrane. The membrane sample is then placed in an electrodeposition cell (made by glass or teflon). A schematic illustration of the experimental arrangement is shown in Fig. 1. In Fig. 2 is schematically shown an array of nanowires in a nanoporous membrane.

Fig. 1. Schematic illustration of the experimental nanowires set-up for deposition of magnetic nanowires.

Fig. 2 Schematic of an array of nanowires in a nanoporous polymer membrane.

Cobalt nanowires can be electrodeposited from a solution of 40 g/l $\text{CoSO}_4 \cdot 7\text{H}_2\text{O}$, 40 g/l H_3BO_3 , 20 g/l ammonium citrate buffered to pH 3.5 [5]. The solution for nickel nanowires deposition can be 270 g/l $\text{NiSO}_4 \cdot 7\text{H}_2\text{O}$, 40 g/l H_3BO_3 , 40 g/l $\text{NiCl}_2 \cdot \text{H}_2\text{O}$ buffered to pH 3.6 [5]. Iron nanowires can be electrodeposited using a sulfate bath containing 200 g/l $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$, 0.50 g/l $\text{H}_2\text{C}_2\text{O}_4$, 8.50 g/l glycine buffered to pH 4.5 [6]. Similarly, NiFe (14 at % Fe, 86 at % Ni) alloy nanowires can be electrodeposited from an electrolyte containing 6 g/l $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$, 218 g/l $\text{NiSO}_4 \cdot 7\text{H}_2\text{O}$, 25 g/l H_3BO_3 , 10 g/l NaCl buffered to pH 3.6 [5]. The electrodeposition process is controlled by a computer which continuously integrates the charge during nanowires deposition. The deposition process is stopped when the wires emerge from the surface (as evidenced by a sudden increase of the plating current). Figure 3a shows a potentiostatic electric current I versus time t characteristic (I - t characteristic) for the reduction of Ni^{2+} on track-etched polycarbonate membrane [12]. The schematic displays three different stages of the growth process.

Fig. 3. (a) Electrochemical reduction current $I(t)$ as a function of time t for the potentiostatic plating of Ni in pores of polycarbonate membrane with pore-diameter $d = 80$ nm. (b) Three detailed characteristics of $I(t)$ and the charge $Q(t)$ for Ni growth at $-1.0 \text{ V}_{\text{SCE}}$ (SCE – saturated-calomel electrode).

In the same figure, two pores are schematically drawn in cross-section at three different stages of the growth process. During the first stage (left schematics labeled I) the metal (shown hatched) is growing in the pores while the reduction current takes on a value of ≈ 2 mA. Growth proceeds in the pores until they are filled up to the top surface of the membrane (middle schematics). Beyond this, growth can continue in three

dimensions. This is the transition region (labeled II), which starts at the position of the arrow in Fig. 3a when current rapidly increases since the effective electrode area increases (a right schematics labeled III).

Electrodeposited multilayered nanowires are usually obtained from a single bath using a pulsed deposition technique. Typical cathode current transients resulting from potentiostatic pulses of pulse-plated Co/Cu multilayered nanowires are represented in Fig. 4 [8]. A computer continuously integrates the charge during each layer deposition.

Fig. 4 Time traces of the potential and plating current of pulse-plated Co/Cu multilayered nanowires.

The potential is switched when the deposition charges for the nonmagnetic (Cu) and the magnetic layers reach the set value. Such a procedure is required to give uniform layer thicknesses all along the multilayered filament (nanowire). Dividing the membrane thickness by the number of cycles gives the average period for the wires involved in the nanowire arrays.

The control of the wire structure can be achieved via the overpotential used to initiate growth. Therefore, nanotubes, whose formation could result from a complexation between metal ions and the polymeric membrane, have been also synthesized [6]. By changing the pulse cycles of the two pulse steps electrodeposition current, metallic hollow nanotubes can be electrochemically synthesized. In Fig. 5a, a TEM micrograph clearly shows interlaced iron nanotubes [6].

Fig. 5. (a) TEM image of Fe nanotubes growth in a polycarbonate membrane by using two pulses steps electrodeposition current. (b) An aperture is clearly visible at the last extremity of a Fe tube.

The observation of the tubes reveals clusters coalescing inside a tube (dark spot). This image clearly illustrates the two steps proposed growth mechanism with the filling of the tubes after the formation of the outer wall. The early stage of growth is likely a complexation of Fe^{2+} metal ions together with the CO_3^{2-} carbonate function of the polymeric membranes, which is highly favorable because the interaction between the chemical species is strong. This first stage results in a coating of the inner part of the membrane pores with metal ions. In the second stage, reduction via electrochemistry of the metal species from Fe^{2+} into Fe leads to the formation of the tubes (deposition time $\sim 6\text{--}8$ min). At higher resolution, an aperture at one extremity of a tube is clearly visible (Fig. 5b). The wall was evaluated to be ~ 1 to 2 nm thick, which corresponds to a few atomic planes. The polymer and alumite membranes have successfully been used to prepare colloidal suspensions in which the nanorods are dispersed and stabilized in water. For example, the polycarbonate membranes can be dissolved in 40°C dichloromethane (CH_2Cl_2), rinsed in fresh, dichloromethane, chloroform and ethanol. In case of the aluminium oxide model system, the oxide can be dissolved in a 1.25 M NaOH solution containing 0.1 mM polyvinylpyrrolidone (PVP, $M = 40,000$). Figure 6 shows SEM image of Ni nanorods from a colloidal suspension obtained after completely dissolving the polycarbonate membrane in dichloromethane (CH_2Cl_2) and collecting the wires on holey carbon grids [12].

It has been found that there is a significant influence of deposition conditions on the deposit properties. It was found that pH of the electrolyte shows a strong effect on the phase structures obtained. The increasing the bath acidity favors formation of more phase structures. It also decreases the amount of deposited alloys, which is explained by the lower Faraday efficiency in the solutions of lower pH. The temperature of solution exerts a profound influence on the deposit and it favors the formation of new phases. It was also found that the rate of deposition

depends strongly on electrolyte temperature. Among all parameters investigated the deposition current density exerts the greatest effects, both on the appearance of the deposit and its phase structure. Figure 7 shows anodic linear sweep voltammetry (ALSV) diagrams of Fe nanowires deposited at different current densities (4, 7, 9 and 12 A dm⁻²) at $t = 40^\circ\text{C}$ for $t = 8\text{ min}$ [1, 12].

Fig. 6. SEM image of Ni nanorods nanowires from a colloidal suspension.

Fig. 7. ALSV voltammograms of Fe in a sulfate solution of pH 2.5 at 23°C.

Alloys deposited at low current densities (4 A dm⁻²) contain only one phase structure, since only one dissolution peak is observed. Alloys deposited at higher current densities (7 and 9 A dm⁻²) show more dissolution peaks, indicating the presence of more different phase structures. However, at current densities larger than 12 A dm⁻², peak II is not observed, indicating that the phase structure which corresponds to peak II and which is the only one present in the deposits obtained at low current densities, is absent in the deposits obtained at very high current densities. It can be seen from Fig. 7 that the deposition current density also influences the total Faraday efficiency of the deposit and increases with current density irrespective of the temperature.

3. CHARACTERIZATION

Microanalysis of nanowires and multilayered nanowires can be performed in TEM and scanning TEM (STEM) by X-rays energy dispersive spectroscopy (XEDS) and electron energy loss spectroscopy (EELS), the former being more quantitative and the latter having a higher spatial resolution [1, 12]. In the case of multilayered nanowires, we can alternatively use another method based on the relationship between the layer thickness d_{NM} and d_M and the electric charges Q_{NM} and Q_M transferred at the cathode during the corresponding pulses. Figure 7 shows d_{bilayer} as a function of Q_{Cu} for the Co/Cu system [8].

Fig. 8. Mean thickness of bilayer as a function of electric charge transferring at cathode

Fig. 9 XRD pattern of Ni nanowires deposited during in the nanoporous anodic alumina membrane. Cu deposition in Co/Cu multilayered nanowires.

Using the Faraday's law, the following relationship can be derived:

$$d_{bilayer} (nm) = 36.7 \frac{\eta_{Cu} Q_{Cu}}{A} + 34.3 \frac{\eta_{Co} Q_{Co}}{A} \quad (1)$$

where A is the cathode surface area (in mm^2) which depends on the pore density diameter; η_{Cu} and η_{Co} are the cathode current efficiencies for pulsed electrodeposition of Cu and Co, respectively; the two charges Q_{Cu} and Q_{Co} in Eq. (1) are expressed in mC. From the slope and intercept of the straight line of Fig. 7, we can obtain $\eta_{Co}/\eta_{Cu} = 0.72$ and d_{Co} 24 nm.

Detailed structural characterization of nanowires and multilayered nanowires can be done by X-ray diffraction (XRD), scanning electron microscopy (SEM) analytical transmission electron microscopy (TEM) and atomic force microscopy (AFM) [1]. Figure 8 shows XRD pattern of Ni nanowires deposited in the nanoporous anodic alumina membrane [1]. Figure 9 shows SEM images of Ni wires grown in 80 nm diameter pores of a polycarbonate membrane [1]. Hemispherical caps form on top of the wires if the growth will proceed after the pores will be filled up to the top surface of the membrane. The total length of a wire is $\approx 6 \mu m$. The right most image shows the top a bottom $2 \mu m$ of one and the same wire. Figure 10 shows TEM images of a short-period Py/Cu multilayer grown on a pure permalloy ($Ni_{80}Fe_{20}$ -Py). The structure is FCC and the $\langle 110 \rangle$ axis is parallel to the growth direction [1, 8]. The period of the super lattice shown in Fig. 10 is about 5 nm. It is noted that for a $20 \mu m$ -thick membrane, multilayered nanowires composed of more than 3000 bilayers can be prepared.

Fig. 10. SEM images of Ni wires grown in a polycarbonate membrane.

Fig. 11. TEM observations in $\langle 111 \rangle$ zone axis of a Py/Cu multilayered nanowire.

4. PROPERTIES OF ELECTRODEPOSITED NANOWIRES

Magnetization of the nanowires can be determined at room temperature using a vibrating sample magnetometer (VSM). Low temperature magnetization measurements can be carried out using a superconducting quantum interface device (SQUID). Magnetic domain structure can be evidenced by magnetic force microscopy (MFM) [4, 9, 12]. Generally, the enhancement of coercivities of ferromagnetic nanowires increases for decreasing wire diameter due to the decreasing probability of multiple domains in the nanowires. The high anisotropy observed for the nanowire arrays has possible application to high density perpendicular magnetic recording media. By having their preferred magnetization perpendicular to the sample plane (parallel to nanowire axis), magnetic media with perpendicular anisotropy can allow smaller bit size and thus increase the recording density. As has been shown, the magnetic nanowire arrays studied exhibit high perpendicular anisotropy due to their unique artificial structure. For example, highly ordered $\text{Fe}_{14}\text{Ni}_{86}$ alloy nanowire arrays (with diameter 25-43 nm, distance between the neighboring pore centers 60 nm) exhibit enhanced coercivity (about 80 kA/m) and remanent magnetization up to 70 % [10]. Therefore, the coercivity is comparable to that of a 1.44 Mb, 3.5 inch floppy disk (64 kA/m). The easy magnetization axis of the magnetic nanowire arrays is perpendicular to the membrane. Thus, it has potential application to be used as rewritable ultra-high density vertical magnetic storage media. Its

storage density would be more than 2×10^5 times than that of 3.5 inch floppy disk.

The transport properties of nanowire have been mainly studied by measurements on arrays of nanowires because the high pore density and the random arrangement of the pores make difficult the resistance measurement of a simple metal nanowire. However, it has been recently developed strategies that allow performing measurements on single metal nanowires and multilayers. Till now, three different approaches have been proposed [1, 8, 12]. A single nanowire has been connected by evaporating a thin metallic layer on the face of the porous membrane exposed to the electrolyte. The film is thin enough in order to ensure that it does not cover the pores (Fig. 11a).

Fig. 12. (a) Schema of the polymer membrane used for the electrodeposition. The bottom Au thin film is used as cathode; the top Au thin film strip used for contacting a single nanowire. (b) Short increase of the plating current when the wire is contacted to the metal strip.

In the second method, combination of the chemical methods and e-beam lithography is used for contacting a single wire after electroplating and formation of metallic caps at the surface [1]. Another method, also combining e-beam lithography and electrodeposition was recently reported [1]. In this method, submicron cylindrical cavities of typical height $0.3 \mu\text{m}$ and diameter $0.1 \mu\text{m}$ were fabricated and precisely located in a PMMA layer deposited on a patterned substrate. In a second step, electroplating of nanowires was performed into these cavities and caps are formed at the surface. The final step of the process consists in sputtering a metal layer at the top of the device allowing contacting electrically single pillars. Figure 11b shows the short increase of the plating current when the wire is contacted to the metal strip.

The reversal of magnetization in individual magnetic nanowires was studied using transport measurements, i.e., anisotropic magnetoresistance (AMR) measurements. Multilayered nanowires are ideal structures to study conveniently the giant magnetoresistance (GMR) and its temperature dependence in the current perpendicular to the layer plane

(CPP) geometry. Up to now, most measurements have been performed on Co/Cu, Fe/Cu and Py/Cu systems. Magnetoresistance and magnetization curves obtained with magnetic fields parallel to the layers at 4.2 K on $\text{Ni}_{80}\text{Fe}_{20}$ (12 nm)/Cu (14 nm) multilayered nanowires are shown in Fig. 12a and Fig. 12b [8]. In order to reduce saturation field, can be used another structure composed of Py (3 nm)/Cu (10 nm)/Py (3 nm) trilayers magnetically isolated by thick layers of Cu (100 nm or more) [8]. A typical magnetoresistance curve for in-plane field is shown in Fig. 3 c. The multilayered nanowires exhibit high MR ratio with a fairly large resistance (between a few Ω and a few $\text{k}\Omega$ depending on the number of wires which are connected in parallel). It has also been shown that the field required to saturate the magnetoresistance can be relatively small, of the order of 8-10 kA/m, in nanowires composed of Py/Cu/Py trilayers spaced by thick Cu layers.

Fig. 13 CPP – GMR and magnetization curves versus applied field parallel to the layers at 4,2 K for Py/Cu multilayered nanowires (a, b) and for multilayered nanowires composed of Py/Cu/Py trilayers separated by a thick (90 nm) long Cu rods (c, d).

In hybrid structures, (e.g., Ni/NiO/Co system), the most striking result is the observation of two-level telegraphic noise (RTSN) which is ascribed to the trapping and untrapping of a single electron by a defect in ultra-small NiO barrier [11].

5. PERSPECTIVES

Research on magnetic nanowires are driven towards the progress of the fabrication techniques and to novel properties what implies to obtain wires of smaller diameter, down to 10 nm or smaller than certain characteristic length scales, such as spin diffusion length, carrier mean free path, magnetic domain wall width etc. The effect of confinement, proximity and order govern the interplay between the relevant physical length scales and the sizes of the nanowires. For example, ballistic transport appears in material confined to the appropriate length, smaller than the electron mean free path, or magnetization reversal processes can be drastically modified in nanowires confined to sizes that preclude the domain wall formation. The recent microsquid (μ - SQUID) experiments have suggested the existence of quantum tunnelling effects in the magnetization reversal magnetic wires (45 nm thick Ni) and experiments of thinner nanowires can be of great interest to make these quantum effects to appear more clearly. Another type of promising experiment is the study of telegraphic noise due to quantum fluctuations in mesoscopic tunnel junctions fabricated in the pores of membranes.

Nanowires should be ideal devices to achieve very high injection densities and study the effects of spin injection on the magnetic configuration of a multilayered structure. GMR experiments can be extended to other systems, for example ferromagnetic metal/superconductor multilayers.

The fabrication of organized arrays of nanowires there is another necessity which should go with a more flexible control of the length of the wires, for example by developing the fabrication of thinner porous membranes. The last studies of magnetic nanowires indicate less appropriate to fabricate well-organized arrays.

Referring to technological applications, the electrodeposited nanowires and arrays of nanowires are of stringent interest for magnetoresistive devices of very small size and for perpendicular recording media. The nanowires embedded in polymer membranes cannot be integrated directly into conventional devices but their possible biocompatibility is of interest to medical devices. For application to conventional devices, it will be necessary to develop techniques of electroplating into other types of templates, supported membranes on silicon or patterned insulator layers.

6. CONCLUSIONS

Electrodeposition method is capable of producing high-quality magnetic nanowires and ordered arrays of nanowires with desirable features, including nanowires with reproducible sizes in the range of 10 nm, and arrays which can be extended over large areas ($\sim 100 \times 100 \text{ nm}^2$). Usually there are many variable parameters that can be used to tune the properties of nanowires, such as material, crystallinity (polycrystalline,

single-crystal, amorphous), structure single layer, multilayered, array geometry etc.

The structure of the nanowires and arrays of nanowires can be investigated by XRD, nuclear magnetic resonance (NMR), SEM, TEM, AFM, etc. The magnetic properties of the nanowires and arrays of nanowires can be characterized by techniques such as magnetization measurements (VSM, SQUID, MFM, AGM – alternating gradient magnetometry, MOKE – magneto-optical Kerr effect) or transport measurements.

The main magnetic properties of the nanowires present important differences with respect to continuous films: the remanent state is usually metastable shape anisotropy usually plays an important role in magnetization reversal process; coercive field are often larger than the values found in the unpatterned samples; the spin wave spectrum may be quantized due to the small size of the nanowires. The shape anisotropy of individual wires dominates the magnetic properties. Dipolar interactions between nanowires are fundamental key to understand the experimental behavior of the array. The arrays of the magnetic nanowires are not only interesting for their intrinsic magnetic properties, but also due to their interaction with other systems. Arrays of magnetic nanowires can constitute effective ordered spinning centers for the vortex lattice when they interact with type II superconducting films. Also, ordered magnetic nanowire arrays can be used in hybrid semiconductor/ferromagnetic systems to produce a periodic magnetic field that modulates, in a controlled fashion, the transport properties of two-dimensional electron gases (2 DEG). Technologically, applications of nanowire arrays are becoming increasingly important, especially in fields like high density magnetic recording (HD MR), magnetic random access memory (MRAM), sensors, switching and magneto electronics.

The fabrication of large arrays of ordered, ultra fine (~ 10 nm or smaller), uni-disperse nanoelements, remains challenging. More systematic studies of the magnetization reversal processes are necessary, including the associated dynamic effects in the short time scales. It also crucial to achieve a good understanding of interaction effects in arrays of nanowires or between magnetic nanowire arrays and other systems.

References

1. Wang, L.W., Liu, Y. and Zhang, Z. (2002) *Handbook of Nanophase and Nanostructured Materials*, Kluwers Academic Publishers, Dordrecht.
2. Sulitanu, N. (2002) *Electrochemical deposition of novel nanostructured magnetic thin films for advanced applications*, Mater. Sci. Eng. **B95**, 230-235.
3. Osaka, T. (2000) *Electrodeposition of highly functional thin films for magnetic recording devices of the next century*, Electrochimica Acta **45**, 3311-3321.
4. Raposo, V., Garcia, J.M., Gonzalez, J.M. and Vasquez, M. (2000) Long-range magnetostatic interactions in arrays of nanowires, *J. Magn. Magn. Mater.* **222**, 227-232.
5. Chiriac, H., Moga, A.E., Urse, M. and Ovari, T. – A. (2003) Preparation and magnetic properties of electrodeposited magnetic nanowires, *Sensors and Actuators A* **206**, 348-351.

6. Tourillon, G., Pontonnier, L., Levy, J.P. and Langlais, V. (2000) Electrochemically synthesized Co and Fe nanowires and nanotubes, *Electrochem. Solid-State Lett.* **3**, 20-23.
7. Yin, A.J., Li, J., Jian, W., Bennett, A.J. and Xu, J.M., (2001) Fabrication of highly ordered metallic nanowire arrays by electrodeposition, *Appl. Phys. Lett.* **79**, 1039-1041.
8. Fert, A. and Piroux, L. (1999) Magnetic nanowires, *J. Magn. Magn. Mater.* **200**, 338-358.
9. Henry, Y., Ounadjela, K., Piroux, L., Dubois, S., George, J.-M. and Duvail, J.-L. (2001) Magnetic anisotropy and domain patterns in electrodeposited cobalt nanowires, *Eur. Phys. J. B* **20**, 35-54.
10. Zhu, H., Yang, S., Ni, G., Yu, D. and Du, Y. (2001) Fabrication and magnetic properties of $\text{Co}_{67}\text{Ni}_{33}$ alloy nanowire array, *Scripta Mater.* **44**, 2291-2295.
11. Doudin, B., Redmond, G., Gilbert, S.E. and Ansermet, J. P. (1997) Magnetoresistance governed by fluctuations in ultrasmall Ni/NiO/Co junctions, *Phys. Rev. Lett.* **79**, 933-936.
12. Cohen, M.L. (2001) Nanotubes, Nanoscience and Nanotechnology, *Mat. Sci. Eng. C* **15**, 1-11.

AFM AS A MOLECULAR NUCLEIC ACID SENSOR

Ş. DOĞUTAN ÜLGEN, CENGİZ KOÇUM, EMRECAN ÇUBUKÇU, ERHAN PIŞKIN

Hacettepe University, Department of Chemical Engineering and Bioengineering Division 06532 Beytepe, Ankara, Turkey

Abstract: Model single strand DNA (ssDNA) was covalently immobilized onto Atomic Force Microscope (AFM) tips (cantilevers) as specific ligand. Then these tips were interacted with the buffer solutions with or without free ssDNA molecules as strand were used for comparison. Immobilization and hybridization onto the cantilever surfaces were observed by optical and fluorescence microscopies. Interactions between the AFM cantilever (tip) and the aqueous medium (therefore with the target ssDNAs) were quantified by obtaining the “percent descending distance” (“PDD”) as the main variable. The PDD values obtained for the buffer solutions were between -2.07 and +4.91%. There were slight increases in the negative values when a non-complementary ssDNA molecules were introduce into the buffer. However, after hybridization with its complemenray ssDNA, the PDD values were significantly increased (between -32.24 and -43.47 %). There was a correlation between the concentration of the complementary target ssDNA in the medium and the PDD value. However, there were significant changes from one AFM cantilever to another, which was considered as a problem to be solved. However, it was concluded that this approach may be further develop to create AFM based molecular sensors.

Keywords: AFM cantilevers/tip; nucleic acid molecular sensors; percent descending distance

1. INTRODUCTION

The ability for AFM to measure forces of 10 pN or less will make it an essential tool for measuring biological interaction. A number of studies have been performed to investigate serum albumin and its associated antibody using AFM (Ducker *et al.*, 1991; Stuart and Hlady, 1995; Hinterdorfer *et al.*, 1996; Williams and Blanc, 1994; Chowdhury and Lunckham, 1998). Streptavidin-biotin interactions have been studied with AFM (Lee *et al.*, 1994). Recently, the concept of cantilever-based biosensor techniques driven from AFM was proposed, in which the mechanical responses of the microcantilever due to changes surfaces stresses upon the interaction of the

ligands immobilized onto cantilever and the target molecules in the medium (Moulin *et al.*, 2000; Battiston *et al.*, 2001).

Sequence-specific hybridizations between nucleic acids, either in solution or immobilized on fixed support, are widely used for the detection and analysis of genetic material for diverse applications including identification of genetic diseases and disorders, detection and characterization of viruses, bacteria, and parasites, etc. (Symons, 1989; Downs, 1991).

Also interaction forces between the strands of DNA were measured with the AFM by a procedure in which DNA strands were covalently attached on probe and surface (Lee *et al.*, 1994). Recently, Holmberg *et al.* investigated the formation and modulation of a mixed molecular layer, containing single strand DNA (ssDNA) and a spacer arm (mercaptohexanol, MCH), immobilized on gold using in-situ AFM (Holmberg *et al.*, 2003). The introduction of the complementary DNA to the mixed monolayer of ssDNA and MCH resulted an increase in smoothness and thickness of the monolayer, which, they suggested in, is due to hybridization.

In this study we propose to use ssDNA, covalently bound (immobilized) onto AFM tips as a molecular nucleic acid sensor for the detection of the complementary strand by a very simple measurement using AFM.

2. MATERIALS AND METHODS

2.1 Materials

Three model DNA single strands given in Scheme 1 were studied. The first one was the “ligand” ssDNA (MWG Biotech AG, USA) it has one extra amino group at the 5’th-end for immobilization onto the AFM tips. The second one was the “target”, complementary ssDNA (MWG Biotech AG, USA). The third one was an arbitrarily selected non complementary ssDNA (Xeragon, USA), for compare and to show the nonspecific interactions between the non-complementary DNA chains. Nitric acid, aminopropyltrimethoxysilane, gluteraldehyde, fluorescent dyes, Hoechst, Orange G were purchased from Sigma Chemicals (USA). Standard silicone nitride cantilevers (tips) were purchased from Digital Instrument (USA).

2.2. Immobilization of the Ligand ssDNA onto AFM Tips

A two step procedure was applied to covalently attach the ligand ssDNA to the silicon nitride AFM tips for immobilization of antibody molecules onto AFM tips (Chowdhury and Lunckham, 1998) (Scheme 2). The conditions applied in these steps were optimized in the preliminary studies (Ülgen, 2003). Briefly, in the first step (“the silanization step”), the silicon nitride tips were treated with 10% nitric acid solution which was left in a silicone bath for 20 min at 80°C. This causes the formation of surface hydroxyl groups on the

Si₃N₄ tips. The tips were then thoroughly rinsed with distilled water and placed into 10% aminopropyltrimethoxysilane (APTS) solution with a pH of 7.0 adjusted with acetic acid for 4 h at 80°C. This treatment provides reactive primary amine groups on the nitride surface, and is known as the linker group. The surfaces were thoroughly rinsed with water. The tips were then reacted in 10% glutaraldehyde solution at room temperature for 1 h. Glutaraldehyde acts as a bridging agent between the solid support and the ssDNA. At the last step, the tips were left in 2 pmol/μL of the ligand ssDNA for 2.5 hr for immobilization, then the unbound DNA molecules were removed by rinsing with the buffer solution. A schematic view of the AFM tip as a molecular sensor is shown in Fig. 1.

(A) The “Ligand” DNA

(B) The “Target” Complementary DNA

(C) The “Non-complementary DNA

Scheme 1. Oligonucleotides used in this study: (A) Ligand ssDNA which is immobilized onto AFM tips; (B) the complementary strand (target DNA) which was dissolved in the medium; (C) the non-complementary DNA (used for comparison).

Scheme 2. Immobilization of the ligand ssDNA onto AFM tips: (A) Silanization; (B) attachment of glutaraldehyde; and (C) Immobilization of the ligand ssDNA, where “P” denotes the ssDNA strand.

Fig.1. Schematic description of the AFM tip prepared as a molecular nucleic acid sensor carrying the ligand ssDNA immobilized through gluteraldehyde molecules on the tip.

2.3. Microscopic Observations

In order to follow changes on the AFM cantilever surfaces after treatments, images of the surfaces were taken both with an optical microscope (Axioskop 20, Zeiss, Germany) and fluorescence inverted microscope (Olympus, Model IX70, Japan). Hoechst and Orange G (Sigma, USA) were used as fluorescence dyes for single strand and double strand DNA, respectively.

2.4. Measurements with AFM

The apparatus used for the measurements was a homemade atomic force microscope. To control the approach of the target solution to the AFM tips, a Burleigh Aris 11 Approach Module was used, which was controlled by a computer. In a typical test, the sample containing a pure buffer solution (phosphate buffer, pH: 7.4) or a buffer solution having the target (or non-target) ssDNA molecules was driven (+z direction) to the AFM tip (untreated or carrying the ligand ssDNA) until the tip touches the solution. It is waited at this position for about 10 min to complete hybridization (if there is any), and then the sample was driven to the opposite direction (+z direction) with a predetermined rate, 900 nm/sec (Ülgen 2003). The “separation distance”, or the so-called “the discenting distance” (in nm), at which the AFM tip gets rid of the solution that sticks on its surface, was measured. The “percent discenting distance” was calculated from the following equation and used as the main variable in this study.

$$\text{“Percent Discenting Distance”}(\%) = \{(L_1 - L_2) / L_1\} \times 100 \quad (1)$$

Where, L_1 : discenting distance for the reference solution (i.e., phosphate buffer) (nm); and L_2 : discenting distance for the same buffer solution containing the target ssDNA (nm). Note that the negative value shows the decrease in the interaction between the AFM tip and liquid phase.

For each AFM tip, phosphate buffer (pH: 7.4) was used as the reference. Then, separation distance was measured, without replacing the tip from tip holder or changing the position. The target DNA solution diluted with reference buffer solution, was added to the buffer and the same procedure was applied. To determine nonspecific bindings to the unmodified surface, unmodified AFM tips were also used. Measurements were repeated with the solutions containing the target complementary ssDNA at different concentrations (46.8, 117, 234, and 468 pmol ssDNA in 10 μ L buffer). To determine the non-specific interaction between the non-complementary DNA strands, the AFM tips carrying the ligand ssDNA were dipped in buffers containing only the non-complementary ssDNA (the third ss DNA given in Scheme 1).

3. RESULTS AND DISCUSSION

3.1. Microscopic Observations

Representative micrographs of the AFM cantilever taken with an optical microscope before and after chemical modifications are given in Fig. 2. There were no changes after the silanization step, while structures with different sizes on different parts of the cantilever surface, including at the top corner where the tip is located, were very much observable. It is not possible to see the individual glutaraldehyde (GA) molecules by optical microscopy, therefore, most probably these structures most probably some GA polymeric chains or aggregates that may occur during the treatment of the surfaces with GA. From these images we assumed that the other parts of the surface of both the cantilever and the tip were cover with GA surface groups (maybe evenly) that are available for further modifications.

Fig.2. Representative optical micrographs of the AFM cantilever: (A) untreated; (B) after silanization step; and (C) after glutaraldehyde attachment. Magnifications: $\times 100$. Pictures at the left colulfiltering.

Fluorescence microscopy images of the untreated and carrying the ligand ssDNA (before and after hybridization) were also taken. Note that two different fluorescent dyes, Hoechst and Orange G were used. The first one was utilized to observe the immobilized ligand ssDNA, while the second one was applied after the hybridization of the ligand DNA with its complementary, again on the AFM cantilever surfaces.

Figs. 3A and 3B give the representative fluorescent microscopy images of the untreated AFM cantilever, which show that there was no significant nonspecific adsorption of the dye molecules on the surfaces before ssDNA immobilization. Figs. 3C and 3D clearly exhibit that a high percentage of the cantilever surface (including the tip) was covered with the fluorescence dye Hoechst (means with the ligand ssDNA). In order to examine the specificity of the second fluorescence dye, namely Orange G, which should be specific for only double strand DNA (rather than for single strands), the fluorescence microscopy images of the cantilevers carrying only the immobilized ligand ssDNA. As seen in Figs. 3F and 3H, there was very low absorption of Orange G onto the cantilever carrying ssDNA. While Figs. 3E and 3G demonstrated that very significant orange color on a large part of the cantilever surface carrying the hybridized (double strand) DNA molecules.

Fig.3. Representative fluorescence microscopy images of the AFM cantilever: (A, B) before ssDNA immobilization; (C, D) carrying the immobilized ligand ssDNA (dyed with Hoechst); and (E, G) carrying the immobilized ligand ssDNA hybridized with its complementary (dyed with Orange G). (F, H) carrying the immobilized ligand ssDNA (dyed with Orange G)

3.2. Studies with AFM

In this study we applied a simple approach to detect a model target single strand ssDNA in solution by using an AFM tip (cantilever) carrying its complementary ssDNA as the ligand, which is prepared by the method given in the previous sections. It is well-known from the surface tension (contact angle) measuring systems that when a surface is dipped in (“descent”) and out (“ascent”) from a liquid, forces representing the interactions between the surface and liquid are measured, which is related to the surface tension of the

liquid (Hiemenz, 1986) and depend on not only the liquid phase properties but also on the surface properties (hydrophobicity, ionic charges, etc.)

In this study we used the “percent descending distance” (“PDD”) as the main parameter measured in the AFM sensor, which is calculated from Eq.1 as described above. The PDD values for five different nonmodified AFM cantilevers at room temperature are as follows: -3.88, +4.91, -3.59, -2.07 and +4.77 %. As seen here there are both positive and negative values, but not very significantly different from each other. This is expected, because the cantilevers, even if they are the product of the same company, have different surface characteristics. Also there is no specific interaction between SiN tips and DNA solution.

These AFM tips were then dipped into buffer solution containing the target (the complementary) ssDNA with a concentration of 468 pmol/10 μ L. The PDD values determined are as follows: -43.47, -35.12, -32.24, -32.45 and -38.31 %. These significant changes (about ten times compared to those obtained with the buffer solution alone, containing no DNA) are indication of the hybridization (double strand formation onto the surfaces, which caused changes of the surface properties, and therefore the PDD values. Interestingly, the values are quite close to each other, the differences are most probably due to differences in the surface properties of the original AFM cantilevers.

Table 1 shows the PDD values obtained for the experiments done with different concentration of the target ssDNA in the buffer solutions. Note that five AFM cantilevers were used in each group.

Table 1. Effects of concentration of the target DNA in phosphate buffer on the PDD values.

Concentration of the target ssDNA (pmol/10 μ L)	PDD Values (%) For the AFM Tip				
	1	2	3	4	5
468	-43.47	-35.12	-32.24	-32.45	-38.31
234	-30.69	-31.64	-28.98	-34.40	-33.42
117	-28.85	-27.67	-32.33	-27.77	-29.81
46.8	-29.72	-13.84	-12.85	-16.64	-10.41

As a general trend, can be seen here the PDD values decrease with the concentration of the target ssDNA in the medium. There is a non-linear relationship between PDD values and concentration. However, there are also strong fluctuations in the PDD values (changing from one AFM cantilever to another) which, we believe, may be improved by special design of the cantilevers that will be more suitable for these kinds of molecular sensor.

In order to exhibit the specificity of these AFM sensors, we have performed a final group of study, in which buffer solutions containing 468 pmol/10 μ L the non-complementary ssDNA (the third ssDNA given in

Scheme 1). The PDD values obtained with five different AFM cantilevers were as follows: +5.45, -6.26, -12.30, +6.07 and -6.98 %. Note that these values were slightly higher than those observed with pure buffer solutions, but clearly much lower than those observed for the hybridization with the complementary ssDNA (see the first line Table 1).

In conclusion these preliminary results show very strong promising application of AFM nucleic acid sensors not only for qualitative but also quantitative characterisation of the target complementary DNA in aqueous medium.

References

1. Battiston, F.M., Ramseyer, J.-P., Lang, H.P., Baller, M.K., Gerber, Ch., Gimzewski, J.K., Meyer, E., Güntherodt, 2001, A Chemical sensor based on a multifabricated cantilever array with simultaneous resonance-frequency and bending readout, *Sensors and Actuators B*, 77, 122.
2. Chowdhury, P.B., Luckham, P.F., 1998. Probing recognition process between an antibody and antigen using atomic force microscopy, *Colloids and Surfaces A, Physicochemical and Engineering Aspects*, 143, 53.
3. Downs, M.E.A., 1991. Prospects for nucleic acid biosensors. *Biochemical Society Transactions* 19, 39.
4. Ducker, W.A., Senden, T.J., Pashley, R.M., 1991. Direct measurements of colloidal forces using an atomic force microscope, *Nature* 353, 239.
5. Hiemenz, P.C., Ed., 1986. Principles of colloid and surface chemistry. *Marcel Dekker, Inc., New York*, 1986.
6. Hinterdorfer, P., Baumgartner, W., Gruber, H.J., Schindler, K., Schindler, H., 1995. Detection and localization of individual antibody-antigen recognition events by atomic force microscopy. *Proceedings of National Academy of Science USA* 93, 3477.
7. Holmberg, M., Kühle, A., Garnaes, J., Boisen, A., 2003. Hybridization of short DNA molecules investigated with in situ atomic force microscopy. *Ultramicroscopy* 97, 257.
8. Lee, G.U., Kiddwell, D.A., Colton, R.J., 1994. Sensing discrete streptavidin-biotin Interactions with atomic force microscopy, *Langmuir* 10, 354.
9. Lee, G.U., Chrisey, L.A., Colton, R.J., 1994. Direct measurement of the forces between complementary strands of DNA, *Science*, 266, 771.
10. Moulin, A.M., O'Shea, S.J., Welland, M.E., 2000, Microcantilever-based biosensors, *Ultramicroscopy*, 82, 23.
11. Stuart, J.K., Hlady, V., 1995. Effects of Discrete Protein-Surface Interactions in Scanning Force Microscopy Adhesion Force Measurements, *Langmuir* 11, 368.
12. Symons, R.H., 1989. Nucleic Acid Probes. *CRC Press, Boca Raton, FL*.
13. Ülgen, D., 2003. AFM based molecular biosensors. M.Sc. thesis, Hacettepe University, Ankara.
14. Williams R.A., Blanch H.W., 1994. Covalent immobilisation of protein monolayers for biosensor applications, *Biosensor and Bioelectronics* 9, 159.

ELECTROPHORETIC DEPOSITION OF ZnO THIN FILM IN AQUEOUS MEDIA

A. DOGAN, E. SUVACI, G. GUNKAYA, E. UZGUR
Anadolu University, Department of Materials Science and Engineering, Eskisehir/Turkey

Abstract: In thin films, controlled porous structures are desired for certain ceramic gas sensors. The aim of this study was to fabricate ZnO coated substrates starting with aqueous suspensions with electrophoretic deposition technique. Sub-micron sized ZnO particles were synthesized by using homogenous precipitation method. A 5 wt% ZnO aqueous suspension prepared for Electrophoretic Deposition (EPD) and an anionic dispersant was used as stabilizer. Electroded surface of the alumina substrates were coated with EPD technique at various voltages. Coated samples were sintered at 1200°C for two hours. Characteristics of the sintered ZnO coated substrates were investigated with SEM and XRD techniques.

1. INTRODUCTION

Chemical sensor research is focused on new studies to develop specific sensors. Producing smaller, more efficient devices is very important in the electronic industry and is pursued with increasing demand [1]. Some of the ceramic semiconductors such as tin oxide and zinc oxide with controlled porous bodies show an electrical conductivity as the response of trace amount of hydrocarbon based gases, hydrogen, and ammonia etc. at elevated temperature in air [2,3]. ZnO is one of the first and most widely used ceramic materials for sensor applications. Gas sensing in n-type semiconductor gas sensors like ZnO is achieved by the decrease in resistivity as a response of increasing amount of reducing gases in the air. The reason for a decrease in resistivity is explained by desorption of oxygen absorbed on the surface and grain boundaries of metal-oxides at high temperatures in air [3]. Furthermore, thin film type sensor devices are rising because of their low power consumption and easy integration into other devices. Film type devices can be fabricated with various techniques such as spray pyrolysis, sputtering, laser ablation, sol-gel method, MOCVD, CVD, PECVD, LPCVD, and LPE [4]. There is also another deposition technique, called electrophoretic (EPD), that involves migration of charged particles driven by an electric field in a liquid media by electric field to the surface of a substrate. Although, the above-mentioned techniques produce films with a limited thickness, the EPD

process can easily achieve thicknesses from 10nm to 1m, as seen on Fig.1. Because of its simplicity and versatility electrophoretic deposition might have potential for being the preferable technique for ceramic sensor applications. Accordingly there are some studies reporting the use of deposited ZnO films for sensor application. In this investigation, EPD techniques were used for the formation of ZnO thin films with controlled porosity on alumina substrates for sensor application.

2. EXPERIMENTAL PROCEDURE

Sub-micron sized ZnO particles were synthesized by using homogenous precipitation method [5]. The synthesized powders were characterized by using a particle size analyzer. It was observed that the particles were highly agglomerated even in 4 μ m size. To disperse the agglomerated particles a grinding process was employed. In this study, two types of milling, conventional and chemical added milling (CAM), were used to see the effect of dispersants on particle de-agglomeration during the milling of ZnO particles. The powder was milled for 22 hours.

Figure. 1. Comparison of different techniques by EPD [1].

An anionic dispersant was used for the chemical aided milling to stabilize the 5 wt% ZnO aqueous suspension prepared for Electrophoretic Deposition (EPD). After milling sedimentation experiments were performed to test the stability of suspensions from each milling process.

After obtaining a well dispersed medium EPD works were carried out under constant DC voltage. High-grade alumina (Coors Ceramics) with 1 in.² dimension was used as the substrate. The surfaces of the substrates were electroded with gold-palladium by sputtering process. A Pyrex glass deposition chamber was used for EPD studies due to its chemical and electrical inertness. By using stable suspension of ZnO, coating was done altering voltage and time. Coating was carried out in the range of 5-240 V. Coated samples were dried at room temperature to eliminate surface tension originated cracks [6]. Samples were sintered at 1200°C for two

hours. Characteristics of the sintered ZnO coated substrates were investigated by scanning electron microscope (SEM) and X-ray diffractometer (XRD).

3. RESULTS AND DISCUSSION

XRD pattern of synthesized powder shows that the formed phase is pure ZnO Fig.2.

Figure. 2. XRD chart of the synthesized ZnO powder.

Figure. 3. Effect of dispersant to the stability of ZnO particles in aqueous media. a) Beginning of sedimentation test of ZnO particles without dispersant b) Sedimentation of ZnO particles without dispersant after 10 minutes c) Starting point of sedimentation test of ZnO particles with dispersant d) Sedimentation of ZnO particles with dispersant after 6 hours e) Sedimentation of ZnO particles with dispersant after 24 hours.

ZnO powder in aqueous medium is stabilized using anionic polyelectrolyte by negatively charging the surface, Fig.3. shows the well dispersed suspension. The reason of choosing anionic polyelectrolyte was the dissolution of ZnO in acid.

The particles in chemical aided milling form a sediment within about 10 minutes and have a diameter of approximately 120nm. The prepared suspension had a conductivity of 0.87mS/cm and a pH of 8.4 so it was stable enough for EPD. This study shows that chemical milling is required to achieve stable suspension of ZnO particles Fig.3. Coating layers were formed with EPD. However, for sensor applications rather thin porous layers are preferable. For that reason we focused on coating layers around 10 μ m Fig.4. Fig.5 shows SEM photographs of sintered coatings for 2 hours at 1200°C. As it is seen on the figure it is possible to create porous structure. However, our pore distribution was not homogeneous and for sensor applications uniform porosity is required. As a next step of this research, homogeneous distribution of nanopores in EPD coated films will be investigated.

Figure. 4. SEM image of porous Al_2O_3 substrate and ZnO coating.

Figure. 5. SEM images of porous body by EPD after sintering 1200°C for 2 hours.

Density of the sintered body should be changed by using different powders, which have different grain sizes and sintering temperatures. In this experiment nearly 5 μ m powders and 2 μ m pores were get after sintering as seen on Fig.5.

4. SUMMARY

It has been demonstrated that the EPD technique can be utilized to form ZnO films with $\sim 10\mu\text{m}$ thickness for sensor applications. A stable suspension is necessary for a successful EPD process. The stable suspension of submicron ZnO particles can be achieved by chemically-aided milling approach.

Acknowledgements: The authors gratefully thank to C. A. Randall and J. Van Tassel of The Pennsylvania State University, MRI for their support. They also would like to thank Cem Caglar for the ZnO synthesis. This study is sponsored by Turkish State Planning Organization DPT (2003K120170).

References

1. OGATA, N., TASSEL, J. V. and RANDALL, C.A. (2001) Electrode formation by electrophoretic deposition of nanopowders, *Mater. Let.*, 49, 7-14.
2. TRIVIKRAMA RAO, G.S. and TARAKARAMA RAO, D. (1999) Gas sensitivity of ZnO based thick film sensor to NH_3 at room temperature, *Sensors and Actuators*, B 55, 166-169.
3. MOON, W. J., YU, J. H. and CHOI, G. M. (2002) The CO and H_2 gas selectivity of CuO -doped SnO_2 -ZnO composite sensor, *Sensors and Actuators*, B 87, 464-470.
4. CHOI, W. K., SONG, S.K., CHO, J. S., YOON, Y. S., CHOI, D., JUNG, H.J. and KOH, S. K., (1997) H_2 gas-sensing characteristics of SnO_x sensors fabricated by a reactive ion-assisted deposition with/without an activator layer, *Sensors and Actuators*, B 40, 21-27.
5. SAKKA, Y., HALADA, K., and OZAWA, E. (1988) *Ceramic Transactions- Ceramic Powder Science II A, Synthesis of ZnO Particles by the Homogeneous Precipitation Method*, The American Ceramic Society, Inc, Westerville, OH.
6. TANG, F., UCHIKOSHI, T. and SAKKA, Y. (2002) Electrophoretic Deposition Behaviour of Aqueous Nanosized Zinc Oxide Suspensions, *J. Am. Ceram. Soc.*, 85, 2161-2165.

SYNTHESIS AND OPTICAL SPECTROSCOPY OF SINGLE-WALL CARBON NANOTUBES

E.D. OBRAZTSOVA¹, M. FUJII², S. HAYASHI²,
A.S. LOBACH³, I.I. VLASOV¹, A.V. KHOMICH⁴,
V.Yu. TIMOSHENKO⁵, W. WENSELEERS⁶,
E. GOOVAERTS⁶

¹ *Natural Sciences Center of A.M. Prokhorov General Physics Institute,
RAS, 38 Vavilov str., 119991, Moscow, Russia,
elobr@kapella.gpi.ru*

² *Department of Electrical and Electronics Engineering, Kobe
University, 1-1 Rokkodai, Nada, Kobe 657-8501, Japan*

³ *Institute of Chemical Physics Problems, RAS, 142432,
Chernogolovka, Russia*

⁴ *Institute of Radio Engineering & Electronics, RAS, 11 Mokhovaya str.,
103907, Moscow, Russia*

⁵ *Physics Department of M.V. Lomonosov Moscow State University,
119899, Vorob'evy gory, Moscow, Russia*

⁶ *Department of Physics, University of Antwerp, 2610 Antwerp, Belgium*

Abstract: The abilities of three optical techniques (Raman scattering, UV-VIS-IR optical absorption and photoluminescence spectroscopy) for diagnostics of single-wall carbon nanotubes have been overviewed on example of nanotubes synthesized by two different methods - arc discharge and catalytical CO decomposition under high pressure.

Key words: Single-wall carbon nanotubes, Raman scattering, UV-VIS IR optical absorption, photoluminescence spectroscopy

1. INTRODUCTION

Discovery of carbon fullerenes and nanotubes has opened a new era in investigations of nanostructured materials. The existence of closed carbon shells has shown a possibility of self-organization of materials at nano-level leading to appearance of unique physical properties, often very different from those of bulk materials. As soon as a mass-production of carbon nanotubes has been developed [1], the diagnostics techniques being informative at typical distances 0.4-2 nm have been demanded. The optical methods appeared to be as effective as well-known high resolution structural methods (transmission electron microscopy, tunneling electron microscopy, atomic force microscopy). Data of optical measurements allowed to estimate a variety of single-wall carbon nanotube (SWNT) parameters: their diameters and chiralities, the distribution over diameters, rope diameters, conductivity type, positions of van Hove singularities in

one-electron density of states (DOS) for nanotubes of different geometry [2,3]. This work overviews possibilities of three optical methods – Raman scattering, optical absorption and photoluminescence spectroscopy- for diagnostics of single-wall carbon nanotubes, synthesized by two different techniques – direct dc-arc discharge and catalytical CO-gas decomposition under high pressure (HipCO).

2. EXPERIMENTAL

Nowadays more than fifteen different techniques are used for production of single-wall carbon nanotubes [4]. In this work we dealt with two of them: dc-arc discharge [5] and HipCO [6]. They have been chosen due to a big difference in geometrical parameters of tubes synthesized. For arc-produced material an average tube diameter is about 1.3-1.4 nm. Tube distribution over diameter is quite narrow (0.2-0.3 nm). For HipCO nanotubes the diameters vary in much wider range - from 0.7 nm to 2.0 nm.

The arc nanotubes have been produced with a home-made apparatus (Fig.1). The synthesis has been performed in helium atmosphere with

FIGURE 1. A scheme of dc-arc apparatus for SWNT synthesis.

FIGURE 2. HRTEM image of arc-produced SWNT rope .

Ni:Y₂O₃ catalyst [7]. The raw material, containing about 20 weight % of SWNT, aggregated into ropes (Fig.2) [8], has been purified partially by chemical method, including the successive steps of acid treatment and oxidative annealing [9].

A commercially available raw HipCO material (Carbon Nanotechnologies, Inc., Houston, TX) has been used. A nanotube content was 80% already in the raw material. A high pressure (30 atm) of a buffer gas during synthesis (Fig.3) [6] provided a super-saturation of the catalyst particle with carbon atoms, resulting in a high yield of nanotubes and a presence of small-diameter nanotubes in the soot. HRTEM confirms a wide distribution of nanotubes over diameter in HipCO material [10].

FIGURE 3. A scheme of apparatus for HipCO SWNT synthesis [6].

FIGURE 4. A cross-sectional HRTEM image of HiPCO nanotube rope.

The UV-VIS-NIR absorption spectra of SWNT dispersed in 2%-solution of SDS (sodium dodecyl sulfate) in D₂O were taken with a spectrophotometer (*Shimadzu UV-3101PC*), equipped with a double monochromator. It covered a wavelength range between 200 and 1800 nm. The SDS/D₂O solution without nanotubes was used as a reference sample in a second channel of the spectrometer. D₂O (instead of H₂O) was used to avoid the strong absorption bands of water in IR spectral range. For the rope disintegration the suspension was treated with *Tomy ultrasonic disruptor UD-201* (1 hour, power 40 W), followed by ultracentrifugation (*Himac CS150GX, Hitachi*) during 1 hour with acceleration 265 000 g. The upper fraction of the solution has been taken for measurements.

The Raman spectrometer *Jobin Yvon S-3000* was used. The spectra were excited by irradiation of Ar⁺-ion laser with different wavelengths. In some cases the radiation of *Ti: sapphire laser* was used also.

For photoluminescence (PL) measurements a 90°- geometry was used: the SWNT suspension in a quartz cell was excited from the side and the

photoluminescence signal was collected from the front surface of the cell. The emitted light was focused on the slit of a single monochromator (30 cm focal length) and detected by a liquid nitrogen cooled InGaAs CCD (Princeton instruments). The excitation was made by a continuous wave *Ti: sapphire laser* (Spectra Physics Model 3900S) pumped with 532-nm diode-pumped solid state laser. The wavelength range covered by *Ti: sapphire* laser was between 700 and 1000 nm.

3. RAMAN SPECTROSCOPY OF SINGLE-WALL CARBON NANOTUBES

Raman technique appeared to be very efficient for identification of SWNT and characterization of their geometrical parameters. Among various carbon materials only SWNT demonstrates a split tangential Raman mode at 1592 cm^{-1} simultaneously with the acoustical Raman modes in the range $100\text{--}400\text{ cm}^{-1}$ [13,3]. They correspond to radial “breathing” vibrations of nanotubes of different diameter, constituting the material. There were a lot of discussions about a quantitative correspondence between the Raman “breathing” mode frequency and the nanotube diameter value. One of the most plausible formulas is

$$\omega = \frac{C_1}{d} + C_2, \quad (1)$$

FIGURE 5. The typical Raman spectra for arc- and HiPCO-produced single-wall carbon nanotubes and for HOPG (as a reference).

where ω is measured in cm^{-1} , d is measured in nm , $C_1=234$, $C_2=10\text{ cm}^{-1}$ [11]. The tube diameter estimation may be improved after comparison of

FIGURE 6. A schematic view of one-electron DOS for a two-dimensional graphite sheet (left), and for a single-wall carbon nanotube (right).

FIGURE 7. The Raman spectra of HiPCO single-wall carbon nanotubes registered with different laser excitation wavelengths.

the Raman and photoluminescence (*PL*) data for the same tubes [12]. The Raman spectra of two types of SWNT materials (arc and HiPCO) and for HOPG (highly oriented pyrolytic graphite), are shown in Fig. 5. The number and positions of the “breathing” Raman modes indicate that a tube diameter distribution is much wider for HiPCO material than for the arc one. A different shape of the tangential modes [3] points to a preferable contribution to the Raman signal of semiconducting nanotubes in arc material and metallic nanotubes in HiPCO material (for $\lambda_{\text{exc}}=514.5 \text{ nm}$).

Due to a quantum-scale circumference of a nanotube its electronic structure is different from that of graphite (Fig. 6). Two-dimensional graphite is a zero-gap semiconductor (Fig. 6, left). A nanotube may have semiconducting or metallic properties depending on the diameter value

FIGURE 8. The optical absorption spectrum for suspension of arc-produced single wall carbon nanotubes in 2% SDS/D₂O solution.

FIGURE 9. The optical absorption spectrum for suspension of HipCO single-wall carbon nanotubes in 2% SDS/D₂O solution.

[2]. One electron density of states (DOS) for nanotube looks as a set of the discrete maxima symmetric relative to Fermi level (E_F) (Fig.6, right). A separation of the maxima depends on the tube diameter. Optical transitions are allowed between the symmetrical maxima: E_{11} , E_{22} , E_{33} , etc. If the laser photon energy coincides with one of the transitions a resonance Raman scattering condition is realized for the tube with a fixed diameter. A laser tuning provides a step-by-step selective Raman

excitation of all tubes constituting the material. This is an efficient way to estimate a tube diameter distribution. Fig. 7 shows Raman spectra of HiPCO material registered with the different excitation energies ranging from 1.66 eV (746 nm) to 2.54 eV (488 nm) [10]. The contributions of nanotubes with diameters from 0.8 nm to 1.5 nm are evident.

4. OPTICAL ABSORPTION SPECTROSCOPY OF SINGLE-WALL CARBON NANOTUBES

The efficiency of UV-VIS-IR (ultraviolet-visible-infrared) optical absorption spectroscopy for SWNT diagnostics has been demonstrated in the first time by H. Kataura et al. [14]. The absorption demonstrates features corresponding to E_{11} , E_{22} , E_{33} ... optical transitions. Each nanotube material contains an ensemble of different nanotubes rather than a mono-diameter fraction. Due to this the features in the absorption spectrum should be broadened in accordance with the nanotube distribution over diameter. A raw nanotube material usually includes a lot of contaminations (polyhedral graphitic particles, amorphous carbon, catalyst particles, etc.). Their optical absorption contributes to the spectrum background. To reduce the background a suspension of SWNT in 2% solution of SDS in D_2O , treated by ultrasonication and ultracentrifugation, was used for the measurements.

The optical absorption spectrum of arc-produced nanotubes is shown in Fig.8. The absorption bands corresponding to E_{11} (centered at 1735 nm), E_{22} (1011 nm) and E_{33} (516 nm) transitions for semiconducting nanotubes and E_{11} (690 nm) transition for metallic nanotubes are well pronounced. The absorption band widths (about 0.1 eV) confirm a narrow distribution of arc nanotubes over diameter: 1.4 ± 0.15 nm. There are two local maxima in absorption at 1350 nm and 1080 nm. They may be ascribed to the smallest arc nanotubes. The photoluminescence measurements have shown that these maxima actually correspond to E_{11} transition.

The spectrum of HiPCO nanotubes is shown in Fig.9. Due to a wide distribution of nanotubes over diameter the bands corresponding to E_{11} , E_{22} , E_{33} ... optical transitions are not separated in this case. The resolved peaks observed may be considered as the absorption of the individual tubes of fixed geometry. The peak widths (about 0.03 eV) are very close to a thermal broadening of the absorption bands.

5. PHOTOLUMINESCENT SPECTROSCOPY OF SINGLE-WALL CARBON NANOTUBES

Recently an efficiency of *photoluminescence (PL) spectroscopy* for characterization of single-wall carbon nanotubes has been demonstrated [15-17]. From general principles the semiconducting tubes should demonstrate the photoluminescence in any case of optical excitation with the photon energy exceeding the gap value. In practice, during several years all attempts to observe PL signal from carbon nanotubes failed. The

problem has been solved only when experimentalists have succeeded in disintegration of ropes into individual nanotubes. The rope is not a chaotic agglomeration of individual nanotubes (Fig.2, Fig.4). It is a one-dimensional crystal consisting of aligned nanotubes with van der Waals interaction between them. The tubes in the same rope may have different geometry [18]. Depending on geometry they are metals or semiconductors. Usually there are few metallic nanotubes in each rope. They serve as a non-radiative channel for relaxation of excitation occurred in the neighboring semiconducting tubes. Due to this relaxation no photoluminescence signal is observed.

This obstacle may be overcome by disintegration of nanotube ropes via interaction with the surfactant molecules under ultrasonic treatment in the water suspensions. This process leads to formation of surfactant-coated micelles. There are three types of micelle nucleus: an individual tube, a rope fragment (containing a few tubes) or a carbon nanoparticle. The single-tube micelles constitute a lightest fraction of the suspension. Namely this fraction should demonstrate PL. For the lightest micelle separating the suspension is subjected to ultracentrifugation followed by decanting of the upper fraction.

An electronic DOS for SWNT has only one real gap (E_{11}). All others are called "pseudo"-gaps due to a presence of a very small, but non-zero DOS between the symmetric van Hove singularities (Fig.10). This means that PL emission process is possible only for E_{11} electronic transition, while for PL excitation any wavelength in a wide spectral range may be used. As a result, a spectral structure of PL peak for a given nanotube material informs about a set of energies of the first electronic transitions and, as a consequence, about the diameters and geometries of nanotubes, constituting the material.

The photoluminescence spectra of *arc* (Fig.11) and *HiPCO* (Fig.12) nanotubes have demonstrated different sets of E_{11} peaks. A comparison of PL peak positions with the Raman data (Fig.7) taken with the same excitation energy ($E_{exc}=2.33$ eV, $\lambda=532$ nm) has allowed to estimate the

Figure 10. A scheme of PL excitation in individual semiconducting carbon SWNT. **CB**- conduction band. **VB**- valence band. DOS has shown as a set of van Hove singularities. The dashed lines show non-radiative transitions for electrons and holes [16].

individual tube geometries [17]. The indices (n,m) are indicated above the PL peaks in Fig.11 and Fig.12. PL data have confirmed the estimations of the tube diameter distributions for *arc* and *HipCO* materials made by Raman and UV-VIS-NIR techniques.

FIGURE 11. The photoluminescence (upper) and the optical absorption (lower) spectra for the suspension of *arc-produced* SWNT in 2% -SDS/D₂O solution.

FIGURE 12. The photoluminescence (upper) and the optical absorption (lower) spectra for the suspension of HipCO SWNT in 2% -SDS/D₂O solution.

5. CONCLUSION

A complex optical diagnostics based on Raman, UV-VIS-NIR absorption and photoluminescence techniques, has been demonstrated as

an efficient tool for structural characterization of single-wall carbon nanotubes synthesized by different methods.

Acknowledgements: The work is supported by INTAS project 01-254 and by programs of Russian Academy of Sciences “Low-dimensional Quantum structures” and “Optical Spectroscopy and Frequency Standards”.

References

1. A. Thess, R. Lee, P. Nikolaev et al., *Science* **273** (1996) 483.
2. M.S. Dresselhaus, G. Dresselhaus, P. Avouris, “*Carbon Nanotubes: Synthesis, Structure, Properties and Applications*”, Springer, 2001.
3. M. Dresselhaus, G. Dresselhaus, A. Jorio et al., *Carbon* **40** (2002) 2043.
4. C. Journet, P. Bernier, *Appl. Phys. A* **67** (1998) 1.
5. C. Journet, W.K. Maser, P. Bernier et al., *Nature* **388** (1997) 756.
6. P. Nikolaev, M.J. Bronikowski, et al., *Chem. Phys. Lett.* **313** (1999) 91.
7. E.D. Obratsova, J.-M. Bonard, V.L. Kuznetsov et al., *NanoStructured Materials* **12** (1999) 567.
8. V.L. Kuznetsov, A.N. Usoltseva, et al., *Phys. Rev.* **B64** (2001) 235401.
9. S.V. Terekhov, E.D. Obratsova, A.S. Lobach, V.I. Konov, *Appl. Phys. A* **74**, 393 (2002).
10. E.D. Obratsova, S.N. Bokova, V.L. Kuznetsov et al., *AIP Conferences Proceedings*, v. 685 (2003) 215.
11. H. Kuzmany, W. Plank, M. Hulman et al., *Eur. Phys. J.* **B22** (2001) 307.
12. M.S. Strano, *J. Am. Chem. Soc.* **125** (2003) 16148.
13. A. M. Rao, E. Richter, S. Bandow et al., *Science* **275** (1997) 187.
14. H. Kataura, Y. Kumazawa, Y. Maniwa et al., *Synth. Met.* **103** (1999) 2555.
15. M. O'Connell, S.M. Bachilo, C.B. Huffman et al., *Science* **297** (2002) 593.
16. S.M. Bachilo, M.S. Strano, C. Kittrel et al., *Science* **298**, 2361 (2002).
17. R.B. Weisman, S.M. Bachilo, *NanoLetters* **3** (2003) 1235.
18. E.D. Obratsova, V.Yu. Yurov, V.M. Shevluga et al., *NanoStructured Materials* **11**(1999) 295.

AQUEOUS FLUIDS IN CARBON NANOTUBES: ASSISTING THE UNDERSTANDING OF FLUID BEHAVIOR AT THE NANOSCALE

Almila G. Yazicioglu, Constantine M. Megaridis
*Department of Mechanical and Industrial Engineering, University of
Illinois at Chicago, Chicago, IL, 60607, USA*

Nevin Naguib, Haihui Ye, Yury Gogotsi
*Department of Materials Engineering, Drexel University, Philadelphia,
PA, 19104, USA*

Abstract: Transmission electron microscopy (TEM) experiments are performed on carbon nanotubes filled with a multiphase aqueous fluid. It is shown through high resolution TEM that the dense aqueous fluid wet the inner surface of the carbon nanotube, possibly due to the presence of oxygen-based groups, which modify the carbon surface such that it becomes hydrophilic. Electron energy loss spectroscopy (EELS) analysis confirms the presence of oxygen inside the fluid-filled nanotubes, as well as on the inner and outer surfaces of the nanotube walls. Fluid experiments involving controlled liquid evaporation and condensation, as driven by external heating, demonstrate that liquid transport in nanochannels of less than 100 nm in diameter is achievable. The present results offer promise for the development and functional performance of future micro- and nanofluidic devices.

Keywords: Carbon nanotubes, liquid transport, wetting, hydrophilic

1. INTRODUCTION

The study of carbon nanotubes has been a rapidly progressing research area for the past decade. Most of the ongoing research is focussed on nanotube structure and their electronic, transport and optical properties [1]. However, multiwall carbon nanotubes also show potential for use in various micro- and nanofluidic devices, since they resemble cylindrical channels used in the macroscopic world. They provide a test platform orders of magnitude smaller than capillaries used in previous fluid experiments that allowed in-situ observations of fluid phenomena. It is therefore essential to investigate their thermal and fluidic properties.

Understanding fluid behavior at the nanoscale would facilitate the effective design and operation of future micro- and nanofluidic devices, such as drug delivery systems, biosensors and micro heat pipes. Fluid behavior in carbon nanotubes may be significantly different from that in conventional pipes, even microcapillaries. However, very few studies have been reported on the dynamic behavior of fluids at the nanoscale [2,3]. Some reports have shown that nanotubes can be filled partially with salts, molten metals, and metal oxides, such as lead [4,5], silver [5,6], chromium oxide [7], and cobalt [8] through capillarity if the liquid shows good wettability of the inner carbon walls. The procedure in these studies was either a chemical method, such as wet chemistry, or a physical method, such as capillarity induced filling. In either case, little has been reported on the *dynamic* aspects of fluid filling and fluid transport in the nanotubes. Molecular dynamics simulations of water in cylindrical nanopores showed that confined water remains fluid and bulk-like [9]. Hummer et al. [10] performed molecular dynamics simulations and observed pulse-like transmission of a one-dimensionally ordered chain of water molecules through a nanotube, due to the tight hydrogen-bonding network inside the tube. Noon et al. [11] reported that water molecules inside nanotube segments tend to organize themselves in a solid-like network, due to the hydrogen-bonding, in forms of wrapped-around ice sheets. In all of the abovementioned cases, the diameter of the channel was no more than 2 nm, which may be too small for nanofluidic applications. Furthermore, most of these theoretical studies lack experimental verification.

The objectives of this study are to investigate high quality multi walled carbon nanotubes with aqueous fluid inclusions, and to perform high resolution in-situ thermal experiments using electron irradiation as a means of heating the contents of individual nanotubes in the high vacuum of a transmission electron microscope (TEM) column. Wetting of these nanotubes by the aqueous liquid is observed with high resolution microscopy as well. As the fluids investigated herein are contained at very high pressures (hundreds of atmospheres), the present work offers a unique opportunity for studying the dynamic behavior of multicomponent, multiphase fluids in nanosize channels at conditions corresponding to sub-, near- or even super-critical regions of the thermodynamic diagram, which may help create an experimental database for the parallel development of theoretical models describing fluid behavior in nanosize channels.

2. EXPERIMENTAL

The nanotubes are synthesized hydrothermally from a mixture of ethylene glycol, de-ionized water, and Ni powder (catalyst) sealed into gold capsules, using a two-step process, see procedure in Ref. 12. This procedure produces nanotubes, which have high aspect ratios, high degree of graphitization, and smooth internal walls, with wall thickness $\sim 10\text{-}25$ nm (30-70 fringes per wall), outer diameter ~ 100 nm, and lengths $1\text{-}10$ μm . They are rarely open-ended, while most of the closed-end nanotubes encapsulate a high-pressure multiphase aqueous fluid, displaying segregated liquid and gas inclusions with clearly defined interfaces [13,14]. A schematic of this system can be seen in Fig. 1. The composition of the multicomponent fluid at room temperature is predicted to be 85.2% H_2O , 7.4% CO_2 , and 7.4% CH_4 , with traces of H_2 and CO , as based on thermodynamic calculations performed at the synthesis conditions [15]. It is also estimated that this composition is almost independent of pressure at room temperature [16].

Figure 1 Schematic of the experimental system utilized in this work. The dot-shaded areas show aqueous liquid inclusions constrained by curved menisci.

TEM samples are prepared by dispersing the hydrothermal synthesis products in ethanol, then depositing the nanotube-containing liquid onto lacey carbon grids. The nanotubes remain attached to the carbon grid after evaporation of the liquid carrier. Thermal experiments are performed using electron irradiation as a means of heating the contents of individual nanotubes in the high vacuum of the TEM (JEOL JEM-3010, 300 kV, 0.14 nm lattice resolution), where the multiphase fluid is excited by expanding/contracting the low-intensity electron beam. The dynamics of the fluid phenomena in the nanotubes are visualized and recorded using a CCD camera and a Betacam video recorder.

The nanotubes in the present study are leak-tight, often for days, and they can maintain the pressurized fluid in the vacuum environment of a TEM column ($\sim 10^{-6}$ Pa) even at temperatures above 500°C , thus demonstrating a high strength and wall perfection. This makes them very suitable for studying dynamic fluid behavior at length scales possibly approaching the continuum limit. Moreover, the superior smoothness of their inner surfaces and the

excellent definition of fluid interfaces make these nanotubes a perfect candidate for contact-line and wettability studies at the nanoscale.

3. RESULTS AND DISCUSSION

High-resolution TEM experiments performed on liquid-carbon interfaces, such as the ones presented in Fig. 1, revealed that the aqueous fluid wet the inner surface of the carbon nanotube. Previously there have been contradictory reports on the hydrophobic/philic behavior of carbon. Dujardin *et al.* [17] suggested that materials with surface tensions lower than 100-200 mN/m should be drawn into the nanotube via capillarity. Also, Ebbesen [18] reported experiments of placing a droplet of water (surface tension 73 mN/m) on a bundle of carbon nanotubes; the water was sucked into the nanotube channels, leaving a dry surface. On the other hand, Li *et al.* [19] studied experimentally the wettability of aligned carbon nanotubes, and reported the contact angle for water droplets on untreated aligned nanotube films to be $\sim 160^\circ$, which confirmed super-hydrophobic behavior of the aligned carbon nanotube films. In another experiment [20], the maximum contact angle measured for a nanosize water droplet on a graphite surface was reported to be about 30° . However, it was noted therein that the value would be higher for a macroscopic water droplet, and that atmospheric aerosols may be responsible for altering the highly hydrophobic character of the graphite substrate.

EELS analysis performed on a multiwall carbon nanotube with trapped aqueous fluid revealed that oxygen is present inside the nanotube, as well as on the inner and outer surface of the nanotube walls [21]. Figure 2 presents the composite EELS map of oxygen and carbon distribution in a carbon nanotube with trapped fluid inside, where the brighter areas indicate the presence of oxygen. As can be seen from this image the fluid is rich in oxygen, and traces of oxygen are also present on the inner and outer walls of the carbon nanotube. This result indicates that the surface of the carbon nanotube can adsorb oxygen, leading to the formation of functional groups, such as hydroxyl, which have been shown to transform the carbon nanotube surface to a hydrophilic one [19].

Figure 2 Composite EELS map of oxygen and carbon distribution in a carbon nanotube with trapped fluid inside. Brighter areas indicate more intense presence of oxygen. The nanotube wall is marked by thick white lines. Traces of oxygen are present on the inner and outer walls of the nanotube. Scale bar 50 nm.

Structural changes have been seen in the graphite layers in contact with the liquid inside the carbon nanotube. This concept is presented in Fig. 3. Layers of graphite sheets terminating at the inner surface of the nanotube often bend away from the wall, towards the axis of the nanotube, in the presence of a thin aqueous liquid layer. It should be mentioned that similar changes occur on the outer nanotube wall due to the presence of the fluid on both sides of the wall during the hydrothermal synthesis process, which clarifies the adsorption of oxygen on the outer wall, as shown on the EELS map. Three inner sheet endings are shown, marked by arrows, in Fig. 3(a), with the corresponding schematic for possible attachments of functional groups presented in Fig. 3(b). When graphite sheets are terminated with oxygen based groups, as shown in Fig. 3(b), this allows water bonding to the inner wall of the nanotube, thus rendering the surface hydrophilic.

As an example of the dynamic phase change experiments performed in this work, an amount of the aqueous liquid was transported from one end of a closed carbon nanotube compartment, 100 nm in diameter, to the other end via evaporation and condensation. Initially, the liquid inclusion was constrained between an internal closure and a long gas bubble. Adjacent to the gas bubble was another internal closure, encapsulating the liquid and the gas in a closed compartment of the carbon nanotube, about 1 μm long. The experiment consisted of gently heating the liquid via electron irradiation, by

focusing the beam around the inclusion. As the electron beam was contracted, the liquid gradually evaporated upon heating. When the heating was ceased, approximately 65% of the liquid had been evaporated. The field of view was then moved to the other end of the nanotube, which was relatively cool during the heating of the liquid-containing end, and it was seen that the liquid had condensed there. This experiment demonstrates that the transport of liquids in response to external thermal stimulation is possible in nanochannels.

Figure 3 Structural changes occur in the graphite layers that come in contact with the liquid inside the carbon nanotube. (a) Arrows show graphite sheets terminating at the inner surface of the nanotube, bending away from the wall in the presence of the liquid. Scale bar 2 nm. (b) Oxygen based groups attached to carbon allow water bonding to the inner wall of the nanotube.

4. CONCLUSIONS

Carbon nanotubes with aqueous fluid inclusions have been used as a test platform for unique in-situ nanofluidic experiments in the TEM. It has been shown that the aqueous fluid wet the inner surface of the carbon nanotube,

possibly due to the formation of functional groups, such as hydroxyl, which render the surface hydrophilic. The results demonstrate the feasibility of liquid transport in response to external thermal stimuli in pipes of <100 nm in diameters, which could allow for future development of various micro- and nanofluidic devices.

References

1. R. Saito, G. Dresselhaus and M. S. Dresselhaus, *Physical Properties of Carbon Nanotubes*. Imperial College Press, London, 1998.
2. V. D. Sobolev, N. V. Churaev, M. G. Velarde, and Z. M. Zorin, Surface Tension and Dynamic Contact Angle of Water in Thin Quartz Capillaries, *Journal of Colloid and Interface Science*, vol. 222, pp. 51-54, 2000.
3. V. N. Bogomolov, Capillary Effects in Ultrathin Channels, *Soviet Physics-Technical. Physics*, vol. 37, pp. 79-82, 1992.
4. P.M. Ajayan and S. Iijima, Capillarity-induced Filling of Carbon Nanotubes, *Nature*, vol. 361, pp. 333-334, 1993.
5. D. Ugarte, T. Stockli, J.M. Bonard, A. Chatelain, and W.A. de Heer, Filling Carbon Nanotubes, *Applied Physics A*, vol. 67, pp. 101-105, 1998.
6. J. Sloan, D.M. Wright, H.G. Woo, S. Bailey, G. Brown, A.P.E. York, K.S. Coleman, J.L. Hutchison, and M.L.H. Green, Capillarity and Silver Nanowire Formation Observed in Single Walled Carbon Nanotubes, *Chemical Communications.*, vol. 8, pp. 699-700, 1999.
7. J. Mittal, M. Monthieux, H. Allouche, and O. Stephan, Room Temperature Filling of Single-wall Carbon Nanotubes with Chromium Oxide in Open Air, *Chemical Physics Letters*, vol. 399, pp. 311-318, 2001.
8. Y.L. Hsin, K.C. Hwang, F.R. Chen, and J.J. Kai, Production and In-situ Metal Filling of Carbon Nanotubes in Water, *Advanced Materials*, vol. 13, pp. 830-833, 2001.
9. R. Allen, S. Melchionna, and J.P. Hansen, Intermittent Permeation of Cylindrical Nanopores by Water, *Physical Review Letters*, vol. 89, pp. 175502-1-4, 2002.
10. G. Hummer, J.C. Rasaiah, and J.P. Noworyta, Water Conduction through the Hydrophobic Channel of a Carbon Nanotube, *Nature*, vol. 414, pp. 188-190, 2001.
11. W.H. Noon, K.D. Ausman, R.E. Smalley, and J. Ma, Helical Ice-sheets inside Carbon Nanotubes in the Physiological Condition, *Chemical Physics Letters*, vol. 355, pp. 445-448, 2002.
12. J. Libera and Y. Gogotsi, Hydrothermal Synthesis of Graphite Tubules using Ni Catalyst, *Carbon*, vol.39, pp. 1307-1318, 2001.
13. Y. Gogotsi, J. Libera, A.G. Yazicioglu, and C.M. Megaridis, In situ Multiphase Fluid Experiments in Hydrothermal Carbon Nanotubes, *Applied Physics Letters*, vol. 79, pp. 1021-1023, 2001.
14. C.M. Megaridis, A.G. Yazicioglu, J.A. Libera, and Y. Gogotsi, Attoliter Fluid Experiments in Individual Closed-end Carbon Nanotubes: Liquid Film and Fluid Interface Dynamics, *Physics of Fluids*, vol. 14, pp. L5-L8, 2001.
15. Y. Gogotsi, T. Kraft, K.G. Nickel, and M.E. Zvanut, Hydrothermal Behavior of Diamond, *Diamond and Related Materials*, vol. 7, pp. 1459-1465, 1998.
16. Y. Gogotsi, N. Naguib, and J.A. Libera, In situ Chemical Experiments in Carbon Nanotubes, *Chemical Physics Letters*, vol. 365, pp. 354-360, 2002.
17. E. Dujardin, T. W. Ebbesen, H. Hiura, and K. Tanigaki, Capillarity and Wetting of Carbon Nanotubes, *Science*, vol. 265, pp. 1850-1852, 1994.
18. T. W. Ebbesen, *Annual Review of Materials Research*, vol. 24, p. 235, 1994.
19. H. Li, X. Wang, Y. Song, Y. Liu, Q. Li, L. Jiang, and D. Zhu, Super-"amphiphobic" Aligned Carbon Nanotube Films, *Angewandte Chemie International Edition English*, vol. 40, pp. 1743-1746, 2001.

20. M. Luna, J. Colchero, and A. M. Baro, Study of Water Droplets and Films on Graphite by Noncontact Scanning Force Microscopy, *Journal of Physical Chemistry B*, vol. 103, pp. 9576-9581, 1999.
21. Y. Gogotsi, N. Naguib, H. Ye, A.G. Yazicioglu, and C.M. Megaridis, Analysis of Fluid in Hydrothermal Fluids, *Proc. Electrochemical Society*, in *Fullerenes vol. 12: The Exciting World of Nanocages and Nanotubes*, pp. 451-459, 2002.

NANOFABRICATION OF CARBON NANOTUBE (CNT) BASED FLUIDIC DEVICE

M. Riegelman¹, H. Liu¹, S. Evoy², and H. H. Bau^{1,*}

¹*Department of Mechanical Engineering and Applied Mechanics,
University of Pennsylvania, Philadelphia, PA 19104*

²*Department of Electrical and Systems Engineering, University of
Pennsylvania, Philadelphia, PA 19104*

Abstract: A method for the fabrication of nanotube and nanopore based fluidic devices is described. With the aid of dielectrophoresis, a tube is assembled in the gap between two electrodes that were patterned on a silicon or glass wafer. Subsequently, standard microfabrication techniques were applied to fashion fluidic conduits and wells to facilitate fluid transport through the tube. The device will be used for fundamental studies of the transport of fluids and macromolecules under nanometer scale confinement and as a high sensitivity biosensor. We describe experimental observations of the trapping of a single tube, the fractal patterns formed when the process is allowed to proceed for an extended period of time, and the construction of a nanotube based fluidic device.

1. INTRODUCTION

Recent advances in the synthesis of nanotubes and nanofibers offer numerous opportunities for fundamental studies of transport and interactions under extreme confinement, and for the development of novel, highly sensitive sensors and measurement techniques. As one example of a nanotube-based sensor, we describe the fabrication of a Coulter counter-like device [1]. The device is described schematically in Figure 1.

Figure 1: A schematic depiction of a cross-section of the Coulter counter- type device

The device consists of a nanotube positioned between two wells. Both the wells and the tube are filled with ionic solution. Functionalized particles or macromolecules are introduced in the left well. An electric field is applied across the tube, and the ionic electric current is continuously measured. The electric field causes the particles/macromolecules to (electrophoretically) migrate through the tube. As a particle enters the tube, it interferes with the current flow, causing a depression in the current's magnitude. By monitoring and analyzing the current's intensity as a function of time, one can obtain information on the particle's size and characteristics.

The Coulter Counter can be used as a chemical or biological sensor. As analytes bind to functionalized nanoparticles, the apparent size of the particles changes and can be detected through the monitoring of the alternation in the magnitude of the electric current as the particles pass through the pore. The smaller the pore diameter is, the greater the device's sensitivity.

In this paper, we briefly describe a novel technique for fabricating the nanotube-based device. Since the nanotubes are too small to manipulate mechanically, we utilize dielectrophoresis to assemble the tubes at predetermined locations. Subsequently, standard photolithographic techniques are used to fabricate the wells and the microfluidic conduits.

2. DEVICE FABRICATION

Our device, depicted in Figure 2, was fabricated through a combination of standard microfabrication processes and dielectrophoretic trapping of individual carbon nanotubes.

Figure 2: A SEM image of the nanotube-based fluidic device. SU-8 photoresist spun over a substrate with trapped nanotubes was developed to form fluidic interconnects.

First, on a SiO_2 coated silicon wafer, six Au electrodes were patterned using the liftoff process. Two of the electrodes with $8\mu\text{m}$ gap spacing, were used for nanotube trapping. Other two electrodes were used for driving

particles through the carbon nanotube (CNT) pore, and the last two electrodes were used for sensing through a current or resistance spike, when the particles traveled through the CNT. The electrode layout is depicted in Figure 3.

Figure 3: An image of the electrodes' layout. The trapping, driving, and sensing electrodes are photographed. Also shown are the locations of the liquid reservoirs.

Next the carbon nanotubes [2], synthesized using an alumina template, were suspended in an isopropanol solution to a concentration of approximately $0.1\mu\text{g/L}$. These particular tubes were selected because they are open-ended, straight, and possess uniform pore geometry with outer diameters of approximately 250nm, wall thickness of 15nm, and lengths of up to $50\mu\text{m}$.

The CNTs were then assembled between the two trapping electrodes using dielectrophoresis. This process is discussed in detail in the following section. Next, 200nm of SiO_2 was wet etched in hydrofluoric acid to lift off the isopropanol residue. Finally, a $50\mu\text{m}$ thick layer of SU-8 (MicroChem Inc.) negative photoresist was spun onto the chip and patterned to define the reservoirs on both ends of the CNT.

3. DIELECTROPHORETIC TRAPPING -EXPERIMENTS

Dielectrophoresis (DEP) is the motion of uncharged, polarizable particles in a non-uniform electric field [3]. The dielectrophoretic forces result from the interaction of the electric field with a dipole induced in the particles. Depending on the particles' and the medium's dielectric properties, the motion is directed either toward (positive DEP) or away from (negative DEP) regions of high electric field intensity. While DEP occurs in both DC and AC electric fields, AC fields are often preferred in order to suppress undesired electrochemical interactions at the electrodes' surfaces and migration due to the particles' electric charge.

The dielectrophoretic force is usually approximated through its first dipole moment contribution [4]:

$$\mathbf{F} \sim c \epsilon_0 \epsilon_m V_p \operatorname{Re}(f_{CM}) \nabla |\mathbf{E}_{rms}|^2, \quad (1)$$

where $\mathbf{E}$ is the electric field; ϵ_0 and ϵ_m are, respectively, the dielectric constant of free space and the relative dielectric constant of the suspending liquid; V_p is the particle's volume; c is a numerical coefficient on the order of unity; and $\operatorname{Re}(f_{CM})$ is the real part of the relative particle polarization (i.e., the Clausius-Mossotti factor). Both c and f_{CM} depend on the particle's geometry. For

example, in the case of a spherical particle, $f_{CM} = \frac{\epsilon_p^* - \epsilon_m^*}{\epsilon_p^* + 2\epsilon_m^*}$ and $c = 3/2$,

where ϵ_p^* and ϵ_m^* are the complex permittivities of the particle and of the medium, respectively; $\epsilon^* = \epsilon - j \frac{\sigma}{\omega}$; and σ is the electric conductivity.

Equation (1) is valid only when the particle's dimensions are smaller than 10% of the length scale associated with the electric field ($|\mathbf{E}|/|\nabla \mathbf{E}|$) [5,6]. This is not the case in our experiments. More accurate calculations can be carried out utilizing either the principle of virtual work or the Maxwell stress tensor [7]. Nevertheless, we will use here equation (1) to qualitatively explain our experimental observations. Witness that the dielectrophoretic force's magnitude is proportional to the particle's volume, the difference between the particle's and medium's dielectric properties, and the gradient of the square of the electric field. This last term makes the method attractive for nanoassembly. By patterning small gaps between electrodes, one can obtain very high intensity electric fields with moderate potential differences.

CNTs with high permittivity are suspended in isopropanol solution with low permittivity thereby maximizing the permittivity difference. Large electric field gradients are generated through microfabricated electrodes with small electrode gap spacing. Figure 4 illustrates how microfabricated electrodes with small gap spacing are capable of producing large electric field gradients. The lines correspond to the normalized electric field as a function of x -at various horizontal planes above the microfabricated electrodes: $y=1, 3, 5, 10 \mu\text{m}$. $y=1\mu\text{m}$ corresponds to the plane of the electrodes' surface. The gap between the electrodes is $10 \mu\text{m}$. Witness that at the electrodes' plane, the electric field has two maxima located at the electrodes' edges. As we move away from the electrodes, the two maxima merge into a single maximum located right above the gap's center.

Figure 4: Through planar microfabricated electrodes with small electrode gap spacing, large electric field gradients are generated in the y direction which are represented by the normalized electric field lines. These electric field gradients generate a strong dielectrophoretic force on the CNTs and cause the CNTs to migrate towards the region of the highest electric field gradient and align themselves with the electric field.

In the experiments, we applied 12 V_{pp} potential at 2MHz between a pair of electrodes spaced $8\mu m$ apart. The CNT solution was exposed to the electric field for about 30 seconds. Photographs were taken with a Nikon CoolPix 995 camera mounted on an Olympus BX2 microscope at a magnification of 400x. The set-up allowed us to obtain only the top view of the particle's trajectory. Figures 4a, b, and c depict sequentially the position of the CNT at times 0, 0.2, and 0.28 seconds during the trapping process. For better visibility, we encircled the particle that we were tracking with an ellipse.

Figure 5: Images of the nanotube during various stages of the trapping process: 0s (a), 0.2s (b), and 0.28s (c). The nanotube is encircled with a black ellipse for better visibility.

When the particle was far from the trap, it moved at nearly level height with nearly uniform speed towards the gap, while rotating so as to align itself with the electric field. Once arriving in close vicinity of the gap, the particle's trajectory underwent an abrupt turn, and the particle accelerated towards the gap. At the conclusion of the trapping process, individual CNTs were trapped in the gap between two adjacent electrodes with each of their ends resting on a different electrode. Figure 6 depicts a SEM image of the trapped tube.

Figure 6: SEM Image of a trapped tube in the gap between a pair of electrodes

Another phenomenon which occurred when the trapping process was allowed to continue for a relatively long period of time was chain and tree formation. In the case of the CNT tree structures, positive DEP pulled CNTs suspended in isopropanol solution to the region of the highest electric field gradient located on the edge of a gold microfabricated electrode. Clustered tubes, which were present as a result of the tube synthesis process, were attracted first because the DEP force is proportional to the volume of the particle. These “bigger” particles formed the tree trunks. While in contact with the electrode, the trapped CNT cluster polarized and created a high electric field gradient at the end of the CNT that was not in contact with the electrode. This attracted additional CNTs to this region, and branches of CNTs began to form around the tree base. This effect repeated itself until full tree fractal structures were formed. Images of this phenomenon are shown in Figure 7.

Figure 7: Images of CNT tree fractal structures; a) SEM of a chain formed by individual uniform size CNTs; b) SEM of CNT tree structure; c) CNT tree structure at 400X magnification in bright field.

4. CONCLUSION

The paper describes a practical means of constructing nanotube-based fluidic devices. Dielectrophoresis provides a convenient and efficient technique for the trapping of CNTs at pre-determined locations. We studied the motion of the particles during the trapping process experimentally and described CNT tree formations that developed during the process. Once the nanotube has been trapped at a known position, one can bring to bear the tools of photolithography to fabricate fluidic interfaces that will allow one to transmit various fluids, macromolecules, and nanoparticles through the tube. Such devices can be used for fundamental studies of the behavior of simple and complex fluids under extreme confinement. Moreover, these devices can be used as highly sensitive biological and chemical sensors. The fabrication technique can be readily scaled down to allow one to trap single-walled nanotubes.

Acknowledgements: M. Riegelman, H. Liu, and H. H. Bau are supported by the DARPA SIMBIOSYS program N66001-01-C-8056 and the NSF NIRT program CTS 0210579. M. Riegelman also acknowledges support from a GAANN fellowship. S. Evoy is supported by NSF #ECS-0225496.

References

- [1] H. E. Kubitschek, *Nature (London)* 182, 234 (1958)
- [2] J.-C Bradley, S. Babu, S. Ndungu, P. Nikitin, Y. Gogotsi, 2003, Nanotube Synthesis using Alumina Template, , SMIRP Bradley Research Lab Knowledge Product 10975_0004
- [3] H. A. Pohl, *Dielectrophoresis: The Behavior of Neutral Matter in Non-uniform Electric Fields*, Cambridge University Press, New York, 1978.
- [4] T.B. Jones, *Electromechanics of Particles*, Cambridge University Press, New York, 1995.
- [5] S. Evoy *et al.*, "Dielectrophoretic Assembly and Integration of Nanowire Devices with Functional CMOS Operating Circuitry", in press (2003).
- [6] H. Liu and H. H. Bau, 2003, The Dielectrophoresis of Cylindrical and Spherical Particles Submerged in Shells and in Semi-infinite Media, in review.
- [7] J. A. Stratton, *Electromagnetic Theory*, McGraw-Hill, Inc., New York, 1941.

OPENING MULTIWALL CARBON NANOTUBES WITH ELECTRON BEAM

H. YE, N. NAGUIB and Y. GOGOTSI

*Department of Materials Science & Engineering and
A.J. Drexel Nanotechnology Institute, Drexel University
3141 Chestnut Street, Philadelphia, PA 19104, USA*

Abstract: A new method of nanomachining and opening multiwall carbon nanotubes (MWNTs) has been demonstrated. The puncture is accomplished by moving a converged electron beam in transmission electron microscope (TEM) onto the water inclusion in the multiwall carbon nanotube. The high resolution TEM images show that the reaction between the water inclusion and the walls of the carbon nanotube is the main reason for the appearance of the puncture. The reaction is stimulated by the converged electron beam irradiation. The puncture in different electron microscopy modes occurs with the same mechanism and approximately the same size, independent on the diameter of the electron beam.

1. INTRODUCTION

Opening of MWNTs is of great value in many applications, such as electrochemical energy or gas storage systems, biological nanosensors, and nanofluidic devices [1]. It is not easy to open the originally closed MWNTs owing to their high mechanical strength and chemical stability. Various methods have been developed to open MWNTs, including chemical treatment with nitric acid or oxidants [2], thermal treatment by heating the nanotubes in oxidizing atmosphere [3] and abrasive treatment by rubbing the nanotubes on diamond lapping film disks [4]. However, a common feature of these methods is that the opening only happens at the tips of nanotubes. There is no control over the location of the opening on the tube surface. Laser machining (Fig. 1) [5] or focused ion beam (FIB) which may be used for opening large tubes [6] does not have sufficient spatial resolution to machine small (<100 nm in diameter) tubes with high precision. Here, we report a new method which can open the sidewalls of large MWNTs (nanofibers) by using converged electron beams in transmission electron microscope. In addition, with this method we can specifically select the puncture position on the nanotube.

The interaction between electron beams and carbon nanotubes (CNTs) has been thoroughly investigated [7-10]. Strong electron irradiation was found to cause either disordering of the graphite tube walls or the shrinkage and collapse of the single-wall nanotubes. None of them, however, has led to the puncture of CNTs. The basic difference in our experiment from the previous investigations is that we conducted electron irradiation on liquid-containing CNTs, instead of hollow CNTs. The liquid-containing CNTs were produced hydrothermally at high temperature and high pressure from a supercritical C-H-O system using Ni catalyst [11, 12]. A unique and important feature of these CNTs is that they contain liquid inclusions which are composed of mainly water with dissolved gases. However, as our recent work shows, MWNTs of various diameters can be filled with water by treatment at elevated temperature and pressure. Thus, the proposed technique is applicable to various kinds of closed MWNTs. Movement and shrinkage/ expansion phenomena of the liquid inclusions under electron beam in TEM have been previously demonstrated [13, 14]. In this paper, opening the sidewalls of the liquid-filled CNTs is shown to be possible under an extremely converged electron beam with a high intensity.

2. EXPERIMENTAL

The hydrothermal CNTs were synthesized as described in Ref. [11, 12]. For synthesis, mixtures of ethylene glycol, water and Ni catalyst were sealed into gold capsules and reacted at temperature 700-800°C and pressure up to 100 MPa. The produced hydrothermal multiwall CNTs (MWNTs), were dispersed in ethanol and then placed on the carbon coated copper grid for TEM observation. All irradiation and imaging work was done in a field emission JEOL 2010F TEM with an accelerating voltage of 200 kV and a lattice resolution of 0.1 nm. The microscope could be operated in two modes: conventional TEM mode and scanning transmission electron microscopy (STEM) mode. When electron irradiation was performed in conventional TEM mode, the electron beam through the specimen could be either diverged

Figure 1. Light micrographs showing laser cutting of multiwall carbon nanotubes (nanofibers) in air using a focused laser probe of the Raman spectrometer. Air oxidation temperature established by Raman shift at onset of burning was $\sim 700^{\circ}\text{C}$. 1 - Both ends closed; 2 - Right end cut off; 3 - Left end cut off.

with a low electron flux down to 2×10^{17} electrons/cm²s (measured by a Faraday cup in TEM) or strongly converged, with the electron flux reaching 2×10^{21} electrons/cm²s (beam size 0.1 μ m). When STEM mode was adopted, an extremely small electron probe (1 nm) could be formed for irradiation, with an electron flux up to 6×10^{23} electrons/cm²s. After irradiation, the CNTs were imaged in conventional TEM mode.

3. RESULTS AND DISCUSSION

The TEM image in Fig. 2a shows a typical CNT with liquid entrapped. The liquid is composed of water and a small amount of dissolved CO₂ [13]. When the electron beam in TEM is

converged rapidly (within 1 second) and precisely on the region of the liquid inclusion, a puncture of the nanotube can be immediately observed, as shown in Fig. 2b. The hole formed after puncture has typically an elliptic shape crossing the nanotube and a size larger than the inner diameter of the CNT. Depending on the irradiation intensities, the holes can be produced either on the front wall (part of the nanotube wall directly facing electron beam irradiation, Fig. 2b) or on both front and back walls of the nanotube, as shown in Fig. 3a. Although it can be seen that the front hole has a bigger size than the back hole (Fig. 3a), this is not the case for all punctured CNTs and occasionally the back hole was observed to be larger. High resolution TEM image (Fig. 3b) of the left tube wall of the CNT in Fig. 3a shows that part of the inner wall was damaged as the hole was formed. The broken graphite layers bent toward the center of the CNT, as indicated by white lines in Fig. 3b.

Technically it is not easy to precisely converge an electron beam on such a tiny liquid inclusion (less than 50 nm in diameter) in the conventional TEM mode. Scanning transmission electron microscopy (STEM) mode, because of its ability to converge electron beam to 1 nm or less and control the movement of the probe conveniently, was thus adopted to study the puncture of CNTs. Fig. 4a shows the TEM image of a hole in a CNT which was formed nearly instantaneously when STEM probe was shifted onto the liquid

Figure 2. TEM image of a typical hydrothermal CNT with the liquid inclusion (a) before the converged electron beam irradiation and (b) after the irradiation. Puncture on the nanotube is visible after the strong beam irradiation.

inclusion in the CNT. Although the STEM probe is extremely small, the produced hole is quite large, and comparable in size to those formed by the converged TEM electron beam. This confirms that the tube opening is caused by chemical interaction of the liquid with tube walls rather than by electron beam damage of the wall. HRTEM image in Fig. 4b shows the broken graphite layers of the nanotube wall bent toward the inside of CNT, which is similar to the observation in the conventional TEM mode (Fig. 3b). It therefore indicates that the puncture in two modes has the same mechanism, no matter how different the size and the intensity of the electron beam are. Sometimes a single irradiation with converged TEM electron beam or STEM probe can cause the formation of two or more holes on the tube wall of CNTs, as shown in Fig. 5. In Fig. 5a, a converged electron beam in conventional TEM mode can cause the formation of two holes on the front wall of the CNT. Fig. 5b shows 7 holes formed simultaneously on the front wall of the CNT when the STEM electron probe was used. Three conditions must be satisfied to open the walls of CNTs in TEM.

Figure 3. (a) TEM image of a punctured nanotube, showing that two holes can be produced at the same time, one on the front tube wall and the other on the back wall, by using a single beam irradiation. (b) A high resolution TEM image of the framed region in (a). The orientation of graphene layers in the tube wall is marked by white lines. The inner tube wall is found to be heavily etched and the broken graphite layers bend toward the center of the nanotube, as indicated by the white arrows in (b).

Figure 4. (a) A hydrothermal CNT punctured by an electron probe (1 nm) in STEM mode; (b) HRTEM image of the framed region in (a), showing the etched graphite layers which bend toward the center of the nanotube.

First, the CNTs should contain liquid inclusions which are the targets of the electron-beam irradiation. The irradiation effects on multiwall [7] and single-wall nanotubes [8, 9] in TEM have been investigated previously. The primary cause of irradiation damage to CNTs was revealed to be large-angle electron-nuclear collisions [10], while beam heating played a less important role to induce the structural failure. The rapid atomic diffusion and reconstruction following the irradiation damage, as exhibited in these previous reports, could cause disordering, shrinkage or collapse of CNTs. No observation of the puncture on the tube walls of CNTs was reported. The importance

Figure 5. TEM images showing that several holes appear at the same time after a single exposure: (a) two holes on front wall, opened in conventional TEM mode. (b) 7 holes on front wall with different sizes and shapes, opened in STEM mode.

of the liquid inclusion in the hydrothermal CNTs is therefore clearly demonstrated. Due to the heating with electron beam in TEM, the liquid inclusion undergoes an evaporation. However, the puncture might not be the result of the physical force induced by the inner gas explosion. This is not only because the CNTs can withstand extremely high internal pressures [15], but also because, in that case, the broken tube walls would bend toward outside as the vapor rushes out, which is not the case (Fig. 3b and Fig. 4b). In these HRTEM images, the broken graphite layers were found to bend toward the inside of the nanotube, disproving the explosion-puncture mechanism. Therefore, the chemical mechanism must be considered. A previous study on the hydrothermal CNTs [16] indicated that a chemical reaction between liquid inclusion and carbon tube walls could take place due to the electron beam irradiation in TEM:

The reaction could result in dissolution of the graphite layers and etching of the inner nanotube walls. Since in the present work we performed an extremely strong electron beam irradiation, etching of the graphite layers could be accomplished through the tube walls of the CNTs until the puncture appeared and the residual liquid was lost to the microscope vacuum. This process was very fast because we were dealing with an extremely small liquid inclusion (in the order of 10^{-18} liters). The size and shape of the holes produced were determined by the area where the reaction took place, not by the size of the electron beam. This explains why similar size and shape of

punctures have been observed when either converged electron beam (Fig. 3a) or STEM probe (Fig. 4a) were used.

The second condition required to open CNTs is that the beam intensity (in term of electron flux) through the specimen must be strong enough to stimulate the reaction. A parallel electron beam with large exposure area and low electron flux in conventional TEM mode was not found to be able to puncture the nanotube. A strongly converged beam in the same TEM mode, however, can violently stimulate the etching reaction and the puncture (Fig. 2 and 3). The electron probe in STEM mode, which is extremely converged electron beam and thus possesses high beam intensity, can puncture the nanotube instantly once being shifted upon the liquid inclusion (Fig. 4).

The third condition is that the operation of converging electron beam must be quick. This is especially crucial in conventional TEM mode. Only fast beam converging (within 1 second) can cause the puncture of CNTs. Slow beam converging would not cause sufficient etching reaction in a short time. It would instead lead to liquid transport away from the electron beam or/and its evaporation and condensation in a cold part of the nanotube [13]. It was also shown in our previous work [16] that a slower heating may lead to a local increase in internal tube diameter, thus producing a chamber inside the tube. This can be used for improving flow mixing inside the nanopipe.

Since the CNTs investigated are not always perfect, various shapes and distributions of punctures have been observed when the above three conditions are satisfied. The etching reaction may happen more easily at defects of the nanotube walls. If the defects are random point defects, the punctures caused by etching reaction are also randomly distributed, like in Fig. 5a. If the defects are caused by stacking faults of the nanotube walls during their formation, the distribution of the defects and thus the punctures may appear with some amount of periodicity. An example is shown in Fig. 5b where the punctures form a hexagonal structure, as indicated by lines and solid cycles.

4. SUMMARY AND CONCLUSIONS

It has been shown that the tube walls of the carbon nanotubes containing water can be opened by strongly converged electron beams. The puncture can be done in conventional TEM mode and STEM mode which produce similar results regardless of the large difference in beam size and intensity. The reaction between water and carbon tube walls, stimulated by electron beam irradiation, etches carbon nanotubes from inside until the puncture appears. The necessary conditions to initiate the puncture of the carbon nanotubes include the presence of water inclusion, the high beam intensity and the rapid beam-converging operation (in case of conventional TEM mode). This new method for nanomachining carbon nanotubes provides a way to produce carbon nanotubes with three or more entrances, instead of only two at the

ends, which could be useful in many potential applications, for example, fabrication of nanofluidic devices.

Acknowledgements: We thank Prof. C.M. Megaridis and A.G. Yazicioglu, University of Illinois at Chicago, for helpful discussions. Figure 1 was provided by Joe Libera. The TEM and STEM work was done in the LRSM of the University of Pennsylvania. This work was supported by the US National Science Foundation under NIRT grant CTS-0210579.

References

1. Harris, P. (1999) *Carbon nanotubes and related structures*, Cambridge University Press, Cambridge.
2. Tsang, S.C., Chen, Y.K., Harris, P.J.F. and Green, M.L.H. (1994) A simple chemical method of opening carbon nanotubes, *Nature* **372**, 159-162.
3. Tsang, S.C., Harris, P.J.F. and Green, M.L.H. (1993) Thinning and opening of carbon nanotubes by oxidation using carbon dioxide, *Nature* **362**, 520-522.
4. Maurin, G., Stepanek, I., Bernier, P., Colomer, J.-F., Nagy, J.B. and Henn, F. (2001) Segmented and opened multi-walled carbon nanotubes, *Carbon* **39**, 1273-1278.
5. Libera, J.A. and Gogotsi, Y. (1999) Probing carbon nanostructures using Raman spectroscopy, *MRS Annual Meeting, Boston, MA, poster presentation*.
6. Muradov, N. and Schwitter, A. (2002) Formation of conical carbon structures on vapor-grown carbon filaments, *Nano Lett.* **2**, 673-676.
7. Crespi, V.H., Chopra, N.G., Cohen, M.L., Zettl, A. and Louie, S.G. (1996) Anisotropic electron-beam damage and the collapse of carbon nanotubes, *Phys. Rev. B* **54**, 5927-5931.
8. Ajayan, P.M., Ravikumar, V. and Charlier, J.-C. (1998) Surface reconstructions and dimensional changes in single-walled carbon nanotubes, *Phys. Rev. Lett* **81**, 1437-1440.
9. Smith, B.W. and Luzzi, D.E. (2001) Electron irradiation effects in single wall carbon nanotubes, *J. Appl. Phys.* **90**, 3509-3515.
10. Banhart, F. (1999) Irradiation effects in carbon nanostructures, *Rep. Prog. Phys.* **62**, 1181-1221.
11. Gogotsi, Y., Libera, J.A. and Yoshimura, M. (2000) Hydrothermal synthesis of multiwall carbon nanotubes, *J. Mater. Res.* **15**, 2591-2594.
12. Libera, J. and Gogotsi, Y. (2001) Hydrothermal synthesis of graphite tubes using Ni catalyst, *Carbon* **39**, 1307-1318.
13. Gogotsi, Y., Libera, J., Guvenç-Yazicioglu, A. and Megaridis, C.M. (2001) In situ multiphase fluid experiments in hydrothermal carbon nanotubes, *Appl. Phys. Lett.* **79**, 1021-1023.
14. Megaridis, C.M., Guvenç-Yazicioglu, A., Libera, J.A. and Gogotsi, Y. (2002) Attoliter fluid experiments in individual closed-end carbon nanotubes: liquid film and fluid interface dynamics, *Phys. Fluids* **14**, L5-L8.
15. Galanov, B.A., Galanov, S.B. and Gogotsi, Y. (2002) Stress-strain state of multiwall carbon nanotube under internal pressure, *J. Nanoparticle Res.* **4**, 207-214.
16. Gogotsi, Y., Naguib, N. and Libera, J. (2002) In situ chemical experiments in carbon nanotubes, *Chem. Phys. Lett.* **365**, 354-360.

MOLECULAR CHEMICAL CONCEPTS FOR THE SYNTHESIS OF NANOCRYSTALLINE CERAMICS

S. MATHUR

Institute of New Materials

CVD Division, 66041 Saarbruecken, Germany

1. INTRODUCTION

Nanomaterials research is seeking methods to achieve a precise control over composition, particle size, size-distribution and morphology [1, 2]. The conventional syntheses involving solid-state or liquid phase reactions of two or more components fail to meet the challenge. The chemical syntheses based on the controlled reactions (interactions) of atoms or molecules are becoming promising alternative for a rational synthesis of nanostructured materials. In this context, different chemical approaches have been put forward to synthesize well-defined materials due to the low temperatures required for the synthesis and the possibility of building extended solid-state structures from molecular building blocks [3-7]. When compared to the solid-state reactions, the solution methods allow a controlled interaction of atoms or molecules to form uniform films or particles. Further, the flexibility to combine different ligands or metal combinations allows the precursor designing to meet the demands of the target material [8]. Recently, a one-step strategy for the synthesis of nanomaterials involving ensemble of the phase-forming elements in a single molecular source, has gained significant attention because it enhances the advantages of chemical processing and simultaneously reduces the process parameters [8-14].

2. THE PRECURSOR CONCEPT

Although heterometal alkoxides are invariably formed in a mixture of constituent alkoxides, the simple mixing of two alkoxides $M(OR)_x$ and $M'(OR)_y$ is no guarantee for the formation of a single precursor species $MM'(OR)_{x+y}$ mainly due to the structure potential of alkoxide ligand to bind one, two or three metal centers. As a result, besides the desired precursor, several other compounds can be present in an uncharacterized precursor cocktail. For example, Ba and Zr(Ti) alkoxides can

Figure 1. Molecular structure of different Ba-Zr(Ti) alkoxide clusters: (a) $[\text{BaZr}_2(\text{OBu}^t)_{10}]$ (Ba:Zr = 1:2), (b) $[\text{Ba}_2\text{Zr}(\text{OBu}^t)_8(\text{HOBu}^t)_2(\text{THF})]$ (Ba:Zr = 2:1), (c) $[\text{BaTi}_3(\text{OPr}^i)_{14}]$ (Ba:Ti = 1:3) and (d) $[\text{BaZr}(\text{OPr}^i)_5(\text{OH})(\text{HOPr}^i)_3]_2$ (Ba:Zr = 1:1).

combine in different ways to produce mixed-metal Ba-Zr(Ti) alkoxides with different structures and metal ratios [11]. Some examples of alkoxide clusters based on different Ba:Zr(Ti) ratios are shown in Figure 1a-d. Of course the formation of a particular framework is subject to the chemical nature (neutral or anionic) and size (steric profile) of the ligands.

In most of the chemical methods in practice, the starting materials are commonly available reagents, which are close to the desired composition but often need a heat-treatment step to attain the final composition. Since the material synthesis procedures (e.g., solid-state reactions, combustion reactions, etc.) rely on the intrinsic chemical behaviours (e.g., different hydrolysis rates of the reactants in solution phase reactions or different vapour pressure or thermal stability in the gas phase reactions) of the different components present in a reaction mixture, the stoichiometry of the target material is susceptible to inaccuracies due to the lack of chemical bonding. If the metal-ligand connectivity corresponding to the solid state structure is not given, the different compounds present in the reaction mixture randomly interact to form several intermediate species with metal ratios unfavorable for obtaining a single-phase material. As a consequence, phase separation and element segregation are present at the nanometer scale, although the global stoichiometry of the product may correspond to the desired composition (Scheme I). For instance, a simple mixture of two chemical precursors A and B (Multi Source Process, MSP), to produce the bimetallic oxide system $\text{A}_x\text{B}_y\text{O}_z$, may produce a visibly homogeneous mixture but the molecular level

scenario can be different and despite a correct global stoichiometry the precursor ‘cocktail’ may have element segregation and non-ideal A:B ratios at the nanometer scale that may be carried forward to the end product (Scheme I).

Scheme I

Our investigations on the application of heterometal alkoxides in the material synthesis have shown that **isolation and characterization of preceramic aggregates** is necessary for the phase selective synthesis of materials. For instance, high purity BaZrO_3 powders can be obtained by using a single-source Ba-Zr alkoxide, $[\text{BaZr}(\text{OPr}^i)_5(\text{OH})(\text{HOPr}^i)_3]_2$, whereas perovskite obtained from a mixture

Scheme II

of Ba and Zr precursors was found to contain undesired phases. The main drawback of solution syntheses performed using mixtures of alkoxides is the differential hydrolysis behaviour (kinetics) of individual components, which often leads to the formation of secondary phases. This limitation can be overcome by employing well-characterised heterometal molecules ('single-source') with metallic elements present in the ratio compatible with the targeted ceramic. Such an inorganic cluster can be seen as a molecular template for initiating the formation of a solid-state structure at the nanometer scale (Scheme II).

3. SOL-GEL PROCESS USING ALKOXIDE PRECURSORS

The sol-gel technique using metal alkoxides is based on inorganic polymerisation reactions in which metal alkoxide derivatives such as $M(OR)_x$ or $MM'(OR)_{x+y}$ are carefully hydrolysed to produce species containing $M-O-M$ or $M-O-M'$ linkages [5-7]. These modified molecular entities arrange themselves *via* hydrolysis and cross-condensation reactions to form macromolecular networks with oxo- and/or hydroxo bridges thus favoring the gelation process. The partially hydrolysed alkoxides can be viewed as molecular building blocks for the development of sol (particulate) or gel (polymeric) structure, which can be dried and fired to obtain the desired oxide. Modifying the alkoxide precursors with less hydrolysable or polymerizable groups can chemically control the condensation reactions [5,6]. The metal species bearing a terminal hydroxy group react with other species in the solution to form oligomeric structures linked by oxo- (O^{2-}) or hydroxo (OH^-) ligands, which transforms into polymeric gels by aging. The polymerization reactions and the followed drying and thermal treatments result in the elimination of water (oxolation) and alcohol (alcoholation) to finally produce a solid material (Scheme III).

Scheme III

4. NANOCERAMICS

This section contains the selected examples of the synthesis and characterization of nanoscaled powders of bimetallic oxides obtained by the sol-gel processing of single molecular precursors.

4.1. Perovskites (BaMO_3 ; $\text{M} = \text{Ti, Zr}$)

The dielectric ceramics BaTiO_3 and BaZrO_3 are finding extensive electronic applications due to their high dielectric constant and ferroelectricity [25, 26]. The powders obtained from conventional routes are agglomerated with large and unequal grain sizes and contain varying amounts of undesirable impurities due to incomplete reactions or undecomposed intermediates. The poor control over compositional homogeneity and phase-purity has an adverse effect on their electrical and mechanical properties [27]. Nanocrystalline BaTiO_3 and BaZrO_3 oxides [28] have been synthesised from single-source Ba-Ti(Zr) alkoxide precursors. The improved homogeneity, phase-purity, and lower crystallisation temperatures for gel $\rightarrow$ oxide conversion are attributed to the use of mixed-metal compounds containing preformed Ba–O–Ti and Ba–O–Zr bonds. The TEM images (Fig. 2) of barium-titanate powder obtained from single source route revealed homogeneous nanoparticles, whereas for powder from hydroxide route showed severe agglomeration and abnormal particle growth [28]. The strict control over the metal ratios through stoichiometric clusters allows the crystallisation of perovskite nanoparticles at low-temperature (ca. 600 °C).

Figure 2. TEM images of BaTiO_3 ceramic obtained from (a) hydroxide and (b) single source routes.

The X-ray powder diffractograms (Fig. 3) reveal that the powder obtained from conventional method is contaminated even at 1200 °C by undesired

side-products like BaCO_3 and Ba_2TiO_4 whereas a single-phase material is obtained using the mixed-metal alkoxide precursor. In addition, the volume- and number-weighted size dispersions are significantly narrow for the perovskite powders obtained from alkoxide precursors (Fig. 3), which is not the case for powders obtained by hydroxide route due to severe agglomeration and abnormal particle growth [28].

Figure 3. XRD patterns and corresponding particle size-distribution curves of BaTiO_3 particles obtained by different sol-gel methods (BaCO_3 (●) and Ba_2TiO_4 (■)).

4.2. Spinel ($\text{MM}'_2\text{O}_4$; $\text{M} = \text{Mg, Co, Ni, Cu, Zn}$; $\text{M}' = \text{Al, Ga, Fe}$)

Although MgAl_2O_4 powders and films have been successfully prepared from magnesium-aluminium iso-propoxide containing the appropriate Mg:Al ratio (1:2) [20], the preparation of transition metal-aluminium, -gallium or -iron spinels is

Figure 4. Molecular structure of $[\text{CoAl}_2(\text{OBu})_8]$.

limited to the fusion of the two component oxides [29, 30] at high temperatures (1000-1600 °C) or by co-precipitation reactions [31, 32], in solution. We have used hetero-bimetallic precursors, $[MM'_2(OR)_8]$ ($M(II) = Co, Zn$; $M' = Al, Ga, Fe$), to obtain high purity spinels at low-temperature. The molecular structure (Fig. 4) of the Co-Al derivative reveals the Co:Al ratio suitable for $CoAl_2O_4$ [24]. For a comparative evaluation of the single- and multi-component approaches, $CoAl_2O_4$ spinel was synthesized from (i) $[CoAl_2(OBu^t)_8]$ and (ii) a stoichiometric mixture of $[Al(OPr^i)_3]_4$ and $Co(OR)_2$ ($R = (C_6H_5)_3C^-$).

The XRD patterns (Fig. 5) of the two $CoAl_2O_4$ samples reveal that the single-source synthesis yields, under similar experimental conditions, higher phase

Figure 5. XRD patterns of $CoAl_2O_4$ obtained from (a) single- and (b) multi-source routes. Arrows in the case of multi-source synthesis indicate undesired phases.

purity and crystallinity when compared to the spinel obtained using two separate metal sources. It should be noted that in the later case the different hydrolysis kinetics of Co and Al alkoxides and formation of several species with different metal ratios can adversely affect the homogeneity (with respect to the cation distribution) of the precursor solution. Similarly, nanocrystalline $CuAl_2O_4$ and $NiAl_2O_4$ could be obtained by a single-step processing of $[CuAl_2(OBu^t)_8]$ and $[NiAl_2(OBu^t)_8]$, respectively [24].

Similarly zinc aluminate ($ZnAl_2O_4$), a well-known wide band gap semiconductor with a spinel structure, was prepared by the sol-gel processing [33]

Figure 6. Molecular structure of $[ZnAl_2(OBu^t)_8]$.

of bimetallic precursor shown in Fig. 6. Recent investigations on ZnM_2O_4 ($M = \text{Al, Ga}$) compounds have shown these systems to be new transparent and conductive materials.

The optical band gap of polycrystalline ZnAl_2O_4 (3.8 eV) indicates the material to be transparent for the light possessing wavelength larger than 320 nm. Thus it can be utilized for UV-photoelectronic devices. Owing to the quantum confinement, the energy levels of a semiconductor nanoparticle (quantum dot) are 'blue shifted' with respect to those of the bulk. Moreover, ZnAl_2O_4 spinel is useful in many catalytic reactions such as cracking, dehydration, hydrogenation and dehydrogenation reactions [34]. The XRD pattern of the sample calcined at 400 °C, shows zinc aluminate (Gahnite) to be the only crystalline phase. This is the lowest reported temperature for the formation of single phase crystalline ZnAl_2O_4 . The diffraction peaks in samples calcined at higher temperatures (600-1400 °C) show sharper profiles resulting from the continuation of crystallisation/ordering processes and grain growth. The calculated lattice parameters ($a_0 = 8.0855 \text{ \AA}$) for cubic spinel phase are in good agreement with the reported value ($a_0 = 8.0848 \text{ \AA}$, JCPDS File 5-669). The determination of the crystallite size from the line shape analysis of the diffraction peaks showed a log normal grain growth with increasing calcination temperature (Fig. 7). The above observations were confirmed by the TEM images of the ZnAl_2O_4 samples calcined at different temperatures, which showed a systematic crystal growth [33].

Figure 7. Exponential relationship of the crystallite size in ZnAl_2O_4 ceramic and calcination temperature.

The absorbance spectra (Fig. 8) of ZnAl_2O_4 samples heat-treated (6h) at 700, 800, 1000, 1200 and 1400 °C reveal a systematic shift in the absorption maxima. The absorbance edge became steeper on increasing the calcination temperature and a 'red shift' (4.5 to 4.0 eV) was observed (Fig. 8).

It is known that the band gap, E_g , of a nanocrystalline specimen scales with its diameter, d , as $E_g \sim 1/d$. It can be surmised that the observed variation in absorption is relevant to a strong change in the particle size reflecting the transition of spinel from nanocrystalline to the micron (bulk) state. The absorbance spectra of different ZnAl_2O_4 samples and ZnO , Al_2O_3 standards are shown in Fig. 8. The band gap

Figure 8. (a) Absorbance spectra of nanocrystalline ZnAl_2O_4 samples and (b) relationship between ZnAl_2O_4 bandgap and the particle size.

values (4.0–4.5 eV) were obtained from a linear extrapolation of the absorbance edge to cross the wavelength axis and are quite different from those of Al_2O_3 and ZnO in spite of the existence of the Al^{3+} and Zn^{2+} cations. This corroborates the phase purity of ZnAl_2O_4 samples and the absence of any micro-phase separation.

4.3 Orthoferrite (GdFeO_3)

A designed assembly of trivalent lanthanide and iron ions in a molecular framework (Fig. 9) provided, for the first time, access to metastable rare earth iron perovskites of general formula LnFeO_3 (Ln = any lanthanide ion). The unique magnetic properties such as high coercivity [35] and Faraday rotation [36], make orthoferrites interesting materials for magneto-optical data storage devices. The problem commonly encountered in the selective synthesis of LnFeO_3 compounds is the formation of thermodynamically favored garnet and secondary iron oxide phases caused by the use of a mixture of Ln^{3+} and Fe^{3+} constituents as the precursor. Since no chemical control (bonding) is offered, the lanthanide and iron compounds in the admixture randomly collide to form various intermediate species with metal ratios unfavorable for obtaining a single-phase material. The result is the co-existence of more stable garnet ($\text{Ln}_3\text{Fe}_5\text{O}_{12}$) and magnetite (Fe_3O_4) phases, which in view of their

higher magnetic moments hinder specific investigations on the weak ferrimagnetic behaviour of the orthoferrite, LnFeO_3 . In this context, the precursors with the required cation ratio and preformed Ln-O-Fe bonds are a major break-through in the selective synthesis of orthoferrite films and particles [37].

Figure 9. (a) Molecular structure of $[\text{GdFe}(\text{OPr})_6](\text{HOPr})_2$ and XRD patterns of the materials obtained in the synthesis of GdFeO_3 from (i) single- and (ii) multi-component routes. Peaks due to $\text{Gd}_3\text{Fe}_5\text{O}_{12}$ are marked as •.

Nanoparticles of GdFeO_3 were obtained by a controlled hydrolysis of the heterometal alkoxide. The sol was freeze-dried to obtain the xerogel that was calcined at different temperatures (600, 800 °C) and characterized by powder X-ray diffraction (Fig. 10a). The raw powder was amorphous till 600 °C. A well-developed orthoferrite phase is observed at 800 °C. The crystalline GdFeO_3 forms directly from an amorphous precursor without the crystallisation of any intermediate phases. The garnet composition, invariably formed in the synthesis of orthoferrites, is not observed when a single-source precursor is used. Moreover, no phase segregation or crystallisation of other stoichiometries was observed, which confirms the compositional purity of the sample and our contention that the chemical mixing

Figure 10. (a) XRD patterns and (b) normal and high resolution TEM images of GdFeO_3 ceramic.

of the ions is retained during the various stages of the processing. Further, the crystalline GdFeO_3 is formed at much lower temperature than those required for the solid-state reaction using Gd_2O_3 and Fe_2O_3 powders ($\sim 1800^\circ\text{C}$). The TEM image (Fig. 10b) of the GdFeO_3 ceramic calcined at 1000°C shows faceted crystallites of nearly uniform size (~ 60 nm). The high-resolution image of the GdFeO_3 particles revealed clear lattice fringes with interplanar spacings corresponding to the perovskite lattice [37].

Orthoferrites display antiferromagnetic order for $T < 620\text{--}730$ K, depending on the atomic size of the rare earth involved. The weak ferromagnetism arises from the low symmetry of the magnetic unit cell, producing a spin-canted structure of the Fe sublattice [38]. Both the temperature and field dependence of the magnetization in GdFeO_3 can be explained from the weak ferromagnetism [39] of these systems, and the very different ordering temperatures of Gd (~ 1 K) and Fe (~ 600 K) magnetic sublattices [40]. The magnetic susceptibility χ_{dc} displays a paramagnetic-like behaviour down to the lowest temperature available ($T \sim 2$ K). The fit of the experimental data using the Curie-Weiss law $\chi(T) = C/(T - \Theta)$ was used to calculate the effective magnetic moment $\mu_{\text{eff}} = 8.1(1) \mu_{\text{B}}$ and Curie-Weiss temperature $\Theta = -7(1)\text{K}$. The value of effective moment corresponds to the paramagnetic contribution of Gd^{3+} ions (i.e., $8.0 \mu_{\text{B}}$ for an $^8\text{S}_{7/2}$ state). On the other hand, the small (negative) value of Θ supports the fact that the Gd-Gd (antiferromagnetic) exchange

Figure 11. (a) Magnetization and inverse magnetic susceptibility (inset, a) curves and (b) M-H hysteresis (300 K) for the GdFeO_3 ceramic calcined at 800 and 1000°C .

are remarkably weak. The $M(H)$ curve (Fig. 11) shows a linear increase with field, without signs of saturation up to 5 T, resembling a paramagnet. However, the large coercivity ($H_{\text{C}} = 2.6(1)$ kOe) observed indicates that the sample is not superparamagnetic in spite of the nanosized grains.

4.4 Pure and Lanthanide-Doped Garnet Powders ($\text{Y}_3\text{Al}_5\text{O}_{12}$ and $\text{Ln}:\text{Y}_3\text{Al}_5\text{O}_{12}$)

YAG is a promising high-temperature engineering material for insulating or refractory coatings because of its low creep rate, high oxidation resistance, and low electrical conductivity. Lanthanide-doped yttrium aluminum garnets ($\text{Ln}:\text{YAG}$; $\text{Ln}:\text{Y}_3\text{Al}_5\text{O}_{12}$, Ln = any lanthanide element) have been widely studied due to their application in solid-state lasers [41-45]. YAG is a robust host for luminescent ions because it does not damage easily under high irradiance with an electron beam. Therefore, rare-earth-doped YAG materials are promising phosphor candidates in cathode-ray tubes (CRTs), field-emission display (FED), scintillators, vacuum fluorescent displays (VFDs) and electroluminescent systems.

The solid-state synthesis of YAG ceramic from Al_2O_3 and Y_2O_3 powders usually requires extensive mechanical mixing and lengthy heat treatments [45, 46]. The yttria-alumina system has several stable phases, namely YAP (YAlO_3), YAM ($\text{Y}_4\text{Al}_2\text{O}_9$) and YAG ($\text{Y}_3\text{Al}_5\text{O}_{12}$). Commonly YAP and YAM phases are formed as intermediate byproducts even if YAG is synthesized with stoichiometric mixture of Y_2O_3 and Al_2O_3 . Therefore extensive heat treatments at high temperatures ($> 1600^\circ\text{C}$) [45, 46] and repeated mechanical milling are required to decompose the intermediates so that a pure garnet phase can be formed. These processing conditions do not allow facile control over microstructure, grain size and grain size distribution in the resulting powders or shapes. Several wet-chemical techniques such as polymerized complex route, metal-organic preceramic processing, coprecipitation methods or yttrium carboxylate-alumoxane route have been used to produce YAG phases [47]. Most of these methods suffer from the complex and time consuming (long refluxing times, gelation periods of several days, etc.,) procedures and/or mismatch in the solution behaviour of different chemical species. Further, a precise control of cationic stoichiometry is not achieved, for instance, due to the phase separation tendencies of unimetal phases. In the case of precipitation reactions, the difference in the isoelectric points (different pH level) of the constituent species results in element segregation and non-ideal stoichiometries in the obtained ceramic. For example, significant amounts of Y_2O_3 , Al_2O_3 , YAlO_3 and $\text{Y}_2\text{Al}_4\text{O}_9$ phases are present in the synthesis of $\text{Y}_3\text{Al}_5\text{O}_{12}$ from aqueous yttria and alumina sols [48]. The problems of non-uniform mixing, residual phases, unreacted starting materials pose a challenge on the conventional methods used for the synthesis of doped materials where a few atomic weight percentage of a constituent is to be homogeneously dispersed in a host matrix. Since sol-gel methods are based on molecular precursors, they allow **chemical** cross-linking of different metal

centers in the initial mixture of precursor species leading to a homogeneous distribution of dopant ions in a uniform matrix.

For comparative evaluation of the conventional solution approach and the one based on molecular alkoxide precursors, we have prepared garnet powders by employing common inorganic salts (chloride, nitrate, acetate, etc.) and alkoxide precursors [47]. Both pure and Nd-doped (1-5 wt.%) yttrium aluminum garnet powders were obtained by the complexation of Y^{3+} , Al^{3+} and Nd^{3+} ions with 1,2-ethanediol (**Polymeric Precursor Route**) in an aqueous media as well as by the controlled hydrolysis of Y, Al and Nd alkoxides (**Alkoxide Route**).

The TG/DTA curves for the Y-Al-O gel synthesized by polymeric precursor and alkoxide routes are shown in Fig. 12. Whereas the crystallisation of the garnet phase occurs around 800 °C for the alkoxide-derived powder the onset of crystallisation is observed at higher temperature (> 900 °C) in the polymeric processing. Despite the lower crystallisation temperature, the residual carbon content in alkoxide-derived powders was significantly lower than that found in polymeric precursor case. The higher percentage of carbon impurities in the glycolate route was found to originate from the traces of undecomposed intermediates (e.g., yttrium carbonate or oxycarbonate) or trapped complexing agents. This observation was confirmed by recording the infrared spectra of heat-treated samples that showed the presence of residual organics and carbonate species. The X-ray diffraction profiles of the powders reveal the formation of monophasic garnet powders in both the cases, however the microstructural features of the two samples were found to be significantly different.

Figure 12. TG/DTA profiles of Nd:YAG ceramics obtained from (a) glycolate and (b) alkoxide routes.

The TEM images of the powders heated at 1000 °C showed high agglomeration effects in the case of polymeric precursor synthesis while well-dispersed particles of regular size were obtained in the case of alkoxide processing (Fig. 13). The high C and H contents in YAG powders obtained by using a complexing agent together with the observed morphology suggest that the residual organic materials act as a ‘binder’ for the nanoparticles. A high-resolution TEM image shows that the sintering in alkoxide-derived YAG powder begins at relatively low temperature as revealed by the fusion of YAG crystallites to form sinter-necks (Fig. 14).

Figure 13. Transmission electron micrographs of YAG ceramic, sintered at 1000 °C: (a) glycolate and (b) alkoxide route.

Figure 14. HRTEM image of a YAG specimen, sintered at 1000 °C (alkoxide route).

In the case of Nd-doped (1 wt.%) YAG powders, the XRD results show that although a pure garnet matrix is formed in the case of polymeric precursor route, a homogeneous distribution of Nd ions is not achieved. This is evident in the observance of small peaks in the diffractogram, which correspond to residual neodymium oxide (Fig. 15). A higher homogeneity is achieved in the case of alkoxide synthesis because all the metal precursors bear similar ligands and can form a homogeneous network during the hydrolysis reactions. Consequently, the dopant Nd ions are chemically 'fixed' in a Nd-O-Y-O-Al network which leads to the formation of monophasic Nd:YAG ceramic (Fig. 15).

Figure 15. Room temperature XRD traces of Nd:YAG ceramics obtained from glycolate and alkoxide routes (Nd₂O₃ phase (*)).

Figure 16. Room temperature emission spectra ($^4F_{3/2}$ to $^4I_{11/2}$ transition) of Nd(3%):YAG ceramics obtained from glycolate and alkoxide routes.

The better dispersion of Nd ions in the case of alkoxide processing is also observed in the emission spectra of the compacts obtained from the two different powders. A comparison of the ${}^4F_{3/2} \rightarrow {}^4I_{11/2}$ emission of Nd(3 wt.%):YAG samples (Fig. 16) shows a significantly higher emission efficiency for alkoxide-derived powder, which can be attributed to an ultra-homogeneous incorporation of Nd ions in the garnet matrix when using alkoxide route.

5. CONCLUSIONS AND PERSPECTIVES

The hydrolytic transformation of molecular alkoxide derivatives used for the phase selective synthesis of different ceramics illustrates the potential of alkoxide precursors to 'preform' the material on a molecular level. The incorporation of different elements in a molecular source to obtain the target material from a Single-Source simplifies the material synthesis by drastically reducing the process parameters. Heterometal alkoxides with metal ratios compatible with binary oxide ceramics are effective molecular templates for a controlled growth of nanomaterials at low temperatures. These building blocks have been used in the sol-gel process to obtain high purity oxide nanopowders with a narrow size- and shape-dispersion. Our continuing efforts in the synthesis and characterization of new precursor systems and their use in solution or gas phase methods to obtain nanomaterials have shown that predefined metal stoichiometry and reaction chemistry of the precursor can enforce a molecular level homogeneity in the obtained materials [49-55].

Scheme IV

In the conventional material synthesis procedures (e.g., solid-state reactions, coprecipitations, polymeric precursor methods, etc.), the intrinsic

behaviours of the different components make a precise control over the phase formation rather difficult. In this context, the single-source precursors based on predetermined metal-ligand interactions (e.g., metal-carbon for carbides, metal-nitrogen for nitrides, metal-oxygen for oxides, etc.) are an attractive choice to achieve homogeneous cation distribution at the atomic level and a well-defined stoichiometry.

Acknowledgments: Author kindly acknowledge Prof. H. Schmidt and Prof. M. Veith, Institute of New Materials, Saarbruecken for their continuing support and for providing the necessary infrastructural facilities.

References

1. Edelstein, A. S. and Cammarata, R. C. Eds. (1996) *Nanomaterials: Synthesis, properties and applications*, Institute of Physics Pub., Bristol and Philadelphia.
2. Fendler, J. H. Ed. (1996) *Nanoparticles and Nanostructured Films*, WILEY-VCH, Germany.
3. Segal, D. L. (1989) *Chemical Synthesis of Advanced Materials* Cambridge University Press, Cambridge.
4. Cheetham, A. K. Brinker, C. J. McCartney, M. L. and Sanchez, C. (1994) Better Ceramic Through Chemistry Mat. Res. Soc. Symp. Proc. 360.
5. Klein, L. C. Ed. (1988) *Sol-Gel Technology for Thin Films, Fibers, Preforms, Electronics and Speciality Forms* Noyes Pub., Park Ridge, NJ.
6. Brinker, C. J. Scherer, G. W. (1990) *Sol-Gel Science: The Physics and Chemistry of Sol-Gel Processing* Academic Press, New York.
7. Hench, L. L. West, J. K. (1990) Chem. Rev. **90**, 33.
8. Mathur, S. (2002) in NATO ASI Series: *Chemical Physics of Thin Film Deposition for Micro- and Nano-Technologies*, Y. Pauleau (ed.), Kluwer Academic Publications, 91.
9. Veith, M. (2002) J. Chem. Soc. Dalton Trans. 2405.
10. Mathur, S. Veith, M. Shen, H. and Hüfner, S. (2002) Mat. Sci. Forum **386-388**, 341.
11. Veith, M. Mathur, S. Huch V. and Decker, T. (1998) Eur. J. Inorg. Chem. 1327.
12. Narayanan, R. Laine, R. M. (1997) Appl. Organomet. Chem. **11**, 919.
13. Jones A. C. (1997) Chem. Soc. Rev. 101.
14. Coles, M. P. Lugmair, C. G. Terry, K. W. Tilley, T. D. (2000) Chem. Mater. **12**, 122.
15. Bradley, D. C. (1989) Chem. Rev. **89**, 1317.
16. Mehrotra, R. C. (1990) Chemtracts **2**, 389.
17. Veith, M. Mathur, S. Mathur, C. (1998) Polyhedron **17**, 1005.
18. Mehrotra, R. C. Singh, A. (1997) Prog. Inorg. Chem. **46**, 239.
19. Xu, R. (1997) J. Mater. Res. **49**, 1.
20. Jones, K. Davies, T. J. Emblem, H.G. Parkes, P. (1986) Mat. Res. Soc. Symp. Proc. **73**, 111.
21. Hirano, S. Hayashi, T. Noaski, K. Kato, K. (1989) J. Am. Ceram. Soc. **72**, 707.
22. Bradley, D. C. Mehrotra, R. C. Gaur, D. P. (1978) *Metal Alkoxides*, Academic Press, London.
23. Meyer, F. Dierstein, A. Beck, C. Hempelmann, R. Mathur, S. Veith, M. (1999) Nanostruct. Mater. **12**, 71.
24. Meyer, F. Hempelmann, R. Mathur, S. Veith, M. (1999) J. Mater. Chem. **9**, 1755.
25. Riman, R. E. (1993) *High-performance Ceramics* Eds. Pugh, R. and Bergstroem, L. Marcel-Dekker, New York.
26. Goodman, G. (1986) in *Ceramic Materials for Electronics* ed. Buchanan, R. C. Marcel-Dekker, New York.

27. Deb, K. K. Hill, M. D. and Kelly, J. F. (1992) *J. Mater. Res.* **7**, 3296.
28. Veith, M. Mathur, S. Lecerf, N. Huch, V. Decker, T. Beck, H.P. Eiser, W. Haberkorn, R. (2000) *J. Sol-Gel Sci. Tech.* **17**, 145.
29. Mellor, J. W. (1937) *Trans. Cer. Soc.* **36**, 1.
30. Hedvall, J. A. and Heuberger, J. (1921) *Z. Anorg. Allg. Chem.* **116**, 137.
31. Baker, E. and Burch, R. Yugin, N. (1991) *Appl. Cat.* **73**, 135.
32. Ohgushi, T. and Umeno, S. (1987) *Bull. Chem. Soc. Jpn.* **60**, 4457.
33. Mathur, S. Veith, M. Haas, M. Shen, H. Hüfner, S. Haberkorn, R. Beck, H. P. Jilavi, M. (2001) *J. Amer. Ceram. Soc.* **84**, 1921.
34. Valenzuela, M. A. Bosch, P. Aguilar-Rios, G. Montoya, A. and Schifter, I. (1997) *J. Sol-Gel Sci. Tech.* **8**, 107.
35. Schmool, D. S. Keller, N. Guyot, M. Krishnan, R. Tessier, M. (1999) *J. Magn. Magn. Mater.* **195(2)**, 291.
36. Schmool, D. S. Keller, N. Guyot, M. Krishnan, R. Tessier, M. (1999) *J. Appl. Phys.* **86(10)**, 5712.
37. Mathur, S. Shen, H. Lecerf, N. Fjellvag, H. Goya, G. F. (2002) *Adv. Mater.* **14**, 1405.
38. Dzyaloshinsky, I. E. (1958) *J. Phys. Chem. Solids* **4**, 241.
39. Bozorth, R. M. (1958) *Phys. Rev. Lett.* **1**, 362.
40. Treves, D. (1965) *J. Appl. Phys.* **36**, 1033.
41. Geusic, J. E. Marcos, H. M. van Uitert, L. G. (1964) *Appl. Phys. Lett.* **4**, 182.
42. Machan, J. Kurtz, R. Bess, M. Birnbaum, M. (1987) *J. Opt. Soc. Am.* **20**, 134.
43. Shkadarevich, A. P. (1989) *J. Opt. Soc. Am.* **22**, 60.
44. Izumitani, T. (1991) *Bull. Ceram. Soc. Jpn.* **26**, 108.
45. Ikesue, A. Kamata, K. Yoshida, K. (1995) *J. Am. Ceram. Soc.* **78**, 2545.
46. Yang, J.-M. Jeng, S. M. Chang, S. (1996) *J. Am. Ceram. Soc.* **79**, 1218.
47. Veith, M. Mathur, S. Kareiva, A. Jilavi, M. Zimmer, M. and Huch, V. (1999) *J. Mater. Chem.* **9**, 3069.
48. King, B. H. Halloran, J. W. (1995) *J. Am. Ceram. Soc.* **78**, 2141.
49. Mathur, S. Veith, M. Sivakov, V. Shen, H. Gao, H. B. (2001) *J. Phys. IV* **11**, 487.
50. Mathur, S. Lecerf, N. Shen H. Veith, M. and Huefner S. (2001) *Scripta Mater.* **44**, 2157.
51. Veith, M. Mathur, S. Lecerf, N. Bartz, K. Heinz, M. Huch, V. (2000) *Chem. Mater.* **12**, 271.
52. Mathur, S. Veith, M. Shen, H. Lecerf, N. Hüfner S. and Jilavi, M. (2001) *Chem. Mater.* **13**, 4041.
53. Mathur, S. Veith, M. Shen, H. Hüfner, S. and Jilavi, M. (2002) *Chem. Mater.* **14**, 568.
54. Shen, H. and Mathur, S. (2002) *J. Phys. IV* **12**, PR4-1.
55. Mathur, S. and H. Shen. (2002) *J. Sol-Gel Sci. Tech.* **25**, 143.

NANOSIZED FINE PARTICLES AND FIBERS AS REINFORCING MATERIALS SYNTHESISED FROM SEPIOLITE

A.O. KURT
Sakarya University
Engineering Faculty, Esentepe Kampüsü,
54187 - ADAPAZARI - TURKEY

Abstract: Sepiolite has very small (several hundred nanometre thick and a few micron long) fibers with high internal and external surface areas. It was found to be a good Si source for the thermal reduction- nitridation reaction (with a reducing agent) to produce silicon nitride. Sepiolite of Turkish origin was successfully purified by a hydrometallurgical process using controlled additions of concentrated HCl acid. The crystal structure, morphology and mineral composition of the sepiolite was preserved for later treatment by intercalation and nitridation. Various types of silicon nitride having different morphologies were obtained, ranging from long whiskers to equiaxed fine particles using sepiolite and various reducing agents. Silicon nitride, in the form of nanosized fine particles and fibrous form, has been produced by pyrolysis of purified sepiolite and polyacrylonitrile intercalation complex.

1. INTRODUCTION

Sepiolite is a hydrated magnesium-silicate type clay mineral. Its chemical formula, for a half unit cell, is given as $[(\text{Si}_{12})(\text{Mg}_8)\text{O}_{30}(\text{OH})_4(\text{OH}_2)_4 \cdot 8\text{H}_2\text{O}]$ by Brauner and Preisinger [1]. The unit cell parameters are given as $a=13.4\text{\AA}$, $b=26.8\text{\AA}$, $c=5.28\text{\AA}$ [1]. Typically, sepiolite has a fibrous morphology with micro-channels along the fiber axis. The cross section of such a channel is $13.4\text{\AA}$ by $6.7\text{\AA}$ [1]. Each macro-fiber consists of tens of hundreds of sub-nanometer fibers [2]. The parallel 'piped' fibers are bundled together along the c -axis to form microscopically fibrous structure, which is porous in its crystalline form (Fig. 1-b). The generic molecular structure of sepiolite is given in Figure 1-a.

The crystal structure of sepiolite consists of two tetrahedral sheets that are continuous along the b - and c -axes and an octahedral layer that lies in one dimension is sandwiched between the two tetrahedral sheets (Fig. 1-a). Micro-channels exist along the c -axis and contain free water (zeolitic water) molecules attached to the edges of the octahedral layer. This gives sepiolite

molecular-sieving properties since only certain size molecules can either pass through or be trapped in these channels. In industry, sepiolite and its derivatives have been widely used for adsorption and molecular sieving applications in chemical industries [3-5].

It is a well-known application to exchange some Mg^{2+} for other cations and with that of heavy metals in order to increase sepiolite's sorptive and catalytic properties [6,7]. Mostly the exchange takes place at easily accessible sites at the broken bonds on the fiber surface and in the octahedral sites at the channel edges. It is also possible to disintegrate the bundles in the individual fibers and align them in one direction after replacing some of the Mg^{2+} ions with Fe^{2+} in an ion-exchanged process using aqueous solution while applying

Figure 1. Simplified ionic structure of sepiolite (a), after Brauner and Preisinger [2]. The repeat of the molecular unit in x and y -axis forms the pattern in (b). To give a clear view in b, zeolitic water molecules (H_2O) are not shown in the system.

a continuous magnetic field [8].

Positively several numbers of successful research work could be found in literature where the clay minerals and some other unusual sources of precursors were used to produce ceramic powders. For instance, Si_3N_4 of α -phase was synthesised using rice husk, digested with NH_3 and pyrolysed before heat treating at 1450 °C in flowing nitrogen [9]. Short needle-like and wool-like whiskers of Si_3N_4 were obtained using a quartzite, diatomaceous earth, terra abla and moulding sand, at 1370 °C in an NH_3-N_2 gas-stream [10]. Without paying much attention on the purity level and the rheological properties, the uses of sepiolite (Japanese and Turkish origin clay minerals) as a Si source for the synthesis of Si_3N_4 were previously explored [11-13]. In this paper, it was aimed to provide an overview of the results obtained from the study of the synthesising Si_3N_4 ceramics from sepiolite clay mineral and the potential utility of the findings.

2. MATERIALS

As-received sepiolite of brown colour was obtained from Eskişehir-Turkey. Sepiolite samples were received in the form of coarse particles. These

were crushed and sieved to different size fractions. Charcoal, carbon black and petroleum coke were primarily used as reducing agents (Table 1). Carbon black was used as-received without any further processing. Charcoal, however, was supplied in the form of big granular shaped particles; this was ball-milled to a fine powder with a high surface area. Acrylonitrile monomer supplied by *Hopkin & Willams Ltd.* was used as an alternative carbon source in a polyacrylonitrile (PAN)-sepiolite intercalation compound. Azo-isobutyronitrile (*GPR*) was used as an initiator (0.5wt.%) in acrylonitrile monomer. To stimulate the formation of α -phase, fine α - Si_3N_4 powders (average particle size, $0.5\mu\text{m}$) (NU10, *TENMAT Ltd.*) was added in some of the reactants before the carbothermal reaction.

TABLE 1. Reducing agents used in processing.

Materials	Supplied by	Purity (%)	Pour Density (kg/m^3)	Tap Density (kg/m^3)	Mean Particle size (μm)	Surface Area (m^2/g)
Carbon Black (Vulcan-10H)	Cabot	99.7	<u>345</u> [#]	390	5	<u>110</u>
Charcoal, (C/4120/53)*	Fisher Scientific	92.8	333	488	30	777
Petroleum Coke D44 GAO 43B	James & Durans Ltd.	<u>99.0</u>	761	904	70	60

* Charcoal received in the form of granular was ball milled (4h). # Values underlined are supplier data.

3. EXPERIMENTAL METHODS

Mineral and chemical compositions of sepiolite are given in Table 2 and Table 3, respectively. Sepiolite clay mineral comes with high amount of impurity content (i.e., dolomite). Sepiolite in the form of course particles was sieved to different size fractions. Powders of $-150\mu\text{m}+75\mu\text{m}$ size fraction were purified using 0,21 M HCl acid solutions. Techniques to use and the details of the purification process have been previously reported [14]. Purified samples were used as a precursor for later use in carbothermal reduction-nitridation process and in sepiolite-polyacrylonitrile compound. Analysing of the starting materials, precursors and the reaction products using standard characterisation techniques have been thoroughly described [14,15].

TABLE 2. Mineral composition and features of the clay sample used in this study.

Mineral	Sepiolite (wt.%)	Dolomite (wt.%)	Total Weight Loss at 1000 °C (%)	Surface Area at 25 °C ($\text{m}^2 \text{g}^{-1}$)
As-received	81.52 $\pm$ 1.00	18.48 $\pm$ 1.00	25.25	87
After purification	100	0	-	161

TABLE 3. Chemical composition (wt.%) of sepiolite samples, as-received material - 150 +75 μ m size fraction after sieving.

SiO ₂	MgO	CaO	Al ₂ O ₃	Fe ₂ O ₃	K ₂ O	TiO ₂	Na ₂ O	P ₂ O ₅
47.11	20.48	5.62	0.94	0.44	0.08	0.05	0.02	0.01

4. RESULTS AND DISCUSSION

4.1 Sepiolite

Dolomite impurity, constitutes in approx. 20 % of the as-received mineral, was fully eliminated by treating with 0.21M HCl for 2h at 60 °C (solid to liquid ratio 1/15 g.ml⁻¹) without any obvious effect on the molecular framework of fibrous sepiolite structure. This was confirmed by XRD, IR and SEM data (Fig. 2). The specific surface area of sepiolite is doubled after the elimination of the impurity, from 87 m².g⁻¹ for sepiolite as-received material to 161 m².g⁻¹ for the sample after leaching as expected since dolomite occurs as a cement in-between the parallel pipe-shaped sepiolite fibers.

An initial trial was made to produce silicon nitride from the HCl acid treated sepiolite and a polyacrylonitrile intercalation compound. The purified sepiolite was soaked in either a fixed amount or excess of an acrylonitrile monomer after the dehydration of zeolitic water molecules (at 140 °C, 2h). This precursor was subsequently polymerised and cyclized to produce stabilised PAN (to be a source of carbon in the later stage of pyrolysis) so that the resulting carbon could be used as a reducing agent in the carbothermal reduction-nitridation (CRN) process. The main purpose of using sepiolite-PAN was to obtain an intimate mixture of the reducing agent with the oxide phase(s) so that sepiolite and carbonised organic molecules (i.e., PAN) would contact at a molecular level during the carbothermic-reduction process. In

Figure 2. SEM micrographs of the sepiolite fibers as-purified (a) and after polymerisation and cyclization (b) using the monomer at a weight to volume ratio of 1/2 (g/ml).

addition, the use of a high purity monomer virtually free from inorganic matter would eliminate any ash content. Figure 2-b shows sepiolite fibers

after polymerization and cyclization stages. The specific surface area of the cyclized sepiolite-PAN sample was measured as $6.30 \text{ m}^2.\text{g}^{-1}$, which is well below the value of the total external surface area ($161 \text{ m}^2.\text{g}^{-1}$) of an equal mass of pure sepiolite fibers. This suggests that although there is no optically visible external polymer coating on the fibers, i.e., the sepiolite's fibrous morphology was preserved, a thin coating of polymer must exist over the bundle of fibers. Also, the channels and pores of the fibers, which were previously open, must have been filled by the monomer and the subsequent polymerisation would then block and cover the sepiolite fibers with a thin coating of polymer.

Acrylonitrile monomer having a free radical initiator is successfully impregnated and polymerized into the channels of sepiolite fibers. An expanded account of the polymerisation of sepiolite-AN monomer is given somewhere [15].

Sepiolite as purified form or after polymerization or cyclization stages could be of some use, such as, in polymeric systems where fine fibers as reinforcing or filler elements are needed. Due to very cheap and relatively unsophisticated production processes purified sepiolite having individual fibers (or bundles of fibers) aligned in one direction could be used in, for example micro chemical sensors and membranes for molecular level filtration. Sepiolite fibers were used commercially as components for a carrier in chemical industry, such as for pharmaceuticals, cosmetics, and pesticides. However, application of sepiolite in chemical industry, such as in the pharmaceutical products, could be well explored after fully searching its health related biological behavior. There is a limited research on this therefore it has yet to be demonstrated whether the inhalation of sepiolite fibers is harmful to humans or not [16].

4.2 Silicon Nitride

Fine sized (uniaxial or long whiskers) and surface area up to $11.5 \text{ m}^2.\text{g}^{-1}$ silicon nitride powders were synthesised from sepiolite-PAN and sepiolite-solid carbon precursors; preparations of the precursors and details on the carbothermic reactions have been previously explained [14]. It was found that the amount and the morphology of the products after nitridation were dependent upon several factors in the synthesis and on the constituents, as well as the method of preparation of reagents. The state of the starting materials was found to have a major effect, also impurities, on the formation of Si_3N_4 and the α/β phase ratio. Under the identical testing conditions (i.e. the same purified sepiolite sample used and all samples nitrided identically, for example, at 1400°C for 4h with 300°C/h heating rate and 1000 ml/min N_2 -flow rate); the best results were obtained with sepiolite-PAN and sepiolite-charcoal mixtures. Sepiolite-petroleum coke, on the other hand, yielded only small amounts of $\beta\text{-Si}_3\text{N}_4$ in CRN process. This effect was somewhat attributed to the specific surface area of the reducing agents (Table 1). It was

observed that samples ran at relatively low temperatures (1300 - 1323 °C) with long nitridation time (8 - 16h.) resulted in the formation of Si_3N_4 whiskers (Fig. 3-a), which were identified as α -form constituted 40wt.% of the product. Either increasing the temperature or lowering the reaction time results in the formation of uniaxial fine grains that mainly of β -phase (approx. 74-81wt.%). Changes in powder morphology and particle size with a change in using different reducing agent was obvious since sepiolite-PAN intercalation compound yielded very fine particles mainly of β - Si_3N_4 (Fig. 3-b). Due to the nature of using clay mineral as a main source for Si, small amount of the retained magnesium silicate phases remained in the final product after nitridation. However, they were found beneficial since Si_3N_4 powders require such additives, which forms liquid phase on sintering.

Microscopic examinations using SEM and TEM showed that both precursor and end products after nitridation were submicron (100-200nm) in size (or cross section) that may be utilised as reinforcing material in metallic and polymeric systems. Sepiolite alone or combined with PAN could be of some use in polymeric systems as a cheap filler material. The further work is projected on concentrating the benefits of using such materials as strength inducing mechanisms. Silicon nitride synthesised from sepiolite contains inevitably some retained oxides phases that are not tolerable to make them use in high temperature applications. Therefore, the synthesised powders could be of an alternative source for low temperature applications such as, thermocouple protection sheaths, riser and delivery tubes in low-pressure diecasting operations and cutting edges for scissors. Some powders having high amount of silicon nitride phase were pressureless sintered at 1700 °C for 1h without using any additives. Powders, retained their small average grain size after sintering produced up to 85% theoretical density [17].

Figure 3. The particle morphology of Si_3N_4 whiskers after 16h reaction at 1300 °C using sepiolite-charcoal mixture (a). Mainly fine β -phase particles with some lath-like shaped α -phase short fibers produced from sepiolite-PAN (b). (Carbothermal reduction-nitridation process took place at 1350 °C for 4h.)

5. CONCLUSION

Sepiolite clay mineral retained its fibrous microporous morphology after controlled hydrometallurgical processes. It could be of some use as its pure mineralogical form or after modifying it with hydrometallurgical processes. Sepiolite possesses microfibers, which have parallelepiped tunnels along the fiber axis that were filled with a suitable monomer for the preparation of fibrous silicate - polymer nanocomposite materials. Research and progress on the behaviour of an individual and the group of the fibers with or without intercalation will open new perspective of using sepiolite.

Silicon nitride powders of fine uniaxed grains or long whiskers were produced using sepiolite fibers with a reducing agent under reduction-nitridation atmosphere. The grain size and morphology of silicon nitride were found to be dependent on the reaction conditions and starting reagents.

References

1. Brauner, K. and Preisinger, A. (1956) Structure of Sepiolite, *Miner. Petrogr. Mitt.*, **6**, 120-140.
2. Rautureau, M. and Tchoubar, C. (1976) Structural analysis of sepiolite by selected area electron diffraction relations with physico-chemical properties, *Clays and Clay Minerals*, **24**, 43-49.
3. Daza, L. Mendioroz, S. and Pajares, J.A. (1989) Influence of texture and chemical composition on sulphur deposition onto sepiolites, *Applied Clay Science*, **4**, 389-402.
4. Fujiwara, I. and Sato, M. (1992) Adsorption of water vapor on sepiolite for chemical heat pumps, *Journal of Chemical Engineering of Japan*, **25**, (5), 609-611.
5. Grillet, Y. Llewellyn, P.L. Tosi-Pellenq, N. and Rouquerol, J. (1993) Adsorption of argon, methane, nitrogen, carbon monoxide and water vapour on sepiolite and ALPO4-5 as studied by isothermal microcalorimetry. *Fundamentals of Adsorption, Proc. IVth Int. Conf. on Fundamentals of Adsorption*, p.235-242, International Adsorption Society, Kyoto, May 17-22, 1992.
6. Brigatti, M.F., Lugli, C. and Poppi, L. (2000) Kinetics of heavy-metal removal and recovery in sepiolite, *Applied Clay Science*, **16**, 45-57.
7. Galan, E. (1996) *Clay Minerals*, **31**, 443-453.
8. Esmer, K. and Yenyol, M. (1999) Current-voltage characteristics and aging of sepiolite oriented by magnetic field, *Materials Letters*, **38**, 445-449.
9. Rahman, I.A. (1994) *Ceramic International*, **20**, 195-199.
10. Mizuhara, Y. et al. (1994) *J. Ceram. Soc. Japan, Int. Ed.*, **102**, 489-494.
11. Sugahara, Y. et al. (1985) *J. Mater. Sci. Lett.*, **4**, 928-931.
12. Arık, H. et al. (1995) "Sepiyolitten Karbo-thermal Indirgeme Yöntemiyle Silisyum Nitrür (Si_3N_4) Dönü-şümünün Araştırılması", *VII Ulusal Kil Sempozyumu*, (VII National Clay Symposium), 27-30 September, Ankara, Turkey.
13. Arık, H. (1996) Ph.D. Thesis, Gazi Üniversitesi, Ankara, Turkey.
14. Kurt, A.O. and Davies, T.J. (2001) Synthesis of Si_3N_4 using sepiolite and various sources of carbon, *Journal of Materials Science*, **36**, 5895-5901.
15. Kurt, A.O. and Davies, T.J. (2001) Sepiolite-PAN intercalation used as Si_3N_4 forming precursor, *Journal of Materials Science*, **36**, 957-962.
16. Bellmann, B. Muhle, H. and Ernst, H. (1997) Investigations on health-related properties of two sepiolite samples, *Environmental Health Perspectives*, **105**, (S5), 1049-1052.
17. Kurt, A.O. and Davies, T.J. (2001) Pressureless sintering of Si_3N_4 powders obtained from carbothermally reduced sepiolite, *Journal of Materials Science Letters*, **20**, 1067-1070.

THERMAL CONDUCTIVITY OF PARTICLE REINFORCED POLYMER COMPOSITES

I.H.Tavman

*Mechanical Engineering Department
Dokuz Eylül University, 35100 Bornova /Izmir – Turkey.*

Abstract: In this paper a survey of literature on thermal conductivity of nanometer sized particle and fiber filled polymer composites are given as well as thermal conductivity of nanofluids (nanoparticles in suspension in fluids). Also models predicting the effective thermal conductivity of composites filled with particles are stated and are compared with experimental data with micro-sized Al_2O_3 particle filled HDPE composite.

1. INTRODUCTION

In order to obtain materials of desired thermal, mechanical and electrical properties, matrix materials, such as polymers, are processed with different kind of fillers. Fillers may be in the form of fibers or in the form of particles uniformly distributed in the polymer matrix material. Many of the properties of fibrous composite materials are strongly dependent on the fiber properties as well as on microstructural parameters such as fiber diameter, fiber length, fiber length distribution, volume fraction of fibers and the alignment and packing arrangement of fibers. It is evident that thermophysical properties of fiber filled composites are anisotropic, except for the very short, randomly distributed fibers. Whereas, thermophysical properties of particle filled polymers are isotropic. Many theoretical, numerical and experimental studies exist about thermal conductivity of micrometer sized particles and fiber filled polymer composites.

Recently, techniques have been developed to process matrix materials with nanometer sized grains, particles and fibers. These filler may be used as an effective strategy for either increasing or reducing heat transfer rates of composite materials. There are very few publications about thermal conductivity of nano particle and fiber filled polymer composites, a recent research by Putman et al. [1] used the 3 ω method to study the thermal conductivity of composites of nanoscale alumina particles in polymethylmethacrylate (PMMA) matrices in the temperature range $40 < T < 280$ K. For 10% of 60 nm of alumina particle filler by weight (3.5% by volume) thermal conductivity of the composite is slightly decreased at low

temperatures (below 100 K), the maximum decrease taking place at 40K which is about 2.5% less than the pure PMMA. Whereas, above 100 K, thermal conductivity of the nanocomposite is slightly increased, maximum increase of 4% at room temperature. They also did measurements with micrometer sized alumina particles, thermal conductivity of the composite is increased about 2 to 3% in the whole temperature range.

Another publication by Kruger and Alam [2] is about the thermal conductivity of aligned, vapor grown carbon nanoscale fiber reinforced polypropylene composite. They measured thermal conductivity by Holometrix μ Flash Thermal Properties instrument in the longitudinal and transverse directions for 9%, 17% and 23% fiber reinforcements by volume. The values of thermal conductivity are 2.09, 2.75, 5.38 W/m.K for the longitudinal directions and 2.42, 2.47, 2.49 W/m.K for the transverse direction respectively, while the thermal conductivity of unfilled PP is 0.24 W/m.K. There is anisotropy in thermal conduction, there is increase in both direction.

A recent area of research is about the effective thermal conductivity of liquid with nanoparticle inclusions. The effective thermal conductivity of nanoparticle suspension can be much higher than the normally used industrial heat transfer fluid, such a fluid has been terminologized as "nanofluid", and considered to be a novel enhanced heat transfer fluid. Very recently, Keblinski et al. [3] reported their idea on the possible mechanisms of enhancing thermal conductivity, and suggested that the size effect, the clustering of nanoparticles and the surface adsorption could be the major reason of enhancement, while the Brownian motion of nanoparticles contributes much less than other factors. In particular, it was demonstrated that solid nanoparticle colloids (i.e., colloids in which the grains have dimensions of $\approx 10 - 40$ nm) are extremely stable and exhibit no significant settling under static conditions, even after weeks or months [4]. Furthermore, the enhancement of thermal-transport properties of such "nanofluids" was even greater than that of suspensions of coarse-grained materials [5]. For example, the use of Al_2O_3 particles ≈ 13 nm in diameter at 4.3% volume fraction increased the thermal conductivity of water under stationary conditions by 30% [6]. Use of somewhat larger particles (≈ 40 nm in diameter) only led to an increase of less than $\approx 10\%$ at the same particle volume fraction [5]; more in accord with theoretical predictions [7]. An even greater enhancement was recently reported for Cu nanofluids, where just a 0.3% volume fraction of 10 nm Cu nanoparticles led to an increase of up to 40% in thermal conductivity [8], a result that is more than an order of magnitude above the increase predicted by macroscopic theory. Currently, the origin of such remarkable increases in the thermal conductivity of nanofluids eludes theoretical understanding.

2.THERMAL CONDUCTIVITY MODELS FOR TWO PHASE SYSTEMS

Many theoretical and empirical models have been proposed to predict the effective thermal conductivity of two phase mixtures. The upper or lower bounds of effective thermal conductivity are given when materials are arranged in either parallel or series with respect to heat flow. For the parallel conduction model:

$$(1) \quad k_c = \phi.k_f + (1-\phi).k_m$$

and for series conduction model:

$$(2) \quad \frac{1}{k_c} = \frac{\phi}{k_f} + \frac{1-\phi}{k_m}$$

where, k_c , k_m and k_f are thermal conductivities of composite, matrix and filler, respectively and ϕ is the volume fraction of filler.

In the case of geometric mean model, the effective thermal conductivity is given by:

$$(3) \quad k_c = k_f^\phi . k_m^{(1-\phi)}$$

Using potential theory, Maxwell [9] obtained a simple relationship for the conductivity of randomly distributed and non-interacting homogeneous spheres in a homogeneous medium:

$$(4) \quad k_c = k_m \frac{k_f + 2.k_m + 2.\phi.(k_f - k_m)}{k_f + 2.k_m - \phi.(k_f - k_m)}$$

Based on Tsao's probabilistic model Cheng and Vachon [10], assumed a parabolic distribution of the discontinuous phase. The constants of the parabolic distribution were evaluated as a function of the discontinuous phase volume fraction. The effective thermal conductivity is given for the case $k_f > k_m$:

$$\frac{1}{k_c} = \frac{1}{\sqrt{C.(k_f - k_m)(k_m + B.(k_f - k_m))}} \ln \frac{\sqrt{k_m + B.(k_f - k_m)} + B/2\sqrt{C.(k_f - k_m)}}{\sqrt{k_m + B.(k_f - k_m)} - B/2\sqrt{C.(k_f - k_m)}} + \frac{1-B}{k_m}$$

(5)

$$\text{where, } B = \sqrt{\frac{3.\phi}{2}}, \quad C = -4.\sqrt{\frac{2}{3.\phi}}$$

Lewis and Nielsen [11] derived a semi-theoretical model by a modification of the Halpin-Tsai equation to include the effect of the shape of the particles and the orientation or type of packing for a two-phase system:

$$(6) \quad k_c = k_m \frac{1 + A \cdot \beta \cdot \phi}{1 - \beta \cdot \phi \cdot \psi}$$

$$\beta = \frac{k_f/k_m - 1}{k_f/k_m + A} \quad \text{and} \quad \psi = 1 + \frac{1 - \phi_m}{\phi_m^2} \phi$$

The constant A depends upon the shape and orientation of the dispersed particles. ϕ_m is the maximum packing fraction of the dispersed particles. For randomly packed spherical particles $A=1.5$ and $\phi_m=0.637$, whereas for randomly packed aggregates of spheres or for randomly packed, irregularly shaped particles $A=3$ and $\phi_m=0.637$.

Based on the generalization of models for parallel and series conduction in composites, Agari and Uno [12] propose a new model for filled polymers:

$$(7) \quad \log k_c = \phi \cdot C_2 \cdot \log k_f + (1 - \phi) \cdot \log(C_1 \cdot k_m)$$

where, C_1 , C_2 are experimentally determined constants of order unity. C_1 is a measure of the effect of the particles on the secondary structure of the polymer, like crystallinity. C_2 measures the ease of the particles to form conductive chains, the more easily particles are gathered to form conductive chains, C_2 becomes closer to 1. However, experimental data is needed for each type of composite in order to determine the necessary constants.

Fig. 1. Comparison of the experimental and predicted thermal conductivity values for high density polyethylene filled with Al_2O_3 micro particles at 15°C .

3. EXPERIMENTAL

Samples are prepared by mold compression process. The matrix material is commercial high density polyethylene in powder form, density 0.968 g/cm^3 , melt index 5.8 g/10min and measured thermal conductivity 0.545 W/m.K . The filler is Al_2O_3 powder with particle size 10-20 microns, the solid density of Al_2O_3 is 3.99 g/cm^3 and its thermal conductivity 31 W/m.K . Thermal conductivity measurements are performed using the Shotherm QTM thermal conductivity meter working with a modified hot wire method. Thermal conductivity measurements are performed on HDPE filled with Al_2O_3 particles up to a volumetric fraction of 26%, at 15°C . The results are plotted in Fig.2 and are compared to calculated values from Maxwell, Cheng & Vachon, Lewis & Nielsen, Agari & Uno, geometric mean models. Geometric mean and Agari & Uno models predict quite well the thermal conductivities of the composite in the whole range. In Agari & Uno model the values of the coefficients are calculated as $C_1=1.013$ and $C_2=1.021$.

4. THERMAL CONDUCTIVITY OF POLYMER NANOCOMPOSITES

The existing understanding of the effective thermal conductivity of composites and mixtures is derived from continuum-level phenomenological formulations that typically incorporate only the particle shape and volume fraction as variables and assume diffusive heat transport in both phases; no effects of interfaces or particle mobility are taken into account. This approach, while providing a good description of systems with micro-meter or larger-size particles, fails to describe thermal transport in nanocomposites. Interfaces between materials become increasingly important on small length scales. The thermal conductance (G) of many solid-solid interfaces have been studied experimentally but the range of observed interface properties is much smaller than predicted by simple theory. Classical molecular dynamics simulations are emerging as a powerful tool for calculations of thermal conductance and phonon scattering, and may provide for a lively interplay of experiment and theory in the near future.

For sufficiently small particles, the properties of the polymer/nanoparticle interface also control thermal transport in the composite. Interface effects in thermal transport can be captured by effective medium models if the introduction of particle fillers does not significantly alter the thermal conductivity of the matrix material. Since local vibrations of the atoms and molecules dominate heat transport in an amorphous polymer, this assumption should be well satisfied in a PMMA composite. In the limit of a low volume fraction ϕ of high thermal conductivity spherical particles, the thermal conductivity of the composite k_c is [1]:

$$(8) \quad k_c - k_m = 3\Phi k_m \frac{\gamma - 1}{\gamma - 2}$$

Fig.2. Normalized changes in thermal conductivity of the composite as a function of normalized thermal conductance of the nanoparticle interface

where, k_m is the thermal conductivity of the matrix and $\gamma = rG/k_m$; r is the radius of the particle and G is the thermal conductance per unit area of the particle/matrix interface. This equation is plotted in Fig. 2. A critical particle radius is defined as $r_c = k_m/G$; the thermal conductivity of the composite is increased by particles of size $r > r_c$ and decreased for $r < r_c$. The changes in conductivity are a relatively weak function of (rG) , but the thermal conductivity is sensitive to G over a wide range of particle sizes $0.3 < r/r_c < 8$. Fig.3. shows experimental results by Putman et al. [1] of normalized difference in the thermal conductivity $(k_c - k_m)/k_m$ of nano and micro-scales Al_2O_3 particles in PMMA matrices. In this figure the small differences in conductivity with respect to pure PMMA are highlighted. The conductivity is slightly decreased by the particles fillers at $T < 100$ K and modestly increased at $T > 150$ K. The anomalous increases in conductivity that have been reported recently for nanoparticles in fluids[9] is not observed in this case. As for the μm -sized Al_2O_3 particles filled composite, the constant slight increase in normalized thermal conductivity is roughly in agreement with Eq.8 for the limit of large r or large thermal conductance G

Fig.3. Normalized changes of the measured thermal conductivity of Al_2O_3 particles filled PMMA composites.

References

- [1] Putnam, S.A., David G. Cahili, D.G., Ash, B.J. and Schadler, L.S. (2003), High-precision thermal conductivity measurements as a probe of polymer/nanoparticle interfaces
- [2] Kuriber R.J., Alam M.K. (2002) Thermal conductivity of thermoplastic composites with submicrometer carbon fibers, *Exp. Heat Transfer* 15, 19-30
- [3] Koblinski, P; Phillpot, SR; Choi, SUS; Eastman, JA, Mechanisms of heat flow in suspensions of nano-sized particles, 2002, *Int. J. Heat and Mass Transfer*, 45(4):855-863
- [4] J.A. Eastman, U.S. Choi, S. Li, G. Soye, L.J. Thompson, R.J. Di Marzio, Novel thermal properties of nanostructured materials, *Mater. Sci. Forum* 312-314 (1999) 629-634.
- [5] S. Lee, S.U.S. Choi, S. Li, J.A. Eastman, Measuring thermal conductivity of fluids containing oxide nanoparticles, *ASME J. Heat Transfer* 121 (1999) 280-289.
- [6] H. Masuda, A. Ebata, K. Teramae, N. Hishinuma, Alteration of thermal conductivity and viscosity of liquid by dispersing ultra-fine particles (dispersions of $Y-Al_2O_3$, SiO_2 , and TiO_2 ultra-fine particles), *Netsu Bussei (Japan)* 4 (1993) 227-233.
- [7] R.L. Hamilton, O.K. Crosser, Thermal conductivity of heterogeneous two-component systems, *I & EC Fundamentals* 1 (1962) 187-191.
- [8] Eastman, JA; Choi, SUS; Li, S; Yu, W; Thompson, LJ, 2001, Anomalous increase in effective thermal conductivities of ethylene glycol-based nanofluids containing copper nanoparticles, *Appl. Phys. Lett.* 78(6):718-720
- [9] Maxwell JC. A treatise on electricity and magnetism. Dover (3rd Ed.), New York, Ch.9. 1954.
- [10] Cheng SC, Vachon RI. The prediction of the thermal conductivity of two and three phase solid heterogeneous mixtures. *Int. J. Heat Mass Transfer* 1969; 12: 249.
- [11] Lewis T, Nielsen L. Dynamic mechanical properties of particulate-filled polymers. *J. Appl. Polym. Sci.* 1970; 14: 1449.
- [12] Agari Y, Uno T. Estimation on thermal conductivities of filled polymers. *J. of Appl. Poly. Comp. Sci.* 1986; 32: 5705-5712.

FLUORESCENCE QUENCHING BEHAVIOUR OF HYPERBRANCHED POLYMER TO THE NITRO-COMPOUNDS

HONGXIA WANG¹, TONG LIN^{1*}, FENG LIAN BAI² AND AKIF KAYNAK¹,

School of Engineering and Technology, Deakin University, Geelong, Victoria 3217 Australia¹

The Centre of Molecule Science, Chinese Academic of Sciences. Beijing, 100080, PR China²

Abstract: Fluorescence quenching behaviour of hyperbranched polymer film to various aromatic nitro-compounds is presented. The quenching efficiency of 1% and 1 ppm polymer solution in ethanol is 80% and 40%, respectively, for the nitro aromatic compounds. It has been established that aromatic structure and numbers of nitro groups have almost no effect on the quenching properties. The quenching is concentration dependent. The quenching for the vapour of nitro compounds is fast and related to the vapour pressure. The quenching mechanism was attributed to the strong electron-withdrawing property of the nitro groups. Presence of an electron-donating group showed fluorescence enhancement to hyperbranched polymer. Molecular simulation of the polymer structure has shown that the hyperbranched conjugated polymer has a well-developed network structure, with cavities being large enough for the nitro aromatic molecule to penetrate and interact with the polymer linkage.

Keywords: hyperbranched conjugated polymer, fluorescent quenching, nitro-aromatic compounds, chemical sensor.

1. INTRODUCTION

Recently, accurate and rapid detection of the trace amounts of nitro-compounds in the environment has attracted considerable attention because of its potential applications in exploring the 2,4,6, trinitro toluene (TNT) or picric acid, often occurring in explosives. The sensor device is based on the fact that the nitro-compounds quench the fluorescence of luminescent materials due to the strong electron-withdrawing nature of nitro-groups. The sensor

* Corresponding Author: Tong Lin, Deakin University, School of Engineering and Technology, Geelong, Victoria, 3217, Australia. Email: tongl@deakin.edu.au, Fax: (03) 5227 2539

material includes highly luminescent conjugated polymers and polymer nanowires [1,2].

Porosity of the structure in the solid state and strong interaction with the analysed molecules are very important for developing the highly efficient sensor materials. To improve the absorption ability, large steric substituents were introduced to the side-chain of linear polymers material [3,4]. In addition, the substituents that have special affinity to the nitro compounds were introduced into the polymer to “amplify” the sensor signal [5,6].

A hyperbranched polymer shows a considerably different structure from a linear polymer. The numbers of branches increases in every repeated unit and exhibits a three dimensional network structure, irrespective of existence of large steric substituents in the side chain. In our former research, we have reported the synthesis, photophysical properties and electroluminescent applications of the hyperbranched conjugated polymers. Those materials showed a high fluorescence quantum yield and a network structure, which stimulated us for the further investigation of their potential applications as chemical sensors.

In this report, the fluorescent quench properties of the hyperbranched poly(p-phenyl vinylene) (PPV) in various nitro-compounds are presented.

2. EXPERIMENTAL

All the compounds were reagent grade and used as received. The organic solvent was dried according to the standard dehydrating methods before use. The hyperbranched polymer was synthesized in the Centre for Molecule Science, The Chinese Academic of Sciences, China, according to our former method [7] and the polymer structure was characterized by NMR and GPC.

The polymer films were fabricated on glass slides by spin-coating method. The concentration of the hyperbranched polymer was about 1mg/ml in chloroform. UV-VIS absorption and fluorescence spectra were measured on a HITACHI U-3010 spectrophotometer and a fluorescence spectrophotometer, respectively.

The fluorescent quenching properties of the film device in solution was determined by immersing the device into the ethanol containing the analysed compound for a period of time followed by drying in nitrogen atmosphere for 1 minute. The film fluorescence spectra before and after immersing into the ethanol were recorded and the quenching efficiency η was calculated by the following formula:

$$\eta = \frac{I_0 - I}{I_0} \times 100\% \quad (1)$$

Where, I_0 and I are the emission intensities of the device at the same emission wavelength, before and after the quenching treatment, respectively.

The fluorescence quenching by the nitro compound vapour were obtained by inserting the device into a sealed glass bottle (200 ml size) that contained solid nitro compound. A cotton gauze was used to prevent the direct contact of the polymer film with the nitro compound and maintain a constant vapour pressure. After a period of exposure, the film was taken out and the fluorescence spectrum was recorded immediately. The quenching efficiency was calculated using equation (1).

3. RESULTS AND DISCUSSION

3.1. Photo physical properties of hyperbranched polymer

The structure of hyperbranched PPV (HP1) is shown in Figure 1. The polymer contains a phenyl vinylene unit, which is similar as in the linear poly(p-phenyl vinylene)(PPV). In contrast to the linear PPV, the HP1 had a 1,3,5-trivinyl phenyl moiety in every repeated unit that led the polymer increase its linkage in the hyperbranched way and produce many terminal groups. In this report, HP1 was used with 4-tert-Butyl phenyl vinyl as terminal groups.

Figure 1.

terminal groups.

The UV-visible absorption of HP₁ in CH₂Cl₂ shows maxima at 323 and 405nm, with a molar absorption coefficient in the order of 10⁴. Upon UV excitation, polymer solution exhibited intense fluorescence with the maxima at 457 and 480nm. The large Stokes shift (57nm) suggests that a structural relaxation occurs in the singlet excited states.

Upon exciting at 340nm, the fluorescence quantum yield was measured as 95% by the relative method using the 1,6-diphenyl-1,3,5-hexatriene as standard ($\phi=80\%$) [6].

By spin coating, an optically transparent film was obtained. No crystallization appeared even when the film was exposed to air for a long time. The film shows absorption maxima at 313 and 392 nm and an emission maximum at 502nm, about 20 nm red-shifted with respect to the solution state. The small difference in emission spectra between the solution and solid film states indicated a weak inter-chain interaction in the solid film.

Figure 2. UV-VIS and fluorescence spectra of HP in dichloromethane (solid line) and solid film state (dotted line).

3.2. Solution State Fluorescence Quenching

Ten different aromatic compounds were investigated and their structures are listed in Table 1.

Table 1. Molecular structure and vapour pressure of the quencher compounds

1,3,5- trinitrobenzene	nitrobenzene		4-nitrotoluene	anthraquinone
TNB	NB	p- dimethoxy benzene DMB	NT	AQ
3.2 10-6 mmHg 25°C	0.27mmHg 25 °C	0.08mmHg 25 °C	0.1mmHg 20 °C	1.8mmHg 200 °C

m-dinitrobenzene	2,4-dinitrofluoro benzene DNFB	p- chloronitro benzene CNB	1,4-benzoquinone	p-dichlorobenzene
mDNB Less than 1mmHg 20 °C	0.75 mmHg 20 °C	0.09mmHg 25 °C	BQ 0.8mmHg 25 °C	DCIB 10mmHg 54.8 °C

Because HP1 is not soluble in ethanol, the ethanol solutions of the quenchers were used in the quenching test. The change in quenching efficiency with the concentration of NB can be seen in Figure 3. Concentration dependence was observed with the efficiency decreasing from 75% to 40% as the concentration changed from 1% to 1ppm. As the fluorescence quenching involves an electron transfer between the NB and the polymer, NB molecules should penetrate into the HP1 film and reach luminescent centres. The diffusing speed of the quencher was determined by its concentration and affinity to the polymer.

Figure 3. Quenching efficiency versus NB concentration

When immersed into the NB solution for 5 minutes, the quenching efficiency of the HP1 film reached to 35% (Figure 4). Longer period of immersion, even as long as 1 hour, did not cause a large increase on the quenching efficiency. So the diffusion of NB molecule from ethanol solution

to HP1 film is less time dependent, which indicated that the HP1 film had high penetrability.

Figure 4. Quenching efficiency versus quenching time

Different quencher molecules were used to interact with the HP1 film. The quenching efficiencies of the 1% of nitro compound solutions were around 80% (Figure 5). The aromatic structure had less effect on the quenching efficiency, which suggests that aromatic structure had a minor effect on the diffusion of the nitro compounds to the polymer film. In addition, aromatic compounds with two or three nitro groups showed similar quenching efficiency to the compounds with a single nitro group in the molecule, as the space structure might allow only one nitro group of the molecule to have quenching interaction with HP1 polymer.

Figure 5. Fluorescence quenching yield of different nitro compounds

Quinone was found to quench the fluorescence of HP1 film and revealed a similar quenching efficiency to the nitro compounds. As both the quinone and nitro group are strong electron withdrawing groups, the similarity in fluorescence quenching behaviour suggested strong electronic interaction between the electron-withdrawing groups and the optically excited HP1 molecule. A photo induced electron transport occurred between the excited polymer and the grounded quencher molecule [5,6]. In order to confirm the electronic interaction, an electron-donating compound, p-dimethoxyl benzene was used in the quenching test. The fluorescence determination revealed that the emission intensity increased after the same quenching treatment. A similar result was reported for the linear conjugated polymers, which was attributed to electron-donating interaction of the DMB molecule [8]. The solvent effect was excluded by using a pure ethanol to interact with the HP1 film.

The quenching efficiencies in 1ppm solution showed lower quencher efficiency, around 40%, when compared with the 1% solutions (Figure 5).

3.3 Gas fluorescence quenching

Figure 4 shows the quenching efficiency of HP1 film in mDNB vapour. The quenching efficiency increased as the exposing time of HP1 film in the vapour. The quenching efficiency after a one minute exposure to vapour was 40%, which is very close to the result in the 1ppm solution. After five minutes, the quenching efficiency reached 90%, which corresponded to the HP1 film in 1% solution. The similar quenching efficiency values suggested that similar quantities of quencher molecules interacted with the HP1. So the HP1 film was capable to detect ppm concentration of mDNB vapour in a very short time.

Figure 6. Quenching efficiency versus the exposure time of HP1 film in the mDNB vapour.

The fluorescence quenching efficiencies in other quencher vapours were shown Figure 7. Due to the different vapour pressures, these compounds had different concentrations in air, which led to the different diffusion speeds. In the same exposure time, 5 minutes, the quenching efficiencies of DNFB, mDNB, NB, CNB, BQ reached to 90%, which were higher than results obtained in 1% solution. The quenching efficiency was 70% for NT and 60% for TNB and DCIB. In contrast, the AQ showed low quenching efficiency of 20%. The quench behaviour in the vapours seems relate to the vapour pressure of the quencher compounds. Similar to the result in the solution state, HP1 film showed a fluorescence enhancement in the DMB vapour.

Figure 7. Fluorescence quenching efficiency of the HP1 film in various compounds vapours for 5 minutes.

In order to understand the structural characteristics of the HP1, the geometry of the HP1 was simulated by using the molecular machine method (MMX). Due to the macromolecular nature and the limit of the software, only a model molecule was simulated and the optimised geometry is shown in Fig 8. A high network structure was formed as the main chains increase. Many cavities are formed in the polymer molecule due to the rigid nature of the conjugated main chains. The diameter of the cavity is ~2 nanometres. The quencher molecules were also simulated in the same way and the structure and dimensions of the molecules are shown in Fig. 9. The largest size in molecules is about 1 nm. The cavity size in the polymer molecule is large enough for the quencher molecule to penetrate, rotate and approach the main chain of the polymer and interact with the emission

centres.

Figure 8. Network structure of the optimised geometry of HP1 section and trinitro benzene (TNB) molecule

Figure 9. Simulated dimensions of quencher molecules

4. CONCLUSION

The fluorescence quenching behaviour of the hyperbranched conjugated polymer to various nitro aromatic compounds has been investigated. The polymer film in the quencher solution shows high quenching efficiency and the efficiency is concentration dependent. The number of nitro groups in the quencher molecule had a minor effect on the quenching efficiency. The quenching behaviour to vapour was slightly different from that to solution. This may be attributed to the vapour pressure of the compounds.

MMX molecular simulation has confirmed that the hyperbranched conjugated polymer had a high network structure due to the highly branched main chain structure. The cavity size is about 2 nm, which is large enough for the quencher molecules to penetrate and interact with the polymer. These results indicate potential in the design of new and highly efficient chemical sensors for monitoring the environmental pollutants and security purposes.

Acknowledgement: The authors thank the Department of Chemistry at Deakin University for their support in spectroscopy.

References

1. Yang, J.-S., Swager, (1998) T. M. Porous Shape Persistent Fluorescent Polymer Films: An Approach to TNT Sensory Materials, *Journal of the American Chemical Society*, 120, 5321-5322.
2. Wang, J., Bhada, R. K., Lu, J., MacDonald, D (1998) Remote electrochemical sensor for monitoring TNT in natural waters, *Analytica Chimica Acta*, 361, 85-91.
3. Williams, V. E.; Yang, J. S., Lugmair, C. G., Miao, Y. J., Swager, T. M. (1999) Design of novel ipitycene-containing fluorescent polymers for the detection of TNT, *Proceedings of SPIE-The International Society for Optical Engineering*, 3710, 402-408.
4. Rose, A., Lugmair, C. G., Miao, Y.-J., Kim, J., Levitsky, I. A., Williams, V. E., Swager, T. M. (2000) Optimization of TNT sensory polymers, *Proceedings of SPIE-The International Society for Optical Engineering*, 4038, 512-518.
5. Hancock, L. F., Deans, R., Moon, J., Swager, T. M. (2002) Amplifying fluorescent polymer detection of bioanalytes, *Proceedings of SPIE-The International Society for Optical Engineering*, 4575, 78-82.
6. Swager, T. M. (2000) Self-amplifying sensory materials: The molecular wire concept, *Abstr. Pap. - Am. Chem. Soc.*, 220th, ORGN-305.
7. He, Q., Lin, T., Bai, F. (2001) Synthesis and photophysical properties of linear and hyperbranched conjugated polymer, *Chinese Science Bulletin*, 46, 636-641.
8. Chambers, W. B., Rodacy, P. J., Jones, E. E., Gomez, B. J., Woodfin, R. L (1998) Chemical sensing system for classification of mine-like objects by explosives detection, *Proceedings of SPIE-The International Society for Optical Engineering*, 3392, 453-461.